

ISO/~~DIS~~**FDIS** 14594:2023(**E**)

ISO/TC 202/SC 2

~~Date: 2023-08-07~~

Secretariat: SAC

Date: 2024-02-20

Microbeam analysis — Electron probe microanalysis — Guidelines for the determination of experimental parameters for wavelength dispersive spectroscopy

Analyse par microfaisceaux — Analyse par microsonde électronique (Microsonde de Castaing) — Lignes directrices pour la détermination des paramètres expérimentaux pour la spectrométrie à dispersion de longueur d'onde

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

ISO/FDIS 14594

<https://standards.iteh.ai/catalog/standards/iso/f1/acd94-6aa1-4404-b698-718394814019/iso-fdis-14594>

FDIS stage

© ISO ~~2023~~**2024**

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
~~Email~~**E-mail**: copyright@iso.org
Website: ~~www.iso.org~~**www.iso.org**

Published in Switzerland

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

ISO/FDIS 14594

<https://standards.iteh.ai/catalog/standards/iso/ff7acd94-6aa1-4404-b698-718394814019/iso-fdis-14594>

Contents

Foreword	v
Introduction	vi
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Abbreviated terms	3
5 Experimental parameters	3
5.1 General	3
5.2 Parameters related to the electron probe	3
5.2.1 Accelerating voltage	3
5.2.2 Probe current	3
5.2.3 Magnification and field of view	4
5.3 Parameters related to wavelength dispersive X-ray spectrometers	4
5.3.1 General	4
5.3.2 Take-off angle	4
5.3.3 Wavelength resolution	4
5.3.4 X-ray detector and Pulse height analyser	4
5.3.5 Peak location (wavelength)	4
5.3.6 Background	5
5.4 Parameters related to the specimen	5
5.4.1 Specimen stage	5
5.4.2 Surface roughness	5
5.4.3 X-ray line	5
5.4.4 Analysis volume	6
6 Procedures and measurements	6
6.1 General	6
6.2 Electron probe	6
6.2.1 Probe current	6
6.2.2 Probe diameter	6
6.3 Parameters related to measured peaks	7
6.3.1 Dead time correction	7
6.3.2 Wavelength resolution of detected characteristic X-ray peaks	9
6.3.3 Background subtraction	10
6.4 Parameters related to the specimen	10
6.4.1 General	10

6.4.2	Analysis area	10
6.4.3	Analysis depth	10
6.4.4	Analysis volume	10
7	Test report	11
Annex A (informative) Methods of estimating analysis area		12
Annex B (informative) Methods of estimating analysis depth		15
Annex C (informative) Method of estimating X-ray analysis volume by applying the Monte Carlo (MC) simulation		17
Bibliography		21

Foreword — iv

Introduction — v

1 — Scope — 1

2 — Normative references — 1

3 — Terms and definitions — 1

4 — Abbreviated terms — 3

5 — Experimental parameters — 3

5.1 — General — 3

5.2 — Parameters related to the electron probe — 3

5.3 — Parameters related to wavelength dispersive X-ray spectrometers — 4

5.4 — Parameters related to the specimen — 5

6 — Procedures and measurements — 6

6.1 — General — 6

6.2 — Electron probe — 6

6.3 — Parameters related to measured peaks — 7

6.4 — Parameters related to the specimen — 9

7 — Test report — 10

Annex A (informative) Methods of estimating analysis area — 11

Annex B (informative) Methods of estimating analysis depth — 13

Annex C (informative) Method of estimating X-ray analysis volume by applying the Monte Carlo (MC) simulation — 15

Bibliography — 18

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 202, *Microbeam analysis*, Subcommittee SC 2, *Electron probe microanalysis*.

This third edition cancels and replaces the second edition (ISO 14594:2014), which has been technically revised.

The main changes are as follows:

- ~~ISO14594:2014~~
- Introduction has been added;
- Terms in Clause 3 have been updated;
- Technical terms in Clause 5 have been updated and the clause has been restructured;
- Content of the Test report in Clause 7 has been revised.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

To ensure reliability and reproducibility during electron probe microanalysis (EPMA), the experimental parameters that include beam current, current density, dead time, wavelength resolution, background, analysis area, analysis depth, and analysis volume should be carefully considered. To reliably consider EPMA results, guidelines standardizing the decision procedure of an experimental parameter is veryare important.

iTeh Standards (<https://standards.iteh.ai>) Document Preview

ISO/FDIS 14594

<https://standards.iteh.ai/catalog/standards/iso/ff7acd94-6aa1-4404-b698-718394814019/iso-fdis-14594>

Microbeam analysis — Electron probe microanalysis — Guidelines for the determination of experimental parameters for wavelength dispersive spectroscopy

1 Scope

This document gives general guidelines for the determination of experimental parameters relating to the electron probe, the wavelength spectrometer, and the specimen that need to be taken into account when carrying out electron probe microanalysis. It also defines procedures for the determination of probe current, probe diameter, dead time, wavelength resolution, background, analysis area, analysis depth, and analysis volume.

This document is applicable for the analysis of a well-polished specimen using normal beam incidence.

This document does not apply to energy dispersive X-ray spectroscopy.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO/IEC 17025:2005/2017, *General requirements for the competence of testing and testing laboratories*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

3.1 analysis area

area, projected by the interaction volume on the beam entrance surface, from which X-rays are emitted (at a defined fraction, e.g. 95 % of the total) and collected by the spectrometer

[SOURCE: ISO 23833:2013, 5.7.1.1]

3.2 analysis depth

maximum depth from which a defined fraction (e.g. 95 % of the total) of the X-rays are emitted from the interaction volume after absorption

[SOURCE: ISO 23833:2013, 5.7.1.2]

**3.3
analysis volume**

volume from which a defined fraction (e.g. 95 % of the total) of the X-rays are emitted after generation and absorption

[SOURCE: ISO 23833:2013, 5.7.1.3]

**3.4
background**

non-characteristic component of an X-ray spectrum arising (ideally) from the X-ray continuum

[SOURCE: ISO 23833:2013, 5.7.1.2]

**3.5
probe current**

electron current contained within the electron probe

[SOURCE: ISO 23833:2013, 4.3.1]

**3.6
probe diameter**

diameter of the probe containing a specified fraction of the total current, for example 0,8 (80 %) of the total

[SOURCE: ISO 23833:2013, 4.3.2]

**3.7
dead time**

time that the system is unable to record a photon measurement because it is busy processing a previous event and frequently expressed as a percentage of the total time

[SOURCE: ISO 23833:2013, 4.5.6]

**3.8
wavelength resolution**

full peak width at half maximum of a peak in terms of wavelength ($\Delta\lambda$) obtained from a single X-ray transition by a WDS

[SOURCE: ISO 23833:2013, 4.6.16]

**3.9
field of view**

length in the X- and Y-direction of the image or mapping area

**3.10
overvoltage ratio**

ratio of the incident beam energy to the critical excitation energy for a particular atomic shell

Note_1-to_entry: This factor must be greater than unity for characteristic X-ray production to occur from that atomic shell.

[SOURCE: ISO 23833:2013, 5.1.3]

3.11

Johansson optics

wavelength-dispersive X-ray spectrometer in which the diffractor is bent to a radius twice that of the Rowland circle and then its surface ground to the radius, achieving a fully focussing situation

[SOURCE: ISO 23833:2013, 4.6.14.8]

3.12

Johann optics

wavelength-dispersive X-ray spectrometer in which the diffractor is bent to a radius twice that of the Rowland circle, achieving a “semi focussing” situation

[SOURCE: ISO 23833:2013, 4.6.14.7]

4 Abbreviated terms

EPMA	electron probe microanalysis or electron probe microanalyser
FWHM	full width at half maximum
WDS	wavelength-dispersive spectrometer
WDX	wavelength-dispersive X-ray spectrometry

5 Experimental parameters

5.1 General

The parameters given in [5.2.1](#), [5.2.2](#), [5.2.1](#), [5.2.2](#), and [5.2.3](#) should be setup properly according to the purpose of the experiment and recorded. Checking the calibration of probe current, and magnification together with counter dead time should be included in the maintenance schedule of the instrument.

5.2 Parameters related to the electron probe

<https://standards.iteh.ai/catalog/standards/iso/ff7acd94-6aa1-4404-b698-718394814019/iso-fdis-14594>

5.2.1 Accelerating voltage

The beam energy accelerating voltage typically ranges from 2 keV to 30 keV. Since the sensitivity and spatial resolution (or analysis volume) of analysis depend on the accelerating voltage, the optimization of accelerating voltage can be critical in some cases. However, these performances are also depending on the material of the specimen and the measured X-ray lines. The optimization of accelerating voltage is specified in the guidance for the element and line (see [5.4.3](#)) and the analysis volume (See [5.4.4](#)).

5.2.2 Probe current

Because X-ray peak intensity is directly proportional to the probe current, the precision of the measurement of the probe current should be better than the precision required for quantitative analysis.

Probe current stability over long periods of time is essential for consistent quantitative analysis. The probe current stability should be tested periodically, especially prior to quantitative calibration and analysis. It is possible to compensate for small changes in probe current if this is recorded prior to and following each measurement. Then all X-ray peak and background measurements should be scaled appropriately by I_i/I_m , where I_i is the initial probe current and I_m is the probe current at the time of the measurement.

5.2.3 Magnification and field of view

To properly define the field of view for line-scans and images acquired by deflecting the electron probe, it is essential to calibrate the magnification scale while operating in the scanning electron mode.

5.3 Parameters related to wavelength dispersive X-ray spectrometers

5.3.1 General

An instrument may be fitted with one or more WDX spectrometers, each with a number of diffracting crystals—depending on the line of the analysed element. The following parameters are important for the proper operation of WDX spectrometers.

5.3.2 Take-off angle

The take-off angle affects quantitative analysis. Any comparison of measurements from instruments with different take-off angles should be taken into account and the procedures used be noted in the analysis report.

NOTE The value of this angle, which is normally fixed, is provided by the instrument manufacturer.

5.3.3 Wavelength resolution

The spectral resolution depends on the following parameters:

- — crystal material (and Miller indices of the crystal planes);
- — the radius of curvature of the diffracting crystal (Johansson optics vs. Johann optics);
- — the size and position of the counter entrance window or of the entrance slit if present.

All these settings determine the wavelength resolution of the measured X-ray spectrum and the observed line-width (FWHM) of the characteristic X-ray peaks. X-ray lines of analysed elements and X-ray order shall be recorded in the test report.

Resolution can also influence the ability of the system to discriminate against overlapping peaks, background signals, and the sensitivity of measurements to specimen height and beam position on the specimen.

5.3.4 X-ray detector and Pulse height analyser

Many spectrometers use a gas-filled proportional counter to detect X-rays. The magnitude of the output pulses from these detectors is determined by the incident X-ray energy and/or the voltage applied to the counters. Two discriminators are used to select the pulse of interest. A low discriminator setting is used to eliminate pulses due to noise, while a high discriminator setting excludes pulses from high order reflections of more energetic X-rays. Optimum settings depend on the X-ray lines of interest.

It is important to set the discriminator to ensure that any unintended shift in pulse amplitude, for example, due to high count rates or changes in atmospheric temperature and pressure (flow counter), has no significant effect on the measured count rate.

Because X-ray counting efficiency decreases with increasing count rate, it is important to correct the measured count rate for the effect of the dead time. In an automated system, the discriminator settings can be set automatically. These settings should be routinely checked to ensure proper automatic operation.

5.3.5 Peak location (wavelength)

Under normal circumstances, the wavelength which has the maximum peak intensity is used to define the location of an X-ray peak. It is necessary, using suitable reference materials, to periodically check and correct