



Designation: C361M – 12

Standard Specification for Reinforced Concrete Low-Head Pressure Pipe (Metric)¹

This standard is issued under the fixed designation C361M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This specification covers reinforced concrete pipe intended to be used for the construction of pressure pipelines with low internal hydrostatic heads generally not exceeding 375 kPa.

1.2 This specification is the SI companion to Specification C361. It is compatible in technical content.

NOTE 1—Field tests on completed portions of the pipeline are not covered by this specification for the manufacture of the pipe but should be included in specifications for pipe laying.

2. Referenced Documents

2.1 ASTM Standards:²

- A27/A27M Specification for Steel Castings, Carbon, for General Application
- A36/A36M Specification for Carbon Structural Steel
- A82/A82M Specification for Steel Wire, Plain, for Concrete Reinforcement
- A185/A185M Specification for Steel Welded Wire Reinforcement, Plain, for Concrete
- A283/A283M Specification for Low and Intermediate Tensile Strength Carbon Steel Plates
- A496/A496M Specification for Steel Wire, Deformed, for Concrete Reinforcement
- A497/A497M Specification for Steel Welded Wire Reinforcement, Deformed, for Concrete
- A575 Specification for Steel Bars, Carbon, Merchant Quality, M-Grades
- A576 Specification for Steel Bars, Carbon, Hot-Wrought, Special Quality
- A615/A615M Specification for Deformed and Plain Carbon-Steel Bars for Concrete Reinforcement

¹ This specification is under the jurisdiction of ASTM Committee C13 on Concrete Pipe and is the direct responsibility of Subcommittee C13.04 on Low Head Pressure Pipe.

Current edition approved Sept. 1, 2012. Published October 2012. Originally approved in 1978. Last previous edition approved in 2008 as C361M – 08. DOI: 10.1520/C0361M-12.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

- A675/A675M Specification for Steel Bars, Carbon, Hot-Wrought, Special Quality, Mechanical Properties
 - A1008/A1008M Specification for Steel, Sheet, Cold-Rolled, Carbon, Structural, High-Strength Low-Alloy, High-Strength Low-Alloy with Improved Formability, Solution Hardened, and Bake Hardenable
 - A1011/A1011M Specification for Steel, Sheet and Strip, Hot-Rolled, Carbon, Structural, High-Strength Low-Alloy, High-Strength Low-Alloy with Improved Formability, and Ultra-High Strength
 - C31/C31M Practice for Making and Curing Concrete Test Specimens in the Field
 - C33 Specification for Concrete Aggregates
 - C39/C39M Test Method for Compressive Strength of Cylindrical Concrete Specimens
 - C150 Specification for Portland Cement
 - C260 Specification for Air-Entraining Admixtures for Concrete
 - C309 Specification for Liquid Membrane-Forming Compounds for Curing Concrete
 - C497M Test Methods for Concrete Pipe, Manhole Sections, or Tile [Metric]
 - C595 Specification for Blended Hydraulic Cements
 - C618 Specification for Coal Fly Ash and Raw or Calcined Natural Pozzolan for Use in Concrete
 - C822 Terminology Relating to Concrete Pipe and Related Products
 - C1619 Specification for Elastomeric Seals for Joining Concrete Structures
 - D698 Test Methods for Laboratory Compaction Characteristics of Soil Using Standard Effort (12 400 ft-lbf/ft³ (600 kN-m/m³))
 - D4253 Test Methods for Maximum Index Density and Unit Weight of Soils Using a Vibratory Table
 - D4254 Test Methods for Minimum Index Density and Unit Weight of Soils and Calculation of Relative Density
- #### 2.2 Other Standard:
- ACI Code 318 Standard Building Code Requirements for Reinforced Concrete³

³ Available from American Concrete Institute (ACI), P.O. Box 9094, Farmington Hills, MI 48333-9094, <http://www.concrete.org>.

AISI-C1012⁴

3. Terminology

3.1 *Definitions*—For definitions of terms relating to concrete pipe, see Terminology **C822**.

4. Classification

4.1 Pipe manufactured according to this specification shall be for hydrostatic heads of 75, 150, 225, 300, and 375 kPa measured to the centerline of the pipe. Designs are provided in **Table 1** and **Table 2** for the above hydrostatic heads combined with external loadings of 1.5, 3.0, 4.5, and 6.0 m (designated A, B, C, and D in **Table 1** and **Table 2**) of earth cover over the top of the pipe under specific installation conditions. The specific installation conditions are covered in **Appendix X1**. Where the hydrostatic head, external loadings, and installation conditions vary from those given in **Table 1** and **Table 2** and **Appendix X1**, detailed design calculations shall be made. The design criteria for **Table 1** and **Table 2** are presented in **Appendix X2**.

5. Basis of Acceptance

5.1 Acceptability of the pipe in all diameters and classes shall be determined by the results of such material tests as are required in 6.2 through 6.9 by crushing tests on cured concrete cylinders, by hydrostatic pressure tests on units of the pipe, by joint leakage tests, and by inspection during or after manufacture to determine whether the pipe conforms to this specification as to design and freedom from defects.

5.2 *Age for Acceptance*—Pipe shall be considered ready for acceptance when they conform to the requirements, as indicated by the specified tests.

6. Materials

6.1 *Reinforced Concrete*—The reinforced concrete shall consist of portland cement, mineral aggregates, and water, in which steel has been embedded in such a manner that the steel and concrete act together. Fly ash or pozzolan is not prohibited when used as a partial cement replacement; see 9.1.

6.2 Cementitious Materials:

6.2.1 Cement:

6.2.1.1 *Portland Cement*—Portland cement shall conform to the requirements of Specification **C150**.

6.2.1.2 *Blended Hydraulic Cement*—Blended cement shall conform to the requirements of Specification **C595** for Type IS portland blast furnace slag cement or Type IP portland pozzolan cement, except that the pozzolan constituent in the Type IP portland pozzolan cement shall not exceed 20 % by weight.

6.2.2 *Fly Ash or Pozzolan*—Fly ash or pozzolan shall conform to the requirements of Specification **C618**.

6.2.3 *Allowable Cementitious Materials*—The combination of cementitious materials used in the concrete shall be one of the following:

6.2.3.1 Portland cement only,

6.2.3.2 Portland blast furnace slag cement only,

6.2.3.3 Portland pozzolan cement only, or

6.2.3.4 A combination of portland cement and fly ash or pozzolan, wherein the proportion of fly ash or pozzolan is between 5 and 20 % by weight of total cementitious material (portland cement plus fly ash or pozzolan).

6.3 *Aggregates*—Aggregates shall conform to Specification **C33**, except that the requirements for grading are waived.

6.4 *Admixtures*—Admixtures, except for air-entraining agents, shall not be added to the concrete unless permitted by the owner. At the option of the manufacturer, or if specified by the owner, the concrete in precast concrete pipe placed by the cast-and-vibrated method shall contain an air-entraining agent conforming to Specification **C260**. The amount of air-entraining agent used shall be such as will affect the entrainment of not more than 3 % air by volume of concrete as discharged from the mixer.

6.5 *Steel Reinforcement*—Reinforcement shall consist of wire conforming to Specification **A82/A82M**, Specification **A496/A496M**, or of wire reinforcement conforming to Specification **A185/A185M** or Specification **A497/A497M**, or of bars of Grade 300 steel conforming to Specification **A615/A615M**.

6.6 Steel for Joint Rings:

6.6.1 Steel strips for bell rings less than 6 mm thick shall conform to Grade SS30 of Specification **A1011/A1011M** or Grade Designation 1012 of Specification **A575**. Steel that meets the requirements of AISI-C1012 for chemical components will be acceptable provided it conforms to Grade SS30 of Specification **A1011/A1011M** in other respects.

6.6.2 Steel plate for bell rings 6 mm or more in thickness and special shapes for spigot joint rings shall conform to Specification **A36/A36M**, or to Grade A of Specification **A283/A283M**, or to Grade Designation 1012 of Specification **A576**, or to Grade 50 of Specification **A675/A675M**. Steel that meets the requirements of AISI-C1012 for chemical components will be acceptable provided it conforms to Specification **A36/A36M** or to Specification **A283/A283M** in other respects.

6.7 *Steel Castings for Fittings*—Steel castings for fittings shall conform to Grade 70-36, Normalized, of Specification **A27/A27M**.

6.8 *Steel Plates and Sheets for Specials and Fittings*—Steel plates for specials and fittings shall conform to Specification **A36/A36M** or to Grade B or C of Specification **A283/A283M** or Grade SS30 or SS33 of Specification **A1011/A1011M** or Grade SS30 of Specification **A1008/A1008M**.

6.9 Rubber Gaskets:

6.9.1 *Composition and Properties*—All rubber gaskets shall comply with Specification **C1619** in terms of material and manufacture. The gaskets shall be of a solid circular cross section and shall be extruded or molded to the specified size within a diametrical tolerance of ± 0.4 mm or ± 1.5 % of the diameter, whichever is larger.

6.9.1.1 *Standard Gasket Requirements*—All rubber gaskets shall meet the dimensions, tolerances, and physical requirements of Specification **C1619**, Class A.

⁴ Available from the American Iron and Steel Institute (AISI), 1140 Connecticut Ave. NW, Suite 705, Washington D.C. 20036, <http://www.steel.org>.

TABLE 1 Design Requirements for Reinforced Concrete Low-Head Pressure Pipe [300 to 3650 mm Diameter], Concrete Design Strength 34.5 MPa (except as noted) Steel Reinforced Yield Strength 276 MPa

NOTE 1—See Appendix for specific installation conditions and design criteria conditions required in conjunction with the use of Table 1.

NOTE 2—Designations A, B, C, and D, for class of pipe, denote 1.5, 3.0, 4.5, and 6.0 m of earth cover over top of pipe. Figures 150, Figures 225, etc. for class of pipe, denote hydrostatic pressure heads in kilopascals measured to centerline of pipe.

NOTE 3—An “s” in place of a steel area indicates the pipe class is a special design requiring stirrup reinforcement. Stirrups may be eliminated by changing wall thickness, main reinforcement, concrete strength, or a combination thereof.

NOTE 4—The boldfaced value denotes 41.4 MPa concrete strength required.

Internal Designated Dia., mm	Circumferential reinforcement, mm ² /linear m of pipe ^{A, B}																							
	300			375			450			525			600			675								
	Circular			Circular			Circular			Circular			Circular			Circular								
Wall Thickness, mm	50	75	75	50	75	75	57	75	75	60	75	60	75	63	75	63	75	66	79	82	107	66	82	
Layers of Reinforcement	Single	Single	Single	Single	Single	Single	Single	Single	Single	Single	Single	Single	Single	Single	Single	Single	Single	Single	Single	Single	Inner	Outer	Single	Single
Class	A-75	B-75	C-75	D-75	A-150	B-150	C-150	D-150	A-225	B-225	C-225	D-225	A-300	B-300	C-300	D-300	A-375	B-375	C-375	D-375				
	140	210	280	360	220	270	340	420	340	340	400	480	490	490	490	540	650	650	650	650				
	120	170	220	270	220	270	350	430	520	520	520	580	610	610	610	620	820	820	820	820				
	200	310	420	540	280	380	480	630	790	790	790	880	730	730	730	820	980	980	980	980				
	170	240	310	400	320	420	520	640	640	640	640	730	730	730	730	820	980	980	980	980				
	250	320	400	500	320	430	520	640	640	640	640	730	730	730	730	820	980	980	980	980				
	320	420	500	690	320	430	520	640	640	640	640	730	730	730	730	820	980	980	980	980				
	290	420	500	690	320	430	520	640	640	640	640	730	730	730	730	820	980	980	980	980				
	390	610	870	1150	390	530	600	800	800	800	800	880	880	880	880	980	1140	1140	1140	1140				
	350	540	730	950	480	660	740	990	990	990	1070	1070	1070	1070	1070	1280	1310	1310	1310	1310				
	460	740	1060	1430	600	880	990	1280	1280	1280	1400	1400	1400	1400	1400	1710	1710	1710	1710	1710				
	410	650	890	1170	610	800	880	1020	1020	1020	1130	1130	1130	1130	1130	1330	1330	1330	1330	1330				
	290	440	590	750	430	530	600	800	800	800	880	880	880	880	880	1020	1020	1020	1020	1020				
	200	280	350	440	320	420	500	690	690	690	710	710	710	710	710	860	860	860	860	860				
	410	650	890	1170	610	800	880	1020	1020	1020	1130	1130	1130	1130	1130	1330	1330	1330	1330	1330				
	490	610	730	820	520	630	790	980	980	980	1130	1130	1130	1130	1130	1330	1330	1330	1330	1330				
	500	570	650	720	320	420	500	690	690	690	710	710	710	710	710	860	860	860	860	860				
	590	740	890	1060	610	800	880	1020	1020	1020	1130	1130	1130	1130	1130	1330	1330	1330	1330	1330				
	490	610	730	820	520	630	790	980	980	980	1130	1130	1130	1130	1130	1330	1330	1330	1330	1330				
	540	770	980	1240	320	420	500	690	690	690	710	710	710	710	710	860	860	860	860	860				
	650	820	980	1140	320	420	500	690	690	690	710	710	710	710	710	860	860	860	860	860				
	650	820	980	1140	320	420	500	690	690	690	710	710	710	710	710	860	860	860	860	860				
	650	850	1070	1350	320	420	500	690	690	690	710	710	710	710	710	860	860	860	860	860				
	650	820	1070	1350	320	420	500	690	690	690	710	710	710	710	710	860	860	860	860	860				
	650	820	1070	1350	320	420	500	690	690	690	710	710	710	710	710	860	860	860	860	860				
	650	820	1070	1350	320	420	500	690	690	690	710	710	710	710	710	860	860	860	860	860				
	650	820	1070	1350	320	420	500	690	690	690	710	710	710	710	710	860	860	860	860	860				
	650	820	1070	1350	320	420	500	690	690	690	710	710	710	710	710	860	860	860	860	860				
	650	820	1070	1350	320	420	500	690	690	690	710	710	710	710	710	860	860	860	860	860				
	650	820	1070	1350	320	420	500	690	690	690	710	710	710	710	710	860	860	860	860	860				
	650	820	1070	1350	320	420	500	690	690	690	710	710	710	710	710	860	860	860	860	860				
	650	820	1070	1350	320	420	500	690	690	690	710	710	710	710	710	860	860	860	860	860				
	650	820	1070	1350	320	420	500	690	690	690	710	710	710	710	710	860	860	860	860	860				
	650	820	1070	1350	320	420	500	690	690	690	710	710	710	710	710	860	860	860	860	860				
	650	820	1070	1350	320	420	500	690	690	690	710	710	710	710	710	860	860	860	860	860				
	650	820	1070	1350	320	420	500	690	690	690	710	710	710	710	710	860	860	860	860	860				
	650	820	1070	1350	320	420	500	690	690	690	710	710	710	710	710	860	860	860	860	860				
	650	820	1070	1350	320	420	500	690	690	690	710	710	710	710	710	860	860	860	860	860				
	650	820	1070	1350	320	420	500	690	690	690	710	710	710	710	710	860	860	860	860	860				
	650	820	1070	1350	320	420	500	690	690	690	710	710	710	710	710	860	860	860	860	860				
	650	820	1070	1350	320	420	500	690	690	690	710	710	710	710	710	860	860	860	860	860				
	650	820	1070	1350	320	420	500	690	690	690	710	710	710	710	710	860	860	860	860	860				
	650	820	1070	1350	320	420	500	690	690	690	710	710	710	710	710	860	860	860	860	860				
	650	820	1070	1350	320	420	500	690	690	690	710	710	710	710	710	860	860	860	860	860				
	650	820	1070	1350	320	420	500	690	690	690	710	710	710	710	710	860	860	860	860	860				
	650	820	1070	1350	320	420	500	690	690	690	710	710	710	710	710	860	860	860	860	860				
	650	820	1070	1350	320	420	500	690	690	690	710	710	710	710	710	860	860	860	860	860				
	650	820	1070	1350	320	420	500	690	690	690	710	710	710	710	710	860	860	860	860	860				
	650	820	1070	1350	320	420	500	690	690	690	710	710	710	710	710	860	860	860	860	860				
	650	820	1070	1350	320	420	500	690	690	690	710	710	710	710	710	860	860	860	860	860				
	650	820	1070	1350	320	420	500	690	690	690	710	710	710	710	710	860	860	860	860	860				
	650	820	1070	1350	320	420	500	690	690	690	710	710	710	710	710	860	860	860	860	860				
	650	820	1070	1350	320	4																		



TABLE 1 Continued

Internal Designated Dia, mm	Circumferential reinforcement, mm ² /linear m of pipe ^{A, B}															
	750						825									
	Circular						Circular									
Type of Reinforcement	Circular			Elliptical			Circular			Elliptical						
Wall Thickness, mm	69	79	82	88	119	119	69	88	72	79	82	94	119	72	94	
Layers of Reinforcement	Single	Single	Inner	Outer	Inner	Outer	Single	Single	Single	Single	Inner	Outer	Inner	Outer	Single	
A-75	530	490	340	230	320	220	170	250	250	250	250	250	250	250	250	450
B-75	880	790	530	310	490	310	220	370	370	370	370	370	370	370	370	540
C-75	1260	1110	720	440	660	400	280	490	490	490	490	490	490	490	490	730
D-75	1750	1470	920	550	840	490	330	600	600	600	600	600	600	600	600	930
A-150	680	640	450	350	430	330	270	350	350	350	350	350	350	350	350	950
B-150	1030	940	640	450	600	420	320	470	470	470	470	470	470	470	470	950
C-150	1420	1260	830	550	770	500	370	580	580	580	580	580	580	580	580	950
D-150	1900	1630	1030	650	940	600	430	700	700	700	700	700	700	700	700	1040
A-225	860	860	560	460	530	440	390	470	470	470	470	470	470	470	470	...
B-225	1180	1100	750	560	700	520	420	570	570	570	570	570	570	570	570	...
C-225	1570	1410	940	660	870	610	470	680	680	680	680	680	680	680	680	...
D-225	2060	1780	1130	760	1040	700	520	800	800	800	800	800	800	800	800	...
A-300	1220	1220	670	570	660	560	660	660	660	660	660	660	660	660	660	...
B-300	1340	1250	860	670	810	630	540	690	690	690	690	690	690	690	690	...
C-300	1730	1570	1040	760	980	720	570	780	780	780	780	780	780	780	780	...
D-300	2210	1930	1240	870	1150	810	620	890	890	890	890	890	890	890	890	...
A-375	1630	1630	870	760	870	760	760	870	870	870	870	870	870	870	870	...
B-375	1630	1630	970	780	920	740	730	900	900	900	900	900	900	900	900	...
C-375	1880	1720	1150	870	1080	820	710	930	930	930	930	930	930	930	930	...
D-375	2360	2090	1340	980	1250	910	720	990	990	990	990	990	990	990	990	...



TABLE 1 Continued

Internal Designated Dia, mm	Circumferential reinforcement, mm ² /linear m of pipe ^{A, B}														
	900						975 ^C						1050		
	Circular			Elliptical			Circular			Elliptical			Circular		Elliptical
79	82	100	125	79	100	88	107	132	88	107	94	113	138	94	113
Single	Inner	Outer	Inner	Single	Single	Inner	Outer	Inner	Outer	Single	Inner	Outer	Inner	Outer	Single
670	460	320	380	260	330	220	670	490	340	420	290	360	240	530	360
1130	740	480	600	380	490	300	1130	600	510	650	410	540	330	790	850
1650	1030	640	800	480	640	370	1650	800	1090	870	530	710	420	1090	720
2150	1330	800	1010	600	800	450	2150	1010	1410	1100	650	880	500	1410	1500
850	590	450	510	390	440	340	1040	1040	630	550	420	480	370	1130	670
1320	870	610	720	500	610	420	1320	1040	930	780	540	660	460	1130	990
1840	1150	760	920	610	760	490	1840	1040	1220	1000	660	830	540	1220	1300
2330	1450	930	1130	720	910	570	2330	1130	1540	1230	780	1000	620	1540	1630
1040	720	580	630	510	570	460	770	620	680	550	500	...	810
1500	1000	740	840	620	720	530	1070	780	910	670	790	...	1130
2030	1280	890	1040	730	870	610	1360	950	1130	790	660	...	1440
2520	1580	1060	1250	840	1030	680	1670	1120	1350	910	750	...	1760
1470	860	720	800	670	790	670	910	760	860	730	600	...	960
1690	1130	870	960	740	840	650	1200	920	1040	800	710	...	1270
2210	1400	1020	1160	850	990	720	1490	1080	1250	920	790	...	1580
2700	1700	1180	1370	960	1140	800	1800	1250	1480	1040	870	...	1900
1960	1050	910	1050	910	1050	910	1140	980	1140	980	990	...	1230
1960	1260	1000	1090	870	1090	870	1340	1060	1180	940	950	...	1420
2400	1530	1150	1280	970	1110	850	1620	1220	1380	1050	920	...	1720
2890	1820	1310	1480	1080	1250	910	1920	1390	1600	1160	990	...	2030
570	570	270	390	310	390	270	520	530	360	240	530	...	570
710	850	370	590	450	590	370	650	650	450	330	650	...	710
940	1160	460	780	570	780	460	870	870	570	420	870	...	940
1190	1500	550	970	710	970	550	1100	1100	710	500	1100	...	1190
1210	1210	400	530	450	530	400	670	670	450	370	670	...	1210
1210	1210	500	730	580	730	500	990	990	580	460	990	...	1210
1210	1300	590	910	710	910	590	1220	1130	860	540	1220	...	1300
1330	1630	680	1100	840	1100	680	1540	1230	1000	620	1540	...	1630
...	...	540	670	590	670	540	770	620	680	550	500	...	810
...	...	630	720	660	720	630	1070	780	910	670	580	...	1130
...	...	720	870	750	870	720	1360	950	1130	790	660	...	1440
...	...	820	1030	880	1030	820	1670	1120	1350	910	750	...	1760
...	...	780	930	780	930	780	910	760	860	730	600	...	960
...	...	770	840	770	840	770	1200	920	1040	800	710	...	1270
...	...	850	990	850	990	850	1490	1080	1250	920	790	...	1580
...	...	950	1140	950	1140	950	1800	1250	1480	1040	870	...	1900
...	...	1060	1230	1060	1230	1060	1140	980	1140	980	990	...	1230
...	...	1020	1090	1020	1090	1020	1340	1060	1180	940	950	...	1420
...	...	990	1110	990	1110	990	1620	1220	1380	1050	920	...	1720
...	...	1080	1250	1080	1250	1080	1920	1390	1600	1160	990	...	2030

TABLE 1 Continued

Internal Designated Dia, mm	Circumferential reinforcement, mm ² /linear m of pipe ^{A, B}																															
	1125 ^C						1200						1275 ^C																			
	Circular			Elliptical			Circular			Elliptical			Circular			Elliptical																
Wall Thickness, mm	97		119		144		97		119		144		104		125		144		104		125		107		132		150		107		132	
	Inner	Outer	Inner	Outer	Inner	Outer	Single	Single	Inner	Outer	Inner	Outer	Inner	Outer	Single	Single	Inner	Outer	Inner	Outer	Single	Single	Inner	Outer	Inner	Outer	Inner	Outer	Single	Single		
Layers of Reinforcement	Inner	Outer	Inner	Outer	Inner	Outer	Single	Single	Inner	Outer	Inner	Outer	Inner	Outer	Single	Single	Inner	Outer	Inner	Outer	Single	Single	Inner	Outer	Inner	Outer	Inner	Outer	Single	Single		
Class	570	390	480	330	430	290	610	610	620	420	530	360	480	330	650	650	670	460	570	390	520	350	700	700	570	390	520	350	700	700		
A-75	930	600	760	480	650	400	930	760	1010	650	830	530	740	460	1010	830	1100	710	890	560	790	490	890	890	890	560	790	490	1100	890		
B-75	1280	790	1020	620	850	500	1280	1020	1380	860	1110	680	970	580	1380	1110	1510	940	1190	720	1040	630	1510	1190	1190	720	1040	630	1510	1190		
C-75	1650	1000	1290	770	1060	610	1650	1290	1790	1080	1410	840	1210	710	1790	1410	1950	1190	1500	890	1300	760	1950	1500	1500	890	1300	760	1950	1500		
D-75	720	550	630	480	570	430	720	550	780	590	690	520	640	480	1380	1380	840	640	730	550	680	510	1470	1470	550	680	510	1470	1470			
A-150	1080	750	910	630	790	540	1080	750	1170	810	990	680	890	610	1380	1380	1270	880	1050	720	950	650	1470	1470	720	950	650	1470	1470			
B-150	1420	940	1160	760	990	640	1420	940	1540	1020	1260	830	1120	730	1540	1380	1670	1100	1350	890	1200	780	1670	1470	890	1200	780	1670	1470			
C-150	1790	1150	1420	910	1190	750	1790	1420	1930	1240	1550	990	1360	850	1930	1550	2100	1350	1650	1050	1460	920	2100	1650	1050	1460	920	2100	1650			
D-150	880	710	780	630	710	580	950	760	850	680	790	640	1020	810	900	720	840	680	720	840	680		
A-225	1230	900	1050	770	930	680	1330	970	1140	840	1040	760	1430	1050	1210	890	1110	810	890	1110	810		
B-225	1570	1090	1300	910	1130	780	1690	1180	1410	990	1270	880	1830	1270	1510	1050	1360	940	1050	1360	940		
C-225	1930	1300	1560	1050	1330	880	2080	1390	1700	1140	1500	1000	2260	1510	1810	1210	1610	1070	1210	1610	1070		
D-225	1040	860	1000	840	1000	840	1110	930	1070	890	1060	890	1190	990	1130	940	1130	950	940	1130	950		
A-300	1380	1060	1200	920	1070	830	1490	1140	1300	1000	1190	920	1600	1220	1380	1050	1270	970	1050	1270	970		
B-300	1720	1240	1440	1050	1270	920	1850	1340	1570	1140	1420	1030	1990	1440	1670	1210	1520	1100	1210	1520	1100		
C-300	2070	1440	1700	1190	1470	1020	2230	1550	1850	1290	1650	1150	2410	1670	1960	1370	1760	1230	1370	1760	1230		
D-300	1320	1130	1320	1130	1310	1140	1410	1200	1410	1210	1400	1210	1500	1280	1500	1280	1490	1280	1280	1490	1280		
A-375	1540	1210	1360	1090	1360	1090	1650	1300	1460	1160	1450	1160	1780	1400	1550	1230	1550	1230	1230	1550	1230		
B-375	1860	1400	1590	1200	1410	1060	2010	1500	1720	1300	1570	1180	2160	1610	1830	1370	1670	1260	1370	1670	1260		
C-375	2220	1590	1840	1330	1600	1160	2380	1710	2000	1450	1800	1300	2570	1840	2120	1530	1920	1390	1530	1920	1390		
D-375													



TABLE 1 Continued

Internal Designated Dia, mm		1575 ^C						1650						1725 ^C						
		Circular			Elliptical			Circular			Elliptical			Circular			Elliptical			
Type of Reinforcement	Wall Thickness, mm	Inner	Outer	Inner	Outer	Single	Single	Inner	Outer	Inner	Outer	Single	Single	Inner	Outer	Inner	Outer	Single	Single	
Class																				
A-75	840	570	740	500	690	460	860	880	600	780	530	730	490	900	900	820	550	770	520	940
B-75	1310	840	1110	700	1010	630	1310	1360	870	1160	740	1060	670	1360	1160	1220	770	1120	700	1410
C-75	1840	1140	1520	930	1370	820	1840	1920	1190	1610	980	1450	870	1910	1610	1690	1030	1530	920	1990
D-75	2350	1430	1920	1150	1700	1000	2350	2450	1490	2020	1210	1800	1060	2450	2020	2120	1270	1900	1120	2540
A-150	1040	780	940	700	880	660	1820	1890	810	990	730	930	690	1900	1900	1040	770	980	730	1990
B-150	1510	1040	1300	900	1200	830	1820	1920	1080	1370	940	1260	870	1900	1900	1430	990	1330	910	1990
C-150	2030	1340	1710	1120	1560	1020	2030	2110	1390	1800	1180	1650	1070	2110	1900	1890	1240	1730	1130	2200
D-150	2530	1620	2100	1340	1890	1190	2530	2630	1690	2210	1400	1990	1260	2630	2210	2310	1470	2100	1330	2740
A-225	1250	990	1140	900	1080	860	1030	1190	940	1140	900	1250	990	1200	940	...
B-225	1710	1250	1500	1100	1390	1020	1290	1570	1150	1460	1070	1640	1200	1540	1120	...
C-225	2220	1540	1900	1320	1750	1210	1600	2000	1380	1840	1270	2100	1450	1940	1340	...
D-225	2720	1820	2280	1530	2070	1380	1890	2400	1600	2190	1460	2510	1680	2300	1530	...
A-300	1460	1200	1410	1160	1400	1160	1250	1470	1210	1470	1210	1540	1270	1540	1270	...
B-300	1910	1450	1700	1300	1590	1220	1510	1770	1360	1670	1280	1850	1420	1750	1340	...
C-300	2410	1740	2100	1520	1940	1400	1810	2200	1590	2040	1470	2300	1660	2140	1550	...
D-300	2900	2010	2470	1720	2260	1570	2090	2590	1800	2380	1650	2710	1890	2500	1740	...
A-375	1860	1570	1860	1580	1850	1580	1640	1950	1650	1940	1650	2040	1720	2030	1720	...
B-375	2110	1660	1920	1510	1910	1520	1720	2010	1590	2000	1590	2100	1660	2100	1660	...
C-375	2610	1940	2290	1710	2130	1600	2010	2400	1790	2240	1680	2510	1870	2350	1760	...
D-375	3090	2210	2660	1910	2450	1760	2290	2790	2000	2570	1850	2920	2090	2700	1940	...

TABLE 1 Continued

Internal Designated Dia, mm		Circumferential reinforcement, mm ² /linear m of pipe ^{A, B}																		
		1800				1950				2100										
Type of Reinforcement	Wall Thickness, mm	Circular				Circular				Circular										
		150	175	194	150	175	163	188	207	175	200	219								
Layers of Reinforcement	Inner	Outer	Inner	Outer	Inner	Outer	Inner	Outer	Inner	Outer	Inner	Outer								
													Single	Single	Inner	Outer	Inner	Outer	Inner	Outer
Class	1020	690	910	610	850	570	1020	980	1110	750	1000	670	940	630	1210	810	1100	730	1040	690
A-75	1550	1000	1340	850	1230	770	1550	1340	1660	1060	1460	920	1340	840	1780	1140	1580	1000	1460	920
B-75	2210	1370	1860	1140	1690	1020	2210	1860	2370	1470	2020	1240	1840	1110	2500	1550	2170	1330	1990	1200
C-75	2830	1720	2340	1400	2100	1240	2830	2340	3020	1840	2550	1530	2300	1360	3150	1920	2760	1660	2520	1490
D-75	1260	930	1140	850	1080	800	2080	2080	1370	1010	1250	920	1190	870	1480	1080	1360	1000	1300	950
A-150	1790	1230	1570	1080	1450	1000	2080	2080	1910	1320	1700	1170	1580	1090	2040	1400	1830	1260	1720	1180
B-150	2430	1600	2080	1360	1900	1240	2430	2080	2600	1710	2260	1480	2070	1350	2750	1810	2420	1580	2230	1460
C-150	3040	1940	2550	1620	2310	1460	3040	2550	3250	2070	2770	1760	2530	1600	3400	2180	3000	1910	2760	1740
D-150	1500	1180	1370	1080	1310	1030	1620	1270	1500	1170	1430	1120	1750	1360	1630	1270	1560	1210
A-225	2020	1470	1790	1310	1680	1220	2160	1570	1940	1410	1820	1330	2300	1670	2090	1520	1980	1440
B-225	2660	1830	2310	1590	2120	1460	2840	1960	2490	1720	2310	1590	3000	2070	2670	1840	2480	1710
C-225	3250	2160	2770	1840	2520	1680	3470	2310	3000	2000	2760	1830	3650	2440	3240	2160	3000	1990
D-225	1740	1420	1610	1320	1610	1320	1880	1530	1750	1430	1750	1430	2020	1630	1890	1530	1890	1530
A-300	2260	1710	2020	1540	1900	1450	2410	1820	2190	1660	2070	1570	2560	1940	2350	1790	2230	1700
B-300	2880	2070	2530	1820	2350	1690	3080	2200	2730	1960	2540	1830	3250	2330	2920	2100	2740	1970
C-300	3470	2390	2980	2070	2740	1900	3700	2550	3230	2240	2990	2070	3890	2690	3490	2410	3240	2240
D-300	2130	1790	2130	1790	2130	1790	2310	1930	2310	1940	2310	1940	2500	2080	2490	2080	2490	2080
A-375	2490	1950	2260	1780	2190	1730	2660	2080	2430	1910	2370	1870	2830	2210	2610	2050	2560	2010
B-375	3110	2300	2750	2050	2570	1910	3320	2450	2970	2210	2780	2070	3510	2590	3170	2360	2990	2230
C-375	3690	2620	3200	2290	2960	2120	3930	2790	3470	2480	3220	2310	4150	2960	3730	2660	3490	2490
D-375																		

