



Designation: **B523/B523M—12 B523/B523M – 12a**

## Standard Specification for Seamless and Welded Zirconium and Zirconium Alloy Tubes<sup>1</sup>

This standard is issued under the fixed designation B523/B523M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reappraisal.

### 1. Scope

1.1 This specification<sup>2</sup> covers ~~three~~two grades of zirconium and zirconium alloy seamless and welded tubes.

1.2 Unless a single unit is used, for example corrosion mass gain in  $\text{mg}/\text{dm}^2$ , the values stated in either inch-pound or SI units are to be regarded separately as standard. The values stated in each system are not exact equivalents; therefore, each system must be used independently of the other. SI values cannot be mixed with inch-pound values.

1.3 The following precautionary caveat pertains only to the test methods portion of this specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

### 2. Referenced Documents

2.1 *ASTM Standards*:<sup>3</sup>

[A370 Test Methods and Definitions for Mechanical Testing of Steel Products](#)

[B551/B551M Specification for Zirconium and Zirconium Alloy Strip, Sheet, and Plate](#)

[B614 Practice for Descaling and Cleaning Zirconium and Zirconium Alloy Surfaces](#)

[E8 Test Methods for Tension Testing of Metallic Materials](#)

[E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications](#)

[E213 Practice for Ultrasonic Testing of Metal Pipe and Tubing](#)

[E426 Practice for Electromagnetic \(Eddy-Current\) Examination of Seamless and Welded Tubular Products, Titanium, Austenitic Stainless Steel and Similar Alloys](#)

### 3. Terminology

3.1 *Definitions of Terms Specific to This Standard*:

3.1.1 *annealed, n*—for purposes of this specification “annealed” denotes material that exhibits a recrystallized grain structure.

3.2 *Lot Definitions*:

3.2.1 *tubes, n*—a lot shall consist of a material of the same size, shape, condition, and finish produced from the same ingot or powder blend by the same reduction schedule and the same heat treatment parameters. Unless otherwise agreed between manufacturer and purchaser, a lot shall be limited to the product of an 8 h period for final continuous anneal, or to a single furnace load for final batch anneal.

### 4. Classification

4.1 The tubes are furnished in ~~three~~two grades as follows:

4.1.1 *Grade R60702*—Unalloyed zirconium.

4.1.2 *Grade R60704*—Zirconium-tin alloy.

4.1.3 ~~*Grade R60705*—Zirconium-niobium alloy.~~

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee B10 and is the direct responsibility of Subcommittee B10.02 on Zirconium and Hafnium. Current edition approved May 15, 2012 Aug. 1, 2012. Published June 2012 October 2012. Originally approved in 1970. Last previous edition approved in 2007 2012 as B523/B523M – 07-B523/B523M – 12. DOI: 10.1520/B0523\_B0523M-12-10.1520/B0523\_B0523M-12A.

<sup>2</sup> For ASME Boiler and Pressure Vessel Code Applications, see related Specification SB-523 in Section II of that Code.

<sup>3</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

## 5. Ordering Information

5.1 Orders for material under this specification should include the following information:

5.1.1 Quantity (weight or number of pieces, or both),

5.1.2 Name of material (zirconium seamless or welded tube),

5.1.3 Dimensions (diameter, wall thickness as either average or minimum, lengths),

5.1.4 ASTM designation and year of issue,

5.1.5 Grade number (see 4.1), and

5.1.6 Additions to the specification, if required. See 6.3.1, 7.3, 10.1, 12.7.3, 14.1, and 15.1 for additional optional requirements for the purchase order.

NOTE 1—A typical ordering description is as follows: 1000 pieces of seamless zirconium tubes, 2 in. [50 mm] in outside diameter by 0.06 in. [1.5 mm] in average wall thickness by 10 ft [3 m] in length, vacuum annealed, ASTM B523/B523M - 01, Grade R60702.

## 6. Materials and Manufacture

6.1 Seamless tube shall be made by any seamless method that will yield a product meeting the requirements of this specification.

6.2 Welded tube shall be made from sheet or strip meeting the requirements of Specification B551/B551M by an automatic arc-welding process or other method of welding that will yield a product meeting the requirements of this specification. Filler metal shall not be used. Welded tubing shall be supplied as follows:

6.2.1 As welded, or

6.2.2 As welded and further reduced.

6.2.3 Welds in grade R60705 shall be stress relief annealed within 14 days after welding to prevent delayed hydride cracking. The heat treatment shall be done as follows:

6.2.3.1 The stress-relieving treatment shall consist of holding the fitting at a minimum temperature of 1100°F [600°C] for not less than ½ h/in. [25 mm] of the maximum thickness in a nonreducing atmosphere. The minimum time at this temperature is 15 min. All stress-relieved parts shall be cleaned subsequently and shall be free of oxide scale contamination (see Practice B614).

6.3 The tube shall be furnished annealed.

6.3.1 Purchaser shall specify one of the following:

(a) annealed in air

(b) annealed in vacuum

## 7. Chemical Composition

7.1 The material shall conform to the requirements as to chemical composition prescribed in Table 1.

7.2 The manufacturer's ingot analysis shall be considered the chemical analysis for tubing, except for hydrogen and nitrogen, which shall be determined on the finished product.

**TABLE 1 Chemical Requirements<sup>A</sup>**

Element	Composition, %		
	UNS Grade Designation		
	R60702	R60704	R60705
R60702	R60704		
Zirconium + hafnium, min <sup>B</sup>	99.2	97.5	95.5
Zirconium + hafnium, min <sup>B</sup>	99.2	97.5	
Hafnium, max	4.5	4.5	4.5
Hafnium, max	4.5	4.5	
Iron + chromium	0.2 max	0.2 to 0.4	0.2 max
Iron + chromium	0.2 max	0.2 to 0.4	
Tin	...	1.0 to 2.0	...
Tin	...	1.0 to 2.0	
Hydrogen, max	0.005	0.005	0.005
Hydrogen, max	0.005	0.005	
Nitrogen, max	0.025	0.025	0.025
Nitrogen, max	0.025	0.025	
Carbon, max	0.05	0.05	0.05
Carbon, max	0.05	0.05	
Niobium	...	...	2.0 to 3.0
Niobium	...	...	
Oxygen, max	0.46	0.48	0.48
Oxygen, max	0.16	0.18	

<sup>A</sup> By agreement between the purchaser and the manufacturer, analysis may be required and limits established for elements and compounds not specified in the table of chemical composition.

<sup>B</sup> The value for zirconium + hafnium, min, is a warranted but not a measured value.

**TABLE 2 Permissible Variation in Product Analysis Between Different Laboratories**

Element	Permissible Variation in Product Analysis, %
Hydrogen	0.002
Nitrogen	0.01
Carbon	0.01
Hafnium	0.1
Iron + chromium	0.025
Tin	0.05
Niobium	0.05
Oxygen	0.02

**TABLE 3 Tensile Requirements**

—	UNS Grade Designation		
	R60702	R60704	R60705
Tensile strength, min, ksi [MPa]	55 [380]	60 [415]	80 [550]
Tensile strength, min, ksi [MPa]	55 [380]	60 [415]	
Yield strength, min, ksi [MPa]	30 [205]	35 [240]	55 [380]
Yield strength, min, ksi [MPa]	30 [205]	35 [240]	
Elongation in 2 in. or 50 mm, min, %	46	44	46
Elongation in 2 in. or 50 mm, min, %	16	14	

iTech Standards

<https://standards.itih.ai>

Document Preview

7.3 When requested by the purchaser and stated in the purchase order, a product analysis for any elements listed in Table 1 shall be made on the finished product.

7.3.1 The manufacturer's analysis shall be considered as verified if the check analysis confirms the manufacturer's reported values within the tolerances prescribed in Table 2.

## 8. Tensile Requirements

8.1 The material, as represented by the test specimens, shall conform to the tensile properties prescribed in Table 3.

## 9. Permissible Variation in Dimensions

9.1 *Diameter*—At any point (cross section) along the length of the tube, the variation in outside diameter shall not exceed those prescribed in Table 4.

9.2 *Length*—When tubes are ordered cut to length, the length shall be not less than that specified, but a variation of 1/8 in. [3.2 mm] will be permitted on tube up to 10 ft [3 m], inclusive. For lengths over 10 ft, an additional over-tolerance of 1/8 in. [3.2 mm] for each 10 ft [3 m] or fraction thereof shall be permissible up to 1/2 in. [13 mm], maximum.

9.3 *Straightness*—The tube shall be free of bends or kinks and the maximum uniform bow shall not exceed the values shown in Table 5.

9.4 *Squareness of Cut*—The angle of cut of the end of any tube up to 1 1/2 in. [40 mm] in outside diameter may depart from square not more than 0.016 in./in. [mm/mm].

**TABLE 4 Permissible Variations in Outside Dimensions Based on Individual Measurements**

Outside Diameter, in. [mm]	Diameter Tolerance, in. [mm] <sup>A,B</sup>	Permissible Variations <sup>C</sup> in Wall Thickness, t, %
Under 1 [25], excl	±0.004 [±0.100]	10
Over 1 to 1 1/2 [25 to 40], incl	±0.005 [±0.125]	10
Over 1 1/2 to 2 [40 to 50], incl	±0.006 [±0.150]	10
Over 2 to 2 1/2 [50 to 65], incl	±0.007 [±0.180]	10
Over 2 1/2 to 3 1/2 [65 to 90], incl	±0.010 [±0.250]	10

<sup>A</sup> These permissible variations in outside diameter apply only to tubes as finished at the mill before subsequent swaging, expanding, bending, polishing, or other fabricating operations.

<sup>B</sup> Ovality is the maximum and minimum outside diameter of a tube measured at any one cross section. If the measurement is made with a ring gage, the following formula shall apply: Ovality = specified OD tube + diameter tolerance + 0.002 in. [.05 mm] (length of ring gage, 1 in. [25 mm] × specified tube OD).

<sup>C</sup> When minimum wall tubes are ordered, tolerances are all plus and shall be double the values shown.