



Standard Specification for Concentric-Lay-Stranded Aluminum 1350 Conductors¹

This standard is issued under the fixed designation B231/B231M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This specification covers aluminum 1350-H19 (extra hard), 1350-H16 or -H26 ($\frac{3}{4}$ hard), 1350-H14 or -H24 ($\frac{1}{2}$ hard), and 1350-H142 or -H242 ($\frac{1}{2}$ hard), bare concentric-lay-stranded conductors constructed with a straight round central wire surrounded by one or more layers of helically layed wires. The conductors are for general use for electrical purposes (Explanatory Note 1 and Note 2).

1.2 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.2.1 For density, resistivity and temperature, the values stated in SI units are to be regarded as standard.

NOTE 1—Prior to 1975, aluminum 1350 was designated as EC aluminum.

NOTE 2—The aluminum and temper designations conform to ANSI Standard H35.1/H35.1M. Aluminum 1350 corresponds to Unified Numbering System A91350 in accordance with Practice E527.

NOTE 3—Sealed conductors that are intended to prevent longitudinal water propagation and are further covered/insulated are also permitted within the guidelines of this specification.

2. Referenced Documents

2.1 The following documents of the issue in effect on date of material purchase form a part of this specification to the extent referenced herein:

2.2 ASTM Standards:²

B193 Test Method for Resistivity of Electrical Conductor Materials

B230/B230M Specification for Aluminum 1350–H19 Wire for Electrical Purposes

B263 Test Method for Determination of Cross-Sectional Area of Stranded Conductors

B354 Terminology Relating to Uninsulated Metallic Electrical Conductors

B609/B609M Specification for Aluminum 1350 Round Wire, Annealed and Intermediate Tempers, for Electrical Purposes

B682 Specification for Metric Sizes of Electrical Conductors

E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

E527 Practice for Numbering Metals and Alloys in the Unified Numbering System (UNS)

2.3 ANSI Documents:³

ANSI H35.1 American National Standard Alloy and Temper Designation System for Aluminum

ANSI H35.1M American National Standard Alloy and Temper Designation Systems for Aluminum [Metric]

2.4 NIST Document:⁴

NBS Handbook 100—Copper Wire Tables

2.5 Aluminum Association Document:⁵

Publication 50, Code Words for Overhead Aluminum Electrical Conductors

¹ This specification is under the jurisdiction of ASTM Committee B01 on Electrical Conductors and is the direct responsibility of Subcommittee B01.07 on Conductors of Light Metals.

Current edition approved April 1, 2011; June 1, 2012. Published May 2011; October 2012. Originally approved in 1948. Last previous edition approved in 20042011 as B231/B231M – 04; B231/B231M – 11. DOI: 10.1520/B0231_B0231M-11_10.1520/B0231_B0231M-12.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036.

⁴ Available from National Technical Information Service (NTIS), U.S. Department of Commerce, 5285 Port Royal Rd., Springfield, VA 22161.

⁵ Available from the Aluminum Association, Inc., 900 19th Street, NW, Suite 300, Washington, DC 20006.

3. Classification

3.1 For the purpose of this specification, conductors are classified as follows (Explanatory Note 1 and Note 2):

3.1.1 *Class AA*—For bare conductors usually used in overhead lines.

3.1.2 *Class A*—For conductors to be covered with weather-resistant materials, and for bare conductors where greater flexibility than is afforded by Class AA is required. Conductors intended for further fabrication into tree wire or to be insulated and laid helically with or around aluminum or ACSR messengers, shall be regarded as Class A conductors with respect to direction of lay only (see 7.4).

3.1.3 *Class B*—For conductors to be insulated with various materials such as rubber, paper, varnished cloth, and so forth, and for the conductors indicated under Class A where greater flexibility is required.

3.1.4 *Classes C and D*—For conductors where greater flexibility is required than is provided by Class B conductors.

4. Ordering Information

4.1 Orders for material under this specification shall include the following information:

4.1.1 Quantity,

4.1.2 Conductor size: square millimetres, if cross-sectional area is specified as a requirement (Section 8 and Tables 1-4),

4.1.2.1 Conductor size, number, and diameter of wires for Class B, C, or D conductors, if cross-sectional area is not specified as a requirement (see 8.2),

4.1.3 Class (see 3.1),

4.1.4 Temper (see 5.1),

4.1.5 Details of special-purpose lays, when required (see 7.2 through 7.5),

4.1.6 Special tension tests if required (see 14.1 and 15.1),

4.1.7 Package size and type (see 17.1 and Table 1 or Table 2),

4.1.8 Special package marking, if required (Section 19),

4.1.9 Heavy wood lagging, if required (see 18.2),

4.1.10 Place of inspection (Section 17), and

4.1.11 Method of cross-sectional area determination if not optional (see 12.1).

5. Requirements for Wires

(<https://standards.iteh.ai>)

5.1 Aluminum wire employed in Classes AA and A conductors shall be 1350-H19, unless otherwise specified. The purchaser shall designate the temper of conductors of Classes B, C, and D.

5.1.1 For conductor tempers other than 1350-H19, when temper designations are not more specific in the inquiry and purchase order, the manufacturer shall have the following options on manufacturing method:

5.1.1.1 Strand the conductor from wires drawn to final temper;

5.1.1.2 Strand the conductor from wires drawn to H19 temper and annealed to final temper prior to stranding;

5.1.1.3 Strand the conductor from 1350-H19 wires and anneal the stranded conductor to final temper.

5.2 Before stranding, the aluminum wire used shall meet the requirements of Specifications B230/B230M or B609/B609M, whichever is applicable.

5.3 All wires in the conductor shall be of the same temper.

6. Joints

6.1 Only cold-pressure joints or electric-butt, cold-upset joints may be made in the six outer finished wires of (1) Class AA conductors composed of seven wires or (2) Class A conductors composed of seven wires used in overhead lines. In other conductors, electric-butt welds, cold-pressure welds, or electric-butt, cold-upset welds may be made in the finished wires composing conductors, but such welds shall not be closer than prescribed in Table 5 (Explanatory Note 3).

7. Lay

7.1 For Class AA conductors composed of seven wires or more, the preferred lay of a layer of wires is 13.5 times the outside diameter of that layer, but the lay shall be not less than 10 nor more than 16 times this diameter.

7.2 For all other classes the lay of a layer of wires shall be not less than 8 nor more than 16 times the outside diameter of that layer, except that for conductors composed of 37 wires or more, this requirement shall apply only to the two outer layers. The lay of the layers other than the two outer layers shall be at the option of the manufacturer, unless otherwise agreed upon.

7.2.1 For conductors to be used in covered or insulated wires or cables, the lay length of the wires shall not be less than 8 nor more than 16 times the outer diameter of the finished conductor. For conductors of 37 wires or more, this requirement shall apply to the wires in the outer two layers. The lay of the layers other than the outer two layers shall be at the option of the manufacturer, unless otherwise agreed upon.

7.3 Other lays for special purposes shall be furnished by special agreement between the manufacturer and the purchaser (Explanatory Note 4).

**TABLE 1 Construction Requirements and Recommended Reel Sizes and Shipping Lengths of Aluminum Conductors, Concentric-Lay-Stranded, Class AA, and Class A**

NOTE 1—Metric values listed represent a soft conversion and as such they may not be the same as those masses which are calculated from the basic metric density.

Conductor Size			Required Construction				Mass		Rated Strength		Recommended Package Sizes ^A		
cmils ^B or AWG	mm ²	Code Words ^C	Class	Number of Wires	Diameter of Wire		Per 1000 ft, lb	Per km, kg	Kips	kN	Reel Designation ^D	Nominal Length of Each Piece, ft ^B	Nominal Mass of Each Length, lb ^B
					in.	mm							
3 500 000	1773	Bluebonnet	A	127	0.1660	4.22	3345	4977	58.7	261	RMT 90.45	2840	9530
3 000 000	1520	Trillium	A	127	0.1537	3.90	2840	4226	50.3	223	RMT 90.45	3350	9530
2 750 000	1393	Bitterroot	A	91	0.1738	4.42	2602	3872	46.1	205	RMT 90.45	3490	9100
2 500 000	1267	Lupine	A	91	0.1657	4.21	2365	3519	41.9	186	RMT 90.45	3840	9100
2 250 000	1140	Sagebrush	A	91	0.1572	3.99	2128	3166	37.7	167	RMT 90.45	4270	9100
2 000 000	1013	Cowslip	A	91	0.1482	3.77	1873	2787	34.2	153	RMT 90.45	4850	9100
1 750 000	886.7	Jessamine	AA	61	0.1694	4.30	1641	2442	29.7	132	RMT 90.45	5940	9760
1 590 000	805.7	Coreopsis	AA	61	0.1614	4.10	1489	2216	27.0	120	RMT 90.45	6540	9760
											RM 68.38	3270	4880
1 510 500	765.4	Gladiolus	AA, A	61	0.1574	4.00	1417	2108	25.6	114	RMT 90.45	6880	9760
1 431 000	725.1	Carnation	AA, A	61	0.1532	3.89	1342	1997	24.3	108	RMT 90.45	7270	9760
1 351 000	694.8	Globemallow	—AA, A	—61	0.1488	3.78	1266	1884	23.4	104	RMT 90.45	7690	9760
1 351 000	684.6	Columbine	AA, A	61	0.1488	3.78	1266	1884	23.4	104	RM 68.38	3845	4880
1 272 000	644.5	Narcissus	AA, A	61	0.1444	3.67	1192	1774	22.0	98.1	RMT 90.45	8170	9760
1 192 500	604.2	Hawthorn	AA, A	61	0.1398	3.55	1117	1662	21.1	93.5	RMT 90.45	9340	9760
1 113 000	564.0	Marigold	AA, A	61	0.1351	3.43	1044	1553	19.7	87.3	RMT 90.45	9340	9760
1 033 500	523.7	Bluebell	AA	37	0.1671	4.25	968.4	1441	17.7	78.8	RMT 84.45	7630	7400
1 033 500	523.7	Larkspur	A	61	0.1302	3.31	969.2	1442	18.3	81.3	RM 66.32	3815	3700
1 000 000	506.7	Hawkweed	AA	37	0.1644	4.18	937.3	1395	17.2	76.2	NR 48.28	1910	1850
1 000 000	506.7	Camellia	A	61	0.1280	3.25	936.8	1394	17.7	78.3	RMT 90.45	10 060	9760
954 000	483.4	Magnolia	AA	37	0.1606	4.08	894.5	1331	16.4	72.6	RMT 84.45	8260	7400
954 000	483.4	Goldenrod	A	61	0.1251	3.18	894.8	1331	16.9	75.0	RM 66.32	4130	3700
900 000	456.0	Cockscomb	AA	37	0.1560	3.96	844.0	1256	16.4	68.4	NR 48.28	2065	1850
900 000	456.0	Snapdragon	A	61	0.1215	3.09	844.0	1256	15.9	70.8	RMT 90.45	5200	4880
795 00	402.8	Arbutus	AA	37	0.1466	3.72	745.3	1109	13.9	61.8	RMT 84.45	8760	7400
795 000	402.8	Lilac	A	61	0.1142	2.90	745.7	1110	14.3	63.8	RM 66.32	4390	3700
750 000	380.0	Petunia	AA	37	0.1424	3.62	703.2	1046	13.1	58.6	NR 48.28	2190	1850
750 000	380.0	Cattail	A	61	0.1109	2.82	703.2	1046	13.5	60.3	RMT 84.45	5775	4880
715 500	362.6	Violet	AA	37	0.1391	3.53	671	998.5	12.8	56.7	RM 66.32	9920	7400
715 500	362.6	Nasturtium	A	61	0.1083	2.75	671	998.5	13.1	58.4	NR 48.28	5510	3700
700 000	354.7	Verbena	AA	37	0.1375	3.49	655.7	975.7	12.5	55.4	RMT 84.45	2755	1850
700 000	354.7	Flag	A	61	0.1071	2.72	655.8	975.8	12.9	57.1	RMT 90.45	14 530	9760
650 000	329.4	Heuchera	AA	37	0.1326	3.37	609.8	907.4	11.6	51.7	RM 66.32	5630	3700
											NR 48.28	6065	1850
											NR 48.28	3035	1850

TABLE 1 *Continued*

Conductor Size				Required Construction			Mass		Rated Strength		Recommended Package Sizes ^A		
cmils ^B or AWG	mm ²	Code Words ^C	Class	Number of Wires	Diameter of Wire in. mm	Per 1000 ft, lb	Per km, kg	kips	kN	Reel Designation ^D	Nominal Length of Each Piece, ft ^B	Nominal Mass of Each Length, lb ^B	
636 000	322.3	Orchid	AA, A	37	0.1311	3.33	596.0	886.9	11.4	50.4	RMT 84.45	12 400	7400
											RM 66.32	6200	3700
											NR 48.28	3100	1850
600 000	304.0	Meadowsweet	AA, A	37	0.1273	3.23	562.0	836.3	10.7	47.5	RMT 84.45	13 140	7400
											RM 66.32	6570	3700
											NR 48.28	3285	1850
556 500	282.0	Dahlia	AA	19	0.1711	4.35	521.4	775.8	9.75	43.3	RM 66.32	7270	3800
											NR 48.28	3635	1900
											NR 42.28	2425	1265
556 500	282.0	Mistletoe	A	37	0.1226	3.12	521.3	775.7	9.94	44.3	RMT 84.45	14 170	7400
											RM 66.32	7085	3700
											NR 48.28	3545	1850
500 000	253.3	Zinnia	AA	19	0.1622	4.12	468.5	697.1	8.76	38.9	RM 66.32	8100	3800
											NR 48.28	4050	1900
											NR 42.28	2700	1265
500 000	253.3	Hyacinth	A	37	0.1162	2.95	468.3	696.8	9.11	40.5	RMT 84.45	15 760	7400
											RM 66.32	7880	3700
											NR 48.28	3940	1850
477 000	241.7	Cosmos	AA	19	0.1584	4.02	446.8	664.8	8.36	37.0	RM 66.32	8490	3800
											NR 48.28	4245	1900
											NR 42.28	2830	1265
477 000	241.7	Syringa	A	37	0.1135	2.88	446.8	664.8	8.69	38.6	RMT 84.45	16 530	7400
											RM 66.32	8265	3700
											NR 48.28	4135	1850
450 000	228.0	Goldentuft	AA	19	0.1539	3.91	421.8	627.6	7.89	35.0	RM 66.32	9000	3800
											NR 48.28	4500	1900
											NR 42.28	3000	1265
397 500	201.4	Canna	AA, A	19	0.1447	3.67	372.9	554.9	7.11	31.6	RM 66.32	10 180	3800
											NR 48.28	5090	1900
											NR 42.28	3395	1265
350 000	177.3	Daffodil	A	19	0.1357	3.45	327.9	487.9	6.39	28.4	RM 66.32	11 560	3800
											NR 48.28	5780	1900
											NR 42.28	3855	1265
336 400	170.5	Tulip	A	19	0.1331	3.38	315.5	469.5	6.15	27.3	RM 66.32	12 030	3800
											NR 48.28	6015	1900
											NR 42.28	4010	1265
300 000	152.0	Peony	A	19	0.1257	3.19	281.4	418.3	5.48	24.3	RM 66.32	13 490	3800
											NR 48.28	6745	1900
											NR 42.28	4495	1265
266 800	135.2	Daisy	AA	7	0.1953	4.96	250.2	372.3	4.83	21.4	RM 66.32	5590	1400
											NR 36.22	2795	700
											NR 36.22	2795	700
266 800	135.2	Laurel	A	19	0.1185	3.01	250.1	372.2	4.97	22.1	RM 66.32	15 170	3800
											NR 48.28	7585	1900
											NR 42.28	5055	1265
250 000	126.7	Sneezewort	AA	7	0.1890	4.80	234.4	348.8	4.52	20.1	NR 42.28	5970	1400
											NR 36.22	2985	700
250 000	126.7	Valerian	A	19	0.1147	2.91	234.3	348.6	4.66	20.7	RM 66.32	16 190	3800
											NR 48.28	8095	1900
											NR 42.28	5395	1265
4/0	107.2	Oxlip	AA, A	7	0.1739	4.42	198.4	295.2	3.83	17.0	NR 42.28	7050	1400
											NR 36.22	3525	700
3/0	85.0	Phlox	AA, A	7	0.1548	3.93	157.2	233.9	3.04	13.5	NR 42.28	8890	1400
											NR 36.22	4445	700
2/0	67.4	Aster	AA, A	7	0.1379	3.50	124.8	185.7	2.51	11.1	NR 42.28	11 210	1400
											NR 36.22	5605	700
1/0	53.5	Poppy	AA, A	7	0.1228	3.12	98.9	147.2	1.99	8.84	NR 42.28	14 130	1400
											NR 36.22	7065	700
1	42.4	Pansy	AA, A	7	0.1093	2.78	78.4	116.6	1.64	7.30	NR 42.28	17 830	1400
											NR 36.22	8915	700
2	33.6	Iris	AA, A	7	0.0974	2.47	62.2	92.6	1.35	5.99	NR 42.28	22 470	1400
											NR 36.22	11 235	700
4	21.1	Rose	A	7	0.0772	1.96	39.1	58.2	0.881	3.91	NR 42.28	35 710	1400
											NR 36.22	17 855	700
6	13.3	Peachbell	A	7	0.0612	1.56	24.6	36.6	0.563	2.53	NR 42.28	56 910	1400
											NR 36.22	28 455	700

^A For information only.^B Conversion factors: 1 cmil = 5.067 E-04 mm², 1 mil + 2.54 E-02 mm, 1 lb/1000 ft = 1.488 E+00 kg/km, 1 ft = 3.048 E-01 m, 1 lb = 4.536 E-01 kg, 1 lbf = 4.448 E-03 kN.^C Code words shown in this column are from, "Publication 50, Code Words for Overhead Aluminum Electrical Conductors," by the Aluminum Association. They are provided here for information only.

^D See Table 9 for dimensions of standard reels.

7.4 The direction of lay of the outer layer shall be right-hand for Classes AA and A and left-hand for other classes, unless the direction of lay is specified otherwise by the purchaser.

7.5 The direction of lay for conductors having a nominal cross-sectional area larger than No. 8 AWG (8 mm^2) shall be reversed in successive layers, unless otherwise specified by the purchaser.

7.5.1 For conductors to be used in covered or insulated wires or cables, the direction of lay of the outer layer shall be left hand and may be reversed or unidirectional/unilay in successive layers, unless otherwise agreed upon with the purchaser.

8. Construction

8.1 The areas of cross section, numbers, and diameters of wires in the various classes of concentric-lay-stranded conductors shall conform to the requirements prescribed in **Tables 1-4**. Sizes ~~1050;1100~~, 1200, and 1250 kcmil, Class B concentric-lay-stranded conductors may have 61 wires subject to mutual agreement between the manufacturer and customer.

8.2 The diameters of the wires listed in **Tables 3 and 4** are nominal. Where “combination strand” is required in order to insulate the conductor properly, wires of different diameters may be used provided that the area of cross section after stranding is in accordance with Section 12.

8.3 Where compressed stranding is required in order to insulate the conductor properly, one or more layers of any stranded conductor consisting of 7 wires or more may be slightly compressed, thereby reducing the outside diameter of the conductor to the nominal values shown in **Table 3** or **Table 4**, provided that the area of cross section after compressing is in accordance with Section 12.

8.3.1 The average diameter of the conductor in 8.3 shall vary by not more than +1 or -2 % from the diameter specified in **Table 3** or **Table 4**.

8.4 The nominal overall diameter of a Class A and AA stranded conductor shall be calculated based on the numerical sum of the diameter thickness of the individual strand wire component in the conductor. The diameter of the individual strand wire component shall be as specified in **Table 1** and **Table 2** and this diameter shall be referred to as the “mean diameter” value. The minimum and maximum overall diameter of a Class A and AA stranded conductor shall be based on calculations made using the mean diameter tolerances as specified by Specification **B230/B230M** for the corresponding strand wire size.

9. Rated Strength of Conductor

9.1 The rated strength of 1350-H19 conductors shall be taken as the percent, indicated in **Table 6**, of the sum of the strengths of the component wires, calculated using the nominal wire diameters and the specified minimum average tensile strength given in Specification **B230/B230M** for 1350-H19 wire. In the case of compressed conductors, the nominal wire diameter should be that of the corresponding non-compressed construction as listed in **Tables 1-4**.

9.2 Calculations for rated strengths of 1350-H16, -H26, -H14, -H24, -H142, and -H242 conductors shall be made on the basis of the strengths of the component wires using the nominal wire diameters and the specified maximum and minimum tensile strengths for the appropriate temper of the respective component wires given in Specification **B609/B609M**. The minimum rated strengths of the conductors shall be taken as the sum of the calculated minimum strengths of the component wires multiplied by the rating factor given in **Table 6**. The maximum rated strength of the conductors shall be taken as the sum of the calculated maximum strengths of the component wires.

9.3 Rated-strength and breaking-strength values shall be rounded to three significant figures, in the final value only, in accordance with the rounding method of Practice **E29**.

9.4 Rated strengths of conductors are given in **Table 1** or **Table 2**.

10. Density

10.1 For the purpose of calculating mass, cross sections, and so forth, the density of aluminum 1350 shall be taken as 2705 kg/m^3 [0.0975 lb/in.³] at 20°C.

11. Mass and Electrical Resistance

11.1 The mass and electrical resistance of a unit length of a stranded conductor are a function of the length of lay. The approximate mass and electrical resistance may be determined using the standard increments shown in **Table 7**. When greater accuracy is desired, the increment based on the specific lay of the conductor may be calculated (Explanatory **Note 5**).

11.2 The maximum electrical resistance of a unit length of stranded conductor shall not exceed 2 % over the nominal dc resistance shown in **Tables 3 and 4** (Explanatory **Note 8**). When the dc resistance is measured at other than 20°C, it is to be corrected by using the multiplying factor given in **Table 8**.

**TABLE 2 Construction Requirements and Recommended Reel Sizes and Shipping Lengths of Aluminum Conductors, Concentric Lay-Stranded, Classes AA and A**

NOTE 1—Sizes selected from Specification B682.

Conductor Size, mm ²	Class	Stranding		Mass, kg/km	Rated Strength 1350-H19, kN	Recommended Package Sizes ^A		
		Number of Wires	Diameter, mm			Reel Designation ^B	Nominal Length of Each Piece, m	Nominal Mass of Each Length, kg
2000	A	127	4.48	5632	294	RMT 90.45	770	4325
1600	A	127	4.01	4512	236	RMT 90.45	960	4325
1250	A	91	4.18	3479	183	RMT 90.45	1185	4130
1120	A	91	3.96	3123	165	RMT 90.45	1320	4130
1000	A	91	3.74	2785	151	RMT 90.45	1495	4130
900	AA	61	4.33	2478	133	RMT 90.45	1785	4425
800	AA, A	61	4.09	2211	119	RMT 90.45	2000	4425
						RM 68.38	1000	2215
710	AA, A	61	3.85	1959	105	RMT 90.45	2260	4425
						RM 68.38	1130	2215
630	AA, A	61	3.63	1742	96.6	RMT 90.45	2540	4425
						RM 68.38	1270	2215
560	AA, A	61	3.42	1546	85.7	RMT 90.45	2860	4425
						RM 68.38	1430	2215
500	AA	37	4.15	1381	75.1	RMT 84.45	2430	3355
						RM 66.32	1215	1680
						NR 48.28	610	840
500	A	61	3.23	1379	76.5	RMT 90.45	3210	4425
						RM 68.38	1605	2215
450	AA	37	3.94	1245	67.7	RMT 84.45	2695	3355
						RM 66.32	1350	1680
						NR 48.28	675	840
450	A	61	3.06	1238	68.6	RMT 90.45	3575	4425
						RM 68.38	1790	2215
400	AA	37	3.71	1104	61.9	RMT 84.45	3040	3355
						RM 66.32	1520	1680
						NR 48.28	760	840
400	A	61	2.89	1104	63.0	RMT 90.45	4010	4425
						RM 68.38	2005	2215
355	AA	37	3.50	982	55.1	RMT 84.45	3415	3355
						RM 66.32	1710	1680
						NR 48.28	855	840
355	A	61	2.72	978	57.4	RMT 90.45	4525	4425
						RM 68.38	2265	2215
315	AA, A	37	3.29	868	48.7	RMT 84.45	3865	3355
						RM 66.32	1935	1680
						NR 48.28	970	840
280	AA	19	4.33	772	42.9	RMT 84.45	2235	1725
						NR 48.28	1115	860
						NR 42.28	745	575
280	A	37	3.10	771	43.2	RMT 84.45	4350	3355
						RM 66.32	2180	1680
						NR 48.28	1090	840
250	AA	19	4.09	689	38.3	RMT 84.45	2505	1725
						NR 48.28	1250	860
						NR 42.28	835	575
250	A	37	2.93	688	39.7	RMT 84.45	875	3355
						RM 66.32	2440	1680
						NR 48.28	1220	840
224	AA	19	3.87	617	34.3	RMT 84.45	2795	1725
						NR 48.28	1395	860
						NR 42.28	930	575
200	AA, A	19	3.66	552	31.6	RMT 84.45	3125	1725
						RM 66.32	1560	860
						NR 48.28	1040	575
180	A	19	3.47	496	28.4	RMT 84.45	3480	1725
						RM 66.32	1730	860
						NR 48.28	1160	575
160	A	19	3.27	440	25.2	RMT 84.45	3920	1725
						NR 48.28	1955	860
						NR 42.28	1305	575
140	AA	7	5.05	387.0	22.2	RMT 84.45	1640	635
						NR 42.28	830	320
140	A	19	3.06	386	22.1	RMT 84.45	4470	1725
						NR 48.28	2230	860
						NR 42.28	1490	575
125	AA	7	4.77	345	19.8	RMT 84.45	1840	635
						NR 36.22	930	320