

ISO/TC 45/SC 1

Secretariat: DIN

Voting begins on:
2021-12-03

Voting terminates on:
2022-01-28

Rubber and plastics hoses and hose assemblies — Methods of measurement of the dimensions of hoses and the lengths of hose assemblies

*Tuyaux et flexibles en caoutchouc et en plastique — Méthodes de
mesurage des dimensions des tuyaux et de la longueur des flexibles*
(standards.iteh.ai)

ISO/FDIS 4671

<https://standards.iteh.ai/catalog/standards/sist/539519ca-7199-4d0d-8c15-b48dc9c2d951/iso-fdis-4671>

ISO/CEN PARALLEL PROCESSING

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.



Reference number
ISO/FDIS 4671:2021(E)

© ISO 2021

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO/FDIS 4671

<https://standards.iteh.ai/catalog/standards/sist/539519ca-7199-4d0d-8c15-b48dc9c2d951/iso-fdis-4671>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2021

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword.....	v
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	1
4 Test piece conditioning and temperature of measurement.....	1
4.1 Conditioning of test pieces.....	1
4.2 Measurement temperature.....	1
5 Measurement of inside diameter.....	2
5.1 General.....	2
5.2 Method 1.....	2
5.3 Method 2.....	2
5.4 Method 3.....	2
5.5 Method 4.....	3
5.6 Method 5.....	3
5.7 Method 6.....	3
5.8 Method 7.....	3
6 Measurement of outside diameter.....	3
6.1 General.....	3
6.2 Method 1.....	3
6.3 Method 2.....	3
6.4 Method 3.....	3
6.5 Method 4.....	4
6.6 Method 5.....	4
7 Measurement of diameter over reinforcement.....	4
8 Measurement of wall thickness.....	4
8.1 General.....	4
8.2 Method 1.....	4
8.3 Method 2.....	4
8.4 Method 3.....	5
8.5 Method 4.....	5
9 Measurement of concentricity.....	5
9.1 General.....	5
9.2 Method 1.....	5
9.3 Method 2.....	6
9.4 Method 3.....	6
9.5 Method 4.....	6
9.6 Method 5.....	6
10 Measurement of lining and cover thickness.....	6
10.1 General.....	6
10.2 Method 1.....	6
10.3 Method 2.....	7
10.4 Method 3.....	8
11 Measurement of length and identification of measurement points.....	8
11.1 Measurement of length.....	8
11.2 Measurement points.....	8
11.2.1 Hoses.....	8
11.2.2 Hose assemblies.....	8
12 Verification of through-bore of hose assemblies.....	10
13 Test report.....	10

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO/FDIS 4671](https://standards.iteh.ai/catalog/standards/sist/539519ca-7199-4d0d-8c15-b48dc9c2d951/iso-fdis-4671)

<https://standards.iteh.ai/catalog/standards/sist/539519ca-7199-4d0d-8c15-b48dc9c2d951/iso-fdis-4671>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html (standards.iteh.ai)

This document was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 1, *Rubber and plastics hoses and hose assemblies*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 218, *Rubber and plastics hoses and hose assemblies*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This fourth edition cancels and replaces the third edition (ISO 4671:2007), which has been technically revised. It also incorporates the Amendment ISO 4671:2007/Amd 1:2011. The main changes are as follows:

- permissions (using the term “may”) have been changed to requirements (using the term “shall”) throughout the document along with resultant modified text;
- the position at which the outside diameter is measured has been clarified;
- [Clause 3](#) has been added.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO/FDIS 4671

<https://standards.iteh.ai/catalog/standards/sist/539519ca-7199-4d0d-8c15-b48dc9c2d951/iso-fdis-4671>

Rubber and plastics hoses and hose assemblies — Methods of measurement of the dimensions of hoses and the lengths of hose assemblies

1 Scope

This document specifies methods of measuring the inside diameter, outside diameter (including diameter over reinforcement of hydraulic hoses), wall thickness, concentricity and lining and cover thickness of hoses, methods of measurement and identification of the lengths of hoses and hose assemblies, and a method of verifying the through-bore of hydraulic hose assemblies.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 3611, *Geometrical product specifications (GPS) — Dimensional measuring equipment: Micrometers for external measurements — Design and metrological characteristics*

ISO 8330, *Rubber and plastics hoses and hose assemblies — Vocabulary*

ISO 13385-1, *Geometrical product specifications (GPS) — Dimensional measuring equipment — Part 1: Design and metrological characteristics of callipers* 4671

<https://standards.iteh.ai/catalog/standards/sist/539519ca-7199-4d0d-8c15-b48dc9c2d951/iso-fdis-4671>

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 8330 apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

4 Test piece conditioning and temperature of measurement

4.1 Conditioning of test pieces

Unless otherwise specified, test pieces shall be taken at least 16 h after manufacture of the hose and conditioned at 23_{-3}^{+7} °C for at least 3 h before measurement. This 3 h shall be included in the 16 h.

4.2 Measurement temperature

Unless otherwise specified, the measurement temperature shall be 23_{-3}^{+7} °C.

5 Measurement of inside diameter


5.1 General

Measurements by methods 1 to 7 shall be made either on the ends of a full length of hose or on a test piece (minimum length 150 mm) cut from a full length. For wire-reinforced hydraulic hoses, measurements shall be made at a minimum distance of 25 mm from the end of the hose.

Measurements shall be made using one of the following methods, as appropriate.

5.2 Method 1

This method is applicable for inside diameters less than 150 mm and for all sizes of collapsible hose. Use plug gauges with 0,25 mm increments in diameter (see Figure 1) and tapered gauges with 0,1 mm increments in diameter (see Figure 2). Insert the gauge into the hose test piece gently without pressure. Take special care if the hose bore is not precisely circular.



(standards.iteh.ai)
Figure 1 — Plug gauges




Figure 2 — Tapered gauges

5.3 Method 2

This method is applicable for inside diameters less than 63 mm, where greater accuracy is required, e.g. for wire-reinforced hydraulic hoses. Use an expanding ball or telescopic gauge.

5.4 Method 3

This method is applicable for all inside diameters up to and including 100 mm. Use the internal jaws of vernier slide callipers conforming to the requirements of ISO 13385-1. Make two measurements at right angles to each other and take their average as the inside diameter. Take care not to distort the hose when making the measurements. Use callipers of suitable size for inside diameter above 100 mm when greater accuracy than is obtainable by method 5 (see 5.6) is required.

5.5 Method 4

This method is applicable for all inside diameters. Use an internal calliper dial gauge (see ISO 463) with rounded feet designed for use in bores made of elastomeric material, a calliper size being chosen which is suitable for the inside diameter to be measured. Make two measurements at right angles to each other and take their average as the inside diameter.

5.6 Method 5

This method is applicable for inside diameters above 100 mm. Use a graduated steel rule to obtain a sufficient degree of accuracy for normal purposes. Alternatively, digital callipers or a digital micrometer can be used. Make two measurements at right angles to each other and take their average as the inside diameter.

5.7 Method 6

For suitable diameters, and where the hose cross-section has not been distorted by the cutting operation, use an optical magnifier with a scale graduated in 0,1 mm divisions. Make two measurements at right angles to each other and take their average as the inside diameter.

5.8 Method 7

For inside diameters above 300 mm, a sufficient degree of accuracy for normal purposes is obtained by measuring the inside circumference of the hose with a measuring tape. A pi-tape, graduated to give the diameter directly, should be used. Alternatively, use a measuring tape graduated in centimetres. The inside diameter is obtained by dividing the measured value by pi (π).

6 Measurement of outside diameter

<https://standards.iteh.ai/catalog/standards/sist/539519ca-7199-4d0d-8c15-b48dc9c2d951/iso-fdis-4671>

6.1 General

Measurements made by methods 1 to 5 shall be made either on a full length of hose or on a test piece (minimum length 150 mm) cut from a full length. Measurements shall be made at a minimum distance of 25 mm from the ends of the hose in methods 1, 2, 3 and 5 and at the end of the hose in method 4. If the cover is fluted or corrugated, measurements shall be made at the top of an outward-projecting part of the cover.

Measurements shall be made using one of the following methods, as appropriate.

6.2 Method 1

This method is applicable for outside diameters up to and including 100 mm. Use a vernier slide callipers, or a micrometer conforming to the requirements of ISO 3611. Make two measurements at right angles to each other and take their average as the outside diameter. Take care to avoid distorting the hose when making the measurements. When greater accuracy is required, place the test piece on a mandrel of outside diameter equal to the hose inside diameter to prevent distortion.

6.3 Method 2

This method is applicable for outside diameters over 20 mm. Use a vernier stepped pi-tape.

6.4 Method 3

For outside diameters over 100 mm, a sufficient degree of accuracy for normal purposes is obtained by measuring the outside circumference of the hose with a measuring tape. A pi-tape, graduated to give the diameter directly, should be used. Alternatively, use a measuring tape graduated in centimetres. The inside diameter is obtained by dividing the measured value by pi (π).

6.5 Method 4

For suitable diameters, and where the hose cross-section has not been distorted by the cutting operation, use an optical magnifier with a scale graduated in 0,1 mm divisions. Alternatively, use a laser measuring device. Make two measurements at right angles to each other and take their average as the outside diameter.

6.6 Method 5

For all outside diameters, use laser micrometers. Make two measurements at right angles to each other and take their average as the outside diameter.

7 Measurement of diameter over reinforcement

Measurement of the diameter over reinforcement is normally confined to hydraulic hoses in connection with the fitting of couplings and shall be carried out on a test piece cut from the hose.

Make measurements in accordance with [6.2](#) or [6.3](#), after completely removing the cover material.

8 Measurement of wall thickness

8.1 General

Where knowledge of the wall thickness is required, it is normally sufficient to calculate this by taking half the difference between the outside and inside diameters. Alternatively, the wall thickness can be measured directly using one of the following methods. The readings shall be taken at the end of the hose test piece for methods 1 and 4 and at a minimum distance of 15 mm from the end of the hose test piece for methods 2 and 3.

[ISO/FDIS 4671](#)

<https://standards.iteh.ai/catalog/standards/sist/539519ca-7199-4d0d-8c15-b48dc9c2d951/iso-fdis-4671>

8.2 Method 1

Use vernier slide callipers, taking care to avoid errors due to curvature.

8.3 Method 2

Use a micrometer with a rounded anvil contacting the inside of the hose, or a dial gauge using an arrangement similar to that shown in [Figure 3](#).