



Designation: D4670 – 07 (Reapproved 2012)^{ε1}

Standard Test Method for Polyurethane Raw Materials: Determination of Suspended Matter In Polyols ¹

This standard is issued under the fixed designation D4670; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

^{ε1} NOTE—Reapproved with editorial changes in August 2012.

1. Scope*

1.1 This test method covers a procedure for visual inspection to determine the presence of insoluble foreign material in polyols.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

NOTE 1—There is no known ISO equivalent to this standard.

2. Referenced Documents

2.1 *ASTM Standards:*²
[D883 Terminology Relating to Plastics](#)

¹ This test method is under the jurisdiction of ASTM Committee D20 on Plastics and is the direct responsibility of Subcommittee D20.22 on Cellular Materials - Plastics and Elastomers. It was recommended to ASTM by the Center for the Polyurethanes Industry Polyurethane Raw Material Analysis Workgroup.

Current edition approved Aug. 1, 2012. Published November 2012. Originally approved in 1987. Last previous edition approved in 2007 as D4670 – 07. DOI: 10.1520/D4670-07R12E01.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

3. Terminology

3.1 Terminology in this test method is in accordance with Terminology D883.

4. Significance and Use

4.1 This test method is suitable as a quality control or specification test.

5. Procedure

5.1 Invert a colorless, transparent glass bottle containing the well-mixed sample and examine by transmitted light for the presence of suspended matter.

6. Report

6.1 Report the presence or absence of suspended matter.

7. Precision and Bias

7.1 No statement is made about the precision or the bias since this test method merely states whether there is conformance to the criteria for success specified in the procedure.

8. Keywords

8.1 polyols; polyurethane raw materials; suspended matter

SUMMARY OF CHANGES

Committee D20 has identified the location of selected changes to this standard since the last issue (D4670 – 07) that may impact the use of this standard. (August 1, 2012)

(1) Modified Note 1 to be meet the requirements of Guide D4968.

(2) Updated footnote 1 to include the current name for the polyurethane division under the American Chemistry Council and for the current name of the work group.

*A Summary of Changes section appears at the end of this standard