ISO TC 17/SC 3

Secretariat: AFNOR

Date: 2023-05-03

Structural steels — Part 5: Technical delivery conditions for structural steels with improved atmospheric corrosion resistance

Aciers de construction —Partie 5: Conditions techniques de livraison pour aciers de construction à résistance améliorée à la corrosion atmosphérique

iTeh Standards (https://standards.iteh.ai) Document Preview

ISO 630-5

https://standards.iteh.ai/catalog/standards/sist/c6b5e30a-ab03-4ac8-a249-9f688f1ca7fd/iso-630-5

Edited DIS MUST BE USED
FOR FINAL
DRAFT

© ISO 2023

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office

CP 401 • Ch. de Blandonnet 8

CH-1214 Vernier, Geneva

Phone: +41 22 749 01 11

Email: copyright@iso.org

Website: www.iso.org
Published in Switzerland

iTeh Standards (https://standards.iteh.ai) Document Preview

ISO 630-5

https://standards.iteh.ai/catalog/standards/sist/c6b5e30a-ab03-4ac8-a249-9f688f1ca7fd/iso-630-5

Edited DIS MUST BE USED
FOR FINAL 150 2023 - All rights reserved
DRAFT

Contents

Forev	/ordiv		
1	Scope1		
2	Normative references1		
3	Terms and definitions1		
4	Classification and designation2		
4.1	Classification 2		
4.2	Designation (grades and qualities)2		
4.3	Normative annexes2		
5	Information to be supplied by purchaser2		
5.1	Mandatory information 2		
5.2	Options 2		
6	Requirements 3		
6.1	Steelmaking process		
6.2	Delivery condition 3		
6.3	-Chemical composition		
	Heat analysis		
	Product analysis		
6.3.3	Carbon equivalent value		
6.4	Mechanical properties 3		
6.4.1	Tensile properties 3 Charpy V-notch impact properties 3	Ш	
6.5	Surface conditions 3		
6.6	Internal soundness 3	77	
6.7	Dimensions, tolerances on dimensions and shape, mass	V	
7	Inspection 4		
,	Sampling — Frequency of testing		
8			
8.1	Verification 4 Test units 4	-a2	
	Annex A 4		
8.2.2			
0.2.2	Test methods 4		
y			
10	Marking 4		
Anne	x A (normative) Steel grades S235, S295, S355, S420, S460, S500, S550: Chemical		
	composition and mechanical properties		
Anne	RB (normative) Steel grades SG245, SG345, SG365, SG400, SG460, SG500, SG700:		
	Chemical composition and mechanical properties		
Anne	x C (informative) Notes on weldability18		
Annor	D (informative) A Fig. 1 to tied for thou Cotool with improved		
mme	CD (informative) Ad Ition hor Oat Of for how exsteel with improved atmospheric corresion resistance		
	graphy		
DIUIIU	MICT RELICED 20 Fore		
	word Vice District Vice Distri		
	EOD EINIAI		
© ISO	2023 - All rights reserved ORFINAL	ii	i
	DDVL		
	DRAFT		

	Scope	I	
2	Normative references	1	
3	Terms and definitions	1	
4			
<u>4</u> 4.1	Classification and designation		
4.2	Classification Designation (grades and qualities)	2	
4.4			
<u>5</u>	Information to be supplied by purchaser		
5.1	_Mandatory information		
<u>5.2</u>	<u>Options</u>	2	
6	Requirements	3	
6.1	Steelmaking process		
6.2	Delivery condition		
6.3	Chemical composition	3	
<u>6.3.1</u>	Heat analysis		
6.3.2	Product analysis	3	
6.3.3	_Carbon equivalent value		
<u>6.4</u>	Mechanical properties		
6.4.1	_Tensile properties		
	Charpy V-notch impact properties		
<u>6.5</u>	Surface conditions		
6.6	Internal soundness.	3	
<u>6.7</u>	Dimensions, tolerances on dimensions and shape, mass		
7	<u>Inspection</u>	4	
8	Sampling — Frequency of testing	4-	
8.1	Verification	4	
8.2	Test units		
8.2.1	Annex A		
8.2.2	Annex B.		
0	Test methods		
<u>, </u>			
<u>10</u>	_Marking		
Annex	A (normative) Steel grades S235, S295, S355, S420, S460, S500, S550: Chemical		
	composition and mechanical properties	<u>5</u>	
Annes	<u>s B (normative) Steel grades SG245, SG345, SG365, SG400, SG460, SG500, SG700:</u>		
Annex	Chemical composition and mechanical properties	12	
Annex	C (informative) Notes on weldability	18	
Annex	D (informative) Additional information for the use of steel with improved		
	atmospheric corrosion resistance	19	
Dibli-	granhy	20	

Edited DISMUST BE USED FOR FINAL 0 2023 - All rights reserved DRAFT

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives/.

Attention is drawn ISO draws attention to the possibility that some of the elements implementation of this document may be involve the subjectuse of (a) patent(s). ISO takes no position concerning the evidence validity or applicability of any claimed patent rights, in respect thereof. As of the date of publication of this document, ISO had received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declaration received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 17, Steel, Subcommittee SC 3, steels for structural purposes.

This second edition cancels and replaces the first edition (ISO 630-5:2014), which has been technically revised.

The main changes compared to the previous edition are as follows:

- grades S295W, S355WSE, S420W, S460W, S500W, S550W and pertaining requirements have been added;
- applicable thickness ranges have been added in the scope;
- terms and definitions conderwing heat treatments have been deleted because defined in ISO 630-1;
- quality E (impact testing at -40%) has been added;
- list of options has been integrated in ISO 630-1,

© ISO 2023 - All rights reserved OR FINAL DRAFT

- test units have been updated;
- bibliography has been updated;
- the content of the document has been updated to harmonize with the other parts of the ISO 630 series.

A list of all parts in the ISO 630 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

iTeh Standards (https://standards.iteh.ai) Document Preview

ISO 630-5

https://standards.iteh.ai/catalog/standards/sist/c6b5e30a-ab03-4ac8-a249-9f688f1ca7fd/iso-630-5

Edited DIS MUST BE USED
FOR FINAL 150 2023 - All rights reserved
DRAFT

Introduction

The International Organization for Standardization (ISO) draws attention to the fact that it is claimed that compliance with this document may involve the use of a patent concerning steel grade \$3355WSE given

in Annex A.

ISO takes no position concerning the evidence, validity and scope of this patent right.

The holder of this patent right has assured ISO that he/she is willing to negotiate licences under reasonable and non-discriminatory terms and conditions with applicants throughout the world. In this respect, the statement of the holder of this patent right is registered with ISO. Information may

obtained from:

ArcelorMittal

Research & Development, Intellectual Property

6, rue Campra

F-93212 La Plaine St. Denis

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights other than those identified above. ISO shall not be held responsible for identifying any

all such patent rights.

(https://standards.iteh.ai)
Document Preview

ISO 630-5

https://standards.iteh.ai/catalog/standards/sist/c6b5e30a-ab03-4ac8-a249-9f688f1ca7fd/iso-630-5

Edited DISMUST BE USED

© ISO 2023 - All rights reserved CR FINAL
DRAFT

....

Structural steels — Part 5: Technical delivery conditions for structural steels with improved atmospheric corrosion resistance

1 Scope

This document specifies qualities for flat and long products of hot-rolled structural steels with improved atmospheric corrosion resistance in the as-rolled, normalized/normalized rolled, thermomechanical control processed and quenched and tempered delivery conditions. It is applicable to steel plates rolled on a reversing mill, wide flats, hot-rolled sections and bars, which are intended for use in welded or bolted structures.

This document covers 14 grades and 5 qualities. Grades S235, S295, S355, S420, S460, S500 and S550 are covered in Annex A. Grades SG245, SG345, SG365, SG400, SG460, SG500, and SG700 are covered in Annex B. Not all grades are available in all qualities, and some qualities have Charpy V-notch requirements.

The steels specified in this document are applicable to hot-rolled plates, wide flats, sections and bars with a maximum nominal thickness of 150 mm for grades S235W, S295W, S355W, S420W, S460W, S500W and S550W, with a maximum nominal thickness of 200 mm for grades SG245, SG345, SG365, SG400, SG460, SG500, and SG700.

The steels specified in this document are applicable to hot-rolled plates with a maximum nominal thickness of 20 mm for grades S295WP and S355WP.

The steels specified in this document are applicable to hot-rolled wide flats, sections and bars with a maximum nominal thickness of 40 mm for grades S295WP and S355WP.

The steels specified in this document are applicable to hot-rolled plates with a maximum nominal thickness of 80- \pm mm for grade S355WSE.

This document does not include the following structural steels, some of which are covered by other 2240_968811ca7fd/iso-630-5 International Standards.

- sheet and strip—refer to, e.g. ISO TC 17/SC 12-[1];4995 or ISO 4996;
- tubular products—<u>refer to. e.g.</u> ISO TC 5/SC 12633-1-1/4, ISO 12633-2-1-

NOTE 2 In all parts of ISO 630this document, the term of "thickness" is considered as "nominal thickness", unless otherwise stated.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

 ${\tt ISO~630-1}, \textit{Structural steels} - \textit{Part_1: General technical delivery conditions for hot-rolled products}$

ISO 643, Steels — Micrographic determination of the apparent grain size

ISO 4948-1, Steels — Classification — Part-1: Classification of steels into unalloyed and alloy steels based on chemical composition

ISO 10474, Steel and steel products — Inspection documents

ASTM G101, Standard Guide for Estimating the Atmospheric Corrosion Resistance of Low-Alloy Steels

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 630-1 and the following apply. ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at https://www.iso.org/obp
- IEC Electropedia: available at https://www.electropedia.org/

3.1

fine-grain steel

steel with fine grain structure with an equivalent index of ferritic grain size ≥6 determined in accordance with specific requirements \(\frac{150 \, 643}{2} \)

Note 1 to entry: The requirements shall be in accordance with ISO 643.

Note 2 to entry: See 6.1.

3.2

steel with improved atmospheric corrosion resistance

steel in which a certain number of alloying elements, such as P, Cu, Cr, Ni, etc., have intentionally been added in order to increase its resistance to atmospheric corrosion, by forming an auto-protective oxide layer on the base metal

Note 1 to entry: These steels are commonly known as "weathering steels". 655-30a-ab03-4ac8-a249-9168811ca7fd/iso-630-5

Note 2 to entry: For additional information for the use of steel with improved atmospheric corrosion resistance, see Annex_D.

4 Classification and designation

4.1 Classification

The steel grades specified in this document shall be classified as unalloyed or alloy steels in accordance with ISO 4948-1.

4.2 Designation (grades and qualities)

Steel grades and qualities differ in their specified mechanical properties and impact energy requirements.

Grades S295 and SG345 are subdivided into classes W and WP, which differ primarily in their phosphorus contents; grade S355 is subdivided into classes W, WP and WSE, which differ primarily in phosphorus content and alloying element requirements for Sn, Cr, Mo and Cu; grades SG245, SG365, and SG460 are subdivided into classes W1 and W2, which differ primarily in alloying element requirements for Si, Cr, Cu and Ni (see Table B.1). Class W denotes weathering steel; class WP denotes weathering steel with higher

levels of phosphorus; class WSE denotes weathering steel with an improved resistance to saline environments.

- Quality A: no impact testing
- Quality B: impact testing at +20 °C
- Quality C: impact testing at 0 °C
- Qualities D and D1: impact testing at -20 °C
- Quality E: impact testing at -40 °C

NOTE Quality D1 specifies a higher minimum impact energy than D.

5.0 Requirements in Annexes A and B

The requirements of Annex A or Annex B shall be regarded separately. Each annex is independent of the other without combining in any way.

65 Information to be supplied by purchaser

6.15.1 Mandatory information

The information that shall be supplied by the purchaser at the time of the order is specified in ISO 630-1.

6.2<u>5.2</u>Options

The options of ISO 630-1 may apply. If the purchaser does not indicate a wish to implement any of these options at the time of order, the products shall be at least supplied in accordance with the basic specification (see 5.1).

76 Requirements tandards. iteh.ai/catalog/standards/sist/c6b5e30a-ab03-4ac8-a249-9f688f1ca7fd/iso-630-5

7.16.1 Steelmaking process

See The steel making process shall be in accordance with ISO 630-1.

If a special steelmaking process has been specified, this shall be reported in the inspection document.

The steels shall contain sufficient amounts of nitrogen-binding elements and shall be fine-grain steel.

The steels specified in this specification shall be fully killed.

7.26.2 Delivery condition

Grades S235, S295 and S355 are delivered in the as-rolled, normalized rolled, normalized, thermomechanical controlled processed or quenched and tempered condition. Grades S420, S460, S500 and S550 are delivered in the thermomechanical controlled processed or quenched and tempered condition. The delivery condition shall be indicated in the inspection document.

Grades SG245, SG345, SG365, SG400 and SG460 are delivered in the as-rolled, normalized rolled, normalized, thermomechanical controlled processed or quenched and tempered condition.

Grades SG500 and SG700 are delivered in the thermomechanical <u>controlled controlled</u> processed of quenched and tempered condition. The delivery condition shall be indicated in the inspection document.

7.36.3 Chemical composition

7.3.1<u>6.3.1</u> Heat analysis

The chemical composition determined by heat analysis shall $\frac{complyconform}{composition}$ with the values given in Table A.1 or Table B.1.

7.3.26.3.2 Product analysis

The product analysis of grades S235, S295, S355, S420, S460, S500 and S550 shall conform with the values given in Table A.2.

The permitted deviation of product analysis of SG245, SG345, SG365, SG400, SG460, SG500, and SG700 shall conform with the values given in Table B.2.

7.3.36.3.3 Carbon equivalent value

The maximum carbon equivalent value (C_{EV}) requirements-for Annex A-grades are given S235, S295, S355, S420, S460, S500 and S550 shall be in accordance with Table A.1. See ISO 630 1 for carbon equivalent value formula and Annex C for note on weldability.

The carbon equivalent value (C_{EV}) shall be determined using the IIW (International Institute for Welding formula, given as Formula (1):

$$C_{EV} = C + \frac{Mn}{6} + \frac{Cr + Mo + V}{5} + \frac{Ni + Cu}{15}$$
 (1)

7.46.4 Mechanical properties

7.4.16.4.1 Tensile properties

ISO 630-5

The tensile properties at room temperature shall conform with the values given in Table A.3 or Table B.8 9-9168811 ca7fd/iso-630-5 depending on the steel grade.

7.4.26.4.2 Charpy V-notch impact properties

The impact properties of Charpy V-notch test pieces shall conform with the values specifiedgiven in Table A.4 or Table B.4 depending on the steel grade. The orientation of the specimens shall be longitudinal unless transverse orientation is agreed between purchaser and manufacturer (see 5.2 and ISO 630-1).

The impact values for grades S295WP, S355WP shall be verified if agreed at the time of the order (see Table A.4).

7.56.5 Surface conditions

Surface conditions shall be in accordance with ISO 630-1.

7.66.6 Internal soundness

Internal soundness shall be in accordance with ISO 630-1.

Field Code Changed