



Designation: **F880–02 (Reapproved 2008)^{ε1} F880 – 12**

Standard Specification for Stainless Steel Socket-Set Socket, Square Head, and Slotted Headless-Set Screws¹

This standard is issued under the fixed designation F880; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

¹ NOTE—~~12.3.1 was editorially corrected in February 2012.~~

1. Scope-Scope*

1.1 This specification covers the requirements for austenitic grade stainless steel socket-set screws (SSS) sizes 0.060 through 0.500 in., 1.000 in. square head set screws (SHSS) sizes 0.190 through 1.500 in., and slotted headless set screws (HSS) 0.060 through 0.750 in., in two conditions, AF and CW.

1.2 *Units*—The values stated in inch-pound units are to be regarded as standard. No other units of measurement are included in this standard.

NOTE 1—A complete metric companion to Specification F880 has been developed—F880M; therefore, no metric equivalents are shown in this specification.

1.3 The following hazards caveat pertains only to Test Method Section, Section 12 of this specification. *This standard does not purport to address (all of) the safety problems associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

[A262 Practices for Detecting Susceptibility to Intergranular Attack in Austenitic Stainless Steels](#)

[A342/A342M Test Methods for Permeability of Feebly Magnetic Materials](#)

[A380 Practice for Cleaning, Descaling, and Passivation of Stainless Steel Parts, Equipment, and Systems](#)

[A555/A555M Specification for General Requirements for Stainless Steel Wire and Wire Rods](#)

[A751 Test Methods, Practices, and Terminology for Chemical Analysis of Steel Products](#)

[A967 Specification for Chemical Passivation Treatments for Stainless Steel Parts](#)

[D3951 Practice for Commercial Packaging](#)

[E18 Test Methods for Rockwell Hardness of Metallic Materials](#)

[F593 Specification for Stainless Steel Bolts, Hex Cap Screws, and Studs](#)

[F788/F788M Specification for Surface Discontinuities of Bolts, Screws, and Studs, Inch and Metric Series](#)

[F1470 Practice for Fastener Sampling for Specified Mechanical Properties and Performance Inspection](#)

2.2 ASME Standard:³

[B 18.3 Socket Cap, Shoulder and Set Screws, Inch Series](#)

[B 18.6.2 Slotted Head Cap Screws, Square Head Set Screws, and Slotted Headless Set Screws \(Inch Series\)](#)

3. Classification

3.1 The designation of the alloy group and condition for the two materials and conditions of this specification shall be consistent with the stainless steel designations in Specification [F593](#).

¹ This specification is under the jurisdiction of ASTM Committee [F16](#) on Fasteners and is the direct responsibility of Subcommittee [F16.04](#) on Nonferrous Fasteners. Current edition approved May 1, 2008 June 1, 2012. Published August 2008 November 2012. Originally approved in 1986. Last previous edition approved in 2002 as [F880–02](#); [F880–02\(2008\)](#)¹. DOI: 10.1520/F0880-02R08.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

*A Summary of Changes section appears at the end of this standard

3.2 The austenitic stainless steel socket set screw shall be designated F880 Group 1 Condition AF (solution annealed) or F880 Group 1 Condition CW (cold worked).

4. Ordering Information

4.1 Orders for material under this specification shall include the following information:

4.1.1 Quantity (number of screws);

4.1.2 Dimensions, including nominal thread designation, thread pitch, nominal screw length (inches) and point configuration.

A standard part number may be used for this definition;

4.1.3 Name of the screw (~~SSS~~); (SSS, SHSS or HSS);

4.1.4 Condition AF/CW;

4.1.5 Surface finish, if required. If a finish other than passivation is required, it must be specified on the order or product standard;

4.1.6 ASTM specification and year of issue; and

4.1.7 Any special or supplemental requirements.

4.1.8 If torque testing is required for socket set screws sizes over ½ inch.

4.2 *Example*—50 000 pieces 0.250-20 × 0.375 cone point SSS CW ASTM F880 – XX.

5. Materials and Manufacture

5.1 The screw may be forged, formed, extruded, machined, or ground to meet the dimensional characteristics and performance requirements.

5.2 *Heat Treatment*—Austenitic alloys Group 1 Condition AF screw shall be annealed by heating to 1900 ± 50°F to obtain maximum corrosion resistance and minimum permeability. The screws shall be held for a sufficient time at temperature, then cooled at a rate sufficient to prevent precipitation of the carbide and provide the properties in accordance with **Table 1**.

5.3 When condition CW is specified, the austenitic alloys shall be annealed as specified in 5.2, generally by the raw material manufacturer, and then cold worked to develop specific properties.

6. Chemical Composition

6.1 The analysis of the screw material shall conform to the chemical composition specified in **Table 2**.

6.2 Unless otherwise specified in the inquiry and purchase order (see Supplementary Requirement S2), the choice of alloy used shall be that of the fastener manufacturer as determined by his fabrication methods and material availability. The specific alloy used by the manufacturer shall be clearly identified on all certification required in the purchase order and shall have a chemical composition conforming to the limits specified in **Table 2**.

TABLE 1 Socket Set Screw Torsional Strength Requirements^A

Nominal Screw Size	Shortest Nominal Screw Lengths Subject to Torque Testing			Test Torque, in.-lb, min	
	Cup and Flat Points, mm _{min.}	Cone and Oval Points	Half Dog Points, mm _{min.}	AF	CW
0 0.060	0.109	0.125	0.109	0.3	0.6
1 0.073	0.125	0.141	0.125	0.7	1.2
2 0.086	0.125	0.141	0.141	0.7	1.2
3 0.099	0.141	0.156	0.156	1.6	3.3
4 0.112	0.141	0.172	0.156	1.6	3.3
5 0.125	0.188	0.188	0.172	3	5
5 0.125	0.172	0.188	0.172	3	5
6 0.138	0.172	0.203	0.188	3	5
6 0.138	0.188	0.203	0.188	3	5
8 0.164	0.188	0.219	0.203	9	16
10 0.190	0.188	0.250	0.234	16	26
¼ 0.250	0.250	0.312	0.297	40	67
⅜ 0.312	0.312	0.391	0.359	79	135
⅝ 0.375	0.375	0.438	0.438	138	237
⅞ 0.437	0.438	0.547	0.484	220	378
½ 0.500	0.500	0.609	0.547	358	600
⅝ 0.625	0.625	0.875	0.875
¾ 0.750	0.750	1.000	1.000
⅞ 0.875	0.875	1.000	1.000
1 1.000	1.100	1.250	1.250

^AFor socket set screw sizes over ½ inch, torsional strength testing is not required unless specified by purchaser. The test torque values must be supplied by purchaser and agreed upon by the supplier.

TABLE 2 Chemical Requirements

UNS Designation	Alloy	Composition, % maximum except as shown								
		Carbon	Manganese	Phosphorus	Sulfur	Silicon	Chromium	Nickel	Copper	Molybdenum
Austenitic Alloys										
S30300	303	0.15	2.00	0.20	0.15 min	1.00	17.0 to 19.0	8.0 to 10.0		0.60 max^A
S30300	303	0.15	2.00	0.20	0.15 min	1.00	17.0 to 19.0	8.0 to 10.0		0.60 max ^A
S30323	303Se	0.15	2.00	0.20	0.060	1.00	17.0 to 19.0	8.0 to 10.0		Se 0.15 min
S30323	303Se	0.15	2.00	0.20	0.060	1.00	17.0 to 19.0	8.0 to 10.0		Se 0.15 min
S30400	304	0.08	2.00	0.045	0.030	1.00	18.0 to 20.0	8.0 to 10.5	1.00	...
S30400	304	0.08	2.00	0.045	0.030	1.00	18.0 to 20.0	8.0 to 10.5	1.00	...
S30403	304L	0.030	2.00	0.045	0.030	1.00	18.0 to 20.0	8.0 to 12.0	1.00	...
S30403	304L	0.030	2.00	0.045	0.030	1.00	18.0 to 20.0	8.0 to 12.0	1.00	...
S30500	305	0.12	2.00	0.045	0.030	1.00	17.0 to 19.0	10.5 to 13.0	1.00	...
S30500	305	0.12	2.00	0.045	0.030	1.00	17.0 to 19.0	10.5 to 13.0	1.00	...
S38400	384	0.08	2.00	0.045	0.030	1.00	15.0 to 17.0	17.0 to 19.0
S38400	384	0.08	2.00	0.045	0.030	1.00	15.0 to 17.0	17.0 to 19.0
S20300	XM4	0.08	5.0 to 6.5	0.040	0.18 to 0.35	1.00	16.0 to 18.0	5.0 to 6.5	1.75 to 2.25	0.50 max^A
S20300	XM1	0.08	5.0 to 6.5	0.040	0.18 to 0.35	1.00	16.0 to 18.0	5.0 to 6.5	1.75 to 2.25	0.50 max ^A
S30430	18-9LW	0.10	2.00	0.045	0.030	1.00	17.0 to 19.0	8.0 to 10.0	3.0 to 4.0	...
S30430	18-9LW	0.10	2.00	0.045	0.030	1.00	17.0 to 19.0	8.0 to 10.0	3.0 to 4.0	...
S30433	302HQ	0.03	2.00	0.045	0.030	1.00	17.0 to 19.0	8.0 to 10.0	3.0 to 4.0	...
S30433	302HQ	0.03	2.00	0.045	0.030	1.00	17.0 to 19.0	8.0 to 10.0	3.0 to 4.0	...
S31600	316	0.03	2.00	0.045	0.030	1.00	16.0 to 18.0	10.0 to 14.01	...	2.0 to 3.0
S31600	316	0.03	2.00	0.045	0.030	1.00	16.0 to 18.0	10.0 to 14.01	...	2.0 to 3.0
S31603	316L	0.03	2.00	0.045	0.03	1.00	16.0 to 18.0	10.0 to 14.01	...	2.0 to 3.0
S31603	316L	0.03	2.00	0.045	0.03	1.00	16.0 to 18.0	10.0 to 14.01	...	2.0 to 3.0

^A At the manufacturer's option, determined only when intentionally added.

6.3 When chemical analysis is performed by the purchaser using finished fasteners representing each lot, the chemical contents obtained shall conform to the limits specified in **Table 2** for the specific alloy. Chemical composition shall conform to the tolerances specified in Specification **A555/A555M**.

6.3.1 In the event of a discrepancy, a referee analysis of the samples for each lot as specified in **12.1** shall be made in accordance with **11.3.1**.

7. Mechanical Properties

7.1 Socket-set screws, when subjected to a torque test in accordance with **12.3.1**, shall withstand application of the test tightening torque specified in **Table 1** without evidence of the socket reaming or the screw bursting. Socket set screws in sizes in nominal diameters over 1/2 in. are not subject to torques testing unless required by purchaser. The test torque values must be supplied by purchaser and agreed to by the supplier.

7.2 The hardness limits from 70 to 95 HRB (125 to 210 DPH) for Condition AF and 96 HRB to 33 HRC (216 to 327 DPH) for Condition CW shall be met as determined using Test Methods **E18**.

8. Corrosion Resistance Requirements

8.1 Carbide Precipitation:

8.1.1 Rod, bar, and wire in the austenitic alloy groups 1, 2, and 3, except the free-machining grades, 303 and 303Se, used to make fasteners in accordance with this specification shall be capable of passing the test for susceptibility to intergranular corrosion as specified in Practice E of Practices **A262**.

8.1.2 As stated in Practices **A262**, samples may be subjected to the faster and more severe screening test in accordance with Practice A. Failing Practice A, specimens shall be tested to Practice E and be considered satisfactory if passing Practice E.

9. Dimensions

9.1 Unless otherwise specified, the product shall conform to the requirements of ASME ~~B 18.3~~ **B 18.3** or **B 18.6.2** as applicable.

10. Workmanship, Finish, and Appearance

10.1 *Surface Treatment*—Unless otherwise specified, screws shall be cleaned, descaled, and passivated in accordance with Practice **A380** or Specification **A967** at the option of the manufacturer.

10.2 Surface Discontinuities:

10.2.1 The surface discontinuities for these products shall conform to Specification **F788/F788M** and the additional limitations specified herein.

10.2.1.1 Processing cracks that connect the socket to the periphery of the screw are not permissible. Defects originating on the periphery with a traverse indicating a potential to intersect are not permissible. For peripheral discontinuities, the maximum depth may be 0.06 *D*.