



FINAL DRAFT International Standard

ISO/FDIS 5942

Bamboo-wood composite for container flooring

ISO/TC 296

Secretariat: **SAC**

Voting begins on:
2024-04-29

Voting terminates on:
2024-06-24

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

ISO/FDIS 5942

<https://standards.iteh.ai/catalog/standards/iso/6adf975b-4e4c-420a-9358-d19ba124affd/iso-fdis-5942>

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

ISO/FDIS 5942

<https://standards.iteh.ai/catalog/standards/iso/6adf975b-4e4c-420a-9358-d19ba124affd/iso-fdis-5942>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2024

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Classification	2
5 Technical requirements	2
5.1 Specifications	2
5.1.1 Size and tolerance	2
5.1.2 Diagonal difference	2
5.1.3 Edge straightness	2
5.1.4 Degree of warping	2
5.2 Appearance quality	2
5.3 Physical and mechanical properties	6
5.4 Floor strength	6
5.5 Anti-insect and antiseptic treatments	6
6 Inspection methods	7
6.1 Size specification	7
6.2 Diagonal difference	7
6.3 Edge straightness	7
6.4 Degree of warping	7
6.5 Appearance quality	7
6.6 Physical and mechanical properties	7
6.6.1 Specimen preparation	7
6.6.2 Standard conditioning	8
6.6.3 Density	8
6.6.4 Moisture content	8
6.6.5 Bond durability	8
6.6.6 Short span bending force	9
6.6.7 Concentrated load	9
6.6.8 Floor strength	10
7 Inspection rules	10
7.1 Inspection category	10
7.1.1 General	10
7.1.2 Delivery inspection	10
7.1.3 Type inspection	10
7.1.4 Floor strength inspection	11
7.2 Group principle	11
7.3 Sampling methods	11
7.3.1 General	11
7.3.2 Appearance quality inspection	11
7.3.3 Specifications inspection	11
7.3.4 Physical and mechanical properties inspection	12
7.4 Comprehensive judgement	12
7.4.1 Determination of test results	12
7.4.2 Comprehensive judgement	12
8 Marking, packaging, transportation and storage	13
8.1 Marking	13
8.1.1 Product marking	13
8.1.2 Packaging label	13
8.2 Packaging	13
8.3 Transportation and storage	13
Annex A (informative) Details for reference of the simulated freight container base underframe	14

Bibliography	17
---------------------------	-----------

iTeh Standards
(<https://standards.itih.ai>)
Document Preview

[ISO/FDIS 5942](https://standards.itih.ai/catalog/standards/iso/6adf975b-4e4c-420a-9358-d19ba124affd/iso-fdis-5942)

<https://standards.itih.ai/catalog/standards/iso/6adf975b-4e4c-420a-9358-d19ba124affd/iso-fdis-5942>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 296, *Bamboo and rattan*.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

ISO/FDIS 5942

<https://standards.iteh.ai/catalog/standards/iso/6adf975b-4e4c-420a-9358-d19ba124affd/iso-fdis-5942>

Bamboo-wood composite for container flooring

1 Scope

This document specifies the classification, technical requirements, inspection methods, inspection rules, marking, packaging, transportation and storage of bamboo-wood composite for container flooring.

This document is applicable to the types of freight containers specified in ISO 1496-1:2013.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1496-1:2013, *Series 1 freight containers — Specification and testing — Part 1: General cargo containers for general purposes*

ISO 2074, *Plywood — Vocabulary*

ISO 2859-1, *Sampling procedures for inspection by attributes — Part 1: Sampling schemes indexed by acceptance quality limit (AQL) for lot-by-lot inspection*

ISO 9426:2003, *Wood-based panels — Determination of dimensions of panels*

ISO 9427, *Wood-based panels — Determination of density*

ISO 16979, *Wood-based panels — Determination of moisture content*

ISO 21625:2020, *Terminology of bamboo products*

<https://standards.iteh.ai/catalog/standards/iso/6ad1975b-4e4c-420a-9358-d19ba124affd/iso-fdis-5942>

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 2074, ISO 21625:2020 and the following apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

3.1

bamboo-wood composite for container flooring

bamboo-wood composite made from bamboo and a wood element by gluing, hot pressing, used for container flooring

Note 1 to entry: A large range of raw materials for making bamboo-wood composite is included. The bamboo element is processed using a mechanical method with bamboo as the raw material (e.g. bamboo interlaced mat, bamboo curtain, flattened bamboo board, bamboo fibre bundle sheet and bamboo strand). “Wood element” refers to a sheet-like material processed from wood (e.g. wood veneer, wood strand).

[SOURCE: ISO 21625:2020, 3.3.4.9, modified — “for” added in the term. “bamboo and wood element” replaced “wood veneer and bamboo curtain” in the definition. Note 1 to entry added.]

3.2**unfinished bamboo-wood composite for container flooring**

bamboo-wood composite board without coating or special material applied to any exposed sides

3.3**finished bamboo-wood composite for container flooring**

bamboo-wood composite board with coating or special material applied to any exposed sides or both sides

4 Classification

Bamboo-wood composite for container flooring shall be classified based on the surface treatment, as follows:

- a) unfinished bamboo-wood composite for container flooring;
- b) finished bamboo-wood composite for container flooring.

5 Technical requirements**5.1 Specifications****5.1.1 Size and tolerance**

Product size and tolerance shall meet the requirements of [Table 1](#).

Table 1 — Size and tolerance of bamboo-wood composite for container flooring

Items	Size mm	Tolerance mm
Length ^a	1 010, 1 388, 1 626, 1 967, 2 224, 2 400	+0, -1,0
Width ^a	636, 1 160	+0, -1,0
Thickness	28	±0,8

^a Alternative length and width dimensions may be agreed between the buyer and seller.

5.1.2 Diagonal difference

The diagonal difference shall not be greater than 2 mm.

5.1.3 Edge straightness

The edge straightness shall not be greater than 0,5 mm/m.

5.1.4 Degree of warping

The degree of warping in the length and width directions shall not be greater than 0,3 %, see [6.4](#).

NOTE Bamboo-wood composite for container flooring has been chamfered during the manufacturing process, therefore no additional requirements are necessary in this document.

5.2 Appearance quality

The appearance quality requirements for unfinished bamboo-wood composite for container flooring shall be in accordance with [Tables 2](#) and [3](#). The appearance quality requirements for finished bamboo-wood composite for container flooring shall be in accordance with [Table 4](#).

Table 2 — Appearance quality requirements for unfinished bamboo-wood composite for container flooring with wood veneer as surface layer

Nature of defects	Quality requirements	
	Surface layer	Bottom layer
Crack	The width of an individual crack shall be no greater than 2 mm.	The width of an individual crack shall be no greater than 3 mm.
	a) When the length of the crack is not greater than 100 mm, the number of cracks per metre of board width shall be no more than six.	a) When the length of the crack is not greater than 200 mm, the number of cracks per metre of board width shall be no more than six.
	b) When the length of the crack is between 100 mm and 200 mm, the number of cracks per metre of board width shall be no more than four.	b) When the length of the crack is between 200 mm and 300 mm, the number of cracks per metre of board width shall be no more than four.
	c) When the length of the crack is between 200 mm and 300 mm, the number of cracks per metre of board width shall be no more than three.	c) When the length of the crack is between 300 mm and 400 mm, the number of cracks per metre of board width shall be no more than three.
	Cracks beyond the dimensions specified in the row directly above shall be patched. The cracks shall be repaired and levelled with putty which is similar in colour to the board surface. When the cracks of multiple lengths are present simultaneously, the total number shall not exceed the maximum limit specified for each type of crack.	
Live knot	The diameter of an individual live knot shall be no greater than 30 mm and the number of live knots on the entire surface layer shall be no more than three.	The diameter of an individual live knot shall be no greater than 50 mm and the number of live knots on the entire bottom layer shall be no more than six (provided that the live knot is not located within 200 mm of the edge).
Dead knot	The diameter of an individual dead knot shall be no greater than 6 mm and the number of dead knots on the entire surface layer shall be no more than five.	When the diameter of an individual dead knot is not greater than 15 mm, there is no limitation on the number of dead knots (provided that the dead knot is not located within 200 mm of the edge).
Chromatic aberration	No obvious colour difference	No restrictions
Discoloration	Not allowed	Allowed
Decay	Not allowed	
Wormhole, dog holes, hole	Round hole	
	The diameter of an individual hole shall be less than 2 mm. The edge of the hole shall not be discoloured. Holes shall not be aggregated.	The diameter of an individual hole shall be less than 3 mm, and the holes shall not be aggregated; The diameter of an individual hole shall be less than 5 mm. The total number of holes on the entire bottom layer shall be no more than 10, and the distance between holes shall be greater than 100 mm.
	Linear wormhole	
	The length shall be less than 10 mm. The width shall be less than 1 mm. Any wormholes shall not be discoloured. Wormholes shall not be aggregated.	The length shall be less than 10 mm. The width shall be less than 1 mm and not located within 200 mm of the side. Wormholes shall not be aggregated.
	Other types of holes shall not be allowed. All holes shall be repaired and filled with putty.	
Bark pocket, resin canal	Not allowed	

Table 2 (continued)

Nature of defects	Quality requirements	
	Surface layer	Bottom layer
Surface plate lamination	Not allowed	
Surface plate splicing	Not allowed	
Surface plate patched with slice or strip	Not allowed	Allowed
Stacking of long and medium plates	An individual width shall be no greater than 8 mm. Each layer shall be staggered.	
Cross-band veneer lamination	An individual veneer width shall be no greater than 5 mm.	
	Each layer's width per metre of board shall not exceed 3 strips.	
Veneer gap	An individual width not greater than 3 mm shall be filled with putty. An individual width between 3 mm and 10 mm shall be repaired by inserting strips. The gaps in each layer shall be staggered.	
Defects of cross-band veneer	a) When the depth is less than 10 mm and the width is less than 200 mm, there shall be no more than two gaps on the same side. b) When the depth is less than 5 mm, the width shall be ignored. c) The defect of cross-band veneer in the same location on each side shall not exceed two layers of veneer. Defects in the core shall be repaired and filled with putty.	
Grease	Not obvious	Slight, no obvious sticky feeling
Glitch and groove mark	Slight	Glitches and groove marks shall not penetrate the veneer. They shall be repaired and levelled with putty.
Sand through	Not allowed	Not serious
Sand leakage	Slight	
Glue penetration	Slight	Not serious
Sunken and bump	Not allowed	
Indentation	If aesthetics will not be affected after repair, it shall be permitted.	Allowed after repairing
Bubbling and delamination	Not allowed	
Edge defect	The width shall be less than 1,5 mm. The depth shall be less than 2 mm. The cumulative length shall be less than 50 mm.	