

INTERNATIONAL STANDARD

NORME INTERNATIONALE

**Corrugated pressboard and presspaper for electrical purposes –
Part 2: Methods of test**

**Cartons et papiers comprimés ondulés à usages électriques –
Partie 2: Méthodes d'essais**

IEC 61628-2:1998

<https://standards.iteh.ai/catalog/standards/iec/f45ffd62-4e1b-be0b-d85d566c1e3b/iec-61628-2-1998>



THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2007 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

Droits de reproduction réservés. Sauf indication contraire, aucune partie de cette publication ne peut être reproduite ni utilisée sous quelque forme que ce soit et par aucun procédé, électronique ou mécanique, y compris la photocopie et les microfilms, sans l'accord écrit de l'IEC ou du Comité national de l'IEC du pays du demandeur. Si vous avez des questions sur le copyright de l'IEC ou si vous désirez obtenir des droits supplémentaires sur cette publication, utilisez les coordonnées ci-après ou contactez le Comité national de l'IEC de votre pays de résidence.

IEC Central Office
3, rue de Varembe
CH-1211 Geneva 20
Switzerland

Tel.: +41 22 919 02 11
Fax: +41 22 919 03 00
info@iec.ch
www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

IEC Catalogue - webstore.iec.ch/catalogue

The stand-alone application for consulting the entire bibliographical information on IEC International Standards, Technical Specifications, Technical Reports and other documents. Available for PC, Mac OS, Android Tablets and iPad.

IEC publications search - www.iec.ch/searchpub

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished

Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and also once a month by email.

Electropedia - www.electropedia.org

The world's leading online dictionary of electronic and electrical terms containing 20 000 terms and definitions in English and French, with equivalent terms in 15 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

IEC Glossary - std.iec.ch/glossary

65 000 electrotechnical terminology entries in English and French extracted from the Terms and Definitions clause of IEC publications issued since 2002. Some entries have been collected from earlier publications of IEC TC 37, 77, 86 and CISPR.

IEC Customer Service Centre - webstore.iec.ch/csc

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: csc@iec.ch.

A propos de l'IEC

La Commission Electrotechnique Internationale (IEC) est la première organisation mondiale qui élabore et publie des Normes internationales pour tout ce qui a trait à l'électricité, à l'électronique et aux technologies apparentées.

A propos des publications IEC

Le contenu technique des publications IEC est constamment revu. Veuillez vous assurer que vous possédez l'édition la plus récente, un corrigendum ou amendement peut avoir été publié.

Catalogue IEC - webstore.iec.ch/catalogue

Application autonome pour consulter tous les renseignements bibliographiques sur les Normes internationales, Spécifications techniques, Rapports techniques et autres documents de l'IEC. Disponible pour PC, Mac OS, tablettes Android et iPad.

Recherche de publications IEC - www.iec.ch/searchpub

La recherche avancée permet de trouver des publications IEC en utilisant différents critères (numéro de référence, texte, comité d'études,...). Elle donne aussi des informations sur les projets et les publications remplacées ou retirées.

IEC Just Published - webstore.iec.ch/justpublished

Restez informé sur les nouvelles publications IEC. Just Published détaille les nouvelles publications parues. Disponible en ligne et aussi une fois par mois par email.

Electropedia - www.electropedia.org

Le premier dictionnaire en ligne de termes électroniques et électriques. Il contient 20 000 termes et définitions en anglais et en français, ainsi que les termes équivalents dans 15 langues additionnelles. Egalement appelé Vocabulaire Electrotechnique International (IEV) en ligne.

Glossaire IEC - std.iec.ch/glossary

65 000 entrées terminologiques électrotechniques, en anglais et en français, extraites des articles Termes et Définitions des publications IEC parues depuis 2002. Plus certaines entrées antérieures extraites des publications des CE 37, 77, 86 et CISPR de l'IEC.

Service Clients - webstore.iec.ch/csc

Si vous désirez nous donner des commentaires sur cette publication ou si vous avez des questions contactez-nous: csc@iec.ch.



IEC 61628-2

Edition 1.1 2007-07
CONSOLIDATED VERSION

INTERNATIONAL STANDARD

NORME INTERNATIONALE

**Corrugated pressboard and presspaper for electrical purposes –
Part 2: Methods of test**

**Cartons et papiers comprimés ondulés à usages électriques –
Partie 2: Méthodes d'essais**

IEC 61628-2:1998

<https://standards.iteh.ai/catalog/standards/iec/f45ffd62-4232-4e1b-be0b-d85d566c1e3b/iec-61628-2-1998>

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

COMMISSION
ELECTROTECHNIQUE
INTERNATIONALE

ICS 29.035.10

ISBN 2-8318-9236-8

**Warning! Make sure that you obtained this publication from an authorized distributor.
Attention! Veuillez vous assurer que vous avez obtenu cette publication via un distributeur agréé.**

CONTENTS

FOREWORD.....	3
INTRODUCTION.....	5
1 Scope.....	6
2 Normative reference	6
3 General note on tests.....	6
4 Type and dimension of corrugation.....	6
5 Moisture content	8
6 Dimensional changes on drying.....	8
7 Compressive strength and compression modulus	9
8 Conductivity of aqueous extract	11
Figure 1 – Different types of corrugation.....	12
Figure 2 – Positioning of the test specimen.....	13
Figure 3 – Test specimen holder – Side view.....	13
Figure 4 – Curve of deflection versus force.....	14

Itih Standards
(<https://standards.iteh.ai>)
Document Preview

[IEC 61628-2:1998](#)

<https://standards.iteh.ai/catalog/standards/iec/f45ffd62-4232-4e1b-be0b-d85d566c1e3b/iec-61628-2-1998>

INTERNATIONAL ELECTROTECHNICAL COMMISSION

**CORRUGATED PRESSBOARD AND PRESSPAPER
FOR ELECTRICAL PURPOSES –****Part 2: Methods of test**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC provides no marking procedure to indicate its approval and cannot be rendered responsible for any equipment declared to be in conformity with an IEC Publication.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

This consolidated version of the official IEC Standard and its amendment has been prepared for user convenience.

IEC 61628-2 edition 1.1 contains the first edition (1998) [documents 15C/992/FDIS and 15C/1008/RVD] and its amendment 1 (2007) [documents 15/293/CDV and 15/340/RVC].

A vertical line in the margin shows where the base publication has been modified by amendment 1.

International Standard IEC 61628-2 has been prepared by subcommittee 15C: Specifications, of IEC technical committee 15: Insulating materials.

The committee has decided that the contents of the base publication and its amendments will remain unchanged until the maintenance result date indicated on the IEC web site under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[IEC 61628-2:1998](#)

<https://standards.iteh.ai/catalog/standards/iec/f45ffd62-4232-4e1b-be0b-d85d566c1e3b/iec-61628-2-1998>

INTRODUCTION

This part of IEC 61628 is one of a series which deals with corrugated pressboard and presspaper for electrical purposes.

This series consists of three parts:

- IEC 61628-1:1997, *Corrugated pressboard and presspaper for electrical purposes – Part 1: Definitions, designations and general requirements*
- IEC 61628-2:1998, *Corrugated pressboard and presspaper for electrical purposes – Part 2: Methods of test*
- IEC 61628-3,— *Corrugated pressboard and presspaper for electrical purposes – Part 3: Specification for individual materials (under consideration)*

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[IEC 61628-2:1998](https://standards.iteh.ai/catalog/standards/iec/f45ffd62-4232-4e1b-be0b-d85d566c1e3b/iec-61628-2-1998)

<https://standards.iteh.ai/catalog/standards/iec/f45ffd62-4232-4e1b-be0b-d85d566c1e3b/iec-61628-2-1998>

CORRUGATED PRESSBOARD AND PRESSPAPER FOR ELECTRICAL PURPOSES –

Part 2: Methods of test

1 Scope

This part of IEC 61628 gives methods of test applicable for the materials classified in IEC 61628-1.

2 Normative reference

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60641-2:2004, *Pressboard and presspaper for electrical purposes – Part 2: Methods of test*

3 General note on tests

It is recommended to use a high-speed band saw with a cut width less than 1 mm to make the test specimens. The burrs made by cutting should be carefully removed.

Unless otherwise specified, the test specimens after being cut, shall be conditioned according to IEC 60641-2.

4 Type and dimension of corrugation

The shape and type of corrugation are defined by wavelength, maximum amplitude, the length of horizontal parts, angle of slope and the board thickness out of which the corrugated material is made (see figures 1a and 1b).

The following tests are made on the material as received.

4.1 Wavelength

4.1.1 Procedure

Cut at least three test samples, each test sample having a length greater than three complete wavelengths.

With a pencil, mark the starting line of the first wavelength and the end line of the last wavelength (minimum three wavelengths).

(The best starting and end line of a wavelength is the line of maximum amplitude for a sine type corrugation and the centre of a horizontal part in an angular type corrugation.)

Lay the test sample on a flat surface with no strain applied.

Measure with a ruler (precise to 0,5 mm) the distance between the pencil lines.

Divide the measured value by the number of wavelengths between the lines.

4.1.2 Results

Report the mean, minimum and maximum values of the measurements.

4.2 Amplitude

4.2.1 Procedure

Cut at least nine specimens, each being (100 ± 10) mm wide, and one-and-a-half to two wavelengths in length, so that two full bottom peaks are included.

Lay the test specimens on a flat surface with no strain applied.

With a gauge (precise to 0,1 mm), measure the distance between the highest point and the lowest point.

4.2.2 Results

Report the mean, minimum and maximum values of the measurements.

4.3 Length of horizontal parts of corrugation

4.3.1 Procedure

On at least three different corrugations, mark with a pencil the vertical projections of the theoretical points where the oblique parts of the corrugation meet the horizontal part. The pencil marks shall be positioned on a line in the direction of the corrugation wavelength. Measure the distance between the pencil marks with a calliper precise to 0,1 mm (distance E in figure 1b).

Repeat the measurements at the opposite side of the sheet to measure the distance D in figure 1b.

Because D and E may be intentionally different, both measurements shall be reported.

4.3.2 Results

Report for D and E the mean, minimum and maximum values of the measurements.

4.4 Angle of slope

4.4.1 Procedure

Cut at least three specimens, each being (100 ± 10) mm wide, and one-and-a-half to two wavelengths in length, so that two full bottom peaks are included.

Lay the test sample on a flat surface with no strain applied.

With an adequate protractor (precise to $0,5^\circ$), measure the two angles α of the central corrugation.

4.4.2 Results

Report the mean, minimum and maximum values of the measurements.

4.5 Thickness of board

4.5.1 Procedure

With an external screw type micrometer as described in IEC 60641-2, make at least nine different measurements of the board thickness with an accuracy of $\pm 0,01$ mm at points where the corrugation curve is flat, or in the area of the inflection point for a sine type corrugation.

NOTE Measures on the horizontal flat part should be avoided as the board thickness may have been affected by the direct action of the forming press when mechanical pressure has been used to manufacture the corrugated material.

4.5.2 Results

Report the mean, minimum and maximum values of the measurements.

5 Moisture content

Moisture content shall be determined according to IEC 60641-2.

6 Dimensional changes on drying

6.1 Change of amplitude

6.1.1 Procedure (see figure 2)

Cut three specimens (50 ± 5) mm wide and five wavelengths long and condition them according to IEC 60641-2.

Place the specimens on a flat steel plate the dimensions of which shall exceed the dimensions of the specimen by at least 50 mm. Place a second flat rigid plate of calibrated thickness T , 50 mm wide and of sufficient length to cover all the corrugations, on top of the specimen. The weight of this plate shall guarantee that all the corrugations are in flat contact with both top and bottom plate and shall be defined in the specification sheets of IEC 61628-3.

NOTE The weight of the plate can be adjusted by additional weights added on top of it.

If all the corrugations of any specimen are not in contact with top and bottom plate under this pre-load, the specimen shall be discarded.

The amplitude of the corrugation of the specimen is measured by means of a gauge precise to 0,1 mm with a semi-spherical sensor in the following way:

- lower the sensor of the gauge on to the bottom steel plate and adjust the pointer to zero;
- set the sensor on the top plate and read the measured values at three different points near the centre of the plate and form the mean of these three measures.

Record this value as value B for each specimen.

Remove and dry the test specimens in a ventilated oven at $105 \text{ °C} \pm 5 \text{ K}$ for (48 ± 1) h. After cooling at room temperature in a desiccator, repeat the measurements as above.

Record for each specimen the new value as C .

6.1.2 Calculation

The change of amplitude is calculated as a percentage of the original amplitude and is given by the formula:

$$\text{change of amplitude} = \frac{C - B}{B - T} \times 100$$

There is normally an increase of amplitude after drying.

6.1.3 Results

Report the mean value obtained. Minimum and maximum values should also be reported.

6.2 Lengthwise and crosswise dimensional changes

6.2.1 Procedure

Cut three specimens $(250 \pm 0,5) \text{ mm} \times (250 \pm 0,5) \text{ mm}$ and condition them according to IEC 60641-2. Place the specimen on a flat steel plate of at least $300 \text{ mm} \times 300 \text{ mm}$. A second flat rigid plate of the same dimension is placed on top of the specimen. Its mass, which will be defined in the specification sheets of IEC 61628-3, shall guarantee that all corrugations are in contact with both top and bottom plates.

Measure the lengthwise and crosswise dimensions with a calliper precise to 0,1 mm (or equivalent) at two different positions.

Record the mean value of the two measurements as the initial dimensions of the specimen.

Remove and dry the test specimens in a ventilated oven at $105 \text{ °C} \pm 5 \text{ K}$ for $(48 \pm 1) \text{ h}$. After cooling at room temperature in a desiccator, repeat the measurements as above.

6.2.2 Results

The dimensional changes lengthwise and crosswise are calculated for each specimen as the per cent change in dimensions from those of the original conditioned specimen. Report all calculated values and the means of the lengthwise and crosswise values.

7 Compressive strength and compression modulus

7.1 Purpose and principle of the test

The purpose of the test is to calculate the compressive strength and the compression modulus of the material when the corrugation is submitted to a force applied on the corrugation and perpendicular to the original plane of the corrugated material.

The perpendicular force is applied with the ends of the test specimens subjected to total restraint (see figure 3).