

---

---

**Imaging materials — Methods for  
measuring indoor light stability of  
photographic prints —**

**Part 2:  
Xenon-arc lamp exposure**

*Matériaux pour l'image — Méthodes de mesure de la stabilité de la  
lumière en intérieur des épreuves photographiques —  
Partie 2: Exposition à une lampe à arc au xénon*

[ISO 18937-2:2023](https://standards.iteh.ai/catalog/standards/sist/d9c17541-88e2-4f66-b12b-977d062ecdbc/iso-18937-2-2023)

<https://standards.iteh.ai/catalog/standards/sist/d9c17541-88e2-4f66-b12b-977d062ecdbc/iso-18937-2-2023>



# iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 18937-2:2023

<https://standards.iteh.ai/catalog/standards/sist/d9c17541-88e2-4f66-b12b-977d062ecdbc/iso-18937-2-2023>



## **COPYRIGHT PROTECTED DOCUMENT**

© ISO 2023

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

	Page
Foreword.....	iv
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>1</b>
<b>4 Principle</b> .....	<b>2</b>
<b>5 Apparatus</b> .....	<b>2</b>
<b>6 Test specimens</b> .....	<b>3</b>
<b>7 Exposure conditions</b> .....	<b>3</b>
7.1 General.....	3
7.2 General indoor display.....	4
7.2.1 Application.....	4
7.2.2 Filters to simulate general indoor display conditions.....	4
7.2.3 Radiation intensity, temperature, and humidity.....	4
7.3 Simulated in-window display.....	5
7.3.1 Application.....	5
7.3.2 Filtered xenon arc configuration to simulate in-window display conditions.....	5
7.3.3 Radiation intensity, temperature and humidity.....	6
<b>8 Test result measurement and report</b> .....	<b>6</b>
<b>Annex A (informative) Relative spectral transmittance of filters</b> .....	<b>7</b>
<b>Annex B (informative) Sample temperature measurements based on different parameters</b> .....	<b>9</b>
<b>Bibliography</b> .....	<b>13</b>

[ISO 18937-2:2023](https://standards.iteh.ai/catalog/standards/sist/d9c17541-88e2-4f66-b12b-977d062ecdbc/iso-18937-2-2023)

<https://standards.iteh.ai/catalog/standards/sist/d9c17541-88e2-4f66-b12b-977d062ecdbc/iso-18937-2-2023>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 42, *Photography*. This first edition of ISO 18937-2 cancels and replaces the second edition of ISO 18937:2020, which has been technically revised.

The main changes are as follows:

- This revision of the existing ISO 18937 separates the International Standard into three separate parts in a similar way to two other artificial exposure testing series, ISO 4892 (Plastics, in TC 61), and ISO 16474 (Paints and varnishes, in TC 35).

A list of all parts in the ISO 18937 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

# Imaging materials — Methods for measuring indoor light stability of photographic prints —

## Part 2: Xenon-arc lamp exposure

### 1 Scope

This document describes test equipment and procedures for measuring the light stability of photographic prints when subjected to a filtered xenon-arc light source at specified levels of illuminance (irradiance), temperature and relative humidity. It is applicable to both colour and monochrome reflection prints, transparent films, or translucent films. It is also applicable to photographic prints in general, photobooks, or prints for backlit displays.

General indoor display conditions described herein are intended to simulate common use conditions found in houses, apartments and other dwelling places where indirect lighting due to filtering (through window glass) and shading is often the principal illumination causing displayed photographs to fade.

Simulated in-window display conditions are intended to simulate terrestrial daylight transmitted through standard architectural window glass (double glazing). A typical example of such display can be found when images are displayed in store windows, facing toward the outdoors, so that they can be viewed by people outside of the store<sup>[5][6]</sup>.

**NOTE** It is recognized that in some instances, physical degradation such as support embrittlement, image layer cracking, or delamination of an image layer from its support, rather than the stability of the image itself, will determine the useful life of a print material.

General guidance is given in ISO 18937-1.

### 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 9370, *Plastics — Instrumental determination of radiant exposure in weathering tests — General guidance and basic test method*

ISO 18913, *Imaging materials — Permanence — Vocabulary*

ISO 18937-1, *Imaging materials — Photographic reflection prints — Methods for measuring indoor light stability — Part 1: General guidance and requirements*

### 3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 18913 apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

## 4 Principle

A xenon arc lamp, fitted with filters, is used to simulate the relative spectral irradiance of various end-use conditions to simulate standardized indoor lighting conditions by their relative spectral irradiance in the ultraviolet (UV) and visible regions of the spectrum.

Depending on intended user or application cases, specimens are exposed to desired levels of light, heat, and relative humidity under controlled environmental conditions.

The exposure conditions are varied by selection of

- a) the light filter(s),
- b) the irradiance or illuminance level,
- c) the temperature during exposure to light,
- d) the relative humidity in the chamber during light and dark exposures,
- e) the relative duration of the light and dark periods.

The procedure includes measurements of the irradiance or illuminance and radiant exposure in the plane of the specimens.

## 5 Apparatus

### 5.1 Laboratory light source.

#### 5.1.1 General

The light source shall comprise one or more quartz-jacketed xenon-arc lamps which emit radiation from below 270 nm in the ultraviolet through the visible spectrum and into the infrared. In order to simulate the end-use conditions, filters shall be used to remove short-wavelength UV radiation.

#### 5.1.2 Optical filters.

Filters are used with the intention of reproducing as closely as possible different end-use lighting conditions<sup>[3][4]</sup>. Special filtering of the xenon-arc lamp is used to achieve two specific lighting conditions applicable to this method.

The optical filters shall be placed at any position between the light source and the specimens to achieve the required spectral irradiance conditions. The filters can be placed near the light source or near the specimens, but the air gap between the specimens and the filter shall allow an unobstructed airflow between the filter and the specimens.

#### 5.1.3 Irradiance uniformity.

The irradiance at any position in the area used for specimen exposure shall be at least 80 % of the maximum irradiance. Periodic repositioning of specimens when irradiance uniformity is between 80 % and 90 % is described in ISO 18937-1.

**NOTE** For some materials of high sensitivity to irradiance and temperature, periodic repositioning of specimens is recommended to ensure uniformity of exposures, even when the irradiance uniformity in the exposure area is within the limits where repositioning would not be required.

### 5.2 Test chamber.

The design of the test chamber may vary, but it shall be constructed from inert material. The test chamber shall provide control systems for irradiance, temperature and humidity.

The light source(s) shall be located, with respect to the specimens, such that the irradiance (or illuminance) at the specimen surface conforms with [7.1](#).

NOTE If the lamp system (one or more lamps) is centrally positioned in the chamber, the effect of any eccentricity of the lamp(s) on the uniformity of exposure can be reduced by using a rotating rack.

### 5.3 Radiometer.

Radiometers or illuminance meters used shall conform with the requirements outlined in ISO 18937-1 and ISO 9370.

### 5.4 Black-panel thermometer.

The black-panel thermometer shall conform with the requirements for these devices given in ISO 18937-1.

### 5.5 Humidity.

The specific end-use conditions describe the required humidity level control. The location of the sensors used to measure the humidity shall be as specified in ISO 18937-1.

### 5.6 Specimen holders.

Specimen holders may be constructed in the form of an open frame, leaving the backs of the specimens exposed, or they may provide a solid backing for the specimens. Transparent or translucent materials shall always be exposed with an open backing. They shall be made from inert materials that will not affect the results of the exposure. The backing used may affect the results, especially with respect to specimen temperature.

### 5.7 Apparatus to assess changes in properties.

For print materials, measurements of colorimetric or densitometric properties are typically used to assess property change before and after exposure. Data are commonly reported in graph form, with exposure level as the x-axis and densitometric or colorimetric change as the y-axis.

### 5.8 Air quality in the test environment.

Some types of print materials can be highly sensitive to degradation caused by ozone or other airborne pollutants. See ISO 18937-1 for requirements related to monitoring and reduction of these pollutants.

## 6 Test specimens

ISO 18937-1 contains information related to the requirements for test specimen creation, replication, conditioning, handling, and positioning in the exposure area.

## 7 Exposure conditions

### 7.1 General

If a reciprocity behaviour test is conducted, lower radiant intensity, e.g. 10 % of nominal condition, shall be used (details are described in ISO 18937-1:2023, Annex A).

## 7.2 General indoor display

### 7.2.1 Application

This test is intended to simulate common use conditions found in houses, apartments and other dwelling places where indirect lighting due to filtering (through window glass) and shading is often the principal illumination causing displayed photographs to fade. A UV-filtered xenon-arc lamp is found to provide a reasonable match to indirect, window-filtered daylight<sup>[6][7][8]</sup>. The specimen temperature is dominated by ambient conditions.

### 7.2.2 Filters to simulate general indoor display conditions

This filter system shall consist of window-glass filters and an additional UV cut-off filter that has 50 % transmittance at a wavelength between 370 nm and 375 nm. The resulting spectral irradiance shall be in accordance with [Table 1](#).

Examples of the standard UV cut-off filter and their corresponding spectral transmission characteristics are shown in [Table A.1](#) and [Table A.2](#).

NOTE 1 The window-glass filters with a spectral irradiance conforming to [Table 3](#) can be used.

NOTE 2 Examples of an acceptable UV cut-off filter are L-37 (Hoya Co.) and SC-37 (Fujifilm Co.).

In order to maintain conformity, the filter shall be cleaned or replaced per OEM instructions.

Optical filters shall be positioned according to the second paragraph of [5.1.2](#).

[Table 1](#) provides the relative spectral irradiance in the given passband, expressed as a percentage of the total irradiance between 300 nm and 800 nm.

**Table 1 — Relative spectral irradiance for filtered Xenon-arc lamp for simulated general indoor display**

Spectral passband wavelength, $\lambda$ nm	Relative spectral irradiance %
$300 \leq \lambda < 340$	0,0 to 0,1
$340 \leq \lambda < 370$	0,2 to 1,0
$370 \leq \lambda < 400$	2 to 5
$400 \leq \lambda < 430$	4 to 8
$430 \leq \lambda < 800$	86 to 93

### 7.2.3 Radiation intensity, temperature, and humidity

The following range of set points given in [Table 2](#) shall be used, with acceptable deviations based on the data provided in [Annex B](#).

**Table 2 — Set values for simulated general indoor display**

Illuminance at the specimen plane (klx)	$\leq 80$
Black panel temperature (uninsulated) (°C)	25 to 35
Chamber air temperature (°C)	21 to 27
Relative humidity (%RH)	50

The tolerance of operational fluctuation for the parameters above are listed in ISO 18937-1.



The radiation intensity, black panel temperature, and chamber air temperature range of set points in the above table are intended to result in a photographic print exposed under these conditions to be indirectly controlled at a temperature between 25 °C to 30 °C. The construction and absorption properties of the black panel temperature will result in temperatures 3 °C to 8 °C higher than the photographic prints exposed, as shown by the data in [Annex B](#).

An IR-reducing filter can be used if the uninsulated black panel temperature and/or chamber temperature cannot be controlled at the set points listed.

NOTE [Annex B](#) provides a table of temperature measurement data of a gray (0,75 OD) target sample with a variety of illuminance and chamber temperature settings, as well as with/without IR-attenuating filters. Combinations of these variables can be used based on guidance from this table in order to achieve the targeted sample temperature of 25 °C to 30 °C.

Radiation intensity can be measured in irradiance units in place of the stated illuminance units. When testing with the L-37 or SC-37 filter, light intensity shall be measured in lux with an illuminance meter or in irradiance with an irradiance meter. If radiation intensity is measured in irradiance units in place of the stated illuminance units, irradiance may be controlled at 420 nm. Contact the radiant exposure apparatus manufacturer to obtain appropriate conversions from illuminance to irradiance.

### 7.3 Simulated in-window display

#### 7.3.1 Application

This test is intended to simulate terrestrial daylight transmitted through standard architectural window glass (double glazing). A typical example of such display can be found when images are displayed in store windows, facing toward the outdoors, so that they may be viewed by people outside of the store<sup>[2][5]</sup>.

Two testing conditions are noted. [Table 4](#) describes a test that includes higher temperatures caused by strong radiative heating, and light/dark cycling to promote stress fatigue. The cycling simulates episodes with elevated temperature differences between colours and between the imaging layer and support, as well as episodes of elevated specimen temperature with reduced moisture content (hot light phase) and remoistening (cool dark phase). [Table 5](#) describes a continuous light test at lower temperatures to simulate limited radiative heating, such as show windows in an air-conditioned air space, with sun shade or orientation away from the equator. The continuous light simulates limited stress fatigue as compared to the cyclic test conditions.

#### 7.3.2 Filtered xenon arc configuration to simulate in-window display conditions

This filter system shall consist of a window-glass filter with spectral irradiance in accordance with [Table 3](#) and may be used with or without a standard IR filter (the IR filter can be used if it is necessary to attain the black panel temperature).

In order to maintain conformance, the filter shall be cleaned or replaced per OEM instructions.

Optical filters shall be positioned according to the second paragraph of [5.1.2](#).

[Table 3](#) gives the relative spectral irradiance in the given bandpass, expressed as a percentage of the total irradiance between 300 nm and 800 nm.

**Table 3 — Relative spectral irradiance for filtered Xenon-arc lamp for in-window display**

<b>Spectral bandpass</b> <b>Wavelength, <math>\lambda</math></b> nm	<b>Relative spectral irradiance</b> %
$300 \leq \lambda < 340$	0,2 to 1,2
$340 \leq \lambda < 370$	2,8 to 3,5
$370 \leq \lambda < 400$	3 to 5
$400 \leq \lambda < 430$	4 to 7
$430 \leq \lambda < 800$	83 to 88

### 7.3.3 Radiation intensity, temperature and humidity

Two test cycles are listed: a light/dark cycling test and a continuous light test. The conditions for the light cycle and dark cycle are shown in [Table 4](#). The conditions for the continuous light test are shown in [Table 5](#).

Depending on the intended use profile, of the of sets of set points in [Table 4](#) or [Table 5](#) shall be used:

**Table 4 — Set values for light/dark cycling conditions for simulated in-window display**

<b>Parameter</b>	<b>Light phase</b>	<b>Dark phase</b>
Illuminance at the specimen plane (klx)	$\leq 100$	Not controlled
Phase duration (hours)	3,8	1,0
Black panel temperature (uninsulated) (°C)	63	Not controlled
Chamber air temperature (°C)	40	25
Relative humidity (%RH)	40	80

**Table 5 — Set values for continuous conditions for simulated in-window display**

<b>Parameter</b>	<b>Conditions</b>
Illuminance at the specimen plane (klx)	50 to 80
Black panel temperature (uninsulated) (°C)	35
Chamber air temperature(°C)	25
Relative humidity (%RH)	50

The tolerance of operational fluctuation for the parameters above are listed in ISO 18937-1.

Radiant intensity can be measured in irradiance units in place of the stated illuminance units. Contact the radiant exposure apparatus manufacturer to obtain appropriate conversions from illuminance to irradiance.

Exposures to simulate other specific use-cases (backlit displays, for example) may require different exposure conditions than those referenced in the previous sections.

## 8 Test result measurement and report

Reporting requirements are listed in ISO 18937-1:2023, Clause 8.