



Standard Specification for Cationic Emulsified Asphalt¹

This standard is issued under the fixed designation D2397; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This specification covers seven grades of cationic emulsified asphalt for use in pavement construction in the manner designated.

2. Referenced Documents

2.1 *ASTM Standards:*²

[D140 Practice for Sampling Bituminous Materials](#)

[D244 Test Methods and Practices for Emulsified Asphalts](#)

[D3910 Practices for Design, Testing, and Construction of Slurry Seal](#)

[D6930 Test Method for Settlement and Storage Stability of Emulsified Asphalts](#)

[D6933 Test Method for Oversized Particles in Emulsified Asphalts \(Sieve Test\)](#)

[D6935 Test Method for Determining Cement Mixing of Emulsified Asphalt](#)

[D6936 Test Method for Determining Demulsibility of Emulsified Asphalt](#)

[D6997 Test Method for Distillation of Emulsified Asphalt](#)

[D7402 Practice for Identifying Cationic Emulsified Asphalts](#)

[D7496 Test Method for Viscosity of Emulsified Asphalt by Saybolt Furol Viscometer](#)

3. Requirements

3.1 The emulsified asphalt shall be tested within 14 days of delivery. The emulsified asphalt shall be homogeneous after thorough mixing provided separation has not been caused by freezing. Emulsions separated by freezing shall not be tested.

3.2 Emulsified asphalt shall conform to the requirements prescribed in [Table 1](#).

4. Sampling

4.1 Samples of emulsified asphalt shall be taken in accordance with Practice [D140](#).

4.2 Samples shall be stored in clean, airtight sealed containers at a temperature of not less than 4°C (39.2°F) until tested.

5. Test Methods

5.1 The properties of the emulsified asphalts given in [Table 1](#) shall be determined in accordance with the following ASTM test methods:

5.1.1 *Viscosity*—Test Method [D244D7496](#).

5.1.2 *Storage Stability*—Test Method [D6930](#).

5.1.3 *Demulsibility*—Test Method [D6936](#).

5.1.4 *Coating Ability and Water Resistance*—Test Methods [D244](#).

5.1.5 *Particle Charge*—Test Method [D244D7402](#).

5.1.6 *Sieve Test*—Test Method [D6933](#), except use distilled water in all wetting and washing operations in place of the nonionic surfactant solution (1 %).

5.1.7 *Cement Mixing*—Test Method [D6935](#).

5.1.8 *Distillation*—Test Method [D6997](#).

5.1.9 *Tests on Residue from Distillation*—Test Methods [D244](#).

6. Keywords

6.1 cationic; emulsified asphalt; emulsion; medium setting; rapid setting; slow setting