

SLOVENSKI STANDARD

SIST EN 658-3:2004

01-januar-2004

Nadomešča:
SIST ENV 658-3:2000

Advanced technical ceramics - Mechanical properties of ceramic composites at room temperature - Part 3: Determination of flexural strength

Advanced technical ceramics - Mechanical properties of ceramic composites at room temperature - Part 3: Determination of flexural strength

Hochleistungskeramik - Mechanische Eigenschaften von keramischen Verbundwerkstoffen bei Raumtemperatur - Teil 3: Bestimmung der Biegefestigkeit

Céramiques techniques avancées - Propriétés mécaniques des céramiques composites à température ambiante - Détermination de la résistance en flexion

Ta slovenski standard je istoveten z: EN 658-3:2002

ICS:

81.060.30 Sodobna keramika Advanced ceramics

SIST EN 658-3:2004

en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 658-3:2004

<https://standards.iteh.ai/catalog/standards/sist/a834774c-8448-4f38-b8b5-63fd8511b4c/sist-en-658-3-2004>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 658-3

August 2002

ICS 81.060.30

Supersedes ENV 658-3:1992

English version

**Advanced technical ceramics - Mechanical properties of ceramic
composites at room temperature - Part 3: Determination of
flexural strength**

Céramiques techniques avancées - Propriétés mécaniques
des céramiques composites à température ambiante -
Détermination de la résistance en flexion

Hochleistungskeramik - Mechanische Eigenschaften von
keramischen Verbundwerkstoffen bei Raumtemperatur -
Teil 3: Bestimmung der Biegefestigkeit

This European Standard was approved by CEN on 6 July 2002.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

<https://standards.iteh.ai/catalog/standards/sist/a834774c-8448-4f38-b8b5-63fd8511b4c/sist-en-658-3-2004>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

	page
Foreword	3
1 Scope	4
2 Normative references	4
3 Principle	4
4 Terms, definitions and symbols	4
5 Apparatus	5
5.1 Test machine	5
5.2 Test jig	5
5.3 Data recording system	5
5.4 Dimension measuring devices	5
6 Test specimens	5
7 Test specimen preparation	6
7.1 Machining and preparation	6
7.2 Number of test specimens	6
8 Test procedures	7
8.1 Displacement rate	7
8.2 Measurement of dimensions	7
8.3 Testing technique	7
8.4 Test validity	8
9 Calculation of results	8
9.1 Test specimen origin	8
9.2 Flexural strength	8
10 Test report	9
Bibliography	11

Foreword

This document (EN 658-3:2002) has been prepared by Technical Committee CEN/TC 184 "Advanced technical ceramics", the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by February 2003, and conflicting national standards shall be withdrawn at the latest by February 2003.

This document supersedes ENV 658-3:1992.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

EN 658 has six parts:

- *Part 1: Determination of tensile properties.*
- *Part 2: Determination of compressive properties.*
- *Part 3: Determination of flexural strength.*
- *Part 4: Determination of interlaminar shear strength by compression loading of notched test specimens.*
- *Part 5: Determination of interlaminar shear strength by short span bend test (three-points).*
- *Part 6: Determination of interlaminar shear strength by double-punch shearing.*

EN 658-3:2002 (E)

1 Scope

This part of EN 658 describes a method for the determination of the flexural strength of ceramic matrix composite materials with continuous fibre reinforcement, under three-point or four-point bend at room temperature. This method applies to all ceramic matrix composites with a continuous fibre reinforcement, unidirectional (1D), bidirectional (2D), and tridirectional xD with ($2 < x \leq 3$) as defined in ENV 13233, loaded along one principal axis of reinforcement.

NOTE The method should not be used to obtain absolute values of strength for design purposes.

2 Normative references

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text, and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

EN ISO 7500-1, *Metallic materials - Verification of static uniaxial testing machines - Part 1: Tension/compression testing machines (ISO 7500-1:1999)*.

ENV 13233, *Advanced technical ceramics — Ceramic composites — Notations and symbols*.

ISO 3611, *Micrometer callipers for external measurements*.

STANDARD PREVIEW
(standards.iteh.ai)

3 Principle

SIST EN 658-3:2004

A test specimen of specified dimensions is flexion loaded to fracture in such a way that failure occurs in tension or compression along one principal axis of reinforcement. The test is performed at constant crosshead displacement rate.

4 Terms, definitions and symbols

For the purposes of this European Standard, the following terms, definitions and symbols and those given in ENV 13233 apply.

4.1

maximum flexural force, F_m

highest recorded force in a flexural test on the test specimen when tested to failure

4.2

flexural stress, σ

the nominal stress on the outer surface of the test specimen, calculated at mid-span

NOTE This stress is conventionally calculated according to the beam theory, whose basic assumptions cannot be met by ceramic matrix composite materials.

4.3

flexural strength, $\sigma_{f,m}$

maximum flexural stress applied to a test specimen that fractures during a flexural test

5 Apparatus

5.1 Test machine

The machine shall be equipped with a system for measuring the force applied to the test specimen. The system shall conform to grade 1 according to EN ISO 7500-1.

5.2 Test jig

The test jig is composed of two parts, linked to the fixed and mobile parts of the machine. It has two outer support rollers and one (three-point bend) or two (four-point bend) inner support rollers.

The cylindrical rollers shall have a diameter of 4 mm to 10 mm. Their length shall be at least equal to the width of the test specimen. They shall be made of a material with a hardness at least equal to that of the test specimen. The axes of the rollers shall be parallel to within 0,01 mm/mm.

The outer rollers (three and four-point bend) and inner rollers (four-point bend) shall be free to rotate (see Figure 1).

Either two or three rollers, for three-point or four-point bend respectively, shall be free to pivot around an axis parallel to the longitudinal direction of the test specimen, in order to adapt to the non-parallelism of the upper and lower faces of unmachined test specimens (see Figure 1).

The distance between rollers shall be in accordance with clause 6.

The inner rollers shall be centred with respect to the outer rollers to within 0,2 mm. In the case of four-point bend, the test jig shall ensure symmetrical loading of the test specimen.

5.3 Data recording system

SIST EN 658-3:2004

<https://standards.iteh.ai/catalog/standards/sist/a834774c-8448-4f38-b8b5-65831b-402d-en-658-3-2004>

A calibrated recorder shall be used to record the force-time curve. The use of a digital data recording system combined with an analogue recorder is recommended.

5.4 Dimension measuring devices

Devices used for measuring linear dimensions of the test specimen shall be accurate to $\pm 0,1$ mm. Micrometers shall be in accordance with ISO 3611.

6 Test specimens

Recommended test specimen dimensions are given in Table 1. These dimensions have been successfully used and take into account the following factors:

- the amount of material under load shall be representative of the nature of the material and of the reinforcement structure. This sets minimum limits to the span and to the width and thickness of the test specimen. In the case of flexural, as opposed to tensile testing, the distribution of the longitudinal reinforcement through the thickness has to be considered. When this distribution is not symmetrical with respect to the neutral plane, care shall be taken to ensure that it is similar between test specimens.

Two types of test specimens can be distinguished:

- as fabricated test specimens, where only the length and the width are machined to give to the test specimens the specified size. In this case the tensile and compressive surfaces may be unmachined and thus irregular;
- machined test specimens, where the length, the width and the thickness of the test specimen have been machined.

EN 658-3:2002 (E)

Tolerance on thickness is only for machined test specimens. For as fabricated test specimens, the maximum difference in thickness of three measurements (at the centre and at each end of the outer span length) shall not exceed 5 % of the average of the three measurements.

The thickness of the test specimen and the distance between the inner and outer roller(s) shall be chosen so as to avoid shear failure. This is achieved by setting a minimum limit to the ratio between the moment arm and the test specimen thickness (see Table 1). A value of 10 is commonly used and translates into a minimum L/h ratio of 20 in three-point bend, and a minimum $(L-L_i)/h$ ratio of 20 in four-point bend with $L_i = L/3$.

Table 1 — Recommended test specimen and span dimensions

Dimensions in millimetres

	1D, 2D, xD	Tolerance
l_t , total length	$L+10$	± 1
b , width	10	$\pm 0,2$
h , thickness	2,5	$\pm 0,2$
Inner span L_i , four-point bend	25	$\pm 0,1$
Outer span L , four-point bend L , three-point bend	75 50	$\pm 0,1$ $\pm 0,1$

NOTE If it is necessary to define test specimens of different dimensions, the conditions of clause 6 should be taken into account.

SIST EN 658-3:2004

<https://standards.iteh.ai/catalog/standards/sist/a834774c-8448-4f38-b8b5-63f6d8511b4c/sist-en-658-3-2004>

7 Test specimen preparation

7.1 Machining and preparation

During cutting out, care shall be taken to align the longitudinal test specimen axis with one of the principal axes of reinforcement.

Test specimens may be tested with either machined or non-machined tensile and compressive surfaces. In some cases machining is not recommended because it may cause damage to the material near the tensile and compressive surfaces. When machining these surfaces, care shall be taken to maintain a reinforcement geometry across the thickness of the test specimen, which is representative of the material in the as-processed condition. In particular, it shall be assured that the symmetry of an originally symmetric reinforcement geometry is preserved in the test specimen cross section after machining.

Machining parameters which avoid damage to the material shall be established and documented. These parameters shall be adhered to during test specimen preparation.

7.2 Number of test specimens

At least five valid test results (8.4) are required.

For test specimens with a non-symmetric reinforcement geometry with respect to the neutral plane, tests in two orientations for which the tensile and compressive face are interchanged may be necessary.

NOTE If statistical evaluation is required, the number of test specimens should be in accordance with ENV 843-5.

8 Test procedures

8.1 Displacement rate

Use a crosshead displacement rate which allows test specimen failure within 1 min. The displacement rate shall be reported.

8.2 Measurement of dimensions

8.2.1 Test specimen dimensions

The width and thickness shall be measured to the nearest 0,01 mm in three points near the centre for three-point bend and between the inner rollers for four-point bend, and at each end of the test specimen.

The arithmetic means of the measurements shall be used for calculations.

8.2.2 Distances between supporting rollers

The distance between axes of the outer rollers and for four-point bend also the inner rollers, shall be measured to the nearest 0,1 mm.

NOTE This can be achieved by the use of a travelling microscope or other suitable device accurate to 0,05 mm.

8.3 Testing technique iTeh STANDARD PREVIEW (standards.iteh.ai)

8.3.1 Test specimen mounting

The test specimen shall be installed in the test jig, centred with respect to the rollers and with its longitudinal axis perpendicular to the axes of the rollers.

NOTE It is recommended to use a setting tool for this purpose.

Zero the load cell output. When required, a small preload can be applied in order to maintain correct positioning of the test specimen. This preload shall not increase beyond 5 % of the expected failure force at any time.

8.3.2 Measurements

- set the displacement rate on the test machine;
- zero the load cell;
- record the force versus time;
- load the test specimen up to failure;
- read the load signal after test specimen failure;
- note the position of fracture location relative to the mid-point of the test specimen to the nearest 1 mm and the failure mode (tensile or compressive).