# INTERNATIONAL STANDARD

ISO 6128

First edition 2023-07

### Laminated products made of bamboo strips for indoor furniture purposes — Requirements and test methods

# iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>ISO 6128:2023</u> https://standards.iteh.ai/catalog/standards/sist/37bac8dc-3213-4f82-8c71ad00df939817/iso-6128-2023



Reference number ISO 6128:2023(E)

# iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 6128:2023

https://standards.iteh.ai/catalog/standards/sist/37bac8dc-3213-4f82-8c71ad00df939817/iso-6128-2023



#### **COPYRIGHT PROTECTED DOCUMENT**

© ISO 2023

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office CP 401 • Ch. de Blandonnet 8 CH-1214 Vernier, Geneva Phone: +41 22 749 01 11 Email: copyright@iso.org Website: <u>www.iso.org</u>

Published in Switzerland

Page

### Contents

Fore	eword	iv		
Intro	roduction	V		
1	Scope			
2	Normative references			
3	Terms and definitions	1		
4	Requirements			
	<ul> <li>4.1 Appearance requirements</li> <li>4.2 Dimension requirements</li> <li>4.3 Property requirements</li> <li>4.3.1 Physical properties requirements</li> <li>4.3.2 Mechanical properties requirements</li> <li>4.4 Formaldehyde emission</li> <li>4.5 Treatment and durability</li> <li>4.6 Other declarations at the time of the first delivery</li> </ul>	2 2 3 3 3 3 4 4		
5	Handling, storage, packaging and marking5.1Handling, storage and packaging5.2Marking			
Anno	nex A (normative) Determination of moisture content	5		
	nex B (informative) Examples of different types of construction			
Bibli	liography	7		

ISO 6128:2023

https://standards.iteh.ai/catalog/standards/sist/37bac8dc-3213-4f82-8c71ad00df939817/iso-6128-2023

### Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see <a href="https://www.iso.org/directives">www.iso.org/directives</a>).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at <u>www.iso.org/patents</u>. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 296, Bamboo and rattan.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at <u>www.iso.org/members.html</u>.

### Introduction

Laminated bamboo products are used for purposes such as construction, furniture, handicrafts and novelty items. These products, such as floor planks or boards, have a large market in the construction industry. Furniture for the "high end" and "do-it-yourself "markets has also found an application of laminated bamboo products. These products are one of the main materials for bamboo furniture. Accordingly, the market for laminated bamboo furniture is growing steadily. In 2018, the market size for bamboo furniture was valued at USD 10,09 billion and is expected to grow at a compound annual growth rate (CAGR) of 5,2 % from 2019 to 2025.

In view of the above, such applications of laminated bamboo in the furniture industry warrant the development of a standard testing procedure and property requirements. This document aims to address the need for a standard for laminated products made of bamboo strips for indoor furniture purposes.

# iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 6128:2023 https://standards.iteh.ai/catalog/standards/sist/37bac8dc-3213-4f82-8c71ad00df939817/iso-6128-2023

# iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>ISO 6128:2023</u> https://standards.iteh.ai/catalog/standards/sist/37bac8dc-3213-4f82-8c71ad00df939817/iso-6128-2023

# Laminated products made of bamboo strips for indoor furniture purposes — Requirements and test methods

#### 1 Scope

This document specifies the requirements and test methods for laminated products made of bamboo strips for indoor furniture purposes.

It also specifies handling, storage, packaging and marking requirements.

#### 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 9426, Wood-based panels — Determination of dimensions of panels

ISO 9427, Wood-based panels — Determination of density

ISO 12466-1, Plywood — Bonding quality — Part 1: Test methods

ISO 12466-2, Plywood — Bonding quality — Part 2: Requirements

ISO 16979, Wood-based panels — Determination of moisture content

ISO 13061-12, Physical and mechanical properties of wood — Test methods for small clear wood specimens — Part 12: Determination of static hardness

ISO 21625, Vocabulary related to bamboo and bamboo products

#### 3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 21625 and the following apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

— ISO Online browsing platform: available at <u>https://www.iso.org/obp</u>

— IEC Electropedia: available at <u>https://www.electropedia.org/</u>

#### 3.1

#### plank

flat and rectangular piece of board which is longer than it is wide (narrow), typically used for flooring

#### 3.2

panel

rectangular thin sheet, typically used for panelling

#### 3.3

#### lumber

long, rectangular cross-section members, commonly used for framing

#### 3.4

#### construction

arrangement of the strips in a *plank* (<u>3.1</u>), *panel* (<u>3.2</u>), or *lumber* (<u>3.3</u>)

#### **Requirements** 4

#### **Appearance requirements** 4.1

The material used for laminated bamboo products for indoor furniture purposes shall be free from physical damage, decay and insect attack.

There are variations from element to element, but the total impression of laminated bamboo products shall show a homogeneous character.

Any part of the material that impedes preservation, bonding and finishing shall be removed entirely.

As bamboo is a natural material, colour variations may occur, also due to the effect of light over time.

The appearance requirements of laminated bamboo shall be as indicated in Table 1.

Types of defects	Face layer	Sub/ middle layer(s)	
Bamboo outer layer	Not permitted	Not permitted	
Bamboo inner layer		Permitted if this does not impair the bonding strength be- tween the strips and/or the layers of the laminated bamboo product <sup>a</sup>	
Splinters	Not permitted	Permitted as long as these splinters do not impair the use quality of the laminated bamboo product <sup>b</sup>	
Cracks	Permitted as long as these cracks and/or gaps do not impair the use quality of the lami		
Gaps	(stan	a nated bamboo product <sup>c</sup>	
Delamination	Not permitted	Not permitted	
Glue penetration	Not permitted	Permitted as long as the glue penetration does not impair the use quality of the laminated bamboo product <sup>d</sup>	
<sup>a</sup> If the bonding strength between the strips and/or the layers of the laminated bamboo product is impaired by the			

#### Table 1 — Appearance requirements

bamboo inner layer, they shall be removed.

b If the use quality of the laminated bamboo product is impaired by splinters, they shall be removed.

с If the use quality of the laminated bamboo product is impaired by cracks and/or gaps, they shall be filled.

d If the use quality of the laminated bamboo product is impaired by glue penetration, the glue marks shall be removed.

#### 4.2 Dimension requirements

The common dimension requirements for laminated bamboo shall be as specified in Table 2. Other specific dimensions of the product are permitted upon agreement of both the supplier and buyer.

Test method	Product	Common product dimensions	Number of layers	Require- ments
ISO 9426	Plank	1 000 ~ 3 000	—	+5
	Panel	1 000 ~ 4 000	—	
	Lumber	1 000 ~ 5 800		
ISO 9426	Plank	60 ~ 300		
	Panel	600 ~ 1 200		+2
	Lumber	50 ~ 200		-
ISO 9426	Plank / Panel	3 ~ 20	1	±0,5
		7~40	2-5	-
	Lumber	40 ~ 200	>2	
ISO 9426			<1	
	_			±1
1				<3
	method ISO 9426 ISO 9426 ISO 9426	methodPlankISO 9426PanelLumberPlankISO 9426PanelLumberISO 9426Plank / PanelLumber	method         dimensions           ISO 9426         Plank         1 000 ~ 3 000           ISO 9426         Panel         1 000 ~ 4 000           Lumber         1 000 ~ 5 800           ISO 9426         Plank         60 ~ 300           ISO 9426         Panel         600 ~ 1 200           Lumber         50 ~ 200         1000           ISO 9426         Plank / Panel         3 ~ 20           ISO 9426         Lumber         40 ~ 200	method         dimensions         layers           ISO 9426         Plank $1000 \sim 3000$ —           ISO 9426         Panel $1000 \sim 4000$ —           Lumber $1000 \sim 5800$ —           ISO 9426         Plank $60 \sim 300$ —           ISO 9426         Panel $600 \sim 1200$ —           ISO 9426         Panel $600 \sim 1200$ —           ISO 9426         Panel $50 \sim 200$ —           ISO 9426         Panel $7 \sim 40$ 2–5           Lumber $40 \sim 200$ >2

Table 2 — Dimension requirements

#### 4.3 Property requirements

## standards.iteh.ai)

#### 4.3.1 Physical properties requirements

The physical requirements for laminated bamboo shall be as indicated in <u>Table 3</u>.

https://standards.iteh.ai/catalog/standards/sist/37bac8dc-3213-4f82-8c71-

#### Table 3 — Physical requirements

Parameters	Test method	Requirements		
MC (%)	<u>Annex A</u>	$5,0 \le MC \le EMC$		
		or agreement between supplier and customer		
Density (kg/m <sup>3</sup> )	ISO 9427	≥500		
Key				
MC Moisture content				
EMC Equilibrium Moisture Content				

#### 4.3.2 Mechanical properties requirements

The mechanical properties of the laminated bamboo and the minimum requirements depend on the design of the final use of the product. The information shall be provided by the supplier of the laminated bamboo. The mechanical requirements for laminated bamboo shall be as indicated in <u>Table 4</u>, which illustrates the mechanical property requirements of laminated bamboo products for indoor furniture purposes.

Parameters	Test method	Requirements
Hardness (N)	ISO 13061-12	≥ 4 000
Bonding quality	ISO 12466-1	Class 1 or Class 2 (as per ISO 12466-2)

#### 4.4 Formaldehyde emission

It is expected that formaldehyde emission of laminated bamboo complies with the requirements of the country/locality where it will be used.

#### 4.5 Treatment and durability

In case the durability of the final product shall be improved, the bamboo strips can be treated with environment-friendly processes and/or preservatives such as, but not limited to, those without heavy metals that can harm the environment.

#### 4.6 Other declarations at the time of the first delivery

Where it is applicable, the following can be applicable to the bamboo furniture or can be declared accordingly if required by local regulations: emissions and content of dangerous substances, reaction to fire, thermal properties, and biological durability.

#### 5 Handling, storage, packaging and marking

#### 5.1 Handling, storage and packaging

The manufacturer shall have procedures for providing methods of product handling and packaging, and shall provide suitable storage areas to prevent damage or deterioration.

#### 5.2 Marking

### (standards.iteh.ai)

By agreement between the buyer and supplier, the package shall be clearly marked with the following minimum information:

<u>1SO 6128:2023</u>

- name and address of the manufacturer or supplier; ards/sist/37bac8dc-3213-4f82-8c71-
- trade name;
- reference to this document, i.e. ISO 6128:2023;
- dimensions;
- construction (see examples in <u>Annex B</u>);
- category: plank/panel/lumber (optional);
- bamboo species;
- date of production and/or batch number;
- quantity of products.