



Designation: A217/A217M – 12

Endorsed by Manufacturers Standardization Society
of the Valve and Fittings Industry
Endorsed by American Foundrymen's Society
Used in USDOE-NE Standards

Standard Specification for Steel Castings, Martensitic Stainless and Alloy, for Pressure-Containing Parts, Suitable for High-Temperature Service¹

This standard is issued under the fixed designation A217/A217M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope*

1.1 This specification² covers martensitic stainless steel and alloy steel castings for valves, flanges, fittings, and other pressure-containing parts (**Note 1**) intended primarily for high-temperature and corrosive service (**Note 2**).

1.2 One grade of martensitic stainless steel and nine grades of ferritic alloy steel are covered. Selection will depend on design and service conditions, mechanical properties, and the high-temperature and corrosion-resistant characteristics (**Note 3**).

NOTE 1—Carbon steel castings for pressure-containing parts are covered by Specification **A216/A216M**. Low alloy quench-and-tempered grades equivalent to Specification A217/A217M grades may be found in both Specifications **A352/A352M** and **A487/A487M**.

NOTE 2—The grades covered by this specification represent materials that are generally suitable for assembly with other castings or wrought steel parts by fusion welding. It is not intended to imply that these grades possess equal degrees of weldability; therefore, it is the responsibility of the purchaser to establish for himself a suitable welding technique. Since these grades possess varying degrees of suitability for high-temperature and corrosion-resistant service, it is also the responsibility of the purchaser to determine which grade shall be furnished, due consideration being given to the requirements of the applicable construction codes.

NOTE 3—The committee formulating this specification has included nine grades of materials that are considered to represent basic types of ferritic alloy steels suitable for valves, flanges, fittings, and other pressure-containing parts. Additional alloy steels that may better fulfill certain types of service will be considered for inclusion in this specification by the committee as the need becomes apparent.

1.3 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each

¹ This specification is under the jurisdiction of ASTM Committee **A01** on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee **A01.18** on Castings.

Current edition approved Nov. 1, 2012. Published November 2012. Originally approved in 1939. Last previous edition approved in 2011 as A217/A217M – 11. DOI: 10.1520/A0217_A0217M-12.

² For ASME Boiler and Pressure Vessel Code applications, see related Specification SA-217/SA 217M in Section II of that code.

system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

2. Referenced Documents

2.1 ASTM Standards:³

A216/A216M Specification for Steel Castings, Carbon, Suitable for Fusion Welding, for High-Temperature Service
A352/A352M Specification for Steel Castings, Ferritic and Martensitic, for Pressure-Containing Parts, Suitable for Low-Temperature Service

A487/A487M Specification for Steel Castings Suitable for Pressure Service

A488/A488M Practice for Steel Castings, Welding, Qualifications of Procedures and Personnel

A703/A703M Specification for Steel Castings, General Requirements, for Pressure-Containing Parts

A802/A802M Practice for Steel Castings, Surface Acceptance Standards, Visual Examination

A985/A985M Specification for Steel Investment Castings General Requirements, for Pressure-Containing Parts

E165 Practice for Liquid Penetrant Examination for General Industry

E709 Guide for Magnetic Particle Testing

2.2 AWS Specifications:⁴

A5.5/A5.5M Low Alloy Steel Electrodes for Shielded Metal Arc Welding

A5.23/A5.23M Low-Alloy Steel Electrodes and Fluxes for Submerged Arc Welding

A5.28/A5.28M Low Alloy Steel Electrodes and Rods for Gas Shielded Arc Welding

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

⁴ Available from American Welding Society, 550 NW LeJeune Rd., Miami, FL 33126, http://www.aws.org.

***A Summary of Changes section appears at the end of this standard**

A5.29/A5.29M Low-Alloy Steel Electrodes for Flux Cored Arc Welding

3. General Conditions for Delivery

3.1 Except for investment castings, castings furnished to this specification shall conform to the requirements of Specification **A703/A703M** including any supplementary requirements that are indicated in the purchase order. Failure to comply with the general requirements of Specification **A703/A703M** constitutes nonconformance with this specification. In case of conflict between the requirements of this specification and Specification **A703/A703M**, this specification shall prevail.

3.2 Steel investment castings furnished to this specification shall conform to the requirements of Specification **A985/A985M**, including any supplementary requirements that are indicated in the purchase order. Failure to comply with the general requirements of Specification **A985/A985M** constitutes nonconformance with this specification. In case of conflict between the requirements of this specification and Specification **A985/A985M**, Specification **A985/A985M** shall prevail.

4. Ordering Information

4.1 The inquiry and order should include or indicate the following:

- 4.1.1 A description of the casting by pattern number or drawing (dimensional tolerances shall be included on the casting drawing),
- 4.1.2 Grade of steel,
- 4.1.3 Options in the specification,
- 4.1.4 Whether the castings are to be produced using the investment casting process, and
- 4.1.5 The supplementary requirements desired including the standards of acceptance.

5. Heat Treatment

5.1 All castings shall receive a heat treatment proper to their design and chemical composition.

5.2 Castings shall be furnished in the normalized and tempered conditions; Grades WC1, WC4, WC5, WC6, and CA15 shall be tempered at 1100°F [595°C] min; Grades WC9, C5, C12, and WC11 shall be tempered at 1250°F [675°C] min; Grade C12A shall be thermally treated, either by normalizing-and-tempering or by accelerated cooling from the austenitizing temperature by air blasting or liquid quenching, followed by tempering. C12A castings shall be austenitized at 1900-1975°F [1040-1080°C] and tempered at 1350-1470°F [730-800°C].

5.3 Heat treatment shall be performed after castings have been allowed to cool below the transformation range.

Tech Standards
(<https://standards.iteh.ai>)
Document Preview

TABLE 1 Chemical Requirements^A

NOTE 1—All values are maximum unless otherwise indicated.

Grade Identification Symbol	Composition, %									
	Carbon Molybdenum	Nickel Chromium Molybdenum	Nickel Chromium Molybdenum	Chromium Molybdenum	Chromium Molybdenum	Chromium Molybdenum	Chromium Molybdenum	Chromium Molybdenum	Chromium Molybdenum Vanadium	Chromium
UNS Number	J12524	J12082	J22000	J12072	J21890	J11872	J42045	J82090	J84090	J91150
Carbon	0.25	0.05–0.20	0.05–0.20	0.05–0.20	0.05–0.18	0.15–0.21	0.20	0.20	0.08–0.12	0.15
Manganese	0.50–0.80	0.50–0.80	0.40–0.70	0.50–0.80	0.40–0.70	0.50–0.80	0.40–0.70	0.35–0.65	0.30–0.60	1.00
Phosphorus	0.04	0.04	0.04	0.035	0.035	0.020	0.04	0.035	0.025	0.040
Sulfur	0.045	0.045	0.045	0.035	0.035	0.015	0.045	0.035	0.010	0.025
Silicon	0.60	0.60	0.60	0.60	0.60	0.30–0.60	0.75	1.00	0.20–0.50	1.50
Nickel	...	0.70–1.10	0.60–1.00	0.40	1.00
Chromium	...	0.50–0.80	0.50–0.90	1.00–1.50	2.00–2.75	1.00–1.50	4.00–6.50	8.00–10.00	8.0–9.5	11.5–14.0
Molybdenum	0.45–0.65	0.45–0.65	0.90–1.20	0.45–0.65	0.90–1.20	0.45–0.65	0.45–0.65	0.90–1.20	0.85–1.05	0.50
Columbium	0.03	0.060–0.10	...
Nitrogen	0.030–0.070	...
Vanadium	0.06	0.18–0.25	...
Specified Residual Elements										
Aluminum	0.01	0.02	...
Copper	0.50	0.50	0.50	0.50	0.50	0.35	0.50	0.50
Nickel	0.50	0.50	0.50	0.50	0.50	0.50
Chromium	0.35
Titanium	0.01	...
Tungsten	0.10	0.10	0.10	0.10	0.10	...	0.10	0.10
Vanadium	0.03
Zirconium	0.01	...
Total content of these residual elements	1.00	0.60	0.60	1.00	1.00	1.00	1.00	1.00

^A Where ellipses (...) appear in this table, there is no requirement, and the element need not be analyzed for or reported.