



Designation: **B91—07 B91 – 12**

# Standard Specification for Magnesium-Alloy Forgings<sup>1</sup>

This standard is issued under the fixed designation B91; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

## 1. Scope—Scope\*

- 1.1 This specification covers magnesium alloy forgings designated as shown in **Table 1**.
- 1.2 The values stated in inch-pound units are the standard. The SI values in parentheses are provided for information only.

## 2. Referenced Documents

2.1 The following documents of the issue in effect on date of material purchase form a part of this specification to the extent referenced herein:

### 2.2 ASTM Standards:<sup>2</sup>

- [B557 Test Methods for Tension Testing Wrought and Cast Aluminum- and Magnesium-Alloy Products](#)
- [B660 Practices for Packaging/Packing of Aluminum and Magnesium Products](#)
- [B951 Practice for Codification of Unalloyed Magnesium and Magnesium-Alloys, Cast and Wrought](#)
- [B953 Practice for Sampling Magnesium and Magnesium Alloys for Spectrochemical Analysis](#)
- [B954 Test Method for Analysis of Magnesium and Magnesium Alloys by Atomic Emission Spectrometry](#)
- [E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications](#)
- ~~[E35 Test Methods for Chemical Analysis of Magnesium and Magnesium Alloys \(Withdrawn 2008\)](#)~~<sup>3</sup>
- [E55 Practice for Sampling Wrought Nonferrous Metals and Alloys for Determination of Chemical Composition](#)

### 2.3 Federal Standards:

- [No. 123 Marking for Shipment \(Civil Agencies\)](#)<sup>3</sup>
- [No. 184 Identification Marking of Aluminum, Magnesium, and Titanium.](#)

### 2.4 Military Standards:

- [MIL-STD-129 Marking for Shipment and Storage](#)<sup>3</sup>

### 2.5 Military Standards: Aerospace Materials Specification:<sup>4</sup>

- ~~[MIL-M-3171](#)~~ [AMS-M-3171 Magnesium Alloy, Processes for Pretreatment and Prevention of Corrosion on](#)
- ~~[MIL-STD-129 Marking for Shipment and Storage](#)~~<sup>4</sup>

## 3. Terminology

### 3.1 Definitions:

- 3.1.1 *forging*—a metal part worked to a predetermined shape by one or more such processes as hammering, upsetting, pressing, or rolling.
- 3.1.2 *die forging*—a forging formed to the required shape and size by working in impression dies.
- 3.1.3 *hammer forging*—a forging produced by repeated blows in a forging hammer.
- 3.1.4 *hand forging*—a forging worked between flat or simply shaped dies by repeated strokes or blows and manipulation of the piece.

## 4. Ordering Information

- 4.1 Orders for forgings under this specification shall include the following information:
  - 4.1.1 Quantity of each forging,
  - 4.1.2 Alloy (Section 6 and **Table 1**),
  - 4.1.3 Temper (Section 7 and **Table 2**),
  - 4.1.4 Drawing showing dimensions of all die forgings and for all hand forgings not simple disks, rounds, squares, or rectangles (the amount of stock left for machine finish should be indicated),
  - 4.1.5 Surface treatment (see 9.1),

\*A Summary of Changes section appears at the end of this standard

**TABLE 1 Chemical Composition Limits<sup>A,B</sup>**

NOTE 1—Analysis shall regularly be made only for the elements specifically mentioned in this table. If, however, the presence of other elements is suspected or indicated in amounts greater than the specified limits, further analysis shall be made to determine that these elements are not present in excess of the specified limits.

NOTE 2—The following applies to all specified limits in this table. For purposes of acceptance and rejection, an observed value or a calculated value obtained from analysis should be rounded to the nearest unit in the last right-hand place of figures used in expressing the specified limit.

Element	Composition, %			
	Alloy AZ31B (UNS No. M11311)	Alloy AZ61A (UNS No. M11610)	Alloy AZ80A (UNS No. M11800)	Alloy ZK60A (UNS No. M16600)
Magnesium	remainder	remainder	remainder	remainder
Aluminum	2.5–3.5	5.8–7.2	7.8–9.2	...
Manganese	0.20–1.0	0.15–0.5	0.12–0.5	...
Zinc	0.6–1.4	0.40–1.5	0.20–0.8	4.8–6.2
Thorium	...	...	...	...
Zirconium, min	...	...	...	0.45
Silicon	0.10	0.10	0.10	...
Copper	0.05	0.05	0.05	...
Nickel	0.005	0.005	0.005	...
Iron	0.005	0.005	0.005	...
Calcium	0.04	...	...	...
Other impurities <sup>C</sup>	0.30	0.30	0.30	0.30

<sup>A</sup> Limits are in weight percent maximum unless shown as a range or stated otherwise.

<sup>B</sup> These alloy designations were established in accordance with Practice B951.

<sup>C</sup> Includes listed elements for which no specific limit is shown.

**TABLE 2 Tensile Requirements**

NOTE 1—For purposes of determining conformance with this specification, each value for tensile strength and yield strength shall be rounded to the nearest 0.1 ksi (0.7 MPa) and each value for elongation shall be rounded to the nearest 0.5 %, both in accordance with the rounding method of Practice E29.

Alloy and Temper	Tensile Strength, min, ksi (MPa)	Yield Strength <sup>A</sup> (0.2 % offset), min, ksi (MPa)	Elongation in 2 in. (51 mm), or 4 × dia, min, %
AZ31B–F	34.0 (234)	19.0 (131)	6
AZ61A–F	38.0 (262)	22.0 (152)	6
AZ80A–F	42.0 (290)	26.0 (179)	5
AZ80A–T5	42.0 (290)	28.0 (193)	2
ZK60A–T5 die forgings <sup>B</sup>	42.0 (290)	26.0 (179)	7
ZK60A–T6 die forgings <sup>B</sup>	43.0 (296)	32.0 (221)	4

<sup>A</sup> See X1.1.6.

<sup>B</sup> Applicable only to die forgings not more than 3 in. (76 mm) in thickness. The tensile requirements for hand forgings will be lower and as agreed upon by the purchaser and manufacturer.

4.1.6 Whether inspection is required at the manufacturer’s works (see 10.1),

4.1.7 Special inspection requirements (see 10.2),

4.1.8 Whether certification is required (see 12.1), and

4.1.9 Whether marking for identification is required (see 13.1).

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee B07 on Light Metals and Alloys and is the direct responsibility of Subcommittee B07.04 on Magnesium Alloy Cast and Wrought Products.

Current edition approved June 1, 2007; Nov. 1, 2012. Published June 2007; November 2012. Originally approved in 1932. Last previous edition approved in 2004 as B91–97 (2004):B91–07, DOI: 10.1520/B0091-07.10.1520/B0091-12.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard’s Document Summary page on the ASTM website.

<sup>3</sup> Available from Standardization Documents Order Desk, DODSSP, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5098, http://www.dodssp.daps.mil.

<sup>4</sup> Available from SAE International (SAE), 400 Commonwealth Dr., Warrendale, PA 15096-0001, http://www.sae.org.