

DRAFT INTERNATIONAL STANDARD

ISO/DIS 204

ISO/TC 164/SC 1

Secretariat: AFNOR

Voting begins on:
2022-07-07

Voting terminates on:
2022-09-29

Metallic materials — Uniaxial creep testing in tension — Method of test

Matériaux métalliques — Essai de fluage uniaxial en traction — Méthode d'essai

ICS: 77.040.10

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO/FDIS 204

<https://standards.iteh.ai/catalog/standards/sist/8564f46b-cf49-41e6-81fe-942e8a07a371/iso-fdis-204>

This document is circulated as received from the committee secretariat.

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

ISO/CEN PARALLEL PROCESSING



Reference number
ISO/DIS 204:2022(E)

© ISO 2022

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO/FDIS 204

<https://standards.iteh.ai/catalog/standards/sist/8564f46b-cf49-41e6-81fe-942e8a07a371/iso-fdis-204>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2022

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword.....	v
Introduction.....	vi
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	1
4 Symbols and designations.....	6
5 Principle.....	7
6 Apparatus.....	8
6.1 Testing machine.....	8
6.2 Extension and elongation measuring devices.....	8
6.2.1 Extension measuring device.....	8
6.2.2 Elongation measuring device.....	9
6.3 Heating device, temperature measuring equipment and calibration.....	9
6.3.1 Permissible temperature deviations.....	9
6.3.2 Temperature measurement.....	10
6.3.3 Thermocouples.....	11
6.3.4 Calibration of the thermocouples.....	11
7 Test pieces.....	12
7.1 Shape and dimensions.....	12
7.1.1 Shape and dimension of smooth test pieces.....	12
7.1.2 Shape and dimension of notched test pieces.....	13
7.2 Preparation.....	13
7.3 Determination of the original cross-sectional area.....	13
7.4 Marking of the original gauge length, L_0	14
7.5 Determination of the reference length, L_r	14
8 Test procedure.....	15
8.1 Heating of the test piece.....	15
8.2 Application of the test force.....	15
8.3 Test interruptions.....	16
8.3.1 Planned interruptions of the test.....	16
8.3.2 Multiple test piece machine with several test pieces in line.....	16
8.3.3 Combined test.....	16
8.3.4 Accidental interruption of the test.....	16
8.4 Recording of temperature and elongation or extension.....	16
8.4.1 Temperature.....	16
8.4.2 Elongation and extension.....	16
8.4.3 Elongation-time diagram or extension-time diagram.....	17
9 Determination of results.....	17
10 Test validity.....	17
11 Accuracy of the results.....	17
11.1 Expression of the results.....	17
11.2 Final uncertainty.....	17
12 Test report.....	18
Annex A (informative) Information concerning drift of thermocouples.....	23
Annex B (informative) Information concerning methods of calibration of thermocouples.....	26
Annex C (normative) Creep testing using test pieces with V or blunt circumferential notches.....	27

Annex D (informative) Method of estimating the uncertainty of the measurement in accordance with the Guide to the expression of uncertainty in measurement (GUM)	31
Annex E (informative) Representation of results and extrapolation	37
Bibliography	46

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO/FDIS 204

<https://standards.iteh.ai/catalog/standards/sist/8564f46b-cf49-41e6-81fe-942e8a07a371/iso-fdis-204>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 164, *Mechanical testing of metals*, Subcommittee SC 1, *Uniaxial testing*.

This fourth edition cancels and replaces the third edition (ISO 204:2018), which has been technically and editorially revised. The main changes compared to the previous edition are as follows:

- The [Figure 1](#) has been corrected.
- The symbols were revised.
- Formulas in [Table 1](#) has been removed.
- The informative annex relating to computer compatible representation of standards has been deleted.
- Bibliography has been updated.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

Creep is the phenomenon exhibited by materials which slowly deform when subjected to loading at elevated temperature. This document is concerned with the method used to measure such material behaviour.

Annexes are included concerning temperature measurement using thermocouples and their calibration, creep testing test pieces with circumferential V and blunt (Bridgman) notches, estimation of measurement uncertainty, methods of extrapolation of creep rupture life and information about computer compatible representation of standards.

NOTE 1 Information is still sought relating to the influence of off-axis loading or bending on the creep properties of various materials. Based on the future availability of quantitative data, consideration might be given as to whether the maximum amount of bending should be specified and an appropriate calibration procedure be recommended. The decision will need to be based on the availability of quantitative data^[1].

NOTE 2 Information concerning the benefit of standards being produced in a computer compatible format is given in Annex F.

This document incorporates many recommendations developed through the European Creep Collaborative Committee (ECCC).

NOTE 3 For many applications, the term “strain” is synonymous with extension.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO/FDIS 204

<https://standards.iteh.ai/catalog/standards/sist/8564f46b-cf49-41e6-81fe-942e8a07a371/iso-fdis-204>

Metallic materials — Uniaxial creep testing in tension — Method of test

1 Scope

This document specifies the methods for

- a) uninterrupted creep tests with continuous monitoring of extension,
- b) interrupted creep tests with periodic measurement of elongation,
- c) stress rupture tests where normally only the time to fracture is measured,
- d) a test to verify that a predetermined time can be exceeded under a given force, with the elongation or extension not necessarily being reported.

NOTE A creep test can be continued until fracture has occurred or it can be stopped before fracture.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 6892-1, *Metallic materials — Tensile testing — Part 1: Method of test at room temperature*

ISO 6892-2, *Metallic materials — Tensile testing — Part 2: Method of test at elevated temperature*

ISO 7500-2, *Metallic materials — Verification of static uniaxial testing machines — Part 2: Tension creep testing machines — Verification of the applied force*

ISO 9513, *Metallic materials — Calibration of extensometer systems used in uniaxial testing*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <https://www.electropedia.org/>
- ISO Online browsing platform: available at <https://www.iso.org/obp>

Note 1 to entry Several different gauge lengths and reference lengths are specified in this document. These lengths reflect custom and practice used in different laboratories throughout the world. In some cases, the lengths are physically marked on the test piece as lines or ridges; in other cases, the length can be a virtual length based upon calculations to determine an appropriate length to be used for the determination of creep elongation. For some test pieces, L_r , L_o and L_e are the same length (see 3.1, 3.2 and 3.3). “Extension” is used for uninterrupted creep test with continuous measurement of the increase of the length of the test piece by using an extensometer. “Elongation” is mainly used for interrupted creep test with the manual measurement of the increase of the length of the test piece.

**3.1
reference length**

L_r
base length used for the calculation of either percentage elongation or percentage extension

Note 1 to entry: A method to calculate this value is given in [7.5](#).

**3.2
original gauge length**

L_o
length between gauge length marks on the test piece measured at ambient temperature before the test

Note 1 to entry: In general, $L_o \geq 5D$.

**3.3
extensometer gauge length**

L_e
distance between the measuring points of the extensometer

**3.4
parallel length**

L_c
length of the parallel reduced section of the test piece

**3.5
final gauge length after fracture**

L_u
length between gauge length marks on the test piece measured after fracture, at ambient temperature, with the pieces carefully fitted back together with their axes in a straight line

**3.6
original cross-sectional area**

S_o
cross-sectional area of the parallel length as determined at ambient temperature prior to testing

ISO/FDIS 204

<https://standards.iteh.ai/catalog/standards/sist/8564f46b-cf49-41e6-81fe-942e8a07a371/iso->

**3.7
minimum cross-sectional area after fracture**

S_u
minimum cross-sectional area of the parallel length as determined at ambient temperature after fracture, with the pieces carefully fitted back together with their axes in a straight line

**3.8
initial stress**

R_o
applied force divided by the original cross-section area, S_o , of the test piece

**3.9
extension**

ΔL_{et}
increase of extensometer gauge length, L_e , at time t and at test temperature

Note 1 to entry: For further information, see [6.2](#).

**3.10
elongation**

ΔL_{ot}
increase of original gauge length, L_o , at time t

Note 1 to entry: For further information, see [6.2](#).

3.11 percentage extension

e

extension at test temperature expressed as a percentage of the reference length, L_r , as given in [Formula \(1\)](#)

$$e = \frac{\Delta L_{et}}{L_r} \times 100 \quad (1)$$

Note 1 to entry: See [Figure 1](#).

3.12 percentage elongation

A

elongation expressed as a percentage of the reference length, L_r , as given in [Formula \(2\)](#)

$$A = \frac{\Delta L_{ot}}{L_r} \times 100 \quad (2)$$

3.13 percentage elastic extension

e_e

extension at test temperature expressed as a percentage of the reference length, L_r , which is proportional to the initial stress, R_0

Note 1 to entry: This value can be calculated from the stress/percentage extension values during loading. See [8.4.2](#).

Note 2 to entry: See [Figure 1](#).

3.14 percentage initial total extension

e_{ti}

extension at test temperature expressed as a percentage of the reference length, L_r , at end of loading with the initial stress, R_0

Note 1 to entry: See [Figure 1](#).

3.15 percentage initial plastic extension

e_i

extension at end of loading and at test temperature with the initial stress, R_0 , expressed as a percentage of the reference length, L_r , and determined as the difference between the percentage initial total extension, e_{ti} , and the percentage elastic extension, e_e , as given in [Formula \(3\)](#)

$$e_i = e_{ti} - e_e \quad (3)$$

Note 1 to entry: See [Figure 1](#).

Note 2 to entry: This value represents the plastic extension during the loading phase.

3.16 percentage total extension

e_t

extension at the test force at time t and at test temperature, expressed as a percentage of the reference length, L_r

Note 1 to entry: See [Figure 1](#).

3.17 percentage plastic extension

e_p
extension at time t and at test temperature determined as the difference between the percentage total extension, e_t , and the percentage elastic extension, e_e , expressed as a percentage of the reference length, L_r , as given in [Formula \(4\)](#)

$$e_p = e_t - e_e \quad (4)$$

Note 1 to entry: See [Figure 1](#).

3.18 percentage total ultimate extension

e_u
total extension at rupture and at test temperature, expressed as a percentage of the reference length, L_r

3.19 percentage creep extension

e_f
extension, determined under full test force and at test temperature, as the difference between the percentage plastic extension, e_p , and the percentage initial plastic extension, e_i , expressed as a percentage of the reference length, L_r , as given in [Formula \(5\)](#)

$$e_f = e_p - e_i \quad (5)$$

Note 1 to entry: See [Figure 1](#).

Note 2 to entry: Suffix f originates from “fluage”, “creep” in French.

3.20 percentage anelastic extension

e_k
negative extension at end of unloading at test temperature, expressed as a percentage of the reference length, L_r

Note 1 to entry: See [Figure 1](#) and [8.4](#).

3.21 percentage permanent extension

e_{per}
extension at end of unloading and at test temperature determined as the difference between the percentage total extension, e_t , and the sum of percentage elastic extension, e_e , plus the percentage anelastic extension, e_k , expressed as a percentage of the reference length, L_r , as given in [Formula \(6\)](#)

$$e_{per} = e_t - (e_e + e_k) \quad (6)$$

Note 1 to entry: In the case of $e_k \approx 0$, the following relationship may be used: $e_{per} \approx e_p$.

Note 2 to entry: See [Figure 1](#).

3.22 percentage permanent elongation

A_{per}
elongation expressed as a percentage of the reference length, L_r , at end of unloading and at room temperature

3.23**percentage elongation after creep fracture** A_u

permanent elongation after fracture, $L_u - L_o$, expressed as a percentage of the reference length, L_r , as given in [Formula \(7\)](#)

$$A_u = \frac{L_u - L_o}{L_r} \times 100 \quad (7)$$

Note 1 to entry: A_u may have the specified temperature, T , in degrees Celsius as superscript and the initial stress, R_o , in megapascal as subscript; see the example in [Table 1](#).

3.24**percentage reduction of area after creep fracture** Z_u

maximum change in cross-sectional area measured after fracture, $S_o - S_u$, expressed as a percentage of the original cross-sectional area, S_o , as given in [Formula \(8\)](#)

$$Z_u = \frac{S_o - S_u}{S_o} \times 100 \quad (8)$$

Note 1 to entry: Z_u may have the specified temperature, T , in degrees Celsius as superscript and the initial stress, R_o , in megapascal as subscript; see the example in [Table 1](#).

3.25**creep extension time** t_{fx}

time required for a strained test piece to obtain a specified percentage creep extension, x , at the specified temperature, T , and the initial stress, R_o

EXAMPLE $t_{f0,2}$

3.26**plastic extension time** t_{px}

time required to obtain a specified percentage plastic extension, x , at the specified temperature, T , and the initial stress, R_o

Note 1 to entry: An example for t_{p1} is given in [Figure E.2 a](#)) ($t_{p1} = 100\,000$ h corresponds to $e_p = 1\%$ at $R_o = 120$ MPa).

3.27**creep rupture time** t_u

time to rupture for a test piece maintained at the specified temperature, T , and the initial stress, R_o

Note 1 to entry: The symbol t_u can have as superscript the specified temperature, T , in degrees Celsius and as subscript the initial stress, R_o , in megapascal; see the example in [Table 1](#).

3.28**single test piece machine**

testing machine that permits straining of a single test piece

3.29**multiple test piece machine**

testing machine that permits straining of more than one test piece simultaneously at the same temperature

4 Symbols and designations

The symbols and corresponding designations are given in [Table 1](#).

Table 1 — Symbols and designations

Symbol ^a	Unit	Designation
a	mm	Thickness of a test piece of square or rectangular cross-section [see Figure 2 b)]
A_{per}	%	Percentage permanent elongation NOTE As an example, the symbol can be completed as follows: $A_{\text{per}50/5000}^{375}$: percentage permanent elongation with an initial stress of 50 MPa after 5 000 h at the specified temperature of 375 °C.
A_{u}	%	Percentage elongation after creep fracture [see Formula (7)] NOTE As an example, the symbol can be completed as follows: $A_{\text{u}50}^{375}$: percentage elongation after creep fracture with an initial stress of 50 MPa at the specified temperature of 375 °C.
b	mm	Width of the cross-section of the parallel length of a test piece of square or rectangular cross-section
D	mm	Diameter of gauge length of a cylindrical test piece
d	mm	Diameter of gauge length without a notch in a combined notched/unnotched test piece (see Figure C.1)
D_{n}	mm	Diameter of gauge length containing a notch
d_{n}	mm	Diameter across root of circumferential notch For a combined notched/unnotched test piece $d = d_{\text{n}}$
e	%	Percentage extension
e_{e}	%	Percentage elastic extension
e_{f}	%	Percentage creep extension [see Formula (5)] NOTE As an example, the symbol can be completed as follows: $e_{\text{f}50/5000}^{375}$ percentage creep extension with an initial stress of 50 MPa after 5 000 h at the specified temperature of 375 °C.
e_{fu}	%	Percentage creep extension at creep rupture time
e_{i}	%	Percentage initial plastic extension
e_{k}	%	Percentage anelastic extension
e_{p}	%	Percentage plastic extension
e_{per}	%	Percentage permanent extension
e_{pu}	%	Percentage plastic extension at creep rupture time
e_{t}	%	Percentage total extension
e_{ti}	%	Percentage initial total extension
e_{u}	%	Percentage total extension at creep rupture time
L_{c}	mm	Parallel length
<p>^a The main subscripts (r, o and u) of the symbols are used as follows: r corresponds to reference; o corresponds to original; u corresponds to ultimate (after rupture). NOTE 1 Index t can have different meanings, e.g. time, total or transition NOTE 2 For the purposes of creep testing in this document, the terms "fracture" and "rupture" are interchangeable and are used to describe when a test piece breaks.</p>		

Table 1 (continued)

Symbol ^a	Unit	Designation
L_e	mm	Extensometer gauge length
ΔL_{et}	mm	Increase of extensometer gauge length at time t
L_n	mm	Parallel gauge length containing a notch
L_o	mm	Original gauge length
ΔL_{ot}	mm	Increase of original gauge length at time t
L_r	mm	Reference length
L_u	mm	Final gauge length after fracture
n	-	Norton creep exponent
r_n	mm	Notch root radius
R_o	MPa	Initial stress
r_t	mm	Transition radius
S_o	mm ²	Original cross-sectional area of the parallel length
S_u	mm ²	Minimum cross-sectional area after fracture
t	h	Elapsed time from end of loading
T	°C	Specified temperature
T_c	°C	Corrected measured temperature
t_{ix}	h	Creep extension time
t_{px}	h	Plastic extension time
t_u	h	Creep rupture time NOTE As an example, the symbol can be completed as follows: t_{u50}^{375} : creep rupture time with an initial stress of 50 MPa at the specified temperature of 375 °C.
t_{un}	h	Creep rupture time of a notched test piece
x	%	Specified percentage creep or plastic extension
Z_u	%	Percentage reduction of area after creep fracture [see Formula (8)] NOTE As an example, the symbol can be completed as follows: Z_{u50}^{375} : percentage reduction of area after creep fracture with an initial stress of 50 MPa at the specified temperature of 375 °C.
<p>^a The main subscripts (r, o and u) of the symbols are used as follows:</p> <p>r corresponds to reference;</p> <p>o corresponds to original;</p> <p>u corresponds to ultimate (after rupture).</p> <p>NOTE 1 Index t can have different meanings, e.g. time, total or transition</p> <p>NOTE 2 For the purposes of creep testing in this document, the terms "fracture" and "rupture" are interchangeable and are used to describe when a test piece breaks.</p>		

5 Principle

The test consists of heating a test piece to the specified temperature and of straining it by means of a constant tensile force or constant tensile stress (see Note) applied along its longitudinal axis for a period of time to obtain any of the following:

- a specified creep extension (uninterrupted test) with continuous extension measurement;
- values of permanent elongation at suitable intervals throughout the test (interrupted test);

— the creep rupture time (uninterrupted and interrupted test).

NOTE “Constant stress” or “true stress” means that the ratio of the force to the instantaneous cross-section remains constant throughout the test. The results obtained with constant stress are generally different from those obtained with constant force^[2].

6 Apparatus

6.1 Testing machine

The testing machine shall apply a force along the axis of the test piece while keeping inadvertent bending or torsion of the test piece to a minimum. Prior to test, the machine should be visually examined to ensure that loading bars, grips, universal joints and associated equipment are in a good state of repair.

The force shall be applied to the test piece without shock.

The machine should be isolated from external vibration and shock. The machine should be equipped with a device which minimizes shock when the test piece fractures.

NOTE At present, there appears to be insufficient quantitative data in the literature demonstrating the influence of bending upon creep and stress rupture life. Any organization with such information is encouraged to forward it to ISO/TC 164^[4].

The machine shall be verified and shall meet the requirements of at least class 1 in ISO 7500-2.

6.2 Extension and elongation measuring devices

6.2.1 Extension measuring device

In uninterrupted tests, the extension shall be measured using an extensometer which meets the performance requirements of class 1 or better of ISO 9513 or by other means which ensure the same accuracy without interruption of the test. The extensometer can either be directly attached to the test piece or be non-contacting (e.g. a non-contacting optical or laser extensometer).

It is recommended that the extensometer be calibrated over an appropriate range based upon the expected creep strain.

The extensometer shall be calibrated at intervals not exceeding 3 years, unless the test duration is longer than 3 years. If the predicted test duration exceeds the date of the expiry of the calibration certificate, then the extensometer shall be recalibrated prior to commencement of the creep test.

The extensometer gauge length shall not be less than 10 mm.

The extensometer shall be capable of measuring extension of one side of the test piece or, preferably, on opposite sides of the test piece.

The type of extensometer used (e.g. single-sided, double-sided, axial, diametral) should be reported. When the extension is measured on the opposite sides, the average extension should be reported.

When the extension is measured with an extensometer attached to the grip ends of the test piece, the ends shall be of such shape and size that it can be assumed that the observed extension has occurred completely within the reference length of the test piece. Percentage creep extension is measured over L_r .

The extensometer gauge length should normally be as near as possible to the reference length. In the case of accurate creep measurements, a gauge length as long as possible should be used to improve the accuracy of measurements.

Care should be taken to avoid spurious negative creep when using nickel base alloy extensometers. See the Code of Practice^[3].

For low creep strain measurements, e.g. $\leq 1\%$ strain, on test pieces with short gauge lengths, careful consideration should be given to ensure that the measuring device used has sufficient resolution and accuracy over the range of use.

NOTE 1 Information on the long-term stability of transducers used for creep testing and accreditation issues is given in References [4] and [5].

NOTE 2 If only the percentage elongation after creep fracture or the percentage creep elongation for a specified test duration is determined, the use of an extensometer is not necessary.

6.2.2 Elongation measuring device

In interrupted tests, periodically unload the test piece, cool it to ambient temperature and measure the permanent elongation on the gauge length with an appropriate device. The precision of this device shall be $0,01 \Delta L_r$ or 0,01 mm, whichever is the greater. After this measurement, the test piece may be first reheated and then reloaded.

6.3 Heating device, temperature measuring equipment and calibration

6.3.1 Permissible temperature deviations

The heating device shall heat the test piece to the specified temperature, T . The permitted deviations between the corrected measured temperature, T_c , and the specified temperature, T , and the permitted maximum temperature variation along the test piece shall be as given in Table 2.

Table 2 — Permitted deviations between T_c and T and maximum permissible temperature variation along the test piece

Specified temperature T °C	Permitted deviation between T_c and T °C	Maximum permissible temperature variation along the test piece °C
$T \leq 600$	± 3	3
$600 < T \leq 800$	± 4	4
$800 < T \leq 1\ 000$	± 5	5
$1\ 000 < T \leq 1\ 100$	± 6	6

For specified temperatures greater than 1 100 °C, the permitted values, including drift, shall be defined by agreement between the parties concerned.

The corrected measured temperatures, T_c , are the temperatures measured at the surface of the parallel length of the test piece, errors from all sources, including drift (see Annex A), being taken into account and any systematic errors having been corrected.

It is permitted to carry out indirect measurement of the temperature of each heating zone of the furnace provided that it is demonstrated that the tolerance defined above is fulfilled on the test piece instead of measuring the temperature at the surface of each individual test piece.

If an extensometer is used, the parts of this instrument outside the furnace shall be designed and protected in such a way that the temperature variations in the air around the furnace do not significantly affect the measurements of the variations in length.

Variations in temperature of the air surrounding the test machine should not exceed ± 3 °C.

In the interrupted test, the variation of the room temperature during all measurements of the gauge length should not exceed ± 2 °C. If this range is exceeded, corrections for ambient temperature variations shall be applied.