

ISO/~~DIS~~**FDIS** 3785

ISO/TC 164/SC 4

Secretariat: ANSI

Date: 2022(E)-12-19

2022-09-27

Third edition

## **Metallic materials — Designation of test specimen axes in relation to product texture**

*Matériaux métalliques — Désignation des axes des éprouvettes en relation avec la texture du produit*

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

**FDIS stage**

<https://standards.iteh.ai/catalog/standards/sist/fd33c48b-5cfd-4c24-bfb8-8d0702a954db/iso-3785>

Edited DIS — MUST BE USED FOR FINAL DRAFT

**ISO/~~DIS~~-FDIS 3785:2022(E)**

© ISO 2022

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11

Fax: +41 22 749 09 47

Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

ISO/FDIS 3785

<https://standards.iteh.ai/catalog/standards/sist/fd33c48b-5cfd-4c24-bfb8-8d0702a954db/iso-fdis-3785>

**Contents—Page**

Foreword .....	v
Introduction.....	vi
1 Scope .....	1
2 Normative references.....	1
3 Terms and definitions.....	1
4 Designation system.....	1
4.1 General .....	1
4.2 Exception — not aligned.....	1
4.3 Exception — no grain flow.....	1
5 Designation of unnotched specimens.....	2
5.1 General .....	2
5.2 Sheet, plate, bar (flat rolled products).....	2
5.2.1 Aligned, grain flow different in all three orthogonal directions.....	2
5.2.2 Not aligned, grain flow different in all three orthogonal directions.....	2
5.2.3 Aligned, equal cross-sectional grain flow.....	2
5.2.4 Not aligned, equal cross-sectional grain flow.....	2
5.3 Cylinders and thick-walled tubes.....	2
5.4 Thin-walled tubes, helical grain flow.....	2
5.5 Castings.....	2
6 Designation of notched (or precracked) specimens.....	3
6.1 General .....	3
6.2 Aligned.....	3
6.3 Not aligned.....	3
6.4 No grain flow.....	3
6.5 Welds.....	3
6.6 Additive manufacturing.....	3
7 Application of designation system in material specification.....	3
7.1 General .....	3
7.2 Non-uniform grain flow.....	4
7.3 Specifications.....	4
7.4 Comparisons.....	4
Annex A (informative) Influence of mechanical working on material structure and properties.....	8
Bibliography.....	9

Foreword — iii

Introduction — iv

1 — Scope — 1

2 — Designation system — 1

3 — Designation of unnotched specimens — 2

© ISO 2022 – All rights reserved

© ISO 2022 – All rights reserved

**ISO/~~DIS~~ **FDIS 3785:2022(E)****

~~4~~ ~~Designation of notched (or precracked) specimens~~ ~~3~~

~~5~~ ~~Application of designation system in material specification~~ ~~4~~

~~Annex A (informative) Influence of mechanical working on material structure and properties~~ ~~7~~

# iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO/FDIS 3785

<https://standards.iteh.ai/catalog/standards/sist/fd33c48b-5cfd-4c24-bfb8-8d0702a954db/iso-fdis-3785>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 164, *Mechanical testing of metals*, Subcommittee SC 4, *Fatigue, fracture and toughness testing*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC CEN/TC 459/SC 1, *ECISS - European Committee for Iron and Steel Standardization*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This third edition cancels and replaces the first edition (ISO 3785:2006), which has been technically revised.

The main changes are as follows:

- A reference to ~~Annex A~~ **Annex A** was added in the Introduction.
- ~~References to ISO 15653 and ISO/ASTM 52921 were moved from Clause 2 (Normative references) to the Bibliography.~~
- ~~A new Clause 3 (Terms and definition) was added.~~
- ~~In Clause 6.5 (Welds), 6.5~~ a reference to ISO 15653 was added.
- A new ~~Clause 6.6~~ **subclause 6.6** (Additive manufacturing) was added.
- ~~Bibliography was added.~~

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

Field Code Changed

ISO/~~DIS~~ **FDIS** 3785:2022(E)

## Introduction

The measured mechanical properties of a metallic product, especially those characterizing ductility and toughness, such as elongation, reduction of area, fracture toughness and impact resistance, are dependent on the test specimen location within the product and orientation with respect to the product's principal directions of metal working, grain flow or otherwise-produced texture. This International Standard specifies a method for designating specimen orientation in relation to product texture.

Additional information on the influence of mechanical working on material structure and properties is provided in [Annex A-Annex A](#).

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

ISO/FDIS 3785

<https://standards.iteh.ai/catalog/standards/sist/fd33c48b-5cfd-4c24-bfb8-8d0702a954db/iso-fdis-3785>

# Metallic materials — Designation of test specimen axes in relation to product texture

## 1 Scope

This document specifies a method for designating test specimen axes in relation to product texture by means of an X-Y-Z orthogonal coordinate system.

This document applies equally to unnotched and notched (or precracked) test specimens.

This document is intended only for metallic materials with uniform texture that can be unambiguously determined.

Test specimen orientation is decided before specimen machining, identified in accordance with the designation system specified in this document, and recorded.

## 2 Normative references

There are no normative references in this document.

## 3 Terms and definitions

No terms and definitions are listed in this document. ~~For additive manufacturing, the terms and definitions given in ISO/ASTM 52921-13(2019) apply.~~

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

## 4 Designation system

### 4.1 General

The method for relating specimen axes to the characteristic directions of the product makes use of an X-Y-Z orthogonal coordinate system for wrought metals:

- the letter X always denotes the direction of principal deformation (maximum grain flow in the product);
- the letter Y denotes the direction of least deformation;
- the letter Z denotes the direction normal to the X-Y plane.

### 4.2 Exception — not aligned

When the specimen direction does not coincide with the product's characteristic grain-flow directions, two letters are used as described for unnotched specimens in [5.2.2](#) and [5.2.4](#), and for notched specimens in [6.3.3](#).

### 4.3 Exception — no grain flow

When there is no grain-flow direction as in a casting, specimen location and orientation shall be specified on a part drawing and the test result shall carry no orientation designation.

## 5 Designation of unnotched specimens

### 5.1 General

The designations of unnotched specimens variously aligned with respect to the product's characteristic grain-flow directions are depicted in [Figure 1](#). Only specimens fully aligned with, or lying midway between, the product's characteristic grain-flow directions are shown.

### 5.2 Sheet, plate, bar (flat rolled products)

#### 5.2.1 Aligned, grain flow different in all three orthogonal directions

For products of non-circular cross-section and grain flow differing in the three orthogonal directions, specimens aligned with the product's characteristic grain-flow directions are designated as either X-, Y- or Z-direction specimens as depicted in [Figure 1 a](#)).

#### 5.2.2 Not aligned, grain flow different in all three orthogonal directions

For products of non-circular cross-section and grain flow differing in the three orthogonal directions, specimens lying midway between the product's characteristic grain-flow directions are designated as XY-, XZ-, or YZ-direction specimens as depicted in [Figure 1 f](#)). When the specimen lies neither in alignment with the product's characteristic grain-flow directions nor midway between them, but rather at some other angle to them, then that angle shall be stated between the two designation letters, the first letter denoting the direction toward which the specimen axis is inclined, and the second letter the direction from which the specimen axis is inclined. This designation scheme is restricted to direction vectors that lie within any of the three planes described by the orthogonal X, Y and Z directions. When the direction vector lies outside those planes, specimen location and orientation shall be specified on a drawing of the product or part and the test result shall carry no orientation designation.

#### 5.2.3 Aligned, equal cross-sectional grain flow

For products of non-circular cross-section with equal Y- and Z-direction grain flow, specimens oriented normal to the X-direction (principal direction of) grain flow may be designated as either Y- or Z-direction specimens, as depicted in [Figure 1 a](#)).

#### 5.2.4 Not aligned, equal cross-sectional grain flow

For products of non-circular cross-section with equal Y- and Z-direction grain flow, specimens lying midway between the product's characteristic grain-flow directions are designated as XY-, XZ-, or YZ-direction specimens, as depicted in [Figure 1 f](#)). When the specimen lies neither in alignment with the product's characteristic grain-flow directions nor midway between them, but rather at some other angle to them, then that angle shall be stated between the two letters, the first letter denoting the direction toward which the specimen axis is inclined, and the second letter the direction from which the specimen axis is inclined. This designation scheme is restricted to direction vectors the lie within any of the three planes described by the orthogonal X, Y and Z directions. When the direction vector lies outside those planes, specimen location and orientation shall be specified on a drawing of the product or part and the test result shall carry no orientation designation.

### 5.3 Cylinders and thick-walled tubes

Specimen depictions in [Figures 1 b](#)) and [1 c](#)) pertain to solid cylinders; those in [Figure 1 d](#)) apply to hollow cylinders (thick-walled tubes).

### 5.4 Thin-walled tubes, helical grain flow

Specimen depictions in [Figure 1 e](#)) pertain to products with helical grain flow, typically thin-walled tubing.

### 5.5 Castings

When there is no grain-flow direction as in a casting, specimen location and direction shall be specified on a part drawing and the test result shall carry no orientation designation.



## 6 Designation of notched (or precracked) specimens

### 6.1 General

Designating the plane and direction of crack extension for notched (or precracked) specimens, in relation to the product's characteristic grain-flow directions, is done using a hyphenated code wherein the letter(s) preceding the hyphen represent the direction normal to the crack plane and the letter(s) following the hyphen represent the anticipated direction of crack extension.

### 6.2 Aligned

When the specimen direction is aligned with the product's characteristic grain-flow directions, a single letter for each case is used to denote the direction perpendicular to the crack plane and the direction of intended crack extension, as depicted in [Figure 2 a\), 2 c\) and 2 d\)](#).

### 6.3 Not aligned

When the specimen orientation directions lie midway between the product's characteristic grain-flow directions, two letters shall be used to denote the normal to the crack plane or the crack propagation direction, as depicted in [Figure 2 b\)](#). When the specimen orientation directions lie neither in alignment with the product's characteristic grain-flow directions nor midway between them, but rather at some other angle to them, then that angle shall be stated between the two letters, the first letter denoting the direction toward which the crack plane normal or propagation direction is inclined, and the second letter the direction from which the crack plane normal or crack propagation direction is inclined. This designation scheme is restricted to direction vectors that lie within any of the three planes described by the orthogonal X, Y and Z directions. When the direction vector lies outside those planes, the specimen crack plane orientation and propagation direction shall be specified on a drawing of the product or part, and the test result shall carry no orientation designation.

### 6.4 No grain flow

When there is no grain-flow direction as in a casting, specimen location and crack plane orientation shall be specified on a part drawing and the test result shall carry no orientation designation.

### 6.5 Welds

For welds, specimen and crack plane orientation relative to the weld and parent metal, working directions are specified as prescribed in [6.3 of ISO 15653:2018, 6.3](#).

### 6.6 Additive manufacturing

Terms, nomenclature, and acronyms associated with coordinate systems and testing methodologies for additive manufacturing (AM) technologies are specified in ISO/ASTM 52921, in an effort to standardize terminology used by AM users, producers, researchers, educators, press/media, and others, particularly when reporting results from testing of parts made on AM systems. Terms included in ISO/ASTM 52921 cover definitions for machines/systems and their coordinate systems, plus the location and orientation of parts.

## 7 Application of designation system in material specification

### 7.1 General

The designation of specimen location and orientation with respect to the product characteristic directions is straightforward for regular structural configurations like plate and rod. It is more difficult for complex structural shapes, in which case knowledge of production and processing plays an essential role.

## 7.2 Non-uniform grain flow

In cases where grain flow is not uniform, specimen location and orientation shall reference component geometry and be noted on component drawings along with a description of component production and processing.

## 7.3 Specifications

Specimen extraction shall conform to relevant specifications.

## 7.4 Comparisons

When products are to be compared on the basis of mechanical properties, it is essential that specimen location and orientation with respect to the product's grain-flow directions be comparable and that the results not be generalized beyond these limits.

