ISO/TC 206/WG 4

Date: 2023-03-1004-12

Secretariat: JISC

Fine ceramics (advanced ceramics, advanced technical ceramics) — Mechanical properties of ceramic composites at room temperature — Determination of the interlaminar shear strength and shear modulus of continuous-fibre-reinforced composites by the compression of double-notched test pieces and by the losipescu test

iTeh Standards (https://standards.iteh.ai) Document Preview

ISO 20505:2023

https://standards.iteh.ai/catalog/standards/sist/9e81e22a-f121-41fe-9f92-dfb2b5e7a1ae/iso-20505-2023

Edited DIS MUST BE USED
FOR FINAL
DRAFT

© ISO 20222023

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office

CP 401 • Ch. de Blandonnet 8

CH-1214 Vernier, Geneva

Phone: +41 22 749 01 11

Email: copyright@iso.org

Website: www.iso.org

Published in Switzerland

iTeh Standards (https://standards.iteh.ai) Document Preview

ISO 20505:2023

https://standards.iteh.ai/catalog/standards/sist/9e81e22a-f121-41fe-9f92-dfb2b5e7a1ae/iso-20505-2023

Edited DISMUST BE USED FOR FINA 150 2023 - All rights reserved

Contents

Forew	vord	!
Introc	duction	<u></u> ,
	Scope	
	Normative references	
	Terms and definitions	
4	Principle.	4
4.1	General	4
	Double-notched test	
4.3	losipescu test	!
5	Apparatus	 '
5.1	Test machine	
5.2 —	Load train	'
	Generalities	
5.2.2	Test fixtures	 '
5.3 —	Strain gauges for Iosipescu test specimen	1 2
5.4	Data acquisition	 12
	Dimension-measuring devices	
6	Test specimens 11CH Stantuarus	 1:
	Double-notched test piece	
	Iosipescu test piece 588// Svanuar U.S. 100 11-2019	
7	Test specimen preparation	_19
7.1	Machining and preparation	_18
	Bonding of the gauges	
7.3	Number of test specimens ISO 205052023	_18
	andards itch ai/catalog/standards/sist/9e81e22a-f121-41fe-9f92-dfb2b5e7a1ae/iso-20505-2 Test procedures	
	Displacement rate	
	Measurement of test specimen dimensions	
	Testing technique	
	Specimen mounting	
	Measurements Test validity	
		 ∠.
	- Calculation of results	24
	Shear strength	
	Double-notched test piece	
	— losipescu test piece	
	Shear strain (losipescu test)	2!
	Shear-stress-shear-strain curves	<u></u> 2!
	Elastic shear modulus, pseudo-elastic shear modulus	
9.5	- Statistics	<u></u> 20
10 —	Report EUICEU DIS-	<u></u> 20
Anne	x A (informative) New materials: verification of shear stress field in the losipescu t	est
D:L!	171(),) 	
RIDII0	graphy 1 1 0 0 1 D D 0 D D	<u></u> Z

<u>Forew</u>	ord	<u>v</u>
1	Scope	1
2	Normative references	1
3	Terms and definitions	1
4	Principle	
4 4.1	General	
4.1 4.2	Double-notched test	
4.3	Iosipescu test	
<u>5</u> 5.1	Apparatus Test machine	
5.1 5.2	Load train	
5.2.1	Generalities	
5.2.1 5.2.2	Test fixtures	
5.2. <u>2</u> 5.3	Strain gauges for Iosipescu test specimen	
5.4	Data acquisition	
5.4 5.5	Dimension-measuring devices	
3.3	· · · · · · · · · · · · · · · · · · ·	
6	Test specimens	
6.1	Double-notched test piece	
6.2	Iosipescu test piece	<u></u> 16
7	Test specimen preparation Tab Standards	<u></u> 18
7.1	Machining and preparation	<u></u> 18
7.2	Bonding of the gauges.	<u></u> 18
7.3	Bonding of the gauges Number of test specimens	<u></u> 18
8	Test procedures Document Praviaw	18
8.1	Displacement rate	
8.2	Measurement of test specimen dimensions	18
8.3	Testing technique ISO 20505:2023	19
8.3.1 ht	Specimen mounting talog/standards/sist/9eX1e22a-f121-41fe-9f92-dfb2b5e7a1ae/iso	195
8.3.2	Measurements	21
8.4	Test validity	<u></u> 21
9	Calculation of results	24
9.1	Shear strength	24
9.1.1	Double-notched test piece	
	Iosipescu test piece	
9.2	Shear strain (Iosipescu test)	
9.3	Shear-stress-shear-strain curves	25
9.4	Elastic shear modulus, pseudo-elastic shear modulus	
9.5	Statistics	<u></u> 26
10	Report	<u></u> 26
Annon	A (informative) New meterials, verification of sheer stress field in the lesiness.	tost
<u>Amnex</u>	x A (informative) New materials: verification of shear stress field in the losipescu	
	Editod DIC	
<u>Biblio</u>	graphy FACILIC TO THE STATE OF	<u></u> 29

MUST BE USED

DRAFT

FOR FINA © ISO 2023 - All rights reserved

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO <u>documents_document</u> should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives/. (see www.iso.org/directives/.

Attention is drawnISO draws attention to the possibility that some of the elements implementation of this document may be involve the subjectuse of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights- in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 206, Fine ceramics.

This second edition cancels and replaces the first edition (ISO 20505:2005), which has been technically revised.

The main changes are as follows:

- Scope revised to include the possibility of measuring the interlaminar shear modulus through the use of a gauges-instrumented Iosipescu sample;
- new entries added to Clause-_3;
- 5.3 and 7.2 specify requirements on the gauges-instrumented Iosipescu sample;
- 9.3, 9.4 and 9.5 define formulae to determine the shear modulus;
- material orientation added to Figure 2 and Figure 3;



- subclause on test validity added (8.4);
- Table 1 and Table 2 updated;
- Annex A replaced by a method to verify the shear stress field in the Iosipescu test to ensure that that
 there are no coupling effects that make this document unsuitable for determining the interlaminar
 shear properties of the material;
- minor editorial corrections;
- structure revised:
- symbols and notation modified in accordance with ISO 19634.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

iTeh Standards (https://standards.iteh.ai) Document Preview

ISO 20505:2023

https://standards.iteh.ai/catalog/standards/sist/9e81e22a-f121-41fe-9f92-dfb2b5e7a1ae/iso-20505-2023



Introduction

The International Organization for Standardization (ISO) draws attention to the fact that it is claimed that compliance with this document may involve the use of a patent.

ISO takes no position concerning the evidence, validity and scope of this patent right.

The holder of this patent right has assured ISO that he/she is willing to negotiate licences under reasonable and non-discriminatory terms and conditions with applicants throughout the world. In this respect, the statement of the holder of this patent right is registered with ISO. Information may be obtained from the patent database available at www.iso.org/patents.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights other than those in the patent database. ISO shall not be held responsible for identifying any or all such patent rights.

iTeh Standards (https://standards.iteh.ai) Document Preview

ISO 20505:2023

https://standards.iteh.ai/catalog/standards/sist/9e81e22a-f121-41fe-9f92-dfb2b5e/a1ae/iso-20505-2023

Edited DIS -MUST BE USED

© ISO 20222023 – All rights reserved

vii



iTeh Standards (https://standards.iteh.ai) Document Preview

ISO 20505:2023

https://standards.iteh.ai/catalog/standards/sist/9e81e22a-f121-41fe-9f92-dfb2b5e7a1ae/iso-20505-2023

Fine ceramics (advanced ceramics, advanced technical ceramics)

— Mechanical properties of ceramic composites at room
temperature — Determination of the interlaminar shear strength
and shear modulus of continuous-fibre-reinforced composites by
the compression of double-notched test pieces and by the
losipescu test

1 Scope

This document specifies a method for the determination of interlaminar shear strength at ambient temperature by the compression of a double-notched test piece and a method for the determination of interlaminar shear strength and modulus at ambient temperature by the Iosipescu test. This document applies to all ceramic matrix composites with a continuous fibre reinforcement, having unidirectional (1D), bidirectional (2D) and multidirectional (xD, with $x \rightarrow 2$) fibre architecture, where a major part of reinforcements is a stack of plies.

This document is applicable to material development, material comparison, quality assurance, characterization, reliability and design data generation. The simpler compression test method of a double-notched test piece is applicable only when the shear strength has to be measured.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 3611, Geometrical product specifications (GPS) — Dimensional measuring equipment: Micrometers for external measurements — Design and metrological characteristics

ISO 7500-1, Metallic materials — Calibration and verification of static uniaxial testing machines — Part-1: Tension/compression testing machines — Calibration and verification of the force-measuring system

ISO 17161, Fine ceramics (advanced ceramics, advanced technical ceramics) — Ceramic composites — Determination of the degree of misalignment in uniaxial mechanical tests

ISO 19634, Fine ceramics (advanced ceramics, advanced technical ceramics) — Ceramic composites — Notations and symbols

ISO 20507, Advanced ceramics - Vocabulary

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 20507 and ISO 19634 and the following apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at https://www.iso.org/obp
- IEC Electropedia: available at https://www.electropedia.org/

3.1

shear section

section located between the notches of test sample

Note 1 to entry: Due to the orientation of the test sample (see Figures 2 and 3), the shear plane is orthogonal to direction 3 and parallel to the stack of plies (plane 1, 2). Therefore, the shear mechanism occurs between the composite plies and the resulting shear properties, with respect to the definition given in ISO 20507, are labelled as "interlaminar".

3.2

initial shear section area

 S_0

shear section area before test between the notches of the test piece at room temperature

3.3

shear section area

S

effective shear loaded section area of the test piece at room temperature

Note 1 to entry: This effective shear loaded section area is determined when a valid failure occurs in a plane parallel to the shear plane in an Iosipescu test sample.


3.4 shear force

F

Forceforce parallel to the shear section carried by the test specimen at any time during the shear test

https://standards.itch.ai/catalog/standards/sist/9e81e22a-f121-41fe-9f92-dfb2b5e7a1ae/iso-20505-2023 Note 1 to entry: See Figure 1.





Key

F shear force

γ shear strain

L height of the cubic element

 δ displacement

Figure 1— Shear force and shear strain

3.5

maximum shear force

 $F_{\rm m}$

maximum force parallel to the shear section during a test or at fracture

3.6

interlaminar shear strength

 $\sigma_{\rm ILSS.m.i.3}$

ratio of the maximum shear force to the initial shear section area

Note 1 to entry: With respect to the material orientation defined in ISO 19634, subscript "i" is for the direction of the load with respect to the material orientation and subscript "3" is for the material orientation orthogonal to the shear plan (see Figures 2 and 3).

3.7

shear strain

γ

change in angle between two adjacent sides of a cubic-shaped stress element submitted to a shear force

Note 1 to entry: Although shear strain is defined as an angle, for small strains this measure becomes the ratio of displacement δ to the height of the stress element L (see Figure 1).

3.8 strain

 ϵ_{ij}

 ϵ_{θ}

ratio of deformation to initial strain gauge length

Note 1 to entry: The subscripts "ij" and " θ " indicate the orientation of the strain gauge with respect to test sample orientation.

3.9

shear stress

JILSS i 3

ratio of the shear force to the initial shear section area at any time during the test

© ISO 2023 – All rights reserved

