

FINAL
DRAFT

INTERNATIONAL
STANDARD

ISO/FDIS
6324

ISO/TC 163/SC 3

Secretariat: SCC

Voting begins on:
2023-09-08

Voting terminates on:
2023-11-03

Thermal insulation products — Flexible microporous insulation for industrial applications — Specification

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO/FDIS 6324](https://standards.iteh.ai/catalog/standards/sist/319ca6fd-293a-42e9-ad6d-cd1085450631/iso-fdis-6324)

<https://standards.iteh.ai/catalog/standards/sist/319ca6fd-293a-42e9-ad6d-cd1085450631/iso-fdis-6324>

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.



Reference number
ISO/FDIS 6324:2023(E)

© ISO 2023

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO/FDIS 6324

<https://standards.iteh.ai/catalog/standards/sist/319ca6fd-293a-42e9-ad6d-cd1085450631/iso-fdis-6324>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2023

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

| | |
|--|----------|
| Foreword..... | iv |
| 1 Scope..... | 1 |
| 2 Normative references..... | 1 |
| 3 Terms, definitions, symbols and abbreviated terms..... | 2 |
| 3.1 Terms and definitions..... | 2 |
| 3.2 Symbols and units..... | 2 |
| 3.3 Abbreviated terms..... | 3 |
| 3.3.1 Abbreviated terms..... | 3 |
| 3.3.2 Abbreviated terms for declared properties..... | 3 |
| 4 Requirements..... | 3 |
| 4.1 General..... | 3 |
| 4.2 For all applications..... | 3 |
| 4.2.1 Linear dimensions..... | 3 |
| 4.2.2 Density..... | 4 |
| 4.2.3 Thermal conductivity..... | 4 |
| 4.3 For specific applications..... | 4 |
| 4.3.1 Reaction to fire..... | 4 |
| 4.3.2 Water absorption..... | 4 |
| 4.3.3 Water vapour transmission..... | 5 |
| 4.3.4 Permanent linear change..... | 5 |
| 4.3.5 Compressive strength..... | 5 |
| 4.3.6 Corrosiveness to steel..... | 5 |
| 4.3.7 Resistance to fungi..... | 5 |
| 4.3.8 Flexibility..... | 6 |
| 5 Test methods..... | 6 |
| 5.1 Sampling..... | 6 |
| 5.2 Conditioning..... | 6 |
| 5.3 Testing..... | 6 |
| 5.3.1 General..... | 6 |
| 5.3.2 Thermal conductivity..... | 7 |
| 5.3.3 Permanent linear change..... | 7 |
| 6 Designation code..... | 7 |
| 7 Evaluation of conformity..... | 8 |
| 8 Marking and labelling..... | 8 |
| Annex A (normative) Factory production control (FPC)..... | 9 |

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 163, *Thermal performance and energy use in the built environment*, Subcommittee SC 3, *Thermal insulation products, components and systems*.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Thermal insulation products — Flexible microporous insulation for industrial applications — Specification

1 Scope

This document specifies the requirements for factory-made flexible microporous insulation (FMI), which is used for the thermal insulation of industrial applications. It specifies requirements for insulation that exhibits thermal insulating performance through nano-sized pore composite material comprising a blend of inorganic powder, fibres and opacifiers. The products are delivered as a flexible microporous type.

This document describes product characteristics and includes procedures for testing, evaluation of conformity, marking and labelling.

It does not specify the required level of a given property to be achieved by a product to demonstrate fitness for purpose in a particular application. The levels required for a given application can be found in regulations or non-conflicting standards.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 846:2019, *Plastics — Evaluation of the action of microorganisms*

ISO 1663, *Rigid cellular plastics — Determination of water vapour transmission properties*

ISO 8301, *Thermal insulation — Determination of steady-state thermal resistance and related properties — Heat flow meter apparatus*

ISO 8302, *Thermal insulation — Determination of steady-state thermal resistance and related properties — Guarded hot plate apparatus*

ISO 23993, *Thermal insulation products for building equipment and industrial installations — Determination of design thermal conductivity*

ISO 12576-1, *Thermal insulation — Insulating materials and products for buildings — Conformity control systems — Part 1: Factory-made products*

ISO 12624, *Thermal insulating products for building equipment and industrial installations — Determination of trace quantities of water-soluble chloride, fluoride, silicate, sodium ions and pH*

ISO 13787, *Thermal insulation products for building equipment and industrial installations — Determination of declared thermal conductivity*

ISO 16535, *Thermal insulating products for building applications — Determination of long-term water absorption by immersion*

ISO 18097, *Thermal insulating products for building equipment and industrial installations — Determination of maximum service temperature*

ISO 29465, *Thermal insulating products for building applications — Determination of length and width*

ISO 29466, *Thermal insulating products for building applications — Determination of thickness*

ISO 29469:2022, *Thermal insulating products for building applications — Determination of compression behaviour*

ISO 29470, *Thermal insulating products for building applications — Determination of the apparent density*

ISO 29767, *Thermal insulating products for building applications — Determination of short-term water absorption by partial immersion*

3 Terms, definitions, symbols and abbreviated terms

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1 Terms and definitions

3.1.1 inorganic powder

base ingredient of microporous thermal insulation (e.g. fumed silica) composed of SiO₂ and fumed alumina oxide

3.1.2 microporous

composite material that comes in the form of fibre reinforced inorganic powder (e.g. small particles of dispersed silica), creating micro-pores

3.1.3 flexible microporous thermal insulation

type of microporous thermal insulation that is encased in incombustible fabric (e.g. glass fibre fabric, silica fibre fabric) and stitched with sewing thread for flexibility

3.2 Symbols and units

| Symbol | Quantity | Unit |
|-----------------------|---|---------|
| l | length | mm |
| b | width | mm |
| t | thickness | mm |
| $\Delta\varepsilon_l$ | relative change in length | % |
| $\Delta\varepsilon_b$ | relative change in width | % |
| $\Delta\varepsilon_t$ | relative change in thickness | % |
| λ | thermal conductivity | W/(m·K) |
| λ_D | declared thermal conductivity as determined by ISO 13787, and expressed with three significant digits | W/(m·K) |

3.3 Abbreviated terms

3.3.1 Abbreviated terms

| Abbreviated term | Meaning |
|------------------|---------------------------------|
| FMI | Flexible microporous insulation |
| ITT | Initial type test |
| FPC | Factory production control |

3.3.2 Abbreviated terms for declared properties

| Abbreviated term | Declared property |
|------------------|---|
| ST (+) | declared level for maximum service temperature |
| CS(Y) | declared level for compressive strength |
| CS(10) | declared level for compressive strength at 10 % deformation |
| Cl | declared level for chloride content |
| T | declared level for thickness |

4 Requirements

4.1 General

Product properties shall be assessed in accordance with [Clause 5](#). To conform to this document, products shall meet the requirements of [4.2](#), and the requirements of [4.3](#), as appropriate.

The test methods for the determination of each property are given in [Table 6](#), which also shows the required test specimen dimensions and the minimum number of test specimens required to give one test result.

One test result for a product property is the average of the measured values on the number of test specimens given in [Table 6](#).

4.2 For all applications

4.2.1 Linear dimensions

Length and width shall be measured in accordance with ISO 29465 for each of the four specimens.

A minimum of four measurements shall be made for each dimension. Each value shall be within the tolerances specified in [Table 1](#).

The thickness of microporous insulation shall be measured in accordance with ISO 29466 by using a square plate under pressure of 250 Pa and shall be subject to the tolerances detailed in [Table 1](#). The pressure employed during measurement shall be disclosed.

Tighter tolerances can be necessary for certain applications; this shall be agreed by the supplier and purchaser.

Table 1 — Dimensional tolerances

| Length | | Width | | Thickness | |
|--------------|---------------|--------------|---------------|-----------|---------------|
| Nominal | Tolerance(mm) | Nominal | Tolerance(mm) | Nominal | Tolerance (%) |
| ≤ 1 m | -0 / +10 | ≤ 1 m | -0 / +10 | T1 | -0 / +2 |
| | | | | T2 | -0 / +5 |
| 1 m ~ 3 m | -0 / +15 | 1 m ~ 3 m | -0 / +15 | T3 | -0 / +10 |
| | | | | T4 | -0 / +15 |
| > 3 m | -0 / +20 | > 3 m | -0 / +20 | T5 | -0 / > +15 |

4.2.2 Density

Density shall be determined in accordance with ISO 29470 in each of the four specimens and reported as the average of the four specimens.

4.2.3 Thermal conductivity

For thermal conductivity testing, the specimen shall be conditioned according to 5.2.

Thermal conductivity shall be based upon measurements carried out in accordance with ISO 8301 or ISO 8302.

The measured values shall be expressed with three significant figures and the test mean temperatures shall be according to Table 2 depending on the usage environment and requirement.

The declared thermal conductivity shall be determined in accordance with ISO 23993.

Table 2 — Thermal conductivity category

| Thermal conductivity (λ) | Test mean temperature |
|--------------------------|-----------------------|
| | 10 °C or 23 °C |
| | 100 °C |
| | 200 °C |
| | 300 °C |
| | 400 °C |
| | 500 °C |

4.3 For specific applications

4.3.1 Reaction to fire

The fire properties with respect to reaction to fire should be assessed.

NOTE Legislation can apply regarding reaction to fire in the individual territories where the product is used.

4.3.2 Water absorption

The test shall be conducted in accordance with the test method in ISO 29767 or in ISO 16535.

ISO 29767 specifies the equipment and procedures for determining the short-term water absorption of specimens by partial immersion.

ISO 16535 specifies the equipment and procedures for determining the long-term water absorption of test specimens.

4.3.3 Water vapour transmission

Water vapour transmission shall be determined in accordance with ISO 1663 and the mass of the aqueous solution dish shall be measured at appropriate time intervals for at least five points in succession.

Calculate the water vapour transmission by using the water vapour flow rate.

4.3.4 Permanent linear change

Permanent linear change shall be determined in accordance with ISO 18097. At the maximum service temperature of soaking heat for 24 h, the relative changes in length, $\Delta\varepsilon_l$, and width, $\Delta\varepsilon_b$, shall not exceed 2 % and the relative changes in thickness, $\Delta\varepsilon_t$, shall not exceed 10 %. The maximum service temperature, ST (+), shall be declared in °C in levels with steps of 100 °C as given in the examples shown in [Table 3](#). The test specimen shall not be faced or coated.

Table 3 — Levels for maximum service temperature

| Level | Requirement °C |
|--------------|-------------------|
| ST (+) 800 | 800 |
| ST (+) 900 | 900 |
| ST (+) 1 000 | 1 000 |

4.3.5 Compressive strength

Compressive strength at 10 % deformation shall be determined in accordance with ISO 29469. The test result shall not be less than the declared level, CS(10\Y), given in [Table 4](#).

One test result for a product is the average of the measured values out of a number of four specimens.

The compressive strength shall be measured in the direction normal to the surface of the board.

Table 4 — Levels for compressive strength at 10 % deformation

| Level | Requirement kPa |
|-------------|--------------------|
| CS(10\Y)25 | ≥25 |
| CS(10\Y)50 | ≥50 |
| CS(10\Y)75 | ≥75 |
| CS(10\Y)100 | ≥100 |

4.3.6 Corrosiveness to steel

This test is for determining trace quantities of the water-soluble chloride ions in an aqueous extract of the product and shall be carried out in accordance with ISO 12624. Trace quantities of water-soluble chloride ions shall be declared as levels in milligrams per kilogram of product and no test result shall exceed the declared value.

NOTE The determination of this parameter can be relevant for thermal insulating products intended for applications to austenitic stainless-steel surfaces. The presence of chloride ions under certain conditions can influence the risk of stress corrosion cracking.

4.3.7 Resistance to fungi

Test strains listed in [Table 5](#) shall be used when tested according to ISO 846, which provides a test method for fungi resistance. Test specimens that have growth greater than that on the comparative

item shall be considered to have failed. Test specimens on which the growth is not greater than that on the comparative item shall be considered to have passed.

Table 5 — Types of fungi to be tested

| Name | Strain |
|----------------------------------|------------|
| Aspergillus niger van Tieghem | ATCC 6275 |
| Penicillium funiculosum Thom | CMI 114933 |
| Paecilomyces variotii Bainier | ATCC 18502 |
| Gliocladium virens Miller et al. | ATCC 9645 |
| Chaetomium globosum Kunze: Fries | ATCC 6205 |

4.3.8 Flexibility

Flexibility test methods and procedures are as follows.

Test specimen size is (300 x 300) mm and shall be coated with fabric. Place the insulation on the NPS (21,3 mm outer diameter, at least 305 mm of length) iron pipe, gently bend the specimen at a 90° angle and observe if the outer surface shows rupture. If none, then the 'flexible' classification is given. There shall be no visible ruptures on the four specimens tested

5 Test methods

5.1 Sampling

Sufficient test specimens shall be taken in accordance with the test methods.

5.2 Conditioning

Prior to dimensional measurements and physical-property testing, unless otherwise specified in the test method, the test specimens shall be conditioned, with all surfaces exposed, for a minimum of 24 h at (23 ± 2) °C and (50 ± 10) % relative humidity.

When measuring the dimensions of FMI with full size width or length >1,5 m, the conditioning step set above is not required, and may be eliminated at the manufacturer's discretion.

5.3 Testing

5.3.1 General

[Table 6](#) gives the dimensions of the test specimens. It provides the minimum number of measurements required to get one test result and any specific conditions which are necessary.

Table 6 — Test methods, test specimens and conditions

| Clause | | Test method | Test specimens | | Specific conditions |
|-----------------------|----------------------|-------------------------|-----------------|---------------------------------------|---------------------|
| No. | Title | | Dimensions (mm) | Minimum number to get one test result | |
| 4.2.1 | Linear dimensions | ISO 29465 ISO 29466 | Full-size | 4 | — |
| 4.2.2 | Density | ISO 29470 | Full-size | 4 | — |
| 4.2.3 | Thermal conductivity | ISO 8301 or ISO 8302 | ≥200 × 200 × t | 1 | — |