### INTERNATIONAL STANDARD

ISO 6334

First edition 2023-12

# Thermal insulation products for building equipment and industrial installations — Expanded perlite products — Specification

Isolation thermique pour les équipements de bâtiments et les installations industrielles — Produits de perlite expansée — Spécifications

(https://standards.iteh.ai) **Document Preview** 

ISO 6334:2023

https://standards.iteh.ai/catalog/standards/sist/5b1f758c-092f-4849-a339-fb699625d99c/iso-6334-2023



### iTeh Standards (https://standards.iteh.ai) Document Preview

ISO 6334:2023

https://standards.iteh.ai/catalog/standards/sist/5b1f758c-092f-4849-a339-fb699625d99c/iso-6334-2023



#### **COPYRIGHT PROTECTED DOCUMENT**

© ISO 2023

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office CP 401 • Ch. de Blandonnet 8 CH-1214 Vernier, Geneva Phone: +41 22 749 01 11 Email: copyright@iso.org Website: www.iso.org

Published in Switzerland

Con	<b>Contents</b> Pa						
Fore	word			iv			
1	Scop	e		1			
2	_		references				
3	Terms, definitions, symbols, units and abbreviated terms						
	3.1	Term	s and definitions	3			
	3.2		ools, units and abbreviated terms				
		3.2.1	·				
		3.2.2					
		3.2.3	Abbreviated terms	4			
4	Requ	ıiremei	nts	4			
	4.1		ral				
	4.2		ll applications				
		4.2.1	J				
		4.2.2					
		4.2.3	Dimensional stability				
		4.2.4 4.2.5	Fire properties				
	4.3		pecific applications				
	4.5	4.3.1	General				
		4.3.2	Maximum service temperature (ST)				
		4.3.3	Compressive stress or strength	6			
		4.3.4	Trace quantities of water-soluble ions and the pH-value	7			
		4.3.5	Water vapour diffusion resistance	7			
		4.3.6	Short-term water absorption by partial immersion				
5	Test	Test methods Document Preview					
	5.1						
	5.2		itioning				
	5.3	Testi	ng	8			
		5.3.2	Thermal conductivity				
		5.3.3 5.3.4	Maximum service temperature (ST)Fire properties				
6	Deci		ı code				
7			of conformity				
8			d labelling				
			e) Factory production control				
	•						
	•		ve) Additional propertiesve) Preparation of the test specimens to measure thermal conductivity				
	ogrant		vej rreparation of the test specimens to measure thermal conductivity	15			
KINII	norant	W		16			

#### Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see <a href="www.iso.org/directives">www.iso.org/directives</a>).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at <a href="www.iso.org/patents">www.iso.org/patents</a>. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see <a href="https://www.iso.org/iso/foreword.html">www.iso.org/iso/foreword.html</a>.

This document was prepared by Technical Committee ISO/TC 163, *Thermal performance and energy use in the built environment*, Subcommittee SC 3, *Thermal insulation products, components and systems*.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

## Thermal insulation products for building equipment and industrial installations — Expanded perlite products — Specification

#### 1 Scope

This document specifies the requirements for factory-made expanded perlite products which are used for thermal insulation of industrial installations and building equipment with an operating temperature from 23  $^{\circ}$ C to  $\sim 1~000~^{\circ}$ C.

The products are manufactured in the form of boards, pipe sections, segments, prefabricated ware and special ware.

This document describes product characteristics and includes procedures for testing, evaluation of conformity, marking and labelling.

Products covered by this document are also used in prefabricated thermal insulation systems and composite panels; the structural performance of systems incorporating these products is not covered.

This document does not specify the required level or class of a given property required to be achieved by a product in order to demonstrate fitness for purpose in a particular application. The levels required for a given application can be found in regulations and invitations to tender.

This document is not applicable to:

- a) products with a declared thermal conductivity greater than 0 072 W/(m·K) at 70 °C;
- b) products intended to be used for the insulation of the building structure;
- c)/ $_{\rm S}$  the acoustical aspects\_/ $_{\rm S}$  tandards/ $_{\rm S}$  ist/5b1f758c-092f-4849-a339-fb699625d99c/iso-6334-2023
  - 1) direct airborne sound insulation, and
  - 2) impact noise transmission index.

#### 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1182, Reaction to fire tests for products — Non-combustibility test

ISO 1716, Reaction to fire tests for products — Determination of the heat of combustion (calorific value)

ISO 2477, Shaped insulating refractory products — Determination of permanent change in dimensions on heating

ISO 8302, Thermal insulation — Determination of steady-state thermal resistance and related properties — Guarded hot plate apparatus

ISO 8497, Thermal insulation — Determination of steady-state thermal transmission properties of thermal insulation for circular pipes

ISO 8894-1, Refractory materials — Determination of thermal conductivity — Part 1: Hot-wire methods (cross-array and resistance thermometer)

#### ISO 6334:2023(E)

- ISO 9053, Acoustics Determination of airflow resistance
- ISO 9229, Thermal insulation Vocabulary
- ISO 11654, Acoustics Sound absorbers for use in buildings Rating of sound absorption
- ISO 12570, Hygrothermal performance of building materials and products Determination of moisture content by drying at elevated temperature
- ISO 12576-1, Thermal insulation Insulating materials and products for buildings Conformity control systems Part 1: Factory-made products
- ISO 13787, Thermal insulation products for building equipment and industrial installations Determination of declared thermal conductivity
- ISO 21129, Hygrothermal performance of building materials and products Determination of water-vapour transmission properties Box method
- ISO 29465, Thermal insulating products for building applications Determination of length and width
- ISO 29466, Thermal insulating products for building applications Determination of thickness
- ISO 29467, Thermal insulating products for building applications Determination of squareness
- ISO 29468, Thermal insulating products for building applications Determination of flatness
- ISO 29469:2022, Thermal insulating products for building applications Determination of compression behaviour
- ISO 29470, Thermal insulating products for building applications Determination of the apparent density
- ISO 29472, Thermal insulating products for building applications Determination of dimensional stability under specified temperature and humidity conditions
- ISO 29767, Thermal insulating products for building applications Determination of short-term water absorption by partial immersion
- ISO 5017, Dense shaped refractory products Determination of bulk density, apparent porosity and true porosity
- ISO 8841, Dense, shaped refractory products Determination of permeability to gases
- ISO 20392, Thermal-insulating materials Determination of compressive creep
- ISO 16537, Thermal insulating products for building applications Determination of shear behaviour
- ISO 12628, Thermal insulating products for building equipment and industrial installations Determination of dimensions, squareness and linearity of preformed pipe insulation
- ISO 12624, Thermal insulating products for building equipment and industrial installations Determination of trace quantities of water-soluble chloride, fluoride, silicate, sodium ions and pH
- ISO 12629, Thermal insulating products for building equipment and industrial installations Determination of water vapour transmission properties of preformed pipe insulation
- ISO 18099, Thermal insulating products for building equipment and industrial installations Determination of the coefficient of thermal expansion
- ISO 12623, Thermal insulating products for building equipment and industrial installations Determination of short-term water absorption by partial immersion of preformed pipe insulation

#### 3 Terms, definitions, symbols, units and abbreviated terms

#### 3.1 Terms and definitions

For the purposes of this document the terms and definitions given in ISO 9229 and the following apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <a href="https://www.iso.org/obp">https://www.iso.org/obp</a>
- IEC Electropedia: available at <a href="https://www.electropedia.org/">https://www.electropedia.org/</a>

#### 3.1.1

#### production line

equipment that produces products in a continuous process

Note 1 to entry: For initial type test (ITT) and factory production control (FPC), each line is considered separately.

#### 3.1.2

#### production unit

equipment that produces products in a discontinuous process

Note 1 to entry: For initial type test (ITT) and factory production control (FPC), units using the same process in one factory are considered together (as one production line).

#### 3.2 Symbols, units and abbreviated terms

#### 3.2.1 Symbols and units ps://standards.iteh.ai

Symbol	Quantity Quantity	Unit
d	inside diameter of pipe section	mm
b	width	mm
t out/standards it	thickness 180 0534:2023	00/iso 6334/ 2023
$t_{\mathrm{D}}$	declared thickness of the product	mm
$\mathcal{S}_{ ext{lin}}$	deviation from linearity	mm
1	length	mm
$S_{\mathrm{b}}$	deviation from squareness of boards on length and width	mm/m
$S_{t}$	deviation from squareness of boards on thickness	mm
$S_{\rm p}$	deviation from squareness for pipe insulation	mm
$S_{\max}$	deviation from flatness	mm
$\Delta \varepsilon_1$	relative change in length	%
$\Delta \varepsilon_{ m b}$	relative change in width	%
$\Delta \varepsilon_{\mathrm{t}}$	relative change in thickness	%
λ	thermal conductivity	W/(m·K)
$\lambda_{ m D}$	declared thermal conductivity	W/(m·K)
μ	water vapour diffusion resistance factor	_
$\sigma_{ m m}$	bending strength	kPa
$ ho_{ m a}$	apparent density	kg/m <sup>3</sup>

#### 3.2.2 Abbreviated terms for declared properties

Abbreviated term	Declared property		
CS(5/Y)	declared level for compressive stress at 5 % deformation		
Cl	declared level for chloride content		
F	declared level for fluoride content		
Na	declared level for sodium		
К	declared level for potassium content		
рН	declared level for pH		
L	declared class for length tolerances		
MU	declared value for water vapour diffusion resistance factor		
P	declared value for flatness tolerances		
S	declared class for squareness tolerances		
ST	declared level for maximum service temperature		
Т	declared class for thickness tolerances		
W	declared class for width tolerances		

#### Abbreviated terms 3.2.3

Abbreviated term	Full term	
EP	Expanded perlite Standards	
ITT	Initial type test	
ML	Manufacturer's literature	
FPC	Factory production control	
ST	Service temperature	

#### Requirements s.teh.ai/catalog/standards/sist/5b1f758c-092f-4849-a339-fb699625d99c/iso-6334-2023

#### 4.1 General

Product properties shall be assessed in accordance with <u>Clause 5</u>. To be in conformance with this document, products shall meet the requirements of 4.2, and the requirements of 4.3, as appropriate.

The test methods to be used for determination of each property are given in Table 4, which also shows the required test specimen dimensions and the minimum number of test specimens required to give one test result.

One test result for a product property is the average of the measured values on the number of test specimens given in Table 4.

For FPC, see Annex A.

#### 4.2 For all applications

#### Thermal conductivity 4.2.1

The thermal conductivity values shall be declared by the manufacturer at reference mean temperatures covering the product ST range. The following conditions apply:

- the measured values shall be expressed with three significant figures;
- the declared conductivity curve shall be given as a limit curve, as defined in ISO 13787.

#### 4.2.2 Dimensions and tolerances

#### 4.2.2.1 Linear dimensions

The length, l, width, b, and thickness, t, of boards and the dimensions of pipe sections and prefabricated ware shall be declared. When determined, no test result shall deviate from the declared values by more than the tolerance given in Table 1.

Table 1 — Dimensional tolerances

Form of delivery	Length	Width	Thickness	Inside diameter			
Board	±3 mm or ±0,6 % <sup>a</sup>	±3 mm or ±0,4 % <sup>a</sup>	+3 -2 mm				
Pipe section or seg- ment	±3 mm or ±0,6 % <sup>a</sup>		+3 -2 mm	0 mm to ±5 mm			
Whichever gives the greatest numerical tolerance.							

#### 4.2.2.2 Squareness

The deviation from squareness of boards on length and width,  $S_b$ , shall not exceed 6 mm/m and the deviation from squareness of boards on thickness,  $S_t$ , shall not exceed 2 mm. For pipe sections and segments, the deviation from squareness,  $S_n$ , shall not exceed 3 mm.

#### **4.2.2.3** Flatness

The deviation from flatness,  $S_{\text{max}}$ , shall not exceed 6 mm.

#### 4.2.2.4 Pipe section linearity

The deviation from linearity,  $S_{lin}$ , shall not exceed 3 mm or 0,6 % on length, whichever gives the greatest numerical tolerance.

#### **4.2.3** and **Dimensional stability** and dards/sist/5b1f758c-092f-4849-a339-fb699625d99c/iso-6334-2023

Standard atmospheres used for initial and final conditioning shall be chosen in accordance with <u>5.2</u>.

The test shall be carried out after storage for 48 h at (23 ± 2) °C and (90 ± 5) % relative humidity. The relative changes in length,  $\Delta \varepsilon_{\rm b}$ , width,  $\Delta \varepsilon_{\rm b}$ , and thickness,  $\Delta \varepsilon_{\rm t}$ , shall not exceed 1,0 %.

#### 4.2.4 Fire properties

Fire properties with respect to reaction to fire should be assessed, taking into consideration the applicable legislation and building codes in the individual territories in which the product is to be used.

#### 4.2.5 Durability characteristics

#### 4.2.5.1 General

The appropriate durability characteristics have been considered and are covered in 4.2.5.2, 4.2.5.3 and 4.2.5.4.

#### 4.2.5.2 Durability of fire properties against ageing/degradation and high temperature

The fire properties in respect to reaction to fire performance of EP products does not change with time or when subjected to high temperature.

#### 4.2.5.3 Durability of thermal resistance against ageing/degradation

The thermal conductivity of EP products does not change with time.

#### 4.2.5.4 Durability of thermal resistance against high temperature

The thermal conductivity of EP products does not change with time at a high temperature.

#### 4.3 For specific applications

#### 4.3.1 General

If there is no requirement for a property, described in <u>4.3</u> for a product in use, then that property need not be determined and declared by the manufacturer.

If a property described in 4.3 is declared, it shall be determined in accordance with the test method shown in Table 4.

NOTE For information on additional properties, see **Annex B**.

#### 4.3.2 Maximum service temperature (ST)

The maximum ST for flat products shall be determined in accordance with ISO 2477.

At the maximum ST, the relative changes in length,  $\Delta \varepsilon_l$ , and width,  $\Delta \varepsilon_b$ , shall not exceed 2 %. The maximum ST, shall be declared in °C in levels with steps of 50 °C as given in the examples shown in Table 2. The test specimen shall not exhibit evidence of self-heating.

Table 2 — Levels for maximum service temperature (ST)

Requirement Level °C ST 650 ≥650 ST 700 ≥700 ST 750 ≥750 ST 800 ≥800 ST 850 ≥850 ST 900 ≥900 ST 950 ≥950 ST 1000 ≥1 000

https://standards

#### 4.3.3 Compressive stress or strength

No test result shall be lower than the value, given in Table 3, for the declared level.