



Designation: B2 – 12

Standard Specification for Medium-Hard-Drawn Copper Wire¹

This standard is issued under the fixed designation B2; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

1. Scope

1.1 This specification covers medium-hard-drawn round copper wire for electrical purposes (see Explanatory Note 1).

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.2.1 *Exception*—The SI values of density and resistivity are to be regarded as standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 The following documents of the issue in effect on date of material purchase form a part of this specification to the extent referenced herein:

2.2 *ASTM Standards:*²

[B5 Specification for High Conductivity Tough-Pitch Copper Refinery Shapes](#)

[B49 Specification for Copper Rod Drawing Stock for Electrical Purposes](#)

[B170 Specification for Oxygen-Free Electrolytic Copper—Refinery Shapes](#)

[B193 Test Method for Resistivity of Electrical Conductor Materials](#)

[B258 Specification for Nominal Diameters and Cross-Sectional Areas of AWG Sizes of Solid Round Wires Used as Electrical Conductors](#)

¹ This specification is under the jurisdiction of ASTM Committee B01 on Electrical Conductors and is the direct responsibility of Subcommittee B01.04 on Conductors of Copper and Copper Alloys.

Current edition approved Nov. 15, 2012. Published November 2012. Originally approved in 1912. Last previous edition approved in 2008 as B2–08. DOI: 10.1520/B0002-12

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

2.3 *Other Documents:*

[NBS Handbook 100 Copper Wire Tables of the National Bureau of Standards](#)³

3. Ordering Information

3.1 Orders for material under this specification should include the following information:

3.1.1 Quantity of each size;

3.1.2 Wire size: diameter in inches (see 5.1 and Table 1);

3.1.3 Type of copper, if special (see Section 4);

3.1.4 Package size (see 11.1);

3.1.5 Special package marking, if required; and

3.1.6 Place of inspection (Section 10).

4. Materials and Manufacture

4.1 The material shall be copper of such quality and purity that the finished product shall have the properties and characteristics prescribed in this specification.

NOTE 1—Specifications B5, B49, and B170 define the materials suitable for use.

4.2 Copper bars of special qualities, forms, or types, as may be agreed upon between the manufacturer and the purchaser, and which will conform to the requirements prescribed in this specification, may also be used.

5. Dimensions and Permissible Variations

5.1 The wire sizes shall be expressed as the diameter of the wire in decimal fractions of an inch to the nearest 0.0001 in. (0.1 mil) or in millimetres to the nearest 0.001 mm (Explanatory Note 2).

5.2 Within the range of diameters included in Table 1 the wire shall not vary from the specified diameter by more than $\pm 1\%$, expressed to the nearest 0.0001 in. (0.1 mil) 0.001 mm.

5.3 Ten percent, but not less than five coils or spools (or all if the lot is less than five) from any lot of wire shall be gaged at three places. If accessible, one gaging shall be taken near each end and one near the middle. If any of the selected coils or spools fails to conform to the requirements prescribed in 5.2, all coils or spools shall be gaged in the manner specified.

³ Available from National Technical Information Service (NTIS), 5285 Port Royal Rd., Springfield, VA 22161, <http://www.ntis.gov>.

TABLE 1 Tensile Requirements

Diameter		Area at 20°C			Tensile Strength				Elongation, min, %in 10-in. (250 mm)
in.	mm	cmil	in. ²	mm ²	psi		MPa		
					Min	Max	Min	Max	
0.4600	11.684	211 600	0.1662	107.0	42 000	49 000	290	340	3.8
0.4096	10.404	167 800	0.1318	85.0	43 000	50 000	295	345	3.6
0.3648	9.266	133 100	0.1045	67.4	44 000	51 000	305	350	3.2
0.3249	8.252	105 600	0.08291	53.5	45 000	52 000	310	360	3.0
0.2893	7.348	83 690	0.06573	42.4	46 000	53 000	315	365	2.8
0.2576	6.543	66 360	0.05212	33.6	47 000	54 000	325	370	2.5
0.2294	5.827	52 620	0.04133	26.7	48 000	55 000	330	380	2.2
0.2043	5.189	41 740	0.03278	21.2	48 330	55 330	335	380	1.9
0.1819	4.620	33 090	0.02599	16.8	48 660	55 660	335	385	1.7
0.1620	4.115	26 240	0.02061	13.3	49 000	56 000	340	385	1.5
0.1443	3.665	20 820	0.01635	10.5	49 330	56 330	340	390	1.4
0.1285	3.264	16 510	0.01297	8.37	49 660	56 660	340	390	1.3
0.1144	2.906	13 090	0.01028	6.63	50 000	57 000	345	395	1.3
0.1019	2.588	10 380	0.00816	5.26	50 330	57 330	345	395	1.2
0.0907	2.304	8 230	0.00646	4.17	50 660	57 600	350	400	1.2
0.0808	2.052	6 530	0.00513	3.31	51 000	58 000	350	400	1.1
0.0720	1.829	5 180	0.00407	2.63	51 330	58 330	355	400	1.1
0.0641	1.628	4 110	0.00323	2.08	51 660	58 660	355	405	1.0
0.0571	1.450	3 260	0.00256	1.65	52 000	59 000	360	405	1.0
0.0508	1.290	2 580	0.00203	1.31	52 330	59 330	360	410	1.0
0.0453	1.151	2 050	0.00161	1.04	52 660	59 660	365	410	1.0
0.0403	1.024	1 620	0.00128	0.823	53 000	60 000	365	415	1.0

6. Workmanship, Finish, and Appearance

6.1 The wire shall be free from all imperfections not consistent with the best commercial practice.

7. Tensile Properties

7.1 The wire shall conform to the requirements as to tensile properties prescribed in Table 1 (Explanatory Note 3 and Note 4).

7.2 Tests on a specimen containing a joint shall show at least 95 % of the minimum tensile strength given in Table 1. Elongation tests shall not be made on a specimen containing a joint.

7.3 For wire the nominal diameter of which is more than 0.001 in. (1 mil) (0.025 mm) greater than a size listed in Table 1, but which is less than that of the next larger size, the requirements of the next larger size shall apply.

7.4 Determine the elongation of the wire as the permanent increase in length due to the breaking of the wire in tension, measured between gage marks placed originally 10 in. (254 mm) apart upon the test specimen (Explanatory Note 4).

7.5 If any part of the fracture takes place outside the gage marks or in the jaws of the testing machine, or if an examination of the specimen indicates a flaw, the value obtained may not be representative of the material. In such cases the test may be discarded and a new test made.

7.6 *Retests*—If, upon testing a sample from any coil or spool of wire, the results do not conform to the requirements prescribed in Table 1, two additional samples shall be tested and the average of the three tests shall determine the acceptance or rejection of the coil or spool.

8. Resistivity

8.1 Electrical resistivity shall be determined on representative samples by resistance measurements (Explanatory Note 5

and Note 6). At a temperature of 20°C the resistivity shall not exceed the following values:

Nominal Diameter, in.	Resistivity at 20°C,	
	Ω·lb/mile ²	Ω·g/m ²
0.460 to 0.325 (11.684 to 8.255 mm), incl	896.15	0.15694
Under 0.325 to 0.0403 (8.255 to 1.024 mm), incl	905.44	0.15857

8.2 Tests to determine conformance to the electrical resistance requirements shall be made in accordance with Test Method B193.

9. Joints

9.1 No joints shall be made in the completed wire (Explanatory Note 7). Joints in wire and rods, prior to final drawing, shall be made in accordance with the best commercial practice and shall conform to the requirements prescribed in 7.2.

10. Inspection

10.1 Unless otherwise specified in the contract or purchase order, the manufacturer shall be responsible for the performance of all inspection and test requirements specified (Explanatory Note 8).

10.2 All inspections and tests shall be made at the place of manufacture unless otherwise especially agreed to between the manufacturer and the purchaser at the time of the purchase.

10.3 The manufacturer shall afford the inspector representing the purchaser all reasonable manufacturer's facilities to satisfy that the material is being furnished in accordance with this specification.

10.4 Unless otherwise agreed upon between the purchaser and the manufacturer, conformance of the wire to the various requirements listed in this specification shall be determined on samples taken from each lot of wire presented for acceptance.

10.5 The manufacturer shall, if requested prior to inspection, certify that all wire in the lot was made under such conditions that the product as a whole conforms to the