2023-~~04-13~~07-17

ISO/FDIS 10544:2023(E)

ISO/TC 17/SC 16/WG 15

Secretariat: SN

Cold-reduced steel wire for the reinforcement of concrete and the manufacture of welded fabric

~~Edited DIS - MUST BE USED FOR FINAL DRAFT~~

Contents

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO ~~documents~~document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see ~~www.iso.org/directives~~www.iso.org/directives).

~~Attention is drawn~~ISO draws attention to the possibility that ~~some of~~ the ~~elements~~implementation of this document may ~~be~~involve the ~~subject~~use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights~~.~~ in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights. ~~Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).~~

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 17, *Steel*, Subcommittee SC 16, *Steels for the reinforcement and prestressing of concrete*.

This second edition cancels and replaces the first edition (ISO 10544:1992), which has been technically revised.

The main changes are as follows:

— ~~Normative~~ normative references have been revised;~~.~~

— ~~Terms~~ terms and definitions have been revised~~.~~;

— ~~Diameters~~ diameters have been extended to ~~18mm~~ 18 mm;

— ~~Geometry~~ geometry of ribbed and indented wires have been revised;

— ~~Steel~~ steel grade and chemical composition have been revised~~. Example~~;

— example of identification of manufacturer on ribbed wire and indented wire have been added.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Cold-reduced steel wire for the reinforcement of concrete and the manufacture of welded fabric

1 Scope

This document specifies technical requirements for cold-reduced steel wire designed for the reinforcement of concrete or for use in welded fabric.

Two steel grades, CRB500 and CRB540H are defined as examples. Other grades can be used.

This document is applicable to wire made from rod by working through dies or rollers. The production process is at the discretion of the manufacturer.

For wire supplied in coil form, this document is applicable to the straightened product.

Wires produced from finished products, such as plates and railway rails, are outside the scope of this document.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 404, *Steel and steel products — General technical delivery requirements*

ISO 6892-1, *Metallic materials — Tensile testing* ~~ISO 10144, *Steels for the reinforcement and prestressing of concrete — Certification scheme for steel bars and wires*~~ *Part 1: Method* *test at room temperature*

ISO 15630-1, *Steel for the reinforcement and prestressing of concrete — Test methods — Part 1: Reinforcing bars, rods and wire*

~~ISO/TR 9769, *Steel and iron — Review of available methods of analysis*~~

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

— ISO Online browsing platform: available at https://www.iso.org/obp

— IEC Electropedia: available at https://www.electropedia.org/

3.1
cast analysis
chemical analysis of a sample of the molten steel during casting

3.2
~~**conformity assessment scheme**~~

~~conformity assessment system related to specific objects of conformity assessment, to which the same specified requirements, specific rules and procedures apply~~

~~Note 1 to entry: Conformity assessment schemes may be operated at an international, national or sub-national level.~~

~~Note 2 to entry: Certification, i.e. third-party attestation related to products, processes, systems or persons, is applicable to all objects of conformity assessment except for conformity assessment bodies themselves, to which accreditation is applicable.~~

~~3.3~~
characteristic value
value having a prescribed probability of not being attained in a hypothetical unlimited test series

Note 1 to entry: Equivalent to fractile, which is defined in ISO 3534-1:2006.

[SOURCE: ISO 16020:2005, 2.4.10~~, modified — Note 2 to entry has been added.~~]]

3.4~~3~~
core
part of cross-section of the wire that contains neither ribs nor indentations

3.4
indentation ~~3.5~~
inclination ~~of indentation~~
~~β~~
~~the~~ β_{ind}
angle between the indentation and the longitudinal axis of the wire~~(~~

Note 1 to entry: See Figure 3 and Figure 4~~).~~

~~3.6~~
3.5
indentation spacing
~~e~~
ℓ_{ind}
distance between the centres of two consecutive indentations measured parallel to the axis of the wire~~–~~

Note 1 to entry: See Figures 3 and 4.

3.~~7~~6
indented wire
wire whose surface has indentations at regular intervals along the length

3.~~8~~7
inspection
activities such as measuring, examining, testing, gauging one or more characteristics of a product or service and comparing these with specified requirements to determine conformity

3.~~9~~8
nominal cross-sectional area
cross-sectional area equivalent to the area of a circular plain wire of the nominal diameter

3.~~10~~9
plain wire
smooth surfaced wire without bond enhancing properties

3.~~11~~10
product analysis
chemical analysis of a sample from a wire

3.~~12~~11
rib height
a
distance from the highest point of the rib to the surface of the core, ~~to be~~ measured normal to the axis of the wire

Note 1 to entry: See Figures 1 and 2.

3.12
rib inclination
β_{rib}
angle between the rib and the longitudinal axis of the wire

Note 1 to entry: See Figures 1 and 2.

3.13
~~**rib inclination, β, β_1, β_2, β_3**~~
~~angle between the rib and the longitudinal axis of the wire (See Figure 1 and Figure 2)~~

~~**3.14**~~
rib spacing~~, c, c_1, c_2, c_3~~
c_{rib}
distance between the centres of two consecutive transverse ribs measured parallel to the axis of the wire

~~Note 1 to entry: See Figures 1 and 2.~~

Note 1 to entry: See Figures 1 and 2.

3.~~15~~14
ribbed wire
wire whose surface has ribs at regular intervals along the length

3.~~16~~15
test unit
number of pieces or the tonnage of products ~~to~~ be accepted or rejected together, on the basis of the tests ~~to be~~ carried out on sample products in accordance with the requirements of the product standard or order

3.~~17~~16
specific projected indentation area
f_p
area of the projections of all indentations on a plane perpendicular to the longitudinal axis of the wire, divided by the wire length and the nominal circumference

Note 1 to entry: See 5.2.

3.~~18~~17
specific projected rib area
f_r
area of the projections of all ribs on a plane perpendicular to the longitudinal axis of the wire, divided by the wire length and the nominal circumference

Note 1 to entry: See 5.1.

3.~~19~~18
transversal indentationless perimeter
$\sum e_i$
sum of the distances along the surface of the core between the transverse indentations of adjacent rows measured as the projection on a plan perpendicular to the wire axis~~–~~

Note 1 to entry: See Figures 3 and 4.

3.~~20~~19
transversal ribless perimeter
$\sum f_i$
sum of the distances along the surface of the core between the transverse ribs of adjacent rows measured as the projection on a plane perpendicular to the wire axis~~–~~

Note 1 to entry: See Figures 1 and 2.

~~Note 1 to entry: See Figures 1 and 2.~~

3.~~21~~20
passive reinforcement
reinforcement that does not apply a compressive stress to the concrete

4 Dimensions, masses and tolerances

The nominal diameter of the wire shall be in the range from 4 mm to 18 mm. Recommended nominal diameters, *d*, are given in Table 1.

For nominal diameters not listed in Table 1, the mass divided by length shall be 7 850 kg/m^3 x nominal cross-sectional area.

Table 1 — Recommended diameters and required masses

Nominal wire diameter *d* mm	Nominal cross-sectional area mm^2	Mass divided by length	
		Requirement kg/m	Permissible deviation [a] %
4	12,6	0,099	±4
5	19,6	0,154	
6	28,3	0,222	
7	38,5	0,302	
8	50,3	0,395	
9	63,6	0,499	
10	78,5	0,617	
12	113,1	0,888	
14	153,9	1,208	
16	201,1	1,578	

18	254,5	1,998	
[a] Refers to a single wire.			

5 Geometry of ribbed and indented wires

5.1 Ribbed wire

Ribbed wire shall have two or more rows of transverse ribs equally distributed around the perimeter with a substantially uniform spacing shall be between 0,6d to 1,0d, where d is the nominal diameter. Figure 1 shows an example with two rows, Figure 2 shows an example with three rows.

The minimum value for the specific projected rib area, f_r , shall be

0,036 for 4 mm ≤ d < ~~5mm~~5 mm;

0,039 for ~~5mm~~5 mm ≤ d ≤ 6 mm;

0,045 for 6 mm < d ≤ 8 mm;

0,052 for ~~8mm~~8 mm < d ≤ 10 mm;

0,056 for 10 mm < d ≤ 18 mm.

f_r is calculated using ~~the formula~~Formula (1):

~~$f_r = \frac{k \times F_R \times \sin\beta}{\pi \times d \times c}$~~

$$f_r = \frac{k \times F_R \times \sin\beta_{rib}}{\pi \times d \times c_{rib}} \quad (1)$$

where

k is the number of rib rows;

F_R is the area of the projection of one rib on a plane parallel to that rib;

~~β~~β_{rib} is the rib inclination relative to the axis of the wire;

d is the nominal diameter of the wire;

~~c~~c_{rib} is the rib spacing.

In the area of marking, deviations from the requirements of this subclause may occur (see 10.1).

Field Code Changed