



Designation: D448 – 12

# Standard Classification for Sizes of Aggregate for Road and Bridge Construction<sup>1</sup>

This standard is issued under the fixed designation D448; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reappraisal.

*This standard has been approved for use by agencies of the Department of Defense.*

## 1. Scope

1.1 This classification defines aggregate size number designations and standard size ranges for mechanical sieve analyses of coarse aggregate and screenings for use in the construction and maintenance of various types of highways and bridges.

1.2 *Units*—The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

NOTE 1—Sieve size is identified by its standard designation in Specification E11. The alternative designation given in parentheses is for information only and does not represent a different standard sieve size.

1.3 The text of this classification references notes and footnotes which provide explanatory material. These notes and footnotes (excluding those in tables and figures) shall not be considered as requirements of the classification.

## 2. Referenced Documents

2.1 *ASTM Standards*:<sup>2</sup>

C136 Test Method for Sieve Analysis of Fine and Coarse Aggregates

D8 Terminology Relating to Materials for Roads and Pavements

D75 Practice for Sampling Aggregates

E11 Specification for Woven Wire Test Sieve Cloth and Test Sieves

## 3. Terminology

3.1 Definition of terms, see Terminology D8.

## 4. Significance and Use

4.1 Some contract documents specify certain aggregate sizes for specific uses or may suggest one or more of these sizes as appropriate for the preparation of various end-product mixtures. In some cases, closer limits on variability of the aggregate grading are required.

## 5. Manufacture

5.1 The standard sizes of aggregate described in this classification are manufactured by means of any suitable process used to separate raw material into the desired size ranges. Production of standard sizes by blending two or more different components is permitted.

## 6. Standard Sizes

6.1 Standard aggregate sizes shall conform to the requirements prescribed in Table 1 for the size number specified. Conformance shall be determined by means of laboratory sieves having square openings and conforming to Specification E11.

## 7. Basis of Classification

7.1 Classification of an aggregate is based upon the size number designation and size ranges shown in Table 1. Aggregate shall be sampled in accordance with Practice D75 and tested for grading by Test Method C136.

<sup>1</sup> This classification is under the jurisdiction of ASTM Committee D04 on Road and Paving Materials and is the direct responsibility of Subcommittee D04.50 on Aggregate Specifications.

Current edition approved Dec. 1, 2012. Published December 2012. Originally approved in 1937. Last previous edition approved in 2008 as D448 – 08. DOI: 10.1520/D0448-12.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.