

~~2022-11-01~~

~~2023-01-05~~

ISO/FDIS 16245:2023x(E)

ISO/TC 46/SC 10

Secretariat: SIS

**Information and documentation — Boxes, file covers and other enclosures, made from cellulosic materials, for storage of paper and parchment documents**

**Information et documentation — Boîtes, chemises et autres contenants en matériaux cellulosiques, pour le stockage des documents sur papier et parchemin**

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

ISO/FDIS 16245

<https://standards.iteh.ai/catalog/standards/sist/0a0158e4-dbb9-4781-8d70-fb047c412d63/iso-fdis-16245>

ISO/FDIS 16245:20222023(E)

© ISO 20222023

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office

CP 401 • Ch. de Blandonnet 8

CH-1214 Vernier, Geneva

Phone: +41 22 749 01 11

Email: [copyright@iso.org](mailto:copyright@iso.org)

Website: [www.iso.org](http://www.iso.org)[www.iso.org](http://www.iso.org)

Published in Switzerland

# iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO/FDIS 16245

<https://standards.iteh.ai/catalog/standards/sist/0a0158e4-dbb9-4781-8d70-fb047c412d63/iso-fdis-16245>

**Formatted:** Font: 11 pt

**Formatted:** Space After: 12 pt, Line spacing: Exactly 11 pt

2 ————— © ISO 2022 – All rights reserved

ii ————— © ISO 2023 – All rights reserved

## Contents

Foreword.....	iv
Introduction.....	v
1 Scope.....	1
2 Normative references.....	1
3 Terms, definitions and symbols.....	1
3.1 Terms and definitions.....	1
3.2 Symbols.....	3
4 Requirements for boxes.....	3
4.1 General.....	3
4.2 Boards.....	3
4.2.1 General.....	3
4.2.2 Criteria of acceptance.....	3
4.2.3 Categories.....	4
4.3 Cloth covering.....	4
4.4 Lining.....	4
4.5 Adhesives.....	4
4.6 Manufacturer's joints and fasteners.....	5
4.7 Bleeding of colour or additives.....	5
4.8 Surface.....	5
4.9 Design.....	5
4.10 Strength.....	5
4.11 Dimensions.....	5
5 Requirements for file covers and folders.....	6
5.1 General.....	6
5.2 Paper and board.....	6
5.3 Adhesives.....	6
5.4 Fasteners.....	6
5.5 Bleeding of colour and additives.....	6
5.6 Strength.....	6
5.7 Dimensions.....	7
6 Test report.....	7
Annex A (normative) Bleeding test.....	8
Bibliography.....	9
Foreword.....	iv
Introduction.....	v
1 Scope.....	Error! Bookmark not defined.
2 Normative references.....	Error! Bookmark not defined.
3 Terms and definitions.....	Error! Bookmark not defined.
4 Symbols.....	Error! Bookmark not defined.

**Edited DIS -  
MUST BE USED  
FOR FINAL  
DRAFT**

Formatted: Font: 11 pt

Formatted: Space After: 12 pt, Line spacing: Exactly 11 pt

**5 Requirements for boxes** ..... Error! Bookmark not defined.  
**5.1 General**..... Error! Bookmark not defined.  
**5.2 Boards** ..... Error! Bookmark not defined.  
**5.2.1 General**..... Error! Bookmark not defined.  
**5.2.2 Criteria of acceptance**..... Error! Bookmark not defined.  
**5.2.3 Categories**..... Error! Bookmark not defined.  
**5.3 Cloth covering**..... Error! Bookmark not defined.  
**5.4 Lining**..... Error! Bookmark not defined.  
**5.5 Adhesives** ..... Error! Bookmark not defined.  
**5.6 Manufacturer's joints and fasteners**..... Error! Bookmark not defined.  
**5.7 Bleeding of colour or additives** ..... Error! Bookmark not defined.  
**5.8 Surface**..... Error! Bookmark not defined.  
**5.9 Design**..... Error! Bookmark not defined.  
**5.10 Strength** ..... Error! Bookmark not defined.  
**5.11 Dimensions** ..... Error! Bookmark not defined.  
**6 Requirements for file covers and folders** ..... Error! Bookmark not defined.  
**6.1 General**..... Error! Bookmark not defined.  
**6.2 Paper and board**..... Error! Bookmark not defined.  
**6.3 Adhesives** ..... Error! Bookmark not defined.  
**6.4 Fasteners** ..... Error! Bookmark not defined.  
**6.5 Bleeding of colour and additives** ..... Error! Bookmark not defined.  
**6.6 Strength** ..... Error! Bookmark not defined.  
**6.7 Dimensions** ..... Error! Bookmark not defined.  
**7 Test report**..... Error! Bookmark not defined.  
**Annex A (normative) Special instruction for determining the Kappa number**..... Error!  
Bookmark not defined.  
**Annex B (normative) Bleeding test**..... Error! Bookmark not defined.  
**Annex C (normative) Strength test**..... Error! Bookmark not defined.

**Formatted:** Font: 11 pt  
**Formatted:** Space After: 12 pt, Line spacing: Exactly 11 pt

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 46, *Information and documentation*, Subcommittee SC 10, *Requirements for document storage and conditions for preservation*.

This second edition cancels and replaces the first edition (ISO 16245:2009) which has been technically revised.

The main changes are as follows:

- ISO 23404 has been added as a normative reference, and an acceptance limit based on tests carried out in accordance with ~~this ISO~~ [ISO 23404 standard](#) has been determined;
- the bleeding test procedure has been improved;
- the different types of boards used for making boxes, file covers and other enclosures have been defined.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

© ISO 2022 – All rights reserved

© ISO 2023 – All rights reserved

~~Edited DIS -  
MUST BE USED  
FOR FINAL  
DRAFT~~

Formatted: Font: 11 pt

Formatted: Space After: 12 pt, Line spacing: Exactly 11 pt

## Introduction

Boxes, file covers and other enclosures are available in several different materials. Those made of cellulosic materials are the most commonly used enclosures for long-term storage of paper and parchment documents. Experience has shown that properties of the enclosure are of great importance to the protection, permanence and durability of the documents. This document specifies a number of basic requirements relevant to the material composition and construction of cellulose based boxes, file covers and other enclosures.

The purpose of boxes, file covers and other enclosures is to hold and contain documents in prescribed order or grouping, to provide a protective container, and to facilitate identification, transport and storage. Preferably, the same file covers and boxes can be used from storage at the place of work to the final archive storage. Moreover, it is possible to transport, handle and lend a related collection of documents as a unit.

Boxes, through their design and construction, protect documents from environmental risks such as light, rapid temperature and moisture changes and dust, as well as from damage related to handling. File covers and folders further protect documents by enclosing them with materials specified for their preservation qualities. However, even high-quality file covers, folders and boxes cannot compensate for poor storage conditions.

This document can be used as a specification. It can also be incorporated as an element into other specifications, used in trade, or in other national or International Standards for more specialized purposes.

ITEH STANDARD PREVIEW  
(standards.iteh.ai)

ISO/FDIS 16245

<https://standards.iteh.ai/catalog/standards/sist/0a0158e4-dbb9-4781-8d70-fb047c412d63/iso-fdis-16245>

Formatted: Font: 11 pt

Formatted: Space After: 12 pt, Line spacing: Exactly 11 pt

6 © ISO 2022 – All rights reserved

vi © ISO 2023 – All rights reserved

## Information and documentation — Boxes, file covers and other enclosures, made from cellulosic materials, for storage of paper and parchment documents

### 1 Scope

This document specifies requirements for boxes, file covers and other enclosures made of cellulosic material, to be used for long term storage of documents on paper or parchment.

This document is applicable to boxes made of solid or corrugated board and to file covers and other enclosures made of paper or board.

This document can also be applicable to other types of enclosures for long term storage such as cases, portfolios, tubes and envelopes made of cellulosic material.

This document is not applicable to storage of photographic materials.

NOTE ISO 18902 contains requirements on storage materials for photographs.

### 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 5-3, *Photography and graphic technology — Density measurements — Part 3: Spectral conditions*

ISO 5-4, *Photography and graphic technology — Density measurements — Part 4: Geometric conditions for reflection density*

ISO 302, *Pulps — Determination of Kappa number*

ISO 535, *Paper and board — Determination of water absorptiveness — Cobb method*

ISO 536, *Paper and board — Determination of grammage*

ISO 4046-4, *Paper, board, pulps and related terms — Vocabulary — Part 4: Paper and board grades and converted products*

ISO 5626:1993, *Paper — Determination of folding endurance*

ISO 6588-1, *Paper, board and pulps — Determination of pH of aqueous extracts — Part 1: Cold extraction*

ISO 9706:1994, *Information and documentation — Paper for documents — Requirements for permanence*

ISO 10716, *Paper and board — Determination of alkali reserve*

**ISO/FDIS 16245:2023(E)**

ISO 11664-2, *Colorimetry — Part 2: CIE standard illuminants*

ISO 12048:1994, *Packaging — Complete, filled transport packages — Compression and stacking tests using a compression tester*

ISO 23404, *Information and documentation — Papers and boards used for conservation — Measurement of impact of volatiles on cellulose in paper*

**3 Terms, definitions and symbols**

**4.3 Terms and definitions**

For the purposes of this document, the terms and definitions given in ISO 4046-4 and the following apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

**3.1.1 box**  
storage container intended to protect documents and facilitate their shelving and handling

**3.1.2 file cover**  
enclosure made of a sheet of paper or board used for housing of and as a separating agent for document(s)

**3.1.3 folder**  
sheet of heavy paper stock or cardboard, scored near the middle, its halves bent so they rest side by side, and used as a loose cover to keep documents and other flat materials together, especially for purposes of filing

[SOURCE: SAA Glossary <https://dictionary.archivists.org/>]

**3.1.4 viscosity-average degree of polymerization**  
 $DP_v$   
average number of anhydroglucose units (monomers of cellulose) in the cellulose macromolecule, determined by measuring the viscosity of solutions in cupri-ethylenediamine (CED)

[SOURCE: ISO/TS 18344:2016, 3.3, modified — "Viscosity" has been added to the term, and the determination process has been added to the definition.]

**3.1.5 loss of  $DP_v$**   
 $\omega DP_v$ , arithmetic  $\omega DP_v$

2 © ISO 2022 – All rights reserved

2 © ISO 2023 – All rights reserved

Formatted: Font: 11 pt  
Formatted: Space After: 12 pt, Line spacing: Exactly 11 pt



**arithmetic** mean of the  $DP_v$  (3.1.4) of an exposed sample of reference paper against the  $DP_v$  of an unexposed sample of same paper

[SOURCE: ISO 23404:2020, 3.7, modified — "Viscosity average degree of polymerization" has been replaced by  $DP_v$ ]

**3.1.6**

**alkali reserve**

compound, such as calcium carbonate, that neutralizes acid that can be generated as a result of natural aging or from atmospheric pollution

[SOURCE: ISO 9706:1994]

**3.1.7**

**homogenous single-layer board**

board comprising a single furnish layer

Note 1 to entry: This definition is equivalent to a solid board as defined by ISO 4046-4:2016, 4.49.

Note 2 to entry: ~~the~~The term single-ply board can also be used instead of single-layer board.

**3.1.8**

**two-layer board**

board consisting of two furnish layers combined together during manufacture, while still moist

Note 1 to entry: The terms two-ply board and duplex board can also be used instead of two-layer board.

[SOURCE: ISO 4046-4:2016, 4.195]

**3.1.9**

**three-layer board**

board consisting of three furnish layers combined together during manufacture, while still moist

Note 1 to entry: The outer furnish layers may be of the same composition.

Note 2 to entry: The terms three-ply board and triplex board can also be used instead of three-layer board.

[SOURCE: ISO 4046-4:2016, 4.186]

**3.1.10**

**multi-layer board**

board consisting of more than three furnish layers combined together during manufacture

Note 1 to entry: Two or more furnish layers may be of the same composition.

Note 2 ~~to entry~~: The terms multi-ply board and multiplex board can also be used instead of multi-layer board.

[SOURCE: ISO 4046-4:2016, 4.122]

Formatted: Font: 11 pt  
Formatted: Space After: 12 pt, Line spacing: Exactly 11 pt

**ISO/FDIS 16245:2023(E)**

**3.4.11**

**pasted board**

board produced by the operation of pasting two or more boards of similar or different compositions

[SOURCE: ISO 4046-4:2016, 4.135]

**3.4.12**

**corrugated fibreboard**

board consisting of one or more sheets of fluted paper glued to a flat sheet of board or between several sheets

~~cf. single face corrugated fibreboard, single wall corrugated fibreboard, double wall corrugated fibreboard, triple wall corrugated fibreboard~~

cf. single-face corrugated fibreboard, single-wall corrugated fibreboard, double-wall corrugated fibreboard, triple-wall corrugated fibreboard

Note 1 to entry: In this document, corrugated board is used for corrugated fibreboard.

[SOURCE: ISO 4046-4:2016, 4.49]

**3.4.13**

**plasticizer**

**external plasticizer**

non-reactive substance incorporated in an adhesive to improve the flexibility and resilience of the bond

Note 1 to entry A plasticizer gives the adhesive film a greater extension at break, a lower modulus and a lower brittleness temperature. A plasticizer can be soluble in liquids and can migrate from the adhesive film.

[SOURCE: ISO 472:2013, 2.1549]

**5.4 Symbols**

Cobb <sub>60</sub>	The calculated mass of water absorbed in 60 <del>seconds</del> by 1 m <sup>2</sup> of paper or board under specified conditions
D <sub>R</sub>	Visual reflection density
S <sub>A</sub>	<del>influx</del> <u>Influx</u> spectrum, standard CIE illuminant A
S <sub>V</sub>	<del>visual</del> <u>Visual</u> spectral responsivity (with V <sub>λ</sub> , the CIE photopic spectral luminous efficiency function)
p <sub>max</sub>	Maximum pressure

Formatted: Font: 11 pt

Formatted: Space After: 12 pt, Line spacing: Exactly 11 pt

4 © ISO 2022 – All rights reserved

4 © ISO 2023 – All rights reserved