

---

---

**Lubricants, industrial oils and  
related products (Class L) — Family X  
(Greases) — Specifications**

*Lubrifiants, huiles industrielles et produits connexes (classe L) —  
Famille X (Graisses) — Spécifications*

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

ISO 12924:2023

<https://standards.iteh.ai/catalog/standards/sist/53f3e979-1e27-4e8d-8d5b-156a0a99e251/iso-12924-2023>



iTeh STANDARD PREVIEW  
(standards.iteh.ai)

ISO 12924:2023

<https://standards.iteh.ai/catalog/standards/sist/53f3e979-1e27-4e8d-8d5b-156a0a99e251/iso-12924-2023>



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2023

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

	Page
Foreword.....	iv
Introduction.....	v
<b>1 Scope.....</b>	<b>1</b>
<b>2 Normative references.....</b>	<b>1</b>
<b>3 Terms and definitions.....</b>	<b>2</b>
<b>4 Sampling.....</b>	<b>3</b>
<b>5 Requirements for greases.....</b>	<b>3</b>
5.1 General requirements.....	3
5.2 Symbol 1 — Lower operating temperature.....	3
5.3 Symbol 2 — Upper operating temperature.....	4
5.4 Symbol 3 — Water contamination and rust protection.....	5
5.5 Symbol 4 — Ability to lubricate under high loads.....	5
5.6 NLGI consistency number.....	6
5.7 Environmentally acceptable greases — EA.....	6
5.7.1 General.....	6
5.7.2 Biodegradability.....	7
5.7.3 Acute daphnia or copepods toxicity.....	7
<b>6 Additional data.....</b>	<b>7</b>
<b>7 Example of grease designation.....</b>	<b>7</b>
<b>Annex A (informative) Additional data.....</b>	<b>9</b>
<b>Bibliography.....</b>	<b>10</b>

ISO 12924:2023

<https://standards.iteh.ai/catalog/standards/sist/53f3e979-1e27-4e8d-8d5b-156a0a99e251/iso-12924-2023>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 28, *Petroleum and related products, fuels and lubricants from natural or synthetic sources*, Subcommittee SC 4, *Classifications and specifications*.

This second edition cancels and replaces the first edition (ISO 12924:2010), which has been technically revised. It also incorporates the Technical Corrigendum ISO 12924:2010/Cor 1:2012.

The main changes are as follows:

- introduction of environmentally acceptable greases (suffix EA added to the symbol);
- additional data table added to provide to the end user complementary information about important properties of the grease.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

## Introduction

According to Reference [25], grease is a lubricant which has been thickened in order that it remain in contact with the moving surfaces and not leak out under gravity or centrifugal action, or be squeezed out under pressure. Additives may be included to bring special properties like anti-oxidants, rust and corrosion inhibitors, anti-wear and extreme pressure additives, solid lubricants.

Greases are used to keep the lubricant in place in the lubricated organs or mechanisms. The advantages of greases are the reduction of the construction and maintenance costs, the simplicity of the sealing systems, and the possibility for life lubrication.

One of the drawbacks of greases versus liquid lubricants is that they do not easily remove heat and cannot be filtered. So greases limit the operating speed of some mechanisms.

Due to the variety of base oils and thickeners, there is a wide variety of greases. The selection of the liquid lubricant and the thickener depends on the properties required. The low temperature properties are governed by the liquid lubricant characteristics, mainly its flow properties at low temperature. The high temperature properties are linked to the type of thickener and to the heat stability of the liquid lubricant.

Greases can be formulated to meet environmental acceptability requirements (toxicity and biodegradability).

The purpose of this document is to provide guidance to suppliers and end users of greases and to manufacturers of grease-lubricated equipment.

ITIH STANDARD PREVIEW  
(standards.iteh.ai)

ISO 12924:2023

<https://standards.iteh.ai/catalog/standards/sist/53f3e979-1e27-4e8d-8d5b-156a0a99e251/iso-12924-2023>



# Lubricants, industrial oils and related products (Class L) — Family X (Greases) — Specifications

## 1 Scope

This document establishes the specifications relative to family X (greases) for lubricants, industrial oils and related products of Class L (see ISO 6743-9). Those greases are mainly used for the lubrication of anti-friction bearings fitted on machines, vehicles, etc.

This document is written in a general form so that its application can accommodate various climatic conditions throughout the world. It also stipulates the requirements for the lubricating grease at the time of the delivery.

NOTE 1 This document is intended to be read in conjunction with ISO 6743-9.

NOTE 2 Greases for gear applications are specified in ISO 12925-3.

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 2137, *Petroleum products and lubricants — Determination of cone penetration of lubricating greases and petrolatum*

ISO 4259-2, *Petroleum and related products — Precision of measurement methods and results — Part 2: Interpretation and application of precision data in relation to methods of test*

ISO 6341, *Water quality — Determination of the inhibition of the mobility of *Daphnia magna* Straus (Cladocera, Crustacea) — Acute toxicity test*

ISO 6743-9, *Lubricants, industrial oils and related products (class L) — Classification — Part 9: Family X (Greases)*

ISO 7120, *Petroleum products and lubricants — Petroleum oils and other fluids — Determination of rust-preventing characteristics in the presence of water*

ISO 7346-1, *Water quality — Determination of the acute lethal toxicity of substances to a freshwater fish [*Brachydanio rerio* Hamilton-Buchanan (Teleostei, Cyprinidae)] — Part 1: Static method*

ISO 8692, *Water quality — Fresh water algal growth inhibition test with unicellular green algae*

ISO 9439, *Water quality — Evaluation of ultimate aerobic biodegradability of organic compounds in aqueous medium — Carbon dioxide evolution test*

ISO 10253, *Water quality — Marine algal growth inhibition test with *Skeletonema* sp. and *Phaeodactylum tricornerutum**

ISO 11007-1, *Petroleum products and lubricants — Determination of rust-prevention characteristics of lubricating greases — Part 1: Dynamic wet conditions*

ISO 11009, *Petroleum products and lubricants — Determination of water washout characteristics of lubricating greases*

## ISO 12924:2023(E)

ISO 13737, *Petroleum products and lubricants — Determination of low-temperature cone penetration of lubricating greases*

ISO 14593, *Water quality — Evaluation of ultimate aerobic biodegradability of organic compounds in aqueous medium — Method by analysis of inorganic carbon in sealed vessels (CO<sub>2</sub> headspace test)*

ISO 14669, *Water quality — Determination of acute lethal toxicity to marine copepods (Copepoda, Crustacea)*

ISO 23572, *Petroleum products — Lubricating greases — Sampling of greases*

EN 16807, *Liquid petroleum products - Bio-lubricants - Criteria and requirements of bio-lubricants and bio-based lubricants*

EN 17181, *Lubricants - Determination of aerobic biological degradation of fully formulated lubricants in an aqueous solution - Test method based on CO<sub>2</sub>-production*

ASTM D6866, *Standard Test Method for Determining the Biobased Content of Solid, Liquid and Gaseous Samples using Radiocarbon Analysis*

ASTM D1478, *Standard Test Method for Low-Temperature Torque of Ball Bearing Grease*

DIN 51805-2, *Testing of lubricants - Determination of flow pressure of lubricating greases according to Kesternich method – Part 2: Automatic method*

DIN 51813, *Testing of lubricants - Determination of the content of foreign solid matters in lubricating greases - Particle sizes above 25 µm*

DIN 51819-2, *Testing of lubricants - Mechanical-dynamic testing in the roller bearing test apparatus FE8 - Part 2: Test method for lubricating greases - applied test bearing: oblique ball bearing or tapered roller bearing*

DIN 51821-1, *Testing of lubricants - Test using the FAG roller bearing grease testing apparatus FE9 – Part 1: General working principles*

DIN 51821-2, *Testing of lubricants - Test using the FAG roller bearing grease testing apparatus FE9 – Part 2: Test method*

NF T60-629, *Petroleum products and lubricants - Low temperature torque of ball bearing greases*

### 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

#### 3.1

##### **upper operating temperature**

highest operating temperature at which a grease is able to continuously lubricate a bearing during sufficient time without failure

#### 3.2

##### **lower operating temperature**

lowest operating temperature at which a grease can operate in a mechanism without failure

Note 1 to entry: The lowest operating temperature can be expressed in the following ways:

- temperature at which the pressure in dispensing pipes remains acceptable to allow flow of grease;



- temperature at which the resisting torque due to grease hardening remains acceptable to allow a bearing to rotate;
- temperature at which a grease keeps enough plasticity to avoid mechanical blocking of mechanisms.

## 4 Sampling

Sampling of bearing greases for the purpose of this document, unless otherwise specified, shall be carried out in accordance with the pertinent procedure described in ISO 23572. The sample shall be evaluated on a representative portion. Any drum, barrel, tanker compartment or any type of container delivered to the end user may be sampled and analysed at the discretion of the purchaser.

## 5 Requirements for greases

### 5.1 General requirements

The designation of greases shall be in accordance with ISO 6743-9, using the following manner:

**ISO - L - X - symbol 1 - symbol 2 - symbol 3 - symbol 4 - NLGI consistency number**

where

- symbol 1 is a measurement of the lower operating temperature, symbols A to E;
- symbol 2 is a measurement of the upper operating temperature, symbols A to G;
- symbol 3 is a measurement of the water contamination and anti-rust protection, symbols A to I;
- symbol 4 is a measurement of the ability to lubricate under high loads, symbol A or B;
- NLGI (National Lubricating Grease Institute) consistency number is defined in ISO 6743-9 through an evaluation of the penetration in accordance with ISO 2137.

The designation can be completed in the following manner, adding the suffix:

- "EA" for environmentally acceptable greases.

The requirements and test methods specified in [Table 1](#) to Table 7 shall be followed in order to determine the value of each symbol used in the classification system.

Most of the test methods specified contain a precision statement. In cases of dispute, if the conditions of ISO 4259 (all parts) can be met with the relevant test method, the procedure described in ISO 4259-2 shall apply.

NOTE 1 Greases having the same classification according to ISO 6743-9 and the same specification according to this document are not necessarily compatible with each other. Blending of non-compatible greases can lead to equipment failure. Before changing from one grease to another in an equipment, it is preferable to consult the grease suppliers.

NOTE 2 In the classification according to ISO 6743-9, a grease cannot have more than one symbol. This symbol is expected to correspond to the most severe conditions of temperature, water contamination and load in which the grease can be used.

### 5.2 Symbol 1 — Lower operating temperature

The lower operating temperature shall be determined by the following three criteria (see [Table 1](#)):

- the starting and the running torque, in accordance with ASTM D1478 or NF T60-629;
- the flow pressure, in accordance with DIN 51805-2;

- the low temperature penetrability, in accordance with ISO 13737.

Following the criterion selected, the "symbol 1" is completed by a suffix letter between brackets:

- (L) when using the starting/running torque;
- (F) when using the flow pressure;
- (P) when using the low temperature penetrability.

**Table 1 — Lower operating temperature — Symbol 1**

Lower operating temperature °C	Low temperature torque			Flow pressure hPa		Penetrability 1/10 mm	
		Starting torque mN·m	Running torque mN·m	Symbol 1	Value	Symbol 1	Value
	Symbol 1	Value	Value	Symbol 1	Value	Symbol 1	Value
0	A(L)	≤1 000	≤100	A(F)	≤1 400	A(P)	≥140
-20	B(L)			B(F)		B(P)	≥120
-30	C(L)			C(F)		C(P)	≥120
-40	D(L)			D(F)		D(P)	≥100
< -40	E(L)			E(F)		E(P)	≥100
<b>Test method</b>	ASTM D 1478 or NF T60-629			DIN 51805-2		ISO 13737	

### 5.3 Symbol 2 — Upper operating temperature

The upper operating temperature shall be determined using DIN 51821-1 and DIN 51821-2 (see [Table 2](#)).

For greases with an upper operating temperature above 120 °C, the  $F_{50}$  bearing life shall be above 100 h at the considered upper operating temperature.

For greases with base oil kinematic viscosities above 300 mm<sup>2</sup>/s at 40 °C, the rotating speed of 6 000 min<sup>-1</sup> (628,32 rad/s) is considered too high. The FAG FE 9 machine, as described in DIN 51821-1, allows for an alternative rotating speed of 3 000 min<sup>-1</sup> (314,16 rad/s). If the latter speed is used to assess the upper operating temperature of a grease, the "symbol 2" shall be supplemented by the suffix letter S between brackets: (S).

**Table 2 — Upper operating temperature — Symbol 2**

Upper operating temperature °C	Symbol 2	Bearing life h
90	B	No requirement
120	C	$F_{50} > 100$ h at the upper operating temperature
140	D	
160	E	
180	F	
>180	G	
<b>Test methods</b>	-	DIN 51821-1 and DIN 51821-2; test with the FAG FE9 grease testing apparatus, procedure B/1500/6000 or B/1500/3000 for greases with base oil kinematic viscosities above 300 mm <sup>2</sup> /s at 40 °C <sup>a</sup> .

<sup>a</sup> Test results from the comparable tests with the A configuration may also be accepted.