
**Titanium and titanium alloys — Plate,
sheet and strip — Technical delivery
conditions**

*Titane et alliages de titane — Tôle, bande et tôle épaisse —
Conditions techniques de livraison*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 7209:2023](https://standards.iteh.ai/catalog/standards/sist/70702bf4-26fe-4ac5-ae56-d17eff524e22/iso-7209-2023)

<https://standards.iteh.ai/catalog/standards/sist/70702bf4-26fe-4ac5-ae56-d17eff524e22/iso-7209-2023>



iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 7209:2023

<https://standards.iteh.ai/catalog/standards/sist/70702bf4-26fe-4ac5-ae56-d17eff524e22/iso-7209-2023>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2023

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword.....	iv
Introduction.....	v
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	1
4 Information to be supplied by the purchaser.....	2
4.1 General information.....	2
4.2 Options.....	2
5 Manufacturing.....	3
6 Requirements.....	3
6.1 General.....	3
6.2 Chemical composition.....	3
6.3 Tensile properties.....	6
6.4 Bend test.....	7
6.5 Dimensional tolerance.....	8
6.5.1 Tolerance of thickness.....	8
6.5.2 Tolerance of width.....	10
6.5.3 Tolerance of length.....	11
6.5.4 Tolerance of flatness.....	12
6.5.5 Tolerance of straightness.....	13
6.6 Surface conditions, imperfections and defects.....	13
6.6.1 General.....	13
6.6.2 Non-destructive inspection.....	14
7 Inspection.....	14
7.1 Types of inspection and inspection documents.....	14
7.2 Specific inspection.....	15
7.2.1 General.....	15
7.2.2 Samples and test pieces for chemical composition and mechanical testing for product analysis.....	15
8 Rounding-off procedure.....	16
9 Reference test and analysis.....	16
10 Rejection.....	16
11 Marking.....	16
11.1 General.....	16
11.2 Products marking.....	16
12 Packaging.....	17
13 Mill product certificate.....	17
14 Certification.....	17
Bibliography.....	18

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 79, *Light metals and their alloys*, Subcommittee SC 11, *Titanium*.

ISO 7209:2023

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

This document was developed in response to worldwide demand for stabilizing the quality assurance for titanium and titanium alloys by common regulations worldwide.

Determining condition concerning the technical delivery conditions for plate, sheet and strip of titanium and titanium alloys, such as chemical composition, mechanical properties and dimensional tolerance, is extremely important to promote commerce of titanium and titanium alloys products in the global market.

The International Organization for Standardization (ISO) draws attention to the fact that it is claimed that compliance with this document may involve the use of patents concerning titanium alloys given in [Table 1](#), [Table 2](#) and [Table 3](#).

ISO takes no position concerning the evidence, validity and scope of this patent right.

The holder of this patent right has assured ISO that he/she is willing to negotiate licences under reasonable and non-discriminatory terms and conditions with applicants throughout the world. In this respect, the statement of the holder of this patent right is registered with ISO. Information may be obtained from the patent database available at www.iso.org/patents.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights other than those in the patent database. ISO shall not be held responsible for identifying any or all such patent rights.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 7209:2023](#)

<https://standards.iteh.ai/catalog/standards/sist/70702bf4-26fe-4ac5-ae56-d17eff524e22/iso-7209-2023>

Titanium and titanium alloys — Plate, sheet and strip — Technical delivery conditions

1 Scope

This document specifies requirements for the manufacture and technical delivery conditions of plate, sheet and strip made from titanium and titanium alloys.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 377, *Steel and steel products — Location and preparation of samples and test pieces for mechanical testing*

ISO 6892-1:2019, *Metallic materials — Tensile testing — Part 1: Method of test at room temperature*

ISO 7438:2020, *Metallic materials — Bend test*

ISO 10474:2013, *Steel and steel products — Inspection documents*

ISO 11484, *Steel products — Employer's qualification system for non-destructive testing (NDT) personnel*

ISO 28401, *Light metals and their alloys — Titanium and titanium alloys — Classification and terminology*

ASTM E8/E8M, *Standard Test Methods for Tension Testing of Metallic Materials*

ASTM E29, *Practice for Using Significant Digits in test Data to Determine Conformance with Specifications*

ASTM E539, *Standard Test Method for Analysis of Titanium Alloys by Wavelength Dispersive X-Ray Fluorescence Spectrometry*

ASTM E1409, *Test method for determination of oxygen and nitrogen in titanium and titanium alloys by the inert gas fusion technique*

ASTM E1447, *Test method for determination of hydrogen in titanium and titanium alloys by the inert gas fusion thermal conductivity/ Infrared detection method*

ASTM E1941, *Standard Test method for determination of Carbon in Refractory and Reactive Metals and Their Alloys by Combustion Analysis*

ASTM E2371, *Standard Test method for Analysis of Titanium and Titanium alloys by Direct Current Plasma and Inductively Coupled Plasma Atomic Emission Spectrometry (Performance-Based Test Methodology)*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 28401 and the following apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

**3.1
plate**

flat-rolled product of rectangular cross-section with uniform thickness over 5 mm, supplied in straight lengths (i.e. flat) usually with sheared, sawn or flame-cut/plasma-cut edges or water jet cutting

Note 1 to entry: The thickness does not exceed one-tenth of the width.

**3.2
sheet**

flat-rolled product of rectangular cross-section with uniform thickness over 0,20 mm and up to and including 5 mm inclusive, supplied in straight lengths (i.e. flat) usually with sheared or sawn edges or water jet cutting

Note 1 to entry: The thickness does not exceed one-tenth of the width.

**3.3
strip**

flat-rolled product of rectangular cross-section with uniform thickness over 0,20 mm, supplied in coils usually with slit edges

Note 1 to entry: The thickness does not exceed one-tenth of the width.

Note 2 to entry: In some English-speaking countries, "strip" is called "coiled sheet".

4 Information to be supplied by the purchaser

4.1 General information

The purchase order shall include the following information:

- a) quantity (e.g. total mass or total length); [ISO 7209:2023](https://standards.iteh.ai/catalog/standards/sist/70702bf4-26fe-4ac5-ae56-d17eff524e22/iso-7209-2023)
- b) designation; <https://standards.iteh.ai/catalog/standards/sist/70702bf4-26fe-4ac5-ae56-d17eff524e22/iso-7209-2023>
- c) dimensions;
- d) packaging;
- e) inspection (including the type of test piece subjected to tensile testing);
- f) mill product certificate;
- g) certification (document issued and/or validated by an independent third party that assures that a product meets specified requirements such as a purchase order).

4.2 Options

A number of options are specified in this document and listed below. If the purchaser does not indicate a wish to implement any of these options at the time of enquiry and order, the plate or sheet or strip shall be supplied in accordance with the basic specification.

- a) restrictive chemistry (see [6.2](#));
- b) product analysis (see [6.2](#));
- c) special mechanical properties (see [6.3](#));
- d) special tolerance (see [6.5](#));
- e) method of manufacture and finish (see [Clause 5](#) and [6.6](#)).

5 Manufacturing

The plate, sheet and strip shall be manufactured by hot-working or hot-rolling of ingot or intermediate product followed by appropriate cold-rolling, if necessary, and surface conditioning and heat treatment. The plate, sheet and strip shall be supplied as solid wrought product with uniform cross-section in straight shape or in coiled form.

6 Requirements

6.1 General

When supplied in the delivery condition indicated in [4.1](#) and inspected in accordance with [Clause 7](#), the plate, sheet and strip shall conform to the requirements of this document.

6.2 Chemical composition

The plate, sheet and strip of titanium and titanium alloys shall conform to the chemical requirements prescribed in [Table 1](#).

The elements listed in [Table 1](#) are either intentional alloy additions or elements that are inherent to the manufacture of titanium sponge, ingot or mill product.

The content of any element intentionally added to the formulation of heat shall be reported.

Other elements are those not specified in the relevant designated material such as Cr and Mo of Ti-0,18Pd and those not originally specified in the [Table 1](#) such as Co and Hf. Generally, other elements include aluminium, vanadium, tin, molybdenum, chromium, manganese, zirconium, nickel, copper, silicon, cobalt, tungsten, hafnium and yttrium except for alloying elements contained in the designation. The element which is taken as the other element shall be subjected to the agreement between the purchaser and the manufacturer, and shall be noted in the purchase order.

Other elements should not be reported unless the content is greater than 0,1 % for each, or 0,4 % for total. The content of yttrium should not be reported unless the content is greater than 0,005 % for each.

When agreed upon between the manufacturer and the purchaser and specified in the purchase order, other specific residual elements not listed in [Table 1](#) may be added and their content shall be reported.

The chemical analysis shall be conducted by the standard techniques normally used by the manufacturer and the purchaser. In case of disagreement, the test methods defined in ASTM E2371 or ASTM E539 shall be used as the referee method except for carbon, oxygen, and hydrogen, which are not covered in these standards. The test methods defined in ISO 22960, ISO 22961 or ISO 22962 may be used as the referee method for iron instead of ASTM E2371 or ASTM E539. The test method defined in ASTM E1409 shall be used as a referee method for oxygen and nitrogen, and ISO 22963 may be used as a referee method for oxygen. The test method defined in ASTM E1447 shall be used as a referee method for hydrogen and the test method defined in ASTM E1941 shall be used as a referee method for carbon.

Table 1 — Chemical composition

Chemical composition in % mass fraction

Designation	C max	O max	N max	H max	Fe max	Al	V	Pd	Ru	Ni	Mo	Cr	Co	Sn	Other elements max	
															single	total
Ti1	0,08	0,18	0,03	0,015	0,20										0,1	0,4
Ti1H	0,08	0,18	0,03	0,015	0,20										0,1	0,4
Ti2L	0,08	0,20	0,03	0,015	0,25										0,1	0,4
Ti2	0,08	0,25	0,03	0,015	0,30										0,1	0,4
Ti3	0,08	0,35	0,05	0,015	0,30										0,1	0,4
Ti3H	0,08	0,35	0,05	0,015	0,30										0,1	0,4
Ti4	0,08	0,40	0,05	0,015	0,50										0,1	0,4
Ti1-0,18Pd	0,08	0,18	0,03	0,015	0,20			0,12-0,25							0,1	0,4
Ti1H-0,18Pd	0,08	0,18	0,03	0,013	0,20			0,12-0,25							0,1	0,4
Ti2L-0,18Pd	0,08	0,20	0,03	0,015	0,25			0,12-0,25							0,1	0,4
Ti2-0,18Pd	0,08	0,25	0,03	0,015	0,30			0,12-0,25							0,1	0,4
Ti3H-0,018Pd	0,08	0,35	0,05	0,015	0,30			0,12-0,25							0,1	0,4
Ti1-0,06Pd	0,08	0,18	0,03	0,015	0,20			0,04-0,08							0,1	0,4
Ti1H-0,06Pd	0,08	0,18	0,03	0,013	0,20			0,04-0,08							0,1	0,4
Ti2L-0,06Pd	0,08	0,20	0,03	0,015	0,25			0,04-0,08							0,1	0,4
Ti2-0,06Pd	0,08	0,25	0,03	0,015	0,30			0,04-0,08							0,1	0,4
Ti2-0,75Ni-0,3Mo	0,08	0,25	0,03	0,015	0,30					0,6-0,9	0,2-0,4				0,1	0,4
Ti1L-0,5N-0,05Ru	0,08	0,10	0,03	0,015	0,20				0,04-0,06	0,4-0,6					0,1	0,4

Table 1 (continued)

Designation	C max	O max	N max	H max	Fe max	Al	V	Pd	Ru	Ni	Mo	Cr	Co	Sn	Other elements max	
															single	total
Ti2L-0,5Ni-0,05Ru	0,08	0,15	0,03	0,015	0,30				0,04-0,06	0,4-0,6					0,1	0,4
Ti2-0,5Ni-0,05Ru	0,08	0,25	0,05	0,015	0,30				0,04-0,06	0,4-0,6					0,1	0,4
Ti2-0,5Co-0,06Pd	0,08	0,25	0,03	0,015	0,30			0,04-0,08					0,2-0,8		0,1	0,4
Ti3-0,5Co-0,06Pd	0,08	0,35	0,05	0,015	0,30			0,04-0,08					0,2-0,8		0,1	0,4
Ti2-0,45Ni-0,15Cr-0,03Ru-0,015Pd	0,08	0,25	0,03	0,015	0,30			0,01-0,02	0,02-0,04	0,35-0,55		0,1-0,2			0,1	0,4
Ti3-0,45Ni-0,15Cr-0,03Ru-0,015Pd	0,08	0,35	0,05	0,015	0,30			0,01-0,02	0,02-0,04	0,35-0,55		0,1-0,2			0,1	0,4
Ti-5Al-2,5Sn	0,08	0,20	0,03	0,015	0,50	4,0-6,0								2,0-3,0	0,1	0,4
Ti-1,5Al	0,08	0,25	0,03	0,015	0,30	1,0-2,0									0,1	0,4
Ti-3Al-2,5V	0,08	0,15	0,03	0,015	0,25	2,5-3,5	2,0-3,0								0,1	0,4
Ti-6Al-4V	0,08	0,20	0,05	0,015	0,40	5,5-6,75	3,5-4,5								0,1	0,4
Ti-6Al-4VELI	0,08	0,13	0,03	0,0125	0,25	5,5-6,5	3,5-4,5								0,1	0,4
Ti-22V-4Al	0,10	0,25	0,05	0,015	1,00	3,50-4,50	20,0-23,0								0,1	0,4