



Designation: **C535—09 C535 – 12**

## Standard Test Method for Resistance to Degradation of Large-Size Coarse Aggregate by Abrasion and Impact in the Los Angeles Machine<sup>1</sup>

This standard is issued under the fixed designation C535; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

### 1. Scope\*

1.1 This test method covers testing sizes of coarse aggregate larger than 19 mm ( $\frac{3}{4}$  in.) for resistance to degradation using the Los Angeles testing machine (**Note 1**).

NOTE 1—A procedure for testing coarse aggregate smaller than 37.5 mm ( $1\frac{1}{2}$  in.) is covered in Test Method **C131**.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

1.3 The values stated in SI units are to be regarded as the standard. The inch-pound values given in parentheses are for information only.

### 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

**C125 Terminology Relating to Concrete and Concrete Aggregates**

**C131 Test Method for Resistance to Degradation of Small-Size Coarse Aggregate by Abrasion and Impact in the Los Angeles Machine**

**C136 Test Method for Sieve Analysis of Fine and Coarse Aggregates**

**C670 Practice for Preparing Precision and Bias Statements for Test Methods for Construction Materials**

**C702 Practice for Reducing Samples of Aggregate to Testing Size**

**D75 Practice for Sampling Aggregates**

**E11 Specification for Woven Wire Test Sieve Cloth and Test Sieves**

### 3. Terminology

3.1 For definitions of terms used in this test method, refer to Terminology **C125**.

### 4. Summary of Test Method

4.1 This test is a measure of degradation of mineral aggregates of standard gradings resulting from a combination of actions including abrasion or attrition, impact, and grinding in a rotating steel drum containing 12 steel spheres. As the drum rotates, a shelf plate picks up the sample and the steel spheres, carrying them around until they are dropped to the opposite side of the drum, creating an impact-crushing effect. The contents then roll within the drum with an abrading and grinding action until the shelf plate picks up the sample and the steel spheres, and the cycle is repeated. After the prescribed number of revolutions, the contents are removed from the drum and the aggregate portion is sieved to measure the degradation as percent loss.

### 5. Significance and Use

5.1 The test has been widely used as an indicator of the relative quality or competence of various sources of aggregate having similar mineral compositions. The results do not automatically permit valid comparisons to be made between sources distinctly

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee **C09** on Concrete and Concrete Aggregates and is the direct responsibility of Subcommittee **C09.20** on Normal Weight Aggregates.

Current edition approved July 1, 2009; Dec. 15, 2012. Published August 2009; January 2013. Originally approved in 1964. Last previous edition approved in 2003; 2009 as **C535—03**; **C535—09**.<sup>1</sup>—DOI: 10.1520/C0535-09; 10.1520/C0535-12.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

\*A Summary of Changes section appears at the end of this standard

different in origin, composition, or structure. Assign specification limits with extreme care in consideration of available aggregate types and their performance history in specific end uses.

## 6. Apparatus

6.1 *The Los Angeles Machine* shall conform to the requirements of Test Method **C131**.

6.1.1 The operation and maintenance of the machine shall be as prescribed in Test Method **C131**.

6.2 *Sieves*, conforming to Specification **E11**.

6.3 *Balance*—A balance or scale accurate within 0.1 % of test load over the range required for this test

6.4 *Charge*—The charge (**Note 2**) shall consist of 12 steel spheres averaging approximately 47 mm ( $1\frac{27}{32}$  in.) in diameter, each having a mass between 390 and 445 g, and having a total mass of  $5000 \pm 25$  g.

NOTE 2—Steel ball bearings 46.0 mm ( $1\frac{13}{16}$  in.) and 47.6 mm ( $1\frac{7}{8}$  in.) in diameter, having a mass approximately 400 and 440 g each, respectively, are readily available. Steel spheres 46.8 mm ( $1\frac{27}{32}$  in.) in diameter having a mass approximately 420 g may also be obtainable. The charge may consist of a mixture of these sizes conforming to the total mass tolerance of **6.4**.

## 7. Sampling

7.1 Obtain the field sample in accordance with Practice **D75** and reduce to an adequate sample size in accordance with Practice **C702**.

## 8. Test Sample Preparation

8.1 Wash the reduced sample and oven dry at  $110 \pm 5^\circ\text{C}$  ( $230 \pm 9^\circ\text{F}$ ) to substantially constant mass, separate into individual size fractions, and recombine to the grading of **Table 1** most nearly corresponding to the range of sizes in the aggregate as furnished for the work. Record the mass of the sample prior to test to the nearest 1 g.

## 9. Procedure

9.1 Place the test sample and charge in the Los Angeles testing machine and rotate the machine at 30 to 33 r/min for 1000 revolutions (**Note 3**). After the prescribed number of revolutions, discharge the material from the machine and make a preliminary separation of the sample on a sieve coarser than the 1.70-mm (No. 12) sieve. Sieve the finer portion on a 1.70-mm sieve in a manner conforming to Test Method **C136**. Wash the material coarser than the 1.70-mm sieve and oven dry at  $110 \pm 5^\circ\text{C}$  ( $230 \pm 9^\circ\text{F}$ ) to substantially constant mass, and determine the mass to the nearest 1 g.

9.1.1 If the aggregate is essentially free of adherent coatings and dust, the requirement for washing after the test is optional. However, in the case of referee testing, the washing procedure shall be performed. Elimination of washing after test will seldom reduce the measured loss by more than about 0.2 % of the original sample mass.

NOTE 3—Valuable information concerning the uniformity of the sample under test may be obtained by determining the loss after 200 revolutions. This loss should be determined by dry sieving the material on the 1.70-mm (No. 12) sieve without washing. The ratio of the loss after 200 revolutions to the loss after 1000 revolutions should not greatly exceed 0.20 for material of uniform hardness. When this determination is made, take care to avoid losing any part of the sample; return the entire sample, including the dust of fracture, to the testing machine for the final 800 revolutions required to complete the test.

## 10. Calculation

10.1 Calculate the loss (the difference between the original mass and the final mass of the test sample) as a percentage of the original mass of the test sample (**Note 4**).

NOTE 4—The percent loss determined by this method has no known consistent relationship to the percent loss for the same material when tested by Test Method **C131**.

## 11. Report

11.1 Report the following information:

11.2 Identification of the aggregate as to source, type, and nominal size, and

**TABLE 1 Gradings of Test Samples**

Sieve Size, mm (in.) (Square Openings)		Mass of Indicated Sizes, g		
Passing	Retained on	Grading		
		1	2	3
75 (3)	63 ( $2\frac{1}{2}$ )	$2\,500 \pm 50$	...	...
63 ( $2\frac{1}{2}$ )	50 (2)	$2\,500 \pm 50$	...	...
50 (2)	37.5 ( $1\frac{1}{2}$ )	$5\,000 \pm 50$	$5\,000 \pm 50$	...
37.5 ( $1\frac{1}{2}$ )	25.0 (1)	...	$5\,000 \pm 25$	$5\,000 \pm 25$
25.0 (1)	19.0 ( $\frac{3}{4}$ )	...	...	$5\,000 \pm 25$
	Total	$10\,000 \pm 100$	$10\,000 \pm 75$	$10\,000 \pm 50$