

ISO/FDIS 7681:2023(E)

ISO TC 45/SC 3/WG 2

~~Date: 2023-11-28~~

Secretariat: AFNOR

Natural rubber field latex — Determination of dry rubber content

Latex de plantation de caoutchouc naturel — Détermination de la teneur en caoutchouc sec

First edition

Date: 2023-12-05

iTeh Standards
(<https://standards.itih.ai>)
Document Preview

[ISO/FDIS 7681](https://standards.itih.ai/catalog/standards/sist/20e5bc1e-989d-4913-8a04-bde4ef06efbc/iso-fdis-7681)

<https://standards.itih.ai/catalog/standards/sist/20e5bc1e-989d-4913-8a04-bde4ef06efbc/iso-fdis-7681>

© ISO 2023

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO Copyright Office
CP 401 • CH-1214 Vernier, Geneva
Phone: + 41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org
Published in Switzerland.

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[ISO/FDIS 7681](#)

<https://standards.iteh.ai/catalog/standards/sist/20e5bc1e-989d-4913-8a04-bde4ef06efbc/iso-fdis-7681>

Contents

Foreword.....	4
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	2
5 Apparatus	2
6 Reagent	2
7 Procedure	2
7.1 General	2
7.2 Method A: Sheeting by hand	2
7.3 Method B: Mechanical sheeting	3
8 Expression of results	3
9 Precision	3
10 Test report	4
Annex A (informative) Precision data	5
Bibliography	7

iTeh Standards
(<https://standards.itih.ai>)
Document Preview

[ISO/FDIS 7681](#)

<https://standards.itih.ai/catalog/standards/sist/20e5bc1e-989d-4913-8a04-bdc4ef06efbc/iso-fdis-7681>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO ~~documents~~document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had **not** received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 3, *Raw materials (including latex) for use in the rubber industry*.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Natural rubber field latex — Determination of dry rubber content

WARNING — Persons using this document should be familiar with normal laboratory practice. This document does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to determine applicable national regulatory conditions prior to use.

1 Scope

This document specifies a method for the determination of the dry rubber content (DRC) of natural rubber field latex. The method is not suitable for latices from natural sources other than *Hevea brasiliensis*, or for compounded latex, vulcanized latex or artificial dispersions of rubber.

2 Normative references

~~The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.~~

~~ISO 1382:2020, Rubber — Vocabulary~~

~~There are no normative references in this document.~~

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

3.1

field latex

natural rubber latex with or without a preservative and prior to concentration or any other processing

Note 1 to entry: The preservative is added to maintain the original state of the latex as it came from the tree.

[SOURCE: ISO 1382:2020, 3.195]

3.2

dry rubber content

DRC

(rubber latex) concentration of rubber in a latex or latex compound, usually expressed as a percentage by mass

[SOURCE: ISO 1382:2020, 3.156]

4 Principle

A sample of natural rubber field latex is coagulated, the non-rubber matter is removed, and the rubber is dried. The dry rubber content is obtained by expressing the mass of dried coagulum as a percentage of the mass of latex.

5 Apparatus

Ordinary laboratory apparatus and the following.

5.1 Dish, preferably made of glass, porcelain, or aluminium approximately 100 mm in diameter and 50 mm deep.

NOTE Dishes made of aluminium are unsuitable for use with latex concentrate containing potassium hydroxide.

5.2 Oven, capable of being maintained at $70\text{ °C} \pm 5\text{ °C}$.

5.3 Desiccator.

5.4 Steam-bath, or water bath.

5.5 Analytical balance, capable of being read to 1 mg.

5.6 Suitable roller, such as stainless-steel roller.

5.7 Thickness gauge.

6 Reagent

Use only reagents of recognized analytical grade and only distilled water or water of equivalent purity.

6.1 Acetic acid, with a volume fraction of 2,0 % v/v.

6.2 Ethanol, with a volume fraction of 95 % v/v.

7 Procedure

7.1 General

Into the dish, weigh by difference, to the nearest 1 mg, approximately 15 g of the sample. Rotate the dish slowly so that the latex covers the bottom of the dish.

Slowly add sufficient acetic acid down the inside edge of the dish, to bring about complete coagulation of the latex. While adding the acid, slowly rotate the dish, and at frequent intervals gently swirl its content.

Allow the content of the dish to stand until the coagulum becomes sufficiently firm for handling.

Place a watch-glass on the dish and heat on a water bath, heated not exceeding 70 °C for 15 min to 30 min. If the serum remains milky, add 5 cm^3 of the ethanol.

When the serum is clear, collect any small particles of coagulated rubber by rubbing with the main bulk. Then proceed according to either method A (7.2) or method B (7.3).

7.2 Method A (~~Sheeting by hand~~)

Press the coagulated rubber to expel water and obtain a uniform sheet not exceeding about 2 mm in thickness by pressing with suitable roller. A suitable method is to place the coagulated rubber carefully