

ISO/TC 229

Secretariat: BSI

Voting begins on:
2023-01-20

Voting terminates on:
2023-03-17

Nanotechnologies — Vocabulary for cellulose nanomaterial

*Nanotechnologies — Vocabulaire pour les nanomatériaux à base de
cellulose*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO/DTS 20477](https://standards.iteh.ai/catalog/standards/sist/f43bfa76-36e5-4efa-94ee-cf556a64f221/iso-dts-20477)

<https://standards.iteh.ai/catalog/standards/sist/f43bfa76-36e5-4efa-94ee-cf556a64f221/iso-dts-20477>

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.



Reference number
ISO/DTS 20477:2023(E)

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO/DTS 20477

<https://standards.iteh.ai/catalog/standards/sist/f43bfa76-36e5-4efa-94ee-cf556a64f221/iso-dts-20477>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2023

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

| | |
|---|-----------|
| Foreword | iv |
| Introduction | v |
| 1 Scope | 1 |
| 2 Normative references | 1 |
| 3 Terms and definitions | 1 |
| 3.1 Core nanotechnology terms related to cellulose nanomaterials..... | 1 |
| 3.2 Prerequisite non-nanotechnology terms related to cellulose nanomaterials..... | 2 |
| 3.3 Terms related specifically to cellulose nanomaterials..... | 3 |
| Annex A (informative) Images of cellulose nanomaterials | 5 |
| Annex B (informative) Cellulose micromaterials | 7 |
| Bibliography | 8 |
| Index | 9 |

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO/DTS 20477](https://standards.iteh.ai/catalog/standards/sist/f43bfa76-36e5-4efa-94ee-cf556a64f221/iso-dts-20477)

<https://standards.iteh.ai/catalog/standards/sist/f43bfa76-36e5-4efa-94ee-cf556a64f221/iso-dts-20477>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 229, *Nanotechnologies*.

This second edition cancels and replaces the first edition (ISO/TS 20477:2017), which has been technically revised.

The main changes are as follows:

- some existing definitions have been revised;
- new terms and definitions have been introduced;
- micrographic images of cellulose nanomaterials have been introduced to illustrate some of the defined terms.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

Cellulose is a polymer produced in nature. In plants, animals, algae and bacteria, cellulose is extruded from terminal enzyme complexes (TC). TCs are made up of many identical subunits, each containing at least one catalytic site from which a single cellulose chain is synthesized. Cellulose chains from a single TC combine to form an elementary fibril. As TCs in plants, animals, algae and bacteria have different numbers and configurations of subunits, the elementary fibrils they produce have different geometries. [1] Whether cellulose nanomaterials are separated by industrial processes or produced directly by organisms, they all contain a common structural component, which is the elementary fibril. This common component, the elementary fibril, provides a way to describe cellulose nanomaterials from all manufacturing methods and cellulose sources.

Cellulose nanomaterials can be manufactured industrially by conversion of wood pulp through chemical, biological or mechanical processes. Bacterium-based cellulose nanomaterials are produced directly by bacteria and can be further acid-hydrolysed to smaller dimensions. Besides trees and bacteria, algae are another potential source of cellulose nanomaterials for industrial applications. Owing to their unique properties and renewable nature, cellulose nanomaterials have developed into platform materials that have application potential in a wide range of products including those that currently utilize petroleum-based ingredients.

At the current stage of development, several terms to describe cellulose nanomaterials coexist and have created confusion among users. The difficulty of measuring sizes in the low micrometre and nanometre scale has given rise to confusion in the classification materials, particularly for the fibrillate materials. Rather than delaying standards development until knowledge accumulated with research advancement and market maturity, there is an opportunity to define a standard vocabulary for cellulose nanomaterials, and for clarity, describe micro-scale cellulose materials, as given in [Annex B](#). Although terms in the ISO/IEC 80004 series were not developed for specific types of nanomaterials such as cellulose nanomaterials, to be consistent with existing ISO/TC 229 hierarchy, this document utilizes terms from the ISO/IEC 80004 series. It is anticipated that as the market for cellulose nanomaterials matures, so too will the standard vocabulary. Beginning to define a standard vocabulary now will facilitate future communication, eliminate confusion, remove trade barriers, and provide policy makers and regulators with a set of consensus-based terms.

Nanotechnologies — Vocabulary for cellulose nanomaterial

1 Scope

This document defines terms and definitions for different types of cellulose nanomaterials including secondary components found in cellulose nanomaterials originating from their manufacturing processes. This document also provides information on cellulose micromaterials in [Annex A](#).

Where necessary, terms from the ISO/IEC 80004 series are included in this document. Terms in this document are applicable to all types of cellulose nanomaterials, regardless of production methods and their origin (plants, animals, algae or bacteria).

2 Normative references

There are no normative references in this document.

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

3.1 Core nanotechnology terms related to cellulose nanomaterials

3.1.1

nanoscale

length range approximately from 1 nm to 100 nm

Note 1 to entry: Properties that are not extrapolations from larger sizes are predominantly exhibited in this length range.

[SOURCE: ISO/TS 80004-1:2015, 2.1]

3.1.2

nanomaterial

material with any external dimension in the *nanoscale* (3.1.1) or having internal structure or surface structure in the nanoscale

Note 1 to entry: This generic term is inclusive of *nano-object* (3.1.3) and *nanostructured material* (3.1.5).

Note 2 to entry: See also definitions of engineered nanomaterial, manufactured nanomaterial, and incidental nanomaterial in ISO/TS 80004-1:2015.

[SOURCE: ISO/TS 80004-1:2015, 2.4, modified — Note 2 to entry has been added.]

3.1.3

nano-object

discrete piece of material with one, two or three external dimensions in the *nanoscale* (3.1.1)

Note 1 to entry: The second and third external dimensions are orthogonal to the first dimension and to each other.

[SOURCE: ISO/TS 80004-1:2015, 2.5]

3.1.4

nanostructure

composition of inter-related constituent parts in which one or more of those parts is a *nanoscale* (3.1.1) region

Note 1 to entry: A region is defined by a boundary representing a discontinuity in properties.

[SOURCE: ISO/TS 80004-1:2015, 2.6]

3.1.5

nanostructured material

material having internal *nanostructure* (3.1.4) or surface nanostructure

Note 1 to entry: This definition does not exclude the possibility for a *nano-object* (3.1.3) to have internal structure or surface structure. If external dimension(s) are in the *nanoscale* (3.1.1), the term nano-object is recommended.

[SOURCE: ISO/TS 80004-1:2015, 2.7]

3.1.6

nanofibre

nano-object (3.1.3) with two similar external dimensions in the *nanoscale* (3.1.1) and the third dimension significantly larger

Note 1 to entry: The largest external dimension is not necessarily in the nanoscale.

Note 2 to entry: Nanofibril and nanofilament are alternative terms for nanofibre.

Note 3 to entry: See Note 1 to entry of nanoparticle in ISO/TS 80004-2:2015.

[SOURCE: ISO/TS 80004-2:2015, 4.5]

3.1.7

nanocrystal

nano-object (3.1.3) with a *crystalline* (3.2.1) structure

[SOURCE: ISO/TS 80004-2:2015, 4.15]

3.2 Prerequisite non-nanotechnology terms related to cellulose nanomaterials

3.2.1

crystalline

having a solid structure with a three-dimensional arrangement of ions, molecules, or atoms with long range order

3.2.2

paracrystalline

having short- and medium-range ordered lattice structure and lacking long-range order in at least one direction; in the intermediate state between *crystalline* (3.2.1) and amorphous

3.2.3

cellulose

linear polymeric chains of β (1 \rightarrow 4) linked D-glucopyranose units

3.2.4

elementary fibril

structure originating from a single terminal enzyme complex and having a configuration of cellulose chains specific to each cellulose-producing plant, animal, algal and bacterial species

3.2.5**hemicellulose**

non-cellulose heteropolysaccharides in organisms, typically containing monomers such as, but not limited to, xylose, glucose, mannose, galactose, arabinose and glucuronic acid

Note 1 to entry: Hemicellulose can be composed of branched polymers.

Note 2 to entry: Hemicellulose is usually extractable with dilute alkaline solutions.

3.3 Terms related specifically to cellulose nanomaterials**3.3.1****cellulose nanomaterial****CNM**

nanocellulose

NC

cellulosic nanomaterial

CNM

material composed predominantly of *cellulose* (3.2.3), with any external dimension in the *nanoscale* (3.1.1), or a material having internal structure or surface structure in the nanoscale, with the internal structure or surface structure composed predominantly of cellulose

Note 1 to entry: Some cellulose nanomaterials can be composed of chemically modified cellulose.

Note 2 to entry: This term is inclusive of *cellulose nano-object* (3.3.2) and *cellulose nanostructured material* (3.3.3).

3.3.2**cellulose nano-object**

nano-object (3.1.3) composed predominantly of *cellulose* (3.2.4)

3.3.3**cellulose nanostructured material**

nanostructured material (3.1.5) of which the internal or surface *nanostructure* (3.1.4) is predominantly composed of *cellulose* (3.2.3)

3.3.4**cellulose nanofibre**

nanofibre (3.1.6) composed predominantly of *cellulose* (3.2.3)

Note 1 to entry: This definition is a description of the morphology and the size of an object. It should not be confused with wood fibres or wood pulp fibres which typically have diameters of tens of micrometres.

3.3.5**cellulose nanocrystal****CNC**

nanocrystal (3.1.7) composed predominantly of *cellulose* (3.2.3) containing predominantly *crystalline* (3.2.1) and *paracrystalline* (3.2.2) regions, with at least one *elementary fibril* (3.2.4), not exhibiting longitudinal splits

Note 1 to entry: The aspect ratio of cellulose nanocrystals is usually smaller than 50 but usually greater than 5, where aspect ratio refers to the ratio of the longest to the shortest dimensions.

Note 2 to entry: Cellulose nanocrystals do not exhibit interparticle entanglement or network-like structures.

Note 3 to entry: Historically cellulose nanocrystals have been called nanocrystalline cellulose (NCC) and whiskers such as cellulose nanowhiskers (CNW); they have also been called spheres, needles or nanowires based on their shape, dimensions and morphology; other names have included cellulose micelles, cellulose crystallites and cellulose microcrystals.

Note 4 to entry: See [Figure A.1](#) for an image of CNC.

3.3.6

cellulose nanofibril

CNF

cellulose (3.2.3) *nanofibre* (3.1.6) composed of at least one *elementary fibril* (3.2.4) that can contain branches a significant fraction of which are in the nanoscale

Note 1 to entry: The dimensions are typically 3 nm to 100 nm in cross-section and typically up to 100 µm in length.

Note 2 to entry: CNF can form entanglements between particles or network-like structure when the distance between CNF fibres is sufficiently close.

Note 3 to entry: Cellulose nanofibril can be attached to or protruding from other objects such as pulp fibres or cellulose microfibrils.

Note 4 to entry: Cellulose nanofibrils from plant sources, produced by mechanical processes, can be accompanied by *hemicellulose* (3.2.5), and in some cases lignin.

Note 5 to entry: Some cellulose nanofibrils can have functional groups on their surface as a result of the manufacturing process.

Note 6 to entry: The terms nanofibrillated cellulose (NFC), nanofibrillar cellulose (NFC), and cellulose nanofibre (3.3.4) have been used interchangeably with cellulose nanofibril. The terms microfibrillated cellulose (MFC), microfibrillar cellulose (MFC), cellulose microfibril (CMF) have also incorrectly been used to describe cellulose nanofibrils. To provide clarity, cellulose micromaterials are described in Annex B.

Note 7 to entry: The term cellulose nanoribbon has been used to describe cellulose nanofibrils from bacterial sources.

Note 8 to entry: See Figure A.2 for an image of CNF.

3.3.7

individualized cellulose nanofibril

iCNF

discrete *cellulose nanofibril* (3.3.6) composed of one *elementary fibril* (3.2.4) with ionic functional groups on its surface

Note 1 to entry: See Figure A.3 for an image of iCNF.