



## Standard Specification for Aluminum and Aluminum-Alloy Extruded Bars, Rods, Wire, Profiles, and Tubes (Metric)<sup>1</sup>

This standard is issued under the fixed designation B221M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

### 1. Scope\*

1.1 This specification covers aluminum and aluminum-alloy extruded bars, rods, wires, profiles, and tubes in the aluminum alloys (Note 1) and tempers shown in Table 2.

NOTE 1—Throughout this specification the use of the term *alloy* in the general sense includes aluminum as well as aluminum alloy.

NOTE 2—For rolled or cold-finished bars and rods refer to Specification B211M, for drawn seamless tube used in pressure applications, Specification B210M, for structural pipe and tube, Specification B429/B429M, and for seamless pipe and tube used in pressure applications, Specification B241/B241M.

NOTE 3—Structural pipe and tube produced in accordance with this specification is not intended for fluid-carrying applications involving pressure. Refer to either Specification B210M or B241/B241M, as appropriate, for seamless pipe and tube used in fluid-carrying applications involving pressure.

NOTE 1—Throughout this specification the use of the term *alloy* in the general sense includes aluminum as well as aluminum alloy.

NOTE 2—For rolled or cold-finished bars and rods refer to Specification B211M, for drawn seamless tube used in pressure applications, Specification B210M, for structural pipe and tube, Specification B429/B429M, and for seamless pipe and tube used in pressure applications, Specification B241/B241M.

NOTE 3—Structural pipe and tube produced in accordance with this specification is not intended for fluid-carrying applications involving pressure. Refer to either Specification B210M or B241/B241M, as appropriate, for seamless pipe and tube used in fluid-carrying applications involving pressure.

1.2 Alloy and temper designations are in accordance with ANSI H35.1/H35.1M. The equivalent Unified Numbering System alloy designations are those of Table 1 preceded by A9, for example, A91100 for Aluminum 1100 in accordance with Practice E527.

1.3 For acceptance criteria for inclusion of new aluminum and aluminum alloys in this specification, see Annex A2.

1.4 This specification is the metric counterpart of Specification B221.

1.5 The values stated in SI are to be regarded as standard. No other units of measurement are included in this specification.

<https://standards.iteh.ai/catalog/standards/sist/91e0020e-dcac-4e15-b673-2d87821ecea8/astm-b221m-12a>

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee B07 on Light Metals and Alloys and is the direct responsibility of Subcommittee B07.03 on Aluminum Alloy Wrought Products.

Current edition approved Jan. 15, 2012 Nov. 15, 2012. Published March 2012 January 2013. Originally approved in 1979. Last previous edition approved in 2007 2012 as B221M – 07. B221M – 12. DOI: 10.1520/B0221M-12; 10.1520/B0221M-12A.

\*A Summary of Changes section appears at the end of this standard

**TABLE 1 Chemical Composition Limits<sup>A,B,C</sup>**

NOTE 1—In case of a discrepancy between the values listed in **Table 1** and those listed in the “International Alloy Designations and Chemical Composition Limits for Wrought Aluminum and Wrought Aluminum Alloys”(known as the “Teal Sheets”), the composition limits registered with the Aluminum Association and published in the “Teal Sheets” should be considered the controlling composition. The “Teal Sheets” are available at <http://www.aluminum.org/tealsheets>.

Alloy	Silicon	Iron	Copper	Manganese	Magnesium	Chromium	Zinc	Titanium	Vanadium	Other Elements <sup>D</sup>		Aluminum
										Each	Total <sup>E</sup>	
1060	0.25	0.35	0.05	0.03	0.03	...	0.05	0.03	0.05	0.03	...	99.60 min <sup>F</sup>
1100	0.95 Si + Fe		0.05–0.20	0.05	...	...	0.10	...	...	0.05 <sup>G</sup>	0.15	99.00 min <sup>F</sup>
2014	0.50–1.2	0.7	3.9–5.0	0.40–1.2	0.20–0.8	0.10	0.25	0.15 <sup>H</sup>	...	0.05 <sup>H</sup>	0.15	remainder
2024	0.50	0.50	3.8–4.9	0.30–0.9	1.2–1.8	0.10	0.25	0.15 <sup>H</sup>	...	0.05 <sup>H</sup>	0.15	remainder
2219	0.20	0.30	5.8–6.8	0.20–0.40	0.02	...	0.10	0.02–0.10	0.05–0.15	0.05 <sup>I</sup>	0.15 <sup>I</sup>	remainder
3003	0.6	0.7	0.05–0.20	1.0–1.5	...	...	0.10	...	...	0.05	0.15	remainder
Alclad 3003	...		3003 Clad with 7072 alloy		...	...	...	...	...	...	...	...
3004	0.30	0.7	0.25	1.0–1.5	0.8–1.3	...	0.25	...	...	0.05	0.15	remainder
3102	0.40	0.7	0.10	0.05–0.40	...	...	0.30	0.10	...	0.05	0.15	remainder
5052	0.25	0.40	0.10	0.10	2.2–2.8	0.15–0.35	0.10	...	...	0.05	0.15	remainder
5083	0.40	0.40	0.10	0.40–1.0	4.0–4.9	0.05–0.25	0.25	0.15	...	0.05	0.15	remainder
5086	0.40	0.50	0.10	0.20–0.7	3.5–4.5	0.05–0.25	0.25	0.15	...	0.05	0.15	remainder
5154	0.25	0.40	0.10	0.10	3.1–3.9	0.15–0.35	0.20	0.20	...	0.05	0.15	remainder
5454	0.25	0.40	0.10	0.50–1.0	2.4–3.0	0.05–0.20	0.25	0.20	...	0.05	0.15	remainder
5456	0.25	0.40	0.10	0.50–1.0	4.7–5.5	0.05–0.20	0.25	0.20	...	0.05	0.15	remainder
6005	0.6–0.9	0.35	0.10	0.10	0.40–0.6	0.10	0.10	0.10	...	0.05	0.15	remainder
6005A	0.50–0.9	0.35	0.30	0.50 <sup>J</sup>	0.40–0.7	0.30 <sup>J</sup>	0.20	0.10	...	0.05	0.15	remainder
6013	0.6–1.0	0.50	0.6–1.1	0.20–0.8	0.8–1.2	0.10	0.25	0.10	...	0.05	0.15	remainder
6020 <sup>K</sup>	0.40–0.9	0.50	0.30–0.9	0.35	0.6–1.2	0.15	0.20	0.15	...	0.05	0.15	remainder
6041 <sup>L</sup>	0.50–0.9	0.15–0.7	0.15–0.6	0.05–0.20	0.8–1.2	0.05–0.15	0.25	0.15	...	0.05	0.15	remainder
6042 <sup>M</sup>	0.50–1.2	0.7	0.20–0.6	0.40	0.7–1.2	0.04–0.35	0.25	0.15	...	0.05	0.15	remainder
6060	0.30–0.6	0.10–0.30	0.10	0.10	0.35–0.6	0.5	0.15	0.10	...	0.05	0.15	remainder
6061 <sup>N</sup>	0.40–0.8	0.7	0.15–0.40	0.15	0.8–1.2	0.04–0.35	0.25	0.15	...	0.05	0.15	remainder
6063	0.20–0.6	0.35	0.10	0.10	0.45–0.9	0.10	0.10	0.10	...	0.05	0.15	remainder
6064 <sup>O</sup>	0.40–0.8	0.7	0.15–0.40	0.15	0.8–1.2	0.05–0.14	0.25	0.15	...	0.05	0.15	remainder
6066	0.9–1.8	0.50	0.7–1.2	0.6–1.1	0.8–1.4	0.40	0.25	0.20	...	0.05	0.15	remainder
6070	1.0–1.7	0.50	0.15–0.40	0.40–1.0	0.50–1.2	0.10	0.25	0.15	...	0.05	0.15	remainder
6082	0.7–1.3	0.50	0.10	0.40–1.0	0.6–1.2	0.25	0.20	0.10	...	0.05	0.15	remainder
6105	0.6–1.0	0.35	0.10	0.15	0.45–0.8	0.10	0.10	0.10	...	0.05	0.15	remainder
6162	0.40–0.8	0.50	0.20	0.10	0.7–1.1	0.10	0.25	0.10	...	0.05	0.15	remainder
6262	0.40–0.8	0.7	0.15–0.40	0.15	0.8–1.2	0.04–0.14	0.25	0.15	...	0.05 <sup>P</sup>	0.15 <sup>P</sup>	remainder
6351	0.7–1.3	0.50	0.10	0.40–0.8	0.40–0.8	...	0.20	0.20	...	0.05	0.15	remainder
6360	0.35–0.8	0.10–0.30	0.15	0.02–0.15	0.25–0.45	0.05	0.10	0.10	...	0.05	0.15	remainder
6463	0.20–0.6	0.15	0.20	0.05	0.45–0.9	...	0.05	...	...	0.05	0.15	remainder
6560	0.30–0.7	0.10–0.30	0.05–0.20	0.20	0.20–0.6	0.05	0.15	0.10	...	0.05	0.15	remainder
7005	0.35	0.40	0.10	0.20–0.7	1.0–1.8	0.06–0.20	4.0–5.0	0.01–0.06	...	0.05 <sup>Q</sup>	0.15 <sup>Q</sup>	remainder
7072 <sup>R</sup>	0.7 Si + Fe	0.10	0.10	0.10	0.8–1.3	...	...	...	...	...	...	remainder
7075	0.40	0.50	1.2–2.0	0.30	2.1–2.9	0.18–0.28	5.1–6.1	0.20 <sup>S</sup>	...	0.05 <sup>S</sup>	0.15	remainder
7116	0.15	0.30	0.50–1.1	0.05	0.8–1.4	...	4.2–5.2	0.05	0.05	0.05 <sup>T</sup>	0.15	remainder
7129	0.15	0.30	0.50–0.9	0.10	1.3–2.0	0.10	4.2–5.2	0.05	0.05	0.05 <sup>T</sup>	0.15	remainder
7178	0.40	0.50	1.6–2.4	0.30	2.4–3.1	0.18–0.28	6.3–7.3	0.20	...	0.05	0.15	remainder

<sup>A</sup> Limits are in weight percent maximum unless shown as a range, or stated otherwise.

<sup>B</sup> Analysis shall be made for the elements for which limits are shown in this table.

<sup>C</sup> For the purpose of determining conformance to these limits, an observed value or a calculated value obtained from analysis shall be rounded to the nearest unit in the last right-hand place of the figures used in expressing the specified limit, in accordance with the rounding-off method of Practice E29.

<sup>D</sup> Others includes listed elements for which no specific limit is shown as well as unlisted metallic elements. The producer may analyze samples for trace elements not specified in the specification. However, such analysis is not required and may not cover all metallic Others elements. Should any analysis by the producer or the purchaser establish that an Others element exceeds the limit of Each or that the aggregate of several Others elements exceeds the limit of Total, the material shall be considered nonconforming.

<sup>E</sup> Other Elements—Total shall be the sum of unspecified metallic elements 0.010 % or more, rounded to the second decimal before determining the sum.

<sup>F</sup> The aluminum content shall be calculated by subtracting from 100.00 % the sum of all metallic elements present in amounts of 0.010 % or more each, rounded to the second decimal before determining the sum.

<sup>G</sup> Be 0.0003 max for welding electrode, welding rod, and filler wire.

<sup>H</sup> Upon agreement between the purchaser and the producer or supplier, a Zr + Ti limit of 0.20 % max is permitted. Properties in Specification (**Table 2**) are not based on the Zirconium and Titanium algorithm.

<sup>I</sup> Zirconium, 0.10–0.25 %. The total for other elements does not include zirconium.

<sup>J</sup> Manganese plus chromium shall total 0.12–0.50.

<sup>K</sup> Lead 0.05 % max, Tin 0.9–1.5 %.

<sup>L</sup> Bismuth 0.30–0.9 %, Tin 0.35–1.2 %.

<sup>M</sup> Bismuth 0.20–0.8 % Lead 0.15–0.40 %.

<sup>N</sup> In 1965 the requirements for 6062 were combined with those for 6061 by revising the minimum chromium from “0.15 %” to “0.04 %.” This action cancelled alloy 6062.

<sup>O</sup> Bismuth 0.50–0.7 %, Lead 0.20–0.40 %,

<sup>P</sup> Bismuth and lead shall be 0.40–0.7 % each.

<sup>Q</sup> Zirconium 0.08–0.20 %. The total for other elements does not include zirconium.

<sup>R</sup> Composition of cladding alloy applied during the course of manufacture. Samples from finished tube shall not be required to conform to these limits.

<sup>S</sup> Upon agreement between the purchaser and the producer or supplier, a Zr + Ti limit of 0.25 % max is permitted. Properties in Specification (**Table 2**) are not based on the Zirconium and Titanium algorithm.

<sup>T</sup> Gallium 0.03 % max.

**TABLE 2 Tensile Property Limits<sup>A,B</sup>**

Temper	Specified Section or Wall Thickness, mm		Area, mm <sup>2</sup>		Tensile Strength, MPa		Yield Strength (0.2 % offset), MPa		Elongation, <sup>C</sup> %, min	
	over	incl	over	incl	min	max	min	max	in 50 mm	in 5 x Diameter (5.65 $\sqrt{A}$ )
Aluminum 1060										
O	all	all	all		60	95	15	...	25	22
H112	all	all	all		60	15	15	...	25	22
F <sup>D</sup>	all	all	all		...	...	...	...	...	...
Aluminum 1100										
O	all	all	all		75	105	20	...	25	22
H112	all	all	all		75	...	20	...	25	22
F <sup>D</sup>	all				...	...	...	...	...	...
Alloy 2014										
O	all	all	all		...	205	...	125	12	10
T4	all	all	all		345	...	240	...	12	10
T4510 <sup>E</sup>	}									
T4511 <sup>E</sup>	}									
T42 <sup>F</sup>	all		all		345	...	200	...	12	10
T6	...		...		415	...	365	...	7	6
T6510 <sup>E</sup>	...	12.50	...		440	...	400	...	...	6
T6511 <sup>E</sup>	12.50	18.00	...		470	...	415	...	...	6
	18.00	...	...							
T62 <sup>F</sup>	18.00	...	16 000	20 000	470	...	400	...	...	5
	18.00	18.00	all	...	415	...	365	...	7	6
	18.00	...	...	16 000	415	...	365	...	...	6
	18.00	...	16 000	20 000	415	...	365	...	...	5
F <sup>D</sup>	all	all	...	...	...	...	...	...	...	...
Alloy 2024										
O	all	all	all		240	...	130	12	10	
T3	...	6.30	all		395	...	290	...	12 <sup>G</sup>	...
T3510 <sup>E</sup>	...	6.30	18.00	all	415	...	305	...	12 <sup>G</sup>	10 <sup>G</sup>
T3511 <sup>E</sup>	6.30	18.00	35.00	all	450	...	315	...	...	9
	18.00	35.00	...	...						
	35.00	...	...	16 000	485	...	360 <sup>H</sup>	...	...	9
	35.00	...	16 000	20 000	470	...	330 <sup>I</sup>	...	...	7
T42 <sup>F</sup>	...	18.00	all	...	395	...	260	...	12	10
	18.00	35.00	all	...	395	...	260	...	...	9
	35.00	...	...	16 000	395	...	260	...	...	7
	35.00	...	16 000	20 000	395	...	260	...	...	7
T81	1.20	6.30	all		440	...	385	...	4	
T8510 <sup>E</sup>	1.20	6.30	35.00	all	455	...	400	...	5	4
T8511 <sup>E</sup>	6.30	35.00	...	...	455	...	400	...	...	4
F <sup>D</sup>	all	all	...	...	...	...	...	...	...	...
Alloy 2219										
O	all	all	all		220	...	125	12	10	
T31	...	12.50	12.50	...	290	...	180	...	14	
T3510 <sup>E</sup>	...	12.50	80.00	...	310	...	185	...	...	12
	12.50	80.00	16 000	16 000						
T62 <sup>F</sup>	...	25.00	25.00	...	370	...	250	...	6	5
	25.00	...	16 000	20 000	370	...	250	...	...	5
T81	...	80.00	...	16 000	400	...	290	...	6	5
T8510 <sup>E</sup>	...	80.00	...	16 000	400	...	290	...	...	5
T8511 <sup>E</sup>	...	80.00	...	16 000	400	...	290	...	...	5
F <sup>D</sup>	all	all	...	...	...	...	...	...	...	...
Alloy 3003										
O	all	all	all		95	130	35	...	25	22
H112	all	all	all		95	...	35	...	25	22
F <sup>D</sup>	all	all	all		...	...	...	...	...	...
Alclad Alloy 3003										

TABLE 2 *Continued*

Temper	Specified Section or Wall Thickness, mm				Area, mm <sup>2</sup>		Tensile Strength, MPa		Yield Strength (0.2 % offset), MPa		Elongation, <sup>C</sup> %, min	
	over	incl	over	incl	min	max	min	max	in 50 mm	in 5 x Diameter (5.65 $\sqrt{A}$ )		
O H112	all	all	all	all	90	125	30	... <sup>J</sup>	... <sup>J</sup>	25	... <sup>J</sup>	... <sup>J</sup>
	all	all			90	... <sup>J</sup>	30 <sup>J</sup>	... <sup>J</sup>	25	25	... <sup>J</sup>	... <sup>J</sup>
					Alloy 3004							
O F <sup>D</sup>	all	all	all	all	160	200	60	... <sup>J</sup>	... <sup>J</sup>	... <sup>J</sup>	... <sup>J</sup>	... <sup>J</sup>
	all	all			... <sup>J</sup>	... <sup>J</sup>	... <sup>J</sup>	... <sup>J</sup>	... <sup>J</sup>	... <sup>J</sup>	... <sup>J</sup>	... <sup>J</sup>
					Alloy 3102							
H112 <sup>K</sup>	0.70	1.30	all		75	125	30	... <sup>J</sup>	25	... <sup>J</sup>	... <sup>J</sup>	... <sup>J</sup>
					Alloy 5052							
O	all		all		170	240	70	... <sup>J</sup>	... <sup>J</sup>	... <sup>J</sup>	... <sup>J</sup>	... <sup>J</sup>
					Alloy 5083							
O H111	... <sup>L</sup>	130.00 <sup>L</sup>	... <sup>L</sup>	20 000	270	350	110	... <sup>J</sup>	14	12	10	10
H112	... <sup>L</sup>	130.00 <sup>L</sup>	... <sup>L</sup>	20 000	275	... <sup>J</sup>	165	... <sup>J</sup>	12	12	10	10
F <sup>D</sup>	all	130.00 <sup>L</sup>	... <sup>L</sup>	20 000	270	... <sup>J</sup>	110	... <sup>J</sup>	12	12	10	10
		all			... <sup>J</sup>	... <sup>J</sup>	... <sup>J</sup>	... <sup>J</sup>	... <sup>J</sup>	... <sup>J</sup>	... <sup>J</sup>	... <sup>J</sup>
					Alloy 5086							
O H111	... <sup>L</sup>	130.00 <sup>L</sup>	... <sup>L</sup>	20 000	240	315	95	... <sup>J</sup>	14	12	10	10
H112	... <sup>L</sup>	130.00 <sup>L</sup>	... <sup>L</sup>	20 000	250	... <sup>J</sup>	145	... <sup>J</sup>	12	12	10	10
F <sup>D</sup>	all	130.00 <sup>L</sup>	... <sup>L</sup>	20 000	240	... <sup>J</sup>	95	... <sup>J</sup>	12	12	10	10
		all			... <sup>J</sup>	... <sup>J</sup>	... <sup>J</sup>	... <sup>J</sup>	... <sup>J</sup>	... <sup>J</sup>	... <sup>J</sup>	... <sup>J</sup>
					Alloy 5154							
O H112	all		all		205	285	75	... <sup>J</sup>	... <sup>J</sup>	... <sup>J</sup>	... <sup>J</sup>	... <sup>J</sup>
	all		all		205	... <sup>J</sup>	75	... <sup>J</sup>	... <sup>J</sup>	... <sup>J</sup>	... <sup>J</sup>	... <sup>J</sup>
					Alloy 5454							
O H111	... <sup>L</sup>	130.00 <sup>L</sup>	... <sup>L</sup>	20 000	215	285	85	... <sup>J</sup>	14	12	10	10
H112	... <sup>L</sup>	130.00 <sup>L</sup>	... <sup>L</sup>	20 000	230	... <sup>J</sup>	130	... <sup>J</sup>	12	12	10	10
F <sup>D</sup>	all	130.00 <sup>L</sup>	... <sup>L</sup>	20 000	215	... <sup>J</sup>	85	... <sup>J</sup>	12	12	10	10
		all			... <sup>J</sup>	... <sup>J</sup>	... <sup>J</sup>	... <sup>J</sup>	... <sup>J</sup>	... <sup>J</sup>	... <sup>J</sup>	... <sup>J</sup>
					Alloy 5456							
O H111	... <sup>L</sup>	130.00 <sup>L</sup>	... <sup>L</sup>	20 000	285	365	130	... <sup>J</sup>	14	12	10	10
H112	... <sup>L</sup>	130.00 <sup>L</sup>	... <sup>L</sup>	20 000	290	... <sup>J</sup>	180	... <sup>J</sup>	12	12	10	10
F <sup>D</sup>	all	130.00 <sup>L</sup>	... <sup>L</sup>	20 000	285	... <sup>J</sup>	130	... <sup>J</sup>	12	12	10	10
		all			... <sup>J</sup>	... <sup>J</sup>	... <sup>J</sup>	... <sup>J</sup>	... <sup>J</sup>	... <sup>J</sup>	... <sup>J</sup>	... <sup>J</sup>
					Alloy 6005							
T1	... <sup>L</sup>	12.50	all		170	... <sup>J</sup>	105	... <sup>J</sup>	16	14		
T5	... <sup>L</sup>	3.20	all		260	... <sup>J</sup>	240	... <sup>J</sup>	8	7		
	{ 3.20	25.00	all		260	... <sup>J</sup>	240	... <sup>J</sup>	10	9		

## ASTM B221M-12a

	Alloy 6005A						
T1	... <sup>L</sup>	6.30	all	170			
T5	... <sup>L</sup>	6.30	all	260			
	6.30	25.00	all	260			
T61	... <sup>L</sup>	6.30	all	260			
	6.30	25.00	all	260			
				Alloy 6013			
T6	5.00	12.50	all	340			
	12.50	20.00	all	340			
	20.00	50.00	all	340			
T6511	5.00	12.50	all	340			
	12.50	20.00	all	340			
	20.00	50.00	all	340			
				Alloy 6020			
T6511	80.00	160.00	all	260			
				Alloy 6041			
T6 <sup>M</sup>	10.00	50.00	all	310			
T6511 <sup>M</sup>	10.00	50.00	all	310			
				Alloy 6042			
T5	10.00	12.50	all	260			
	12.50	50.00	all	290			
T551	10.00	12.50	all	260			
	12.50	50.00	all	290			
				Alloy 6060			
T51	... <sup>L</sup>	3.20	all	150			
T61	... <sup>L</sup>	3.20	all	205			
	3.20	25.00	all	205			
				Alloy 6061			
O T1	all	16.00	all	180			
	... <sup>L</sup>	16.00	all	180			

TABLE 2 *Continued*

Temper	Specified Section or Wall Thickness, mm		Area, mm <sup>2</sup>		Tensile Strength, MPa		Yield Strength (0.2 % offset), MPa		Elongation, <sup>C</sup> %, min	
	over	incl	over	incl	min	max	min	max	in 50 mm	in 5 x Diameter (5.65 $\sqrt{A}$ )
T4			all		180	...	110	...	16	14
T4510 <sup>E</sup>	all									
T4511 <sup>E</sup>										
T42 <sup>F</sup>	all				180	...	85	...	16	14
T51	...		16.00	all	240	...	205	...	8	7
T6, T62 <sup>F</sup>	...		6.30	all	260	...	240	...	8	7
T6510 <sup>E</sup>	6.30	...	...	all	260	...	240	...	10	9
T6511 <sup>E</sup>										
F <sup>D</sup>	all		all		...	...	...	...	...	...
					Alloy 6063					
O	all		all		...	130	...	...	18	16
T1	...		12.50	all	115	...	60	...	12	10
	12.50		25.00	all	110	...	55	...	...	10
T4, T42 <sup>F</sup>	...		12.50	all	130	...	70	...	14	12
	12.50		25.00	all	125	...	60	...	...	12
T5	...		12.50	all	150	...	110	...	8	7
	12.50		25.00	all	145	...	105	...	...	7
T52	...		25.00	all	150	205	110	170	8	7
T54	...		3.20	all	225	...	205	...	8	...
	3.20		12.50	all	225	...	205	...	10	...
T6, T62 <sup>K,F</sup>	...		3.20	all	205	...	170	...	8	...
	3.20		25.00	all	205	...	170	...	10	9
T65	...		5.00	all	250	...	230	...	7	...
					Alloy 6064					
T6	5.00		80.00	all	290	...	260	...	10	9
T6511	5.00		80.00	all	290	...	260	...	10	9
					Alloy 6066					
O	all		all		...	200	...	125	16	14
T4	all		all		275	...	170	...	14	12
T4510 <sup>E</sup>										
T4511 <sup>E</sup>	all									
T42 <sup>F</sup>			all		275	...	165	...	14	12
T6	...		all		345	...	290	...	8	7
T6510 <sup>E</sup>	all		all		345	...	310	...	6	5
T6511 <sup>E</sup>										
T62 <sup>F</sup>	all		all		345	...	290	...	8	7
					Alloy 6070					
T6, T62 <sup>F</sup>	...		80.00	...	20 000	330	...	310	...	6
					Alloy 6082					
T6	5.00		20.00	all	310	...	260	...	6	8
T6511	20.00		150.00	all	310	...	260	...	6	8
	150.00		200.00	all	280	...	240	...	8	8
					Alloy 6105					
T1	...		12.5	all	170	...	105	...	16	14
T5	...		3.20	all	250	...	240	...	8	...
	3.20		25.00	all	250	...	240	...	10	9
					Alloy 6162					
T5,	...		25.00	all	255	...	235.	...	7	6
T5510 <sup>E</sup>	all									
T5511 <sup>E</sup>										
T6,	...		6.30	all	260	...	240	...	8	...
T6510 <sup>E</sup>	...		6.30	all	260	...	240	...	10	9
T6511 <sup>E</sup>	all		12.50	all						
					Alloy 6262					

TABLE 2 *Continued*

Temper	Specified Section or Wall Thickness, mm		Area, mm <sup>2</sup>		Tensile Strength, MPa		Yield Strength (0.2 % offset), MPa		Elongation, <sup>C</sup> %, min	
	over	incl	over	incl	min	max	min	max	in 50 mm	in 5 x Diameter (5.65 $\sqrt{A}$ )
T6										
T6510 <sup>E</sup>	all		all		260	...	240	...	10	9
T6511 <sup>E</sup>										
Alloy 6351										
T1	...	12.50	...	13 000	180	...	90	...	15	13
T11	...	20.00	all		180	...	110	...	16	14
T4	...	20.00	all		220	...	130	...	16	14
T5	...	6.30	all		260	...	240	...	8	...
	6.30	25.00	all		260	...	240	...	10	9
T51	3.20	25.00	...	13 000	250	...	230	...	10	7
T54	...	12.50	...	13 000	205	...	140	...	10	9
T6	...	3.20	all		290	...	255	...	8	...
	3.20	20.00	all		290	...	255	...	10	9
Alloy 6360										
T5	...	6.30	all		150	...	110	...	8	...
T6	...	3.20	all		205	...	170	...	8	...
	3.20	6.30	all		205	...	170	...	10	...
Alloy 6463										
T1	...	12.50	...	13 000	115	...	60	...	12	10
T5	...	12.50	...	13 000	150	...	110	...	8	7
T6,T62 <sup>F</sup>	...	3.20	...	13 000	205	...	170	...	8	...
	3.20	12.50	...	13 000	205	...	170	...	10	9
Alloy 6560										
T5	2.50	3.20	all	150	...	110	...	8	...	...
T6	2.50	3.20	all	205	...	170	...	8	...	...
Alloy 7005										
T53	20.00	all		345	...	305	...	10	9	
Alloy 7116										
T5	3.20	12.50	all	330	...	290	...	8	7	
Alloy 7129										
T5, T6	...	12.50	all	380	...	340	...	9	8	
Alloy 7075										
O	all		all		...	275	...	165	10	9
T6	all	6.30	all		540	...	485	...	7	...
T62 <sup>F</sup>		12.50	all		560	...	505	...	7	6
T6510 <sup>E</sup>		70.00	all	13 000	560	...	495	...	...	6
T6511 <sup>E</sup>		70.00	110.00	...	560	...	490	...	...	6
	70.00	110.00 <sup>L</sup>	13 000		485	...	485	...	...	5
T73	110.00	130.00 <sup>L</sup>	...	20 000	540	...	470	...	...	5
T73510 <sup>E</sup>	all	1.60	6.30	13 000	470	...	400	...	7	...
T73511 <sup>E</sup>		6.30	35.00	16 000	485	...	420	...	8	7
	35.00	70.00	...	16 000	475	...	405	...	...	7
	70.00	110.00 <sup>L</sup>	...	13 000	470	...	395	...	...	6
	70.00	110.00 <sup>L</sup>	13 000	20 000	450	...	380	...	...	6
T76	all	1.25	all		500	...	435	...	7	...
T76510 <sup>E</sup>		3.20	6.30	13 000	510	...	440	...	7	...
T76511 <sup>E</sup>		6.30	12.50	13 000	515	...	450	...	7	6
	12.50	25.00	...	13 000	515	...	450	...	...	6
	25.00	50.00	...	13 000	515	...	450	...	...	6
	50.00	75.00	...	13 000	510	...	440	...	...	6
	75.00	100.00	...	13 000	510	...	435	...	...	6
F <sup>D</sup>	all		all		...	...	...	...	...	...
Alloy 7178										
O	all		...	20 000	...	275	...	165	10	9

## 2. Referenced Documents

2.1 The following documents of the issue in effect on the date of material purchase form a part of this specification to the extent referenced herein:

TABLE 2 *Continued*

Temper	Specified Section or Wall Thickness, mm		Area, mm <sup>2</sup>		Tensile Strength, MPa		Yield Strength (0.2 % offset), MPa		Elongation, <sup>C</sup> %, min	
	over	incl	over	incl	min	max	min	max	in 50 mm	in 5 x Diameter (5.65 $\sqrt{A}$ )
T6	...	1.60	all		565	...	525	...	...	...
	1.60	6.30	...	13 000	580	...	525	...	5	...
	6.30	35.00	...	16 000	600	...	540	...	5	4
	35.00	60.00	...	16 000	595	...	530	...	...	4
	35.00	60.00	16 000	20 000	580	...	515	...	...	4
	60.00	80.00	...	20 000	565	...	490	...	...	4
	...	1.60	all		545	...	505	...	...	...
T62 <sup>F</sup>	...	1.60	...	13 000	565	...	510	...	5	...
	1.60	6.30	...	16 000	595	...	530	...	5	4
	6.30	35.00	...	16 000	595	...	530	...	...	4
	35.00	60.00	...	20 000	580	...	515	...	...	4
	35.00	60.00	16 000	20 000	565	...	490	...	...	4
	60.00	80.00	...	20 000	565	...	490	...	...	4
	...	1.60	all		525	...	455	...	7	...
T76	3.20	6.30	...	13 000	525	...	460	...	7	...
T76510 <sup>E</sup>	6.30	12.50	...	13 000	530	...	460	...	...	6
T76511 <sup>E</sup>	12.50	25.00	...	13 000	530	...	460	...	...	6
E <sup>D</sup>	all	all			...	...	...	...	...	...

<sup>A</sup> The basis for establishment of tensile property limits is shown in Annex A1.<sup>B</sup> To determine conformance to this specification, each value shall be rounded to the nearest 1 MPa for strength and the nearest 0.5 % for elongation, in accordance with the rounding-off method of Practice E29.<sup>C</sup> Elongations in 50 mm apply for shapes tested in full section and for sheet-type specimens machined from material up through 12.5 mm in thickness having parallel surfaces. Elongations in 5x diameter (5.65  $\sqrt{A}$ )

), where D and A are diameter and cross-sectional area of the specimen respectively, apply to round test specimens machined from thicknesses over 6.30. See 8.1.1 and 8.1.2 for conditions under which measurements are not required.

<sup>D</sup> No mechanical properties are specified or guaranteed.<sup>E</sup> For stress-relieved tempers (T3510, T3511, T4510, T4511, T5510, T5511, T6510, T6511, T73510, T73511, T76510, T76511, T8510, T8511), characteristics and properties other than those specified may differ somewhat from the corresponding characteristics and properties of material in the basic tempers.<sup>F</sup> Material in the T42 and T62 tempers is not available from the material producers.<sup>G</sup> Minimum elongation for tube, 10 % in 50 mm and 9 % in 5x diameter.<sup>H</sup> Minimum yield strength for tube, 330 MPa.<sup>I</sup> Minimum yield strength for tube 315 MPa.<sup>J</sup> Yield strength is not applicable to tube.<sup>K</sup> Only in tube form.<sup>L</sup> Properties not applicable to extruded tube over 70 mm wall thickness.<sup>M</sup> Tentative—properties subject to revision.

## 2.2 ASTM Standards:<sup>2</sup>

**B210M Specification for Aluminum and Aluminum-Alloy Drawn Seamless Tubes (Metric)**

**B211M Specification for Aluminum and Aluminum-Alloy Rolled or Cold-Finished Bar, Rod, and Wire (Metric)**

**B241/B241M Specification for Aluminum and Aluminum-Alloy Seamless Pipe and Seamless Extruded Tube**

**B429/B429M Specification for Aluminum-Alloy Extruded Structural Pipe and Tube**

**B557M Test Methods for Tension Testing Wrought and Cast Aluminum- and Magnesium-Alloy Products (Metric)**

**B594 Practice for Ultrasonic Inspection of Aluminum-Alloy Wrought Products for Aerospace Applications**

**B660 Practices for Packaging/Packing of Aluminum and Magnesium Products**

**B666/B666M Practice for Identification Marking of Aluminum and Magnesium Products**

**B807/B807M Practice for Extrusion Press Solution Heat Treatment for Aluminum Alloys**

**B881 Terminology Relating to Aluminum- and Magnesium-Alloy Products**

**B918 Practice for Heat Treatment of Wrought Aluminum Alloys**

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard's Document Summary page on the ASTM website.

B945 Practice for Aluminum Alloy Extrusions Press Cooled from an Elevated Temperature Shaping Process for Production of T1, T2, T5 and T10-Type Tempers

E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

E34 Test Methods for Chemical Analysis of Aluminum and Aluminum-Base Alloys

E527 Practice for Numbering Metals and Alloys in the Unified Numbering System (UNS)

E607 Test Method for Atomic Emission Spectrometric Analysis Aluminum Alloys by the Point to Plane Technique Nitrogen Atmosphere (Withdrawn 2011)<sup>3</sup>

E716 Practices for Sampling and Sample Preparation of Aluminum and Aluminum Alloys for Determination of Chemical Composition by Spectrochemical Analysis

E1004 Test Method for Determining Electrical Conductivity Using the Electromagnetic (Eddy-Current) Method

E1251 Test Method for Analysis of Aluminum and Aluminum Alloys by Spark Atomic Emission Spectrometry

G34 Test Method for Exfoliation Corrosion Susceptibility in 2XXX and 7XXX Series Aluminum Alloys (EXCO Test)

G47 Test Method for Determining Susceptibility to Stress-Corrosion Cracking of 2XXX and 7XXX Aluminum Alloy Products

2.3 ANSI Standards:<sup>4</sup>

H35.1/H35.1(M) Alloy and Temper Designation Systems for Aluminum

H35.2(M) Dimensional Tolerances for Aluminum Mill Products

2.4 ISO Standards:<sup>4</sup>

ISO 209-1 Wrought Aluminum and Aluminum Alloys—Chemical Composition and Forms of Product

ISO 2107 Aluminum, Magnesium and their Alloys—Temper Designation

ISO 6362-2 Wrought Aluminum and Aluminum Alloy Extruded Rod/Bar, Tube, and Profile—Mechanical Properties

2.5 Federal Standard:<sup>5</sup>

Fed. Std. No. 123 Marking for Shipment (Civil Agencies)

2.6 Military Standard:<sup>5</sup>

MIL-STD-129 Marking for Shipment and Storage

2.7 AMS Specification:<sup>6</sup>

AMS 2772 Heat Treatment of Aluminum Alloy Raw Materials

2.8 Other Standards:

CEN EN 14242 Aluminium and Aluminium Alloys—Chemical Analysis—Inductively Coupled Plasma Optical Emission Spectral Analysis<sup>7</sup>

### 3. Terminology

3.1 Definitions—Refer to Terminology B881 for definitions of product terms used in this specification.

3.2 Definitions of Terms Specific to This Standard:

3.2.1 *capable of*—The term *capable of* as used in this specification means that the test need not be performed by the producer of the material. However, should subsequent testing by the purchaser establish that the material does not meet these requirements, the material shall be subject to rejection.

**TABLE 2 Tensile Property Limits<sup>A,B</sup>**

Temper	Specified Section or Wall Thickness, mm		Area, mm <sup>2</sup>		Tensile Strength, MPa		Yield Strength (0.2 % offset), MPa		Elongation, <sup>C</sup> %, min	
	over	incl	over	incl	min	max	min	max	in 50-mm	in 5-x Diameter (5.65 $\sqrt{A}$ )
Aluminum 1060										
Θ	all		all		60	95	45	...	25	22
H112	all		all		60	...	15	...	25	22
F <sup>D</sup>	all		all		...	...	...	...	...	...
Aluminum 1100										
Θ	all		all		75	105	20	...	25	22
H112	all		all		75	...	20	...	25	22
F <sup>D</sup>	all		all		...	...	...	...	...	...
Alloy 2014										
Θ	all		all		...	205	...	125	12	10

<sup>3</sup> The last approved version of this historical standard is referenced on www.astm.org.

<sup>4</sup> Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, http://www.ansi.org.

<sup>5</sup> Available from Standardization Documents Order Desk, DODSSP, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5098, http://www.dodssp.daps.mil.

<sup>6</sup> Available from Society of Automotive Engineers (SAE), 400 Commonwealth Dr., Warrendale, PA 15096-0001, http://www.sae.org.

<sup>7</sup> Available from European Committee for Standardization, Central Secretariat (CEN), rue de Stassart 36, B1050 Brussels, Belgium. http://www.cen.eu/esearch.

TABLE 2—Continued

Temper	Specified Section or Wall Thickness, mm		Area, mm <sup>2</sup>		Tensile Strength, MPa		Yield Strength (0.2% offset), MPa		Elongation, C %, min	
	over	incl	over	incl	min	max	min	max	in 50 mm	in 5 x Diameter (5.65 $\sqrt{A}$ )
T4	all		all		345	...	240	...	42	10
T4510 <sup>E</sup>	12.50		all		345	...	200	...	12	10
T4511 <sup>E</sup>										
T42 <sup>F</sup>	all		all		415	...	365	...	7	6
T6	...	12.50	all		440	...	400	...	...	6
T6510 <sup>E</sup>	18.00	...	all	16 000	470	...	415	...	...	6
T6511 <sup>E</sup>										
T62 <sup>F</sup>	...	18.00	all	...	415	...	365	...	7	6
	...	18.00	all	16 000	415	...	365	...	...	6
	...	18.00	all	20 000	415	...	365	...	...	5
F <sup>D</sup>	all		all	...	...	...	...	...	...	...
	Alloy 2024									
Θ	all		all		240	...	130	12	10	
T3	...	6.30	all		395	...	290	...	42 <sup>G</sup>	...
T3510 <sup>E</sup>	6.30	18.00	all	16 000	485	...	305	...	42 <sup>G</sup>	10 <sup>G</sup>
T3511 <sup>E</sup>										
	18.00	35.00	all		450	...	315	...	...	9
	35.00	...	all	16 000	485	...	360 <sup>H</sup>	...	...	9
	35.00	...	all	20 000	470	...	330 <sup>I</sup>	...	...	7
T42 <sup>F</sup>	...	18.00	all	...	395	...	260	...	12	10
	...	35.00	all	...	395	...	260	...	...	9
	...	35.00	all	16 000	395	...	260	...	...	9
	...	35.00	all	20 000	395	...	260	...	...	7
T84	...	1.20	all		440	...	385	...	4	...
T8510 <sup>E</sup>	6.30	35.00	all	20 000	455	...	400	...	5	4
T8511 <sup>E</sup>										
F <sup>D</sup>	all		all	...	...	...	...	...	...	...
	Alloy 2219									
Θ	all		all		220	...	125	12	10	
T34	...	12.50	all	16 000	290	...	180	...	14	12
T3510 <sup>E</sup>	12.50	30.00	all	16 000	310	...	185	...	...	12
T62 <sup>F</sup>										
	...	25.00	all	16 000	370	...	250	...	6	5
	...	25.00	all	20 000	370	...	250	...	...	5
T84	...	30.00	all	16 000	400	...	290	...	6	5
T8510 <sup>E</sup>	30.00	...	all	20 000	455	...	400	...	5	4
T8511 <sup>E</sup>										
F <sup>D</sup>	all		all	...	...	...	...	...	...	...
	Alloy 3003									
Θ	all		all		95	130	35	...	25	22
H112	all		all		95	...	35	...	25	22
F <sup>D</sup>	all		all	...	...	...	...	...	...	...
	Al clad Alloy 3003									
Θ	all	all	all		90	125	30	...	25	...
H112	all	all	all		90	...	30 <sup>J</sup>	...	25	...
	Alloy 3004									
Θ	all		all		160	200	60	...	...	...
F <sup>D</sup>	all		all	...	...	...	...	...	...	...
	Alloy 3102									
H112 <sup>K</sup>	-0.70	-1.30	all		75	125	30	...	25	...
	Alloy 5052									
Θ	all		all		170	240	70	...	...	...

TABLE 2—Continued

Temper	Specified Section or Wall Thickness, mm		Area, mm <sup>2</sup>		Tensile Strength, MPa		Yield Strength (0.2% offset), MPa		Elongation, C %, min	
	over	incl	over	incl	min	max	min	max	in 50 mm	in 5 x Diameter (5.65 $\sqrt{A}$ )
Alloy 5083										
Θ	...	130.00 <sup>L</sup>	...	20 000	270	350	110	...	14	12
H111	...	130.00 <sup>L</sup>	...	20 000	275	...	165	...	12	10
H112	...	130.00 <sup>L</sup>	...	20 000	270	...	110	...	12	10
F <sup>D</sup>	all	all			...	...	...	...	...	...
Alloy 5086										
Θ	...	130.00 <sup>L</sup>	...	20 000	240	315	95	...	14	12
H111	...	130.00 <sup>L</sup>	...	20 000	250	...	145	...	12	10
H112	...	130.00 <sup>L</sup>	...	20 000	240	...	95	...	12	10
F <sup>D</sup>	all	all			...	...	...	...	...	...
Alloy 5154										
Θ	...	130.00 <sup>L</sup>	...	20 000	215	285	75	...	...	...
H112	...	130.00 <sup>L</sup>	...	20 000	205	...	75	...	...	...
F <sup>D</sup>	all	all			...	...	...	...	...	...
Alloy 5454										
Θ	...	130.00 <sup>L</sup>	...	20 000	215	285	85	...	14	12
H111	...	130.00 <sup>L</sup>	...	20 000	230	...	130	...	12	10
H112	...	130.00 <sup>L</sup>	...	20 000	215	...	85	...	12	10
F <sup>D</sup>	all	all			...	...	...	...	...	...
Alloy 5456										
Θ	...	130.00 <sup>L</sup>	...	20 000	285	365	130	...	14	12
H111	...	130.00 <sup>L</sup>	...	20 000	290	...	180	...	12	10
H112	...	130.00 <sup>L</sup>	...	20 000	285	...	130	...	12	10
F <sup>D</sup>	all	all			...	...	...	...	...	...
Alloy 6005										
T4	...	-12.50	all		170	...	105	...	16	14
T5	...	-3.20	all		260	...	240	...	8	...
	3.20	-25.00	all		260	...	240	...	10	9
Alloy 6005A										
T4	...	-6.30	all		170	...	100	...	15	...
T5	...	-6.30	all		260	...	215	...	7	...
	-6.30	-25.00	all		260	...	215	...	9	8
T64	...	-6.30	all		260	...	240	...	8	...
	6.30	-25.00	all		260	...	240	...	10	9
Alloy 6020										
T6511	80.00	160.00	all		260	...	240	...	...	9
Alloy 6041										
T6 <sup>M</sup>	10.00	-50.00	all		310	...	275	...	10	9
T6511 <sup>M</sup>	10.00	-50.00	all		310	...	275	...	10	9
Alloy 6042										
T5	10.00	-12.50	all		260	...	240	...	10	...
	12.50	-50.00	all		290	...	240	...	...	9
T554	10.00	-12.50	all		260	...	240	...	10	...
	12.50	-50.00	all		290	...	240	...	...	9
Alloy 6060										
T54	...	-3.20	all		150	...	110	...	8	...
T64	...	-3.20	all		205	...	170	...	8	...
	3.20	25.00	all		205	...	170	...	10	9
Alloy 6061										
Θ	all	all			...	150	...	110	16	14
T4	...	-16.00	all		180	...	95	...	16	14
T4	...	all			180	...	110	...	16	14
T4510 <sup>E</sup>	all				...	...	...	...	...	...
T4511 <sup>E</sup>	all				...	...	...	...	...	...
T42 <sup>E</sup>	all	all			180	...	85	...	16	14
T54	...	-16.00	all		240	...	205	...	8	7
T6 <sup>E</sup>	...	-6.30	all		260	...	240	...	8	...
T62 <sup>E</sup>	{ -6.30		all		260	...	240	...	10	9
T6510 <sup>E</sup>	{ -6.30		all		260	...	240	...	10	9
T6511 <sup>E</sup>	{ -6.30		all		260	...	240	...	10	9
F <sup>D</sup>	all	all			...	...	...	...	...	...
Alloy 6063										
Θ	all	all			...	130	...	...	18	16
T4	...	-12.50	all	...	115	...	60	...	12	10
	12.50	-25.00	all	...	110	...	55	...	...	10
T4, T42 <sup>E</sup>	...	-12.50	all		130	...	70	...	14	12
	12.50	-25.00	all		125	...	60	...	...	12

iTeh Standards  
<https://standards.iteh.ae/>  
 Document Preview