

---

---

**Welding consumables — Covered  
electrodes for manual metal arc  
welding of stainless and heat-resisting  
steels — Classification**

*Produits consommables pour le soudage — Électrodes enrobées pour  
le soudage manuel à l'arc des aciers inoxydables et résistant aux  
températures élevées — Classification*

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

ISO 3581:2023

<https://standards.iteh.ai/catalog/standards/sist/1e4f6480-0766-458c-b205-2a9b44602e1f/iso-3581-2023>



# iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 3581:2023

<https://standards.iteh.ai/catalog/standards/sist/1e4f6480-0766-458c-b205-2a9b44602e1f/iso-3581-2023>



## **COPYRIGHT PROTECTED DOCUMENT**

© ISO 2023

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

	Page
<b>Foreword</b> .....	<b>iv</b>
<b>Introduction</b> .....	<b>vi</b>
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>1</b>
<b>4 Classification</b> .....	<b>2</b>
4.1 General.....	2
4.2 Classification systems.....	4
4.2.1 General.....	4
4.2.2 Classification: nominal composition — A.....	5
4.2.3 Classification: alloy type — B.....	5
<b>5 Symbols and requirements</b> .....	<b>5</b>
5.1 Symbol for the product or process.....	5
5.1.1 Classification according to nominal composition — A.....	5
5.1.2 Classification according to alloy type — B.....	5
5.1.3 Symbol for the chemical composition of all-weld metal.....	5
5.2 Symbol for type of electrode covering.....	6
5.2.1 General.....	6
5.2.2 Classification according to nominal composition — A.....	6
5.2.3 Classification according to alloy type — B.....	6
5.3 Symbol for nominal electrode efficiency and type of current.....	18
5.3.1 Classification according to nominal composition — A.....	18
5.3.2 Classification according to alloy type — B.....	18
5.4 Symbol for welding position.....	19
<b>6 Chemical analysis</b> .....	<b>19</b>
<b>7 Mechanical property tests</b> .....	<b>19</b>
7.1 General.....	19
7.2 Preheat and interpass temperatures.....	19
7.3 Pass sequence.....	20
<b>8 Fillet weld test</b> .....	<b>20</b>
<b>9 Rounding procedure</b> .....	<b>21</b>
<b>10 Retests</b> .....	<b>21</b>
<b>11 Technical delivery conditions</b> .....	<b>22</b>
<b>12 Examples of designation</b> .....	<b>22</b>
12.1 General.....	22
12.2 Example 1: classification according to nominal composition — A.....	22
12.3 Example 2: classification according to alloy type — B.....	22
12.4 Example 3: Z classification.....	23
<b>Annex A (informative) Types of covering</b> .....	<b>24</b>
<b>Annex B (informative) Considerations on weld metal ferrite contents</b> .....	<b>26</b>
<b>Bibliography</b> .....	<b>29</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at [www.iso.org/patents](http://www.iso.org/patents). ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 44, *Welding and allied processes*, Subcommittee SC 3, *Welding consumables*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 121, *Welding and allied processes*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This fourth edition cancels and replaces the third edition (ISO 3581:2016), which has been technically revised.

The main changes are as follows:

- the document has been updated in accordance with the drafting guidelines laid out in the ISO House Style;
- the dates of normative references have been updated to show their latest editions;
- a new [Clause 3](#) (Terms and definitions) has been added in accordance with the standard structure of ISO documents;
- “weld metal recovery” now reads “nominal electrode efficiency” throughout, in accordance with ISO 2401;
- a new [Table 2](#) has been added listing classification systems;
- new alloys have been added to [Table 3](#) (formerly Table 2) and associated clauses of the document;
- the chemical compositions of several alloys have been updated in [Table 3](#) (formerly Table 2);
- certain alloys have been reclassified in [Table 3](#) (formerly Table 2);
- a new footnote was added to [Table 3](#) (formerly Table 2) regarding Co content;

— the wording of [Clause 9](#) (formerly Clause 8) has been updated.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html). Official interpretations of ISO/TC 44 documents, where they exist, are available from this page: <https://committee.iso.org/sites/tc44/home/interpretation.html>.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 3581:2023

<https://standards.iteh.ai/catalog/standards/sist/1e4f6480-0766-458c-b205-2a9b44602e1f/iso-3581-2023>

## Introduction

This document provides a classification system for covered electrodes for manual metal arc welding of stainless and heat-resisting steels in terms of chemical composition of deposited weld metal and type of electrode covering. Other properties of the electrodes are specified by reference to tables.

This document recognizes that there are two somewhat different approaches in the global market for classifying a given covered electrode for arc welding of stainless steel. It allows for either or both to be used to suit a particular need. Application of either (or both) type(s) of classification designation identifies a product as classified according to this document. It is important to note that the two systems are not exactly equivalent; therefore, each system is to be used independently of the other, without combining designators in any way.

The classification according to nominal composition (system A) is mainly based on EN 1600. The classification according to alloy type (system B) is mainly based on standards used around the Pacific Rim.

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

ISO 3581:2023

<https://standards.iteh.ai/catalog/standards/sist/1e4f6480-0766-458c-b205-2a9b44602e1f/iso-3581-2023>

# Welding consumables — Covered electrodes for manual metal arc welding of stainless and heat-resisting steels — Classification

## 1 Scope

This document specifies requirements for classification of covered electrodes, based on the all-weld metal chemical composition, the type of electrode covering and other electrode properties, and the all-weld metal mechanical properties, in the as-welded or heat-treated conditions, for manual metal arc welding of stainless and heat-resisting steels.

This document is a combined standard providing for classification utilizing a system based upon classification according to nominal composition or utilizing a system based upon classification according to alloy type.

- a) Paragraphs and tables which carry the label “classification according to nominal composition-A” or “ISO 3581-A” are applicable only to products classified to that system.
- b) Paragraphs and tables which carry the label “classification according to alloy type-B” or “ISO 3581-B” are applicable only to products classified to that system.
- c) Paragraphs and tables which carry neither label are applicable to products classified according to either or both systems.

[Annex B](#) gives information on considerations on weld metal ferrite content.

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 544, *Welding consumables — Technical delivery conditions for filler materials and fluxes — Type of product, dimensions, tolerances and markings*

ISO 6847, *Welding consumables — Deposition of a weld metal pad for chemical analysis*

ISO 14344, *Welding consumables — Procurement of filler materials and fluxes*

ISO 15792-1:2020, *Welding consumables — Test methods — Part 1: Preparation of all-weld metal test pieces and specimens in steel, nickel and nickel alloys*

ISO 15792-3, *Welding consumables — Test methods — Part 3: Classification testing of positional capacity and root penetration of welding consumables in a fillet weld*

ISO 80000-1:2022, *Quantities and units — Part 1: General*

## 3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

— ISO Online browsing platform: available at <https://www.iso.org/obp>

— IEC Electropedia: available at <https://www.electropedia.org/>

## 4 Classification

### 4.1 General

Classification designations are based upon two approaches for indicating the chemical composition of the all-weld metal deposit obtained with a given electrode.

The “nominal composition ISO 3581-A” approach uses designation components directly indicating the nominal levels of certain alloying elements, given in a particular order, and some symbols for low but significant levels of other elements, whose levels are not conveniently expressed as integers.

The “alloy type ISO 3581-B” approach uses tradition-based three-digit or four-digit designations for alloy families, and occasionally an additional character or characters for compositional modifications of each original alloy within the family.

Both designation approaches include additional designators for some other classification requirements, but not entirely the same classification requirements, as explained in the following clauses.

[Table 1](#) lists the tests required for classification of an electrode under each approach.

In many cases, a given commercial product can be classified using both approaches. Then, either or both classification designations can be used for the product.

**Table 1 — Summary of test requirements**

Electrode designation		Size <sup>a</sup> mm	Position of welding <sup>b</sup>					
			Chemical analysis test		All-weld metal tension test		Fillet weld test	
ISO 3581-A	ISO 3581-B		ISO 3581-A	ISO 3581-B	ISO 3581-A	ISO 3581-B	ISO 3581-A	ISO 3581-B
Coating type symbol B and position symbols 1 and 2	Position and coating type symbol – 15	2,5 (or 2,4 or 2,6)	Not required	PA	Not required	Not required	Not required	Not required
		3,2 or 3,0	PA	PA	Not required	Not required	Not required	Not required
		4,0	PA	PA	PA	PA	Not required	PB, PF, PD
		5,0 or 4,8	Not required	PA	Not required	Not required	Not required	PB
		6,0 (or 5,6 or 6,4)	Not required	PA	Not required	Not required	Not required	PB

<sup>a</sup> If the size is not manufactured, the next nearest size may be substituted (provided that the substituted size is different from that specified in this table).

<sup>b</sup> The abbreviations PA, PB, PD, PF and PG indicate welding positions in accordance with ISO 6947:2019:

PA flat  
 PB horizontal vertical  
 PD horizontal overhead  
 PF vertical up  
 PG vertical down



Table 1 (continued)

Electrode designation		Size <sup>a</sup> mm	Position of welding <sup>b</sup>					
			Chemical analysis test		All-weld metal tension test		Fillet weld test	
ISO 3581-A	ISO 3581-B		ISO 3581-A	ISO 3581-B	ISO 3581-A	ISO 3581-B	ISO 3581-A	ISO 3581-B
All coating types and position symbol 3	Not applicable	3,2 or 3,0	PA	Not applicable	Not required	Not applicable	Not required	Not applicable
		4,0	PA		PA		Not required	
		5,0 or 4,8	Not required		Not required		Not required	
All coating types and position symbol 4	Position symbol – 4 and all coating types	2,5 (or 2,4 or 2,6)	Not required	PA	Not required	Not required	Not required	PG
		3,2 or 3,0	PA	PA	Not required	Not required	Not required	PG
		4,0	PA	PA	PA	PA	Not required	PG
		5,0 or 4,8	Not required	PA	Not required	Not required	Not required	PG
All coating types and position symbol 5	Not applicable	3,2 (or 3,0)	PA	Not applicable	Not required	Not applicable	Not required	Not applicable
		4,0	PA		PA		Not required	
		5,0 (or 4,8)	Not required		Not required		Not required	
Coating type symbol R and position symbols 1 and 2	Position and coating type symbols – 16 and – 17	2,5 (or 2,4 or 2,6)	Not required	PA	Not required	Not required	Not required	Not required
		3,2 (or 3,0)	PA	PA	Not required	Not required	Not required	Not required
		4,0	PA	PA	PA	PA	Not required	PB, PF, PD
		5,0 (or 4,8)	Not required	PA	Not required	Not required	Not required	PB
		6,0 (or 5,6 or 6,4)	Not required	PA	Not required	Not required	Not required	PB

<sup>a</sup> If the size is not manufactured, the next nearest size may be substituted (provided that the substituted size is different from that specified in this table).

<sup>b</sup> The abbreviations PA, PB, PD, PF and PG indicate welding positions in accordance with ISO 6947:2019:

PA flat

PB horizontal vertical

PD horizontal overhead

PF vertical up

PG vertical down

**Table 1 (continued)**

Electrode designation		Size <sup>a</sup> mm	Position of welding <sup>b</sup>					
			Chemical analysis test		All-weld metal tension test		Fillet weld test	
ISO 3581-A	ISO 3581-B		ISO 3581-A	ISO 3581-B	ISO 3581-A	ISO 3581-B	ISO 3581-A	ISO 3581-B
Not applicable	Position and coating type symbols – 26 and – 27	2,5 (or 2,4 or 2,6)	Not applicable	PA	Not applicable	Not required	Not applicable	Not required
		3,2 (or 3,0)		PA		Not required		Not required
		4,0		PA		PA		PB
		5,0 (or 4,8)		PA		Not required		PB
		6,0 (or 5,6 or 6,4)		PA		Not required		PB

<sup>a</sup> If the size is not manufactured, the next nearest size may be substituted (provided that the substituted size is different from that specified in this table).

<sup>b</sup> The abbreviations PA, PB, PD, PF and PG indicate welding positions in accordance with ISO 6947:2019:

PA flat  
 PB horizontal vertical  
 PD horizontal overhead  
 PF vertical up  
 PG vertical down

**4.2 Classification systems**

**4.2.1 General**

<https://standards.iteh.ai/catalog/standards/sist/1e4f6480-0766-458c-b205-81-2023>  
 Table 2 gives the requirements for classification according to: 81-2023

- nominal composition — ISO 3581-A; and
- alloy type — ISO 3581-B.

NOTE The composition of the core wire, which can be substantially different from the weld metal composition, is not considered a classification criterion.

**Table 2 — Classification systems**

Classification according to:	
Nominal composition — ISO 3581-A	Alloy type — ISO 3581-B
The classification is divided into five parts:	The classification is divided into four parts:
1) a symbol indicating the product or process to be identified (see 5.1)	1) a symbol indicating the product or process to be identified (see 5.1)
2) a symbol indicating the chemical composition of all-weld metal (see Table 3)	2) a symbol indicating the chemical composition of all-weld metal (see Table 3)
3) a symbol indicating the type of electrode covering (see 5.3)	3) a symbol indicating the welding position (see Table 6)
4) a symbol indicating the nominal electrode efficiency, $R_N$ , and type of current (see Table 5)	4) a symbol indicating the type of electrode covering. This also serves to specify the type of current which can be used with the electrode classified (see 5.2.3)
5) a symbol indicating the welding position (see Table 6)	

#### 4.2.2 Classification: nominal composition — A

This classification includes all-weld metal properties obtained with a covered electrode as follows. The classification is based on an electrode diameter of 4 mm, with the exception of testing for welding position. When 4-mm-diameter electrodes are not manufactured, the next closest diameter shall be tested.

Classification according to nominal composition is split into two sections.

- Compulsory section: includes the symbols for the type of product, the chemical composition, and the type of covering, i.e. symbols in accordance with [5.1](#) and [5.2](#).
- Optional section: includes the symbols for the nominal electrode efficiency,  $R_N$ , (see ISO 2401) the type of current, and the welding positions for which the electrode is suitable, i.e. the symbols in accordance with [5.4](#) and [Table 5](#).

The full designation (compulsory and optional sections, as applicable) shall be used on packages and in the manufacturer's literature and data sheets.

#### 4.2.3 Classification: alloy type — B

This classification includes all-weld metal properties obtained with a covered electrode as follows. The classification is based on an electrode diameter of 4 mm for mechanical properties, with the exception of testing for welding position and for chemical analysis of the weld metal. When 4-mm-diameter electrodes are not manufactured, the next closest diameter shall be tested. In classifying welding electrodes according to alloy type, the symbols for all four parts (product or process, alloy type, welding position and type of electrode covering) in accordance with [5.1](#), [5.2](#) and [5.4](#) are compulsory.

The full designation shall be used on packages and in the manufacturer's literature and data sheets.

## 5 Symbols and requirements ISO 3581:2023

### 5.1 Symbol for the product or process

#### 5.1.1 Classification according to nominal composition — A

The symbol for a covered electrode using the manual metal arc welding process for stainless and heat-resisting steels in accordance with ISO 3581-A shall be the letter E.

#### 5.1.2 Classification according to alloy type — B

The symbol for a covered electrode using the manual metal arc welding process for stainless and heat-resisting steels in accordance with ISO 3581-B shall be the letters ES. The initial letter “E” indicates a covered electrode while the letter “S” indicates stainless and heat-resisting steels.

#### 5.1.3 Symbol for the chemical composition of all-weld metal

The symbols in [Table 3](#) indicate the chemical composition of all-weld metal determined in accordance with [Clause 6](#). The all-weld metal obtained with the covered electrodes in [Table 3](#), in accordance with [Clause 7](#), shall also fulfil the mechanical property requirements for that electrode as specified in [Table 4](#).

A symbol classification in parentheses indicates a near match in the other designation system, but not an exact match. The correct designation for a given composition is the one without parentheses. A given product may, by having a more restricted chemical composition that fulfils both sets of requirements, be assigned both designations independently, provided that the mechanical property requirements are met.

## 5.2 Symbol for type of electrode covering

### 5.2.1 General

The type of electrode covering determines, to a large extent, usability characteristics of the electrode and properties of the weld metal. See [Annex A](#) for information on coating types.

### 5.2.2 Classification according to nominal composition — A

The following two symbols are used to describe the type of covering:

- B denotes a basic covering;
- R denotes a rutile-based covering.

### 5.2.3 Classification according to alloy type — B

The following three symbols are used to specify the type of covering on the electrode:

- 5 denotes a basic covering intended for DC welding;
- 6 denotes a rutile-based coating intended for DC or AC welding (except that position and coating type –46 is DC);
- 7 denotes a modified rutile-based coating containing a considerable amount of silica, intended for DC or AC welding (except that position and coating type –47 is DC).

(standards.iteh.ai)

ISO 3581:2023

<https://standards.iteh.ai/catalog/standards/sist/1e4f6480-0766-458c-b205-2a9b44602e1f/iso-3581-2023>