

# DRAFT INTERNATIONAL STANDARD

## ISO/DIS 3136

ISO/TC 45/SC 3

Secretariat: **AFNOR**

Voting begins on:  
**2022-11-16**

Voting terminates on:  
**2023-02-08**

---

---

## Rubber latex — Styrene-butadiene — Determination of bound styrene content

*Latex de caoutchoucs — Styène-butadiène — Détermination de la teneur en styrène lié*

ICS: 83.040.10

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

ISO/PRF 3136

<https://standards.iteh.ai/catalog/standards/sist/adc2580b-c4c1-4c8e-b942-a5efbd0ee9ca/iso-prf-3136>

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

This document is circulated as received from the committee secretariat.



Reference number  
ISO/DIS 3136:2022(E)

© ISO 2022

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

ISO/PRF 3136

<https://standards.iteh.ai/catalog/standards/sist/adc2580b-c4c1-4c8e-b942-a5efbd0ee9ca/iso-prf-3136>



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2022

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

	Page
Foreword.....	iv
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>1</b>
<b>4 Principle</b> .....	<b>1</b>
<b>5 Reagents</b> .....	<b>2</b>
<b>6 Apparatus</b> .....	<b>2</b>
<b>7 Sampling</b> .....	<b>2</b>
<b>8 Preparation of dry polymer</b> .....	<b>2</b>
<b>9 Determination of the refractive index</b> .....	<b>2</b>
<b>10 Expression of results</b> .....	<b>2</b>
<b>11 Precision</b> .....	<b>2</b>
<b>12 Test report</b> .....	<b>2</b>
<b>Annex A (informative) Precision</b> .....	<b>3</b>
<b>Bibliography</b> .....	<b>4</b>

iTech STANDARD PREVIEW  
(standards.iteh.ai)

ISO/PRF 3136

<https://standards.iteh.ai/catalog/standards/sist/adc2580b-c4c1-4c8e-b942-a5efbd0ee9ca/iso-prf-3136>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 3, *Raw materials (including latex) for use in the rubber industry*.

This third edition cancels and replaces the second edition (ISO 3136:1983), which has been technically revised.

The main changes compared to the previous edition are as follows:

- move of the preparation of dry polymer to a new [Clause 8](#) and the determination of the refractive index to a new [Clause 9](#);
- amendment of the preparation procedure of dry polymer, in [Clause 8](#);
- addition of [Formula \(1\)](#) in the expression of result, in [Clause 10](#);
- addition of the precision data in [Annex A](#).

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

# Rubber latex — Styrene-butadiene — Determination of bound styrene content

**WARNING** — Persons using this document should be familiar with normal laboratory practice. This document does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to determine the applicability of any other restrictions.

**WARNING** — Certain procedures specified in this document possibly involves the use or generation of substances, or the generation of waste, that could constitute a local environmental hazard. Reference should be made to appropriate documentation on safe handling and disposal after use.

## 1 Scope

This document specifies a method for the determination of the bound styrene content of styrene-butadiene rubber (SBR) latices.

The method is applicable to hot (approximately 50 °C) emulsion polymerized SBR latices having a bound styrene content, expressed on the SBR content, of up to 55 % and to cold (approximately 5 °C) emulsion polymerized SBR latices having a bound styrene content between 18 % and 40 %.

The method is not applicable to reinforced styrene-butadiene rubber (SBR .Y) latices, carboxylic-styrene-butadiene rubber (XSBR) latices and pyridine-styrene-butadiene rubber (PSBR) latices.

## 2 Normative references

ISO/PRF 3136

<https://standards.iteh.ai/catalog/standards/sist/adc2580b-c4c1-4c8e-b942-a5efbd0ee9ca/iso->

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 123, *Rubber latex — Sampling*

ISO 2028, *Synthetic rubber latex — Preparation of dry polymer*

ISO 2453:2020, *Rubber, raw styrene-butadiene, emulsion-polymerized — Determination of bound styrene content — Refractive index method*

## 3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

## 4 Principle

A dry polymer is prepared from the latex and then extracted with ethanol-toluene azeotrope (ETA), followed by pressing into a thin sheet. The bound styrene content is calculated from the refractive index obtained at 25 °C on this sheet.

## 5 Reagents

Use reagents specified in ISO 2028 and ISO 2453.

## 6 Apparatus

Use the apparatus specified in ISO 2028 and ISO 2453.

## 7 Sampling

Carry out sampling in accordance with one of the methods specified in ISO 123.

## 8 Preparation of dry polymer

In accordance with ISO 2028, coagulate the latex with appropriate coagulants in the presence of antioxidant, followed by collecting and drying the resultant crumb.

## 9 Determination of the refractive index

In accordance with ISO 2453, sheet out the dry polymer, followed by extracting with ETA and drying, finally press into a thin sheet and determine the refractive index.

## 10 Expression of results

The bound styrene content,  $w_s$ , of the SBR latices, expressed as a percentage mass fraction, is determined from the refractive index, corrected to 25 °C, by using [Formula \(1\)](#) or according to Table 1 of ISO 2453:2020.

$$w_s = 23,50 + 1\,164(n_{25} - 1,534\,56) - 3\,497(n_{25} - 1,534\,56)^2 \quad (1)$$

where  $n_{25}$  is the refractive index at 25 °C.

## 11 Precision

See [Annex A](#).

## 12 Test report

The test report shall include the following information:

- a) a reference to this document, i.e. ISO 3136;
- b) all details necessary for the complete identification of the sample;
- c) the coagulants used;
- d) the results and the method of expression used;
- d) any unusual features noted during the determination;
- f) details of any operation not included in this document or in the International Standards to which reference is made, as well as details of any operation regarded as optional;
- g) the date of the test.

## Annex A (informative)

### Precision

#### A.1 General

An interlaboratory test programme (ITP) on the basis of styrene-butadiene rubber latices polymerized at 5 °C was conducted in June 2022. The precision evaluated was a type 1 precision in accordance with ISO 19983:2022.

Nine laboratories participated in this programme. Two different types of rubber latices were used in the ITP. The dry polymers were prepared in one laboratory and posted to other participated laboratories. Each laboratory repeated the tests twice for each sample on two different days at intervals of one week.

The precision results as determined by this ITP should not be applied to acceptance or rejection testing of any group of materials or products without documentation that the results of this precision evaluation actually apply to the products or materials tested.

#### A.2 Precision results

The precision results in [Table A.1](#) were calculated by method B of ISO 19983:2022.

- a) Repeatability: the day-to-day repeatability,  $r_D$ , of the test method has been established as the appropriate value tabulated in [Table A.1](#) for each material. Two single test results that differ by more than this value should be considered suspect and suggest that some appropriate investigative action be taken.
- b) Reproducibility: the reproducibility,  $R$ , of the test method has been established as the appropriate value tabulated in [Table A.1](#) for each material. Two single test results that differ by more than this value should be considered suspect and suggest that some appropriate investigative action be taken.

**Table A.1 — Precision data**

Material	Mean content %	Within laboratory day-to-day			Between laboratories			Number of laboratories <sup>a</sup>
		$s_D$	$r_D$	$(r_D)$	$s_R$	$R$	$(R)$	
SBR latex-1	23,30	0,14	0,40	1,72	0,23	0,65	2,79	9
SBR latex-2	40,59	0,19	0,54	1,33	0,27	0,76	1,87	8

$s_D$  is the day-to-day repeatability standard deviation;  
 $r_D$  is the day-to-day repeatability, in measurement units;  
 $(r_D)$  is the relative day-to-day repeatability, in percent;  
 $s_R$  is the reproducibility standard deviation;  
 $R$  is the reproducibility, in measurement units;  
 $(R)$  is the relative reproducibility, in percent.

<sup>a</sup> The final number of laboratories in the ITP after deletion of outliers.