

FINAL  
DRAFT

INTERNATIONAL  
STANDARD

ISO/FDIS  
6588-2

ISO/TC 6

Secretariat: SCC

Voting begins on:  
2021-08-13

Voting terminates on:  
2021-10-08

---

---

## Paper, board and pulps — Determination of pH of aqueous extracts —

### Part 2: Hot extraction

**iTeh STANDARD PREVIEW**  
*Papier, carton et pâtes — Détermination du pH des extraits aqueux —  
Partie 2: Extraction à chaud*  
(standards.iteh.ai)

ISO/FDIS 6588-2

<https://standards.iteh.ai/catalog/standards/sist/62712b04-e352-4acd-859e-8877791ac730/iso-fdis-6588-2>

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.



Reference number  
ISO/FDIS 6588-2:2021(E)

© ISO 2021

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

ISO/FDIS 6588-2

<https://standards.iteh.ai/catalog/standards/sist/62712b04-e352-4acd-859e-8877791ac730/iso-fdis-6588-2>



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2021

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

|  | Page     |
|--|----------|
| Foreword.....  | iv       |
| Introduction.....  | v        |
| <b>1 Scope</b> .....   | <b>1</b> |
| <b>2 Normative references</b> .....  | <b>1</b> |
| <b>3 Terms and definitions</b> .....   | <b>1</b> |
| <b>4 Principle</b> .....   | <b>1</b> |
| <b>5 Reagents</b> .....  | <b>2</b> |
| <b>6 Apparatus and equipment</b> .....   | <b>2</b> |
| <b>7 Sampling and preparation of sample</b> .....                                | <b>2</b> |
| 7.1 Sampling.....  | 2        |
| 7.2 Preparation of sample.....   | 2        |
| <b>8 Procedure</b> .....   | <b>2</b> |
| 8.1 General.....   | 2        |
| 8.2 Weighing.....  | 3        |
| 8.3 Extraction.....  | 3        |
| 8.4 Determination of pH.....   | 3        |
| <b>9 Calculation</b> .....   | <b>3</b> |
| <b>10 Test report</b> .....  | <b>3</b> |
| <b>Annex A (informative) Preparation of some standard buffer solutions</b> ..... | <b>5</b> |
| <b>Annex B (informative) Precision</b> .....                                     | <b>6</b> |
| <b>Bibliography</b> .....  | <b>7</b> |

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 6, *Paper, board and pulps*.

This fourth edition cancels and replaces the third edition (ISO 6588-2:2020), of which it constitutes a minor revision. The changes compared to the previous edition are as follows:

- reference to 7.1 has been corrected to [8.2](#).

A list of all parts in the ISO 6588 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

## Introduction

Kraft fibre is well known to contain ionisable groups that are fixed to or in the fibre wall. In order to fulfil the electro-neutrality, these groups are balanced by an equivalent number of positive charges, which can be either protons or various metal ions. Especially in pulp suspensions at low ionic strengths, this can give rise to a marked uneven distribution of mobile ions between the volume held by the fibre wall and the bulk suspension liquor. This means that the fibre acts as an ion exchanger. These ion-exchange phenomena can be modelled very well with the Donnan theory<sup>[6][7]</sup>.

If a relatively clean pulp fibre sample, as for example bleached dried pulp, is diluted in deionised water, the result will be a pulp suspension with a very low ionic strength. In such a system, most of the cations present, including protons, will be concentrated in the water volume held by the fibre wall. If the pH is measured, it will be measured in the bulk suspension liquor. By adding salt to this kind of system, the ion exchange phenomena will be decreased and the concentration of different cations will be the same in the water held by the fibre wall and in the bulk suspension liquor. Since the process waters always contain a certain amount of ions, such a salt addition will give a more realistic environment when measuring the pH of relatively clean pulp samples.

Based on the foregoing, two ISO Standards, this document and ISO 29681, are available for determination of the pH of hot aqueous extracts of paper, board, or pulps. In ISO 29681, a salt solution is added prior to extraction; however, in this document, the extraction is carried out with distilled or deionized water. ISO 29681 is specifically applicable to bleached pulps from virgin fibres and to pulp samples having a low ionic strength for which the pH-value will give more realistic results related to mill conditions than those obtained with this document.

It is necessary to be aware that the results will not be the same when measuring pH according to this document and to ISO 29681. The difference can be significant especially when measuring pulps having a low ionic strength.

ISO 6588-1 differs from this document, in relation to the extraction conditions. No general guidance can be given as to which of the two procedures (hot or cold) is best suited in a particular situation.

It should be noted that in this document, addition of a salt solution is performed after extraction and filtration only for the purpose of obtaining a more stable and accurate pH measurement.

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

ISO/FDIS 6588-2

<https://standards.iteh.ai/catalog/standards/sist/62712b04-e352-4acd-859e-8877791ac730/iso-fdis-6588-2>

# Paper, board and pulps — Determination of pH of aqueous extracts —

## Part 2: Hot extraction

### 1 Scope

This document specifies a method for the determination of the pH-value defined by the electrolytes extractable by hot water from a sample of paper, board or pulp.

This document is applicable to all kinds of paper, board and pulp.

As the quantity of extractable ionic material approaches zero, as in the case of highly purified pulps, the precision of the method becomes poor because of the difficulties encountered in making pH measurements on water containing little electrolytic material.

Since the extraction in this document is performed with distilled or deionised water, the pH-value measured can sometimes be different (e.g. fully bleached pulp) from the pH-value measured under mill process conditions in which various types of process waters, such as chemically treated river water containing electrolytes, are used. In such cases, ISO 29681 can be used instead, as it is specifically applicable to bleached pulps from virgin fibres and to pulp samples having a low ionic strength for which the pH value gives more realistic results related to mill conditions than those obtained with this document. For cellulosic papers used for electrical purposes, the method used can be that given in IEC 60554-2<sup>[5]</sup>. <https://standards.iteh.ai/catalog/standards/sist/62712b04-e352-4acd-859e-8877791ac730/iso-fdis-6588-2>

### 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 186, *Paper and board — Sampling to determine average quality*

ISO 7213, *Pulps — Sampling for testing*

### 3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

### 4 Principle

Extraction of a sample of 2 g for 1 h with 100 ml of boiling water of high purity. Filtration of the extract and addition of a salt solution. Measurement of the pH-value of the extract at a temperature between 20 °C and 25 °C.

## 5 Reagents

**5.1 Water**, distilled or deionised water shall be used throughout the test. The conductivity of the water shall not exceed 0,1 mS/m after boiling for 1 h and cooling in an acid-free atmosphere (e.g. free of CO<sub>2</sub>, SO<sub>2</sub>, H<sub>2</sub>S) to a temperature between 20 °C and 25 °C. The pH of the water should be in the range of 6,8 to 7,3. Instructions for the determination of conductivity are specified in ISO 3696.

**5.2 Standard buffer solutions**, with known pH-values of about 4, 7 and 9. Such buffer solutions are commercially available. Some examples of suitable buffer solutions are given, and their preparation is described, in [Annex A](#).

**5.3 Potassium chloride solution**, 1M. Dissolve 7,4 g of KCl, analytical grade, in 100 ml of freshly boiled, distilled water. Prepare a fresh solution every week.

## 6 Apparatus and equipment

Use the following, in addition to ordinary laboratory apparatus and equipment.

**6.1 Glassware** of chemically resistant glass, flasks with ground-glass joints, stoppers, beakers, reflux condenser and fritted glass filter. All glassware shall be cleaned with an acid cleaning solution, without the use of soap or detergent, and they shall be carefully rinsed with water ([5.1](#)) and allowed to dry before use.

**6.2 pH-meter**, fitted with glass and calomel electrodes or with a combined electrode, capable of being read to at least 0,05 pH-unit.

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

## 7 Sampling and preparation of sample

ISO/FDIS 6588-2  
<https://standards.iteh.ai/catalog/standards/sist/62712b04-e352-4acd-859e-8877791ac730/iso-fdis-6588-2>

### 7.1 Sampling

The sampling procedure to be followed depends on the particular circumstances in each case. If the analysis is being made to evaluate a lot or a consignment of pulp, paper or board, the sample shall be taken in accordance with ISO 7213 or ISO 186, as relevant. If the analysis is made on another type of sample, report the origin of the sample and, if possible, the sampling procedure, and ensure that the specimen taken in [8.2](#) is representative of the sample received.

Wear clean protective gloves when handling the sample.

NOTE Some gloves are powdered to prevent them from sticking to one another, and this powder can cause contamination of the sample.

### 7.2 Preparation of sample

Do not touch the sample with bare hands and ensure that it has been placed only on clean surfaces. Cut the sample with a knife or cutter, or tear it, into pieces approximately 1 cm<sup>2</sup> in size. Split samples of heavy board.

Mix the pieces thoroughly. Store the pieces in clean, covered containers.

## 8 Procedure

### 8.1 General

Run the procedure in duplicate.



## 8.2 Weighing

Weigh 2,0 g  $\pm$  0,1 g of air-dry sample.

NOTE Since the amount of sample is not critical, there is no need to determine the dry matter content to adjust for minor differences in moisture content.

## 8.3 Extraction

Add 100 ml of water (5.1) to a 250 ml flask (6.1) and heat to boiling. Add the weighed sample, attach the reflux condenser (6.1) fitting the flask, and continue boiling gently for 1 h  $\pm$  5 min on an electric heater.

Cool the flask rapidly to a temperature between 20 °C and 25 °C with the condenser in place. Filter the extract through a coarse, fritted glass filter into a small beaker (6.1). Immediately add 2 ml of potassium chloride solution (5.3) and continue with the measurement.

## 8.4 Determination of pH

Operate the pH-meter in accordance with the manufacturer's instruction. Wash the electrodes with water (5.1); allow the water to drain from the electrodes, but do not wipe them. Calibrate the pH-meter (6.2), at a temperature between 20 °C and 25 °C, with two different buffer solutions (5.2) having pH-values such that the pH of the extract is between the pH-values of the buffer solutions. The first buffer solution shall be chosen so that the pH-value of the buffer solution is in the same region as the electric zero point of the pH-meter (usually = 7). The reading for the second buffer solution should agree with its correct value to within 0,1 pH-unit.

If the pH-meter fails to show the correct pH-value for the second buffer solution, consult the manufacturer's manual. A deviation of, or exceeding, 0,2 pH-units, rounded to the nearest 0,1 pH unit, indicates a faulty electrode. In addition, a slow but continuous increase or decrease in the reading indicates a faulty electrode.

After calibration, rinse the electrodes several times with water (5.1) and once in a small quantity of the extract. Check that the temperature of the extract is between 20 °C and 25 °C. Immerse the electrodes in the extract. Record the pH when there is no measurable drift, within 30 s.

Before measuring the next sample, rinse the electrodes carefully with water (5.1) to remove any traces of sample or buffer solution.

At the end of a series of measurements, check the electrodes with the same buffer solutions. The results for both solutions should agree with their correct value to within 0,1 pH unit. Otherwise repeat the procedure in this subclause.

## 9 Calculation

Calculate the mean of the duplicate determinations.

Report the pH-value to the nearest 0,1 pH-unit. The individual results should not differ by more than 0,2 pH-unit; if they do, repeat the determination with two additional extracts, and report the mean and the range of all measurements.

NOTE See Annex B for precision.

## 10 Test report

The test report shall include the following information:

- a) a reference to this document, i.e. ISO 6588-2:2021;
- b) the date and place of testing;

## ISO/FDIS 6588-2:2021(E)

- c) all the information necessary for complete identification of the sample;
- d) the result, expressed as indicated in [Clause 9](#);
- e) any unusual features observed in the course of the test;
- f) any departure from the procedure described in this document, or any other circumstances which may have affected the result.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO/FDIS 6588-2](#)

<https://standards.iteh.ai/catalog/standards/sist/62712b04-e352-4acd-859e-8877791ac730/iso-fdis-6588-2>