

---

---

**Textiles — Determination of index  
ingredient from coloured textile —**

**Part 2:  
Turmeric**

*Textiles — Détermination d'indicateurs d'ingrédients de textiles  
colorés —  
Partie 2: Curcuma*

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

[ISO 22195-2:2023](https://standards.iteh.ai/catalog/standards/sist/7a9344ab-3ceb-4624-b6fb-ab90f5aa359c/iso-22195-2-2023)

<https://standards.iteh.ai/catalog/standards/sist/7a9344ab-3ceb-4624-b6fb-ab90f5aa359c/iso-22195-2-2023>



# iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 22195-2:2023

<https://standards.iteh.ai/catalog/standards/sist/7a9344ab-3ceb-4624-b6fb-ab90f5aa359c/iso-22195-2-2023>



## **COPYRIGHT PROTECTED DOCUMENT**

© ISO 2023

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

	Page
Foreword.....	iv
Introduction.....	v
<b>1 Scope.....</b>	<b>1</b>
<b>2 Normative references.....</b>	<b>1</b>
<b>3 Terms and definitions.....</b>	<b>1</b>
<b>4 Principle.....</b>	<b>1</b>
<b>5 Reagent.....</b>	<b>2</b>
<b>6 Apparatus.....</b>	<b>2</b>
<b>7 Procedure.....</b>	<b>2</b>
7.1 Standard preparation.....	2
7.2 Preparation of test specimen.....	2
7.3 Analysis.....	3
7.4 Determination and calculation.....	3
7.4.1 Determination of curcumin.....	3
7.4.2 Calibration curve.....	3
7.4.3 Calculation of curcumin.....	3
<b>8 Test report.....</b>	<b>3</b>
<b>Annex A (informative) Example of test result.....</b>	<b>5</b>

(standards.iteh.ai)

[ISO 22195-2:2023](https://standards.iteh.ai/catalog/standards/sist/7a9344ab-3ceb-4624-b6fb-ab90f5aa359c/iso-22195-2-2023)

<https://standards.iteh.ai/catalog/standards/sist/7a9344ab-3ceb-4624-b6fb-ab90f5aa359c/iso-22195-2-2023>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 38, *Textiles*.

This second edition cancels and replaces the first edition (ISO 22195-2:2020), which has been technically revised. <https://standards.iteh.ai/catalog/standards/sist/7a9344ab-3eeb-4624-b6fb-ab90f5aa359c/iso-22195-2-2023>

The main changes are as follows:

- changed extraction solvent from co-solvent to single organic solvent;
- added GC-MS analysis method for the detection and qualification of index material.

A list of all parts in the ISO 22195 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

## Introduction

There is no doubt that dyeing plays the most important role in expressing the colour of clothes. Until the invention of synthetic dyes capable of expressing diverse colours, materials obtained from nature to dye fabric have been used. Typically, colourants were obtained from plants or various materials were extracted from minerals or insects. When dyeing fabrics using materials derived from these natural substances, it becomes necessary to identify which substances the colourant was derived from. In other words, there has been a demand to confirm whether a fabric is dyed using a natural substance.

A test method is developed to identify which types of natural substances have been used.

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

[ISO 22195-2:2023](https://standards.iteh.ai/catalog/standards/sist/7a9344ab-3ceb-4624-b6fb-ab90f5aa359c/iso-22195-2-2023)

<https://standards.iteh.ai/catalog/standards/sist/7a9344ab-3ceb-4624-b6fb-ab90f5aa359c/iso-22195-2-2023>



# Textiles — Determination of index ingredient from coloured textile —

## Part 2: Turmeric

### 1 Scope

This document specifies a test method which determines the index ingredient of chemicals in coloured fabric with turmeric.

### 2 Normative references

The following document is referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 3696, *Water for analytical laboratory use — Specification and test methods*

### 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

— ISO Online browsing platform: available at <https://www.iso.org/obp>

— IEC Electropedia: available at <https://www.electropedia.org/>

#### 3.1

##### **turmeric**

*Curcuma longa* Linne

type of rhizomatous herbaceous perennial plant of the ginger family, Zingiberaceae

Note 1 to entry: Plants are gathered annually for their rhizomes and propagated from some of those rhizomes in the following season. When not used fresh, the rhizomes are boiled and then dried in ovens, after which they are ground into a deep-orange- yellow powder.

#### 3.2

##### **coloured**

expressing of colours to textiles by dyeing or printing

#### 3.3

##### **natural colourant**

colourant obtained from plants, wood, rocks, soil, insects or any other thing existing on earth without any chemical reaction adopted before colouring of textiles

### 4 Principle

Natural colourants usually contain several chemical constituents. Depending on the type of natural colourant, each contains a distinctive chemical. This characteristic chemical remains in the fabric dyed

with natural colourant. Therefore, analysis of natural coloured fabrics by chromatography can detect characteristic chemicals depending on the kind of natural colourant.

NOTE On the other hand, if the index component curcumin is detected through this test method, it cannot be said that it is necessarily stained with turmeric alone. However, based on this principle, applying this test method to unknown coloured fabrics or textiles is useful to provide a minimum amount of information that can be used to confirm whether the fabric is coloured using turmeric.

## 5 Reagent

Unless otherwise specified, use only reagents of recognized HPLC grade.

5.1 **Water**, glass double distilled water or grade 2 water complying with ISO 3696.

5.2 **Methanol**.

5.3 **Acetonitrile**.

5.4 **Formic acid**, volume fraction of 30 %.

5.5 **Curcumin**, reference standard with percentage purity indication, e.g. 95 % or more.

The Safety Data Sheet for Chemicals (FISPQ) of each reagent should be observed.

## 6 Apparatus

6.1 **Analytical balance**, resolution at 0,001 g.

6.2 **Ultrasonic water bath**, to be set up at  $(30 \pm 2)$  °C.

6.3 **Borosilicate glass container with cap**, 50 ml.

6.4 **Membrane filter**, with 0,2 µm pore size.

6.5 **Liquid chromatograph (LC) with mass spectroscopy (MS)**.

6.6 **Gas chromatograph (GC) with mass spectroscopy (MS)**.

## 7 Procedure

### 7.1 Standard preparation

Stock solution of curcumin is prepared in methanol containing 1 000 mg/l.

### 7.2 Preparation of test specimen

Cut the test specimen into pieces of approximately 5 mm × 5 mm and approximately 1 g. Weigh it to the nearest 0,01 g, and then place it into the glass container (6.3).

Add 10 ml of methanol each into the other glass container and it poured to cut test specimen containing glass container. Place the glass container containing the test specimen into an ultrasonic bath at  $(30 \pm 2)$  °C for  $(20 \pm 1)$  min. Afterwards, let the extract cool down to room temperature. Dilute if necessary.



Filter about 1 ml of the diluted solution into a HPLC or GC vial using disposable syringe equipped with a membrane filter (6.4).

### 7.3 Analysis

The detection and qualification of curcumin is conducted using LC-MS (6.5) with ESI mass spectrometer or GC-MS (6.6).

The recommended chromatographic conditions are given in Annex A.

### 7.4 Determination and calculation

#### 7.4.1 Determination of curcumin

Comparison between analyses of standard and test specimen through 7.3 may show the result of existence of curcumin in test specimen.

Detection of curcumin may vary due to conditions of coloured test specimen. In this case, the amount of test specimen and extraction solution can be modified, and concentration of extracted solution can be adopted. The modified test specimen preparation conditions should be described in test result.

#### 7.4.2 Calibration curve

Calibration curves with standards of curcumin at 1 mg/l, 10 mg/l, 20 mg/l, 50 mg/l, and 100 mg/l are prepared with at least 5 calibration points.

NOTE Concentration ranges for the calibration standards are subject to change upon the need of each laboratory and equipment used.

For quantification, the calibration curve shall have a correlation coefficient greater than 0,995 ( $R^2$  greater than 0,990).

#### 7.4.3 Calculation of curcumin

Calculate the concentration of each alizarin in the test specimen, in mg/kg from Formula (1):

$$C_s = \frac{C_1}{W} \times f \times V \quad (1)$$

where

$C_s$  is the concentration of each curcumin in the test specimen, in mg/kg;

$C_1$  is the concentration of each curcumin in the test specimen solution, in mg/l;

$W$  is the mass of the test specimen, in g;

$f$  is the dilution factor;

$V$  is the final extraction volume, in ml.

## 8 Test report

The test report shall include the following information:

- a) a reference to this document, i.e. ISO 22195-2:2023;
- b) identification of the test specimen;

## ISO 22195-2:2023(E)

- c) the concentration of curcumin, in mg/kg
- d) conditions of chromatographic analysis;
- e) any deviation from the specified procedure in this document;
- f) date of the test.

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

ISO 22195-2:2023

<https://standards.iteh.ai/catalog/standards/sist/7a9344ab-3ceb-4624-b6fb-ab90f5aa359c/iso-22195-2-2023>