

SLOVENSKI STANDARD SIST EN 12365-2:2003

01-november-2003

GłUj Vbc˙c_cj ^Y˙Ë˙HYgb]˙U˙]b˙hYgb]˙b]˙lfU_cj]˙nU˙j fUłUzc_bUždc`_bU˙]b˙cVYýYbY ZJgUXY˙Ë˙&"XY˙.˙DfYg_i gbYʿa YhcXY˙nU˙cVfYa Yb^Yj Ub^Y˙n``]b]/g_c˙˙hU bc˙g]˙c

Building hardware - Gasket and weatherstripping for doors, windows, shutters and curtain walling - Part 2: Linear compression force test methods

Schlösser und Baubeschläge - Dichtungen und Dichtungenprofile für Fenster, Türen und andere Abschlüsse sowie vorgehängte Fassaden - Teil 2: Linearer Schließdruck, Prüfverfahren

(standards.iteh.ai)

Quincaillerie pour le bâtiment - Profilés d'étanchéité de vitrage et entre ouvrant et dormant pour portes, fermetures et façades rideaux - Partie 2: Méthodes d'essai pour déterminer la réaction linéique à la déformation

Ta slovenski standard je istoveten z: EN 12365-2:2003

ICS:

91.060.50 Vrata in okna Doors and windows

SIST EN 12365-2:2003 en,fr,de

SIST EN 12365-2:2003

iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>SIST EN 12365-2:2003</u> https://standards.iteh.ai/catalog/standards/sist/3831fa55-e137-440b-b44d-6c50a72c1c85/sist-en-12365-2-2003

EUROPEAN STANDARD NORME EUROPÉENNE EUROPÄISCHE NORM

EN 12365-2

September 2003

ICS 91.060.50; 91.190

English version

Building hardware - Gasket and weatherstripping for doors, windows, shutters and curtain walling - Part 2: Linear compression force test methods

Quincaillerie pour le bâtiment - Profilés d'étanchéité de vitrage et entre ouvrant et dormant pour portes, fenêtres, fermetures et façades rideaux - Partie 2: Méthodes d'essai pour déterminer la réaction linéique à la déformation

Schlösser und Baubeschläge - Dichtungen und Dichtungenprofile für Fenster, Türen und andere Abschlüsse sowie vorgehängte Fassaden - Teil 2: Linearer Schließdruck, Prüfverfahren

This European Standard was approved by CEN on 1 August 2003.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member (no its own language and notified to the Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Slovakia, Spain, Sweden, Switzerland and United Kingdom.

6c50a72c1c85/sist-en-12365-2-2003



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Cont	ents	page
Forew	ord	3
1	Scope	4
2	Normative references	4
3	Terms and definitions	4
4 4.1 4.2	Requirements Working range Linear compression force	4
5	Test apparatus	5
6 6.1 6.2 6.2.1 6.2.2 6.3	Test procedure Test measurements Test samples General Conditioning Preparation of test pieces	5 6 6
7 7.1 7.2 7.3 7.4	Test method Temperature and humidity ANDARD PREVIEW Determination of free height Compression test Standards.item.ai) Expression of results	6 6
8	Test report SIST EN 12365-2:2003 https://standards.iteh.ai/catalog/standards/sist/3831fa55-e137-440b-b44d-	7
Annex	A (informative) Examples of determining the working range of typical gaskets and weatherstripping	
Annex	B (informative) Typical test apparatus	12
Annex	C (informative) Flow chart of test procedure	13

Foreword

This document (EN 12365-2:2003) has been prepared by Technical Committee CEN/TC 33 "Doors, windows, shutters, building hardware and curtain walling", the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by March 2004, and conflicting national standards shall be withdrawn at the latest by March 2004.

EN 12365 – Building hardware – Gaskets and weatherstripping, consists of the following parts:

- Part 1: Performance requirements and classification;
- Part 2 : Linear compression test method;
- Part 3 : Deflection recovery test method;
- Part 4 : Recovery after accelerated ageing test method.

This European Standard is one of a series of European Standards for building hardware.

Annexes A, B and C are informative.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Morway, Portugal, Slovakia, Spain, Sweden, Switzerland and the United Kingdom.

Scope

This European Standard specifies the method to be used to select, prepare condition and test samples of gaskets or weatherstripping, to determine the force required to compress or deflect them by a predetermined amount to their minimum working width, under the conditions laid down for the test.

Examples of determining the working range of typical gaskets and weatherstripping are shown in annex A.

2 Normative references

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text, and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of this publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

EN 12365-1:2003, Building hardware — Gaskets and weatherstripping for doors, windows, shutters and curtain walling — Part 1: Perfomance requirements and classification

prEN 12519:2003, Windows and doors - Terminology PREVIEW

Terms and definitions (standards.iteh.ai) 3

For the purposes of this European Standard the terms and definitions given in EN 12365-1:2003 and prEN 12519:2003 aphtly: //standards.iteh.ai/catalog/standards 6c50a72c1c85/sist-en-12365-2-2003

Requirements

Working range

Examples of determining the working range of typical gaskets and weatherstripping are given in annex A.

Nine grades of working range are identified:

- grade 1: ≤ 1 mm;
- grade 2: > 1 mm to ≤ 2 mm;
- grade 3: > 2 mm to ≤ 4 mm;
- grade 4: > 4 mm to ≤ 6 mm;
- grade 5: > 6 mm to ≤ 8 mm;
- grade 6: > 8 mm to ≤ 10 mm;
- grade 7: > 10 mm to ≤ 15 mm;

- grade 8: > 15 mm to ≤ 30 mm;
- grade 9: > 30 mm.

4.2 Linear compression force

Nine grades of compression force are identified:

- grade 1: ≤ 10 N/m;
- grade 2: > 10 N/m to \leq 20 N/m;
- grade 3: > 20 N/m to $\leq 50 \text{ N/m}$;
- grade 4: > 50 N/m to \leq 100 N/m;
- grade 5: > 100 N/m to ≤ 200 N/m;
- grade 6: > 200 N/m to ≤ 500 N/m;
- grade 7: > 500 N/m to \leq 700 N/m;
- grade 8: > 700 N/m to \leq 1 000 N/m;
- grade 9: > 1 000 N/mTeh STANDARD PREVIEW (standards.iteh.ai)

5 Test apparatus

SIST EN 12365-2:2003

A typical test apparatus_{tal}isarshowni/inalannex|aB₆/sconsisting_of_7al4support for the gasket or weatherstripping which will allow it to be compressed or deflected in accordance with the users design concept.

The apparatus shall be fitted with a displacement dial gauge to measure the deflection of the test piece to its minimum working width.

A force measuring gauge shall be used to determine the force required to compress the test piece to its minimum working width.

6 Test procedure

6.1 Test measurements

Throughout this test method the following tolerances shall apply, unless otherwise stated:

— compression in millimetres (mm) : ± 0,05 mm;

force in newtons (N)
: better than 1 % of measured value;

— length in millimetres (mm) : ± 0.1 mm;

— temperature in degrees Celsius (°C) : ± 1 °C;

— relative humidity : ± 5 %.

6.2 Test samples

6.2.1 General

Wherever possible, the time between forming and testing shall not exceed 3 months. Every care shall be taken to ensure that samples arrive at the Test House in a pristine and fully testable condition.

NOTE This is to ensure that test pieces can be cut from any part of the sample without incurring more than the normal manufacturing variability.

6.2.2 Conditioning

Test samples shall be supplied in a condition truly representative of the standard shape.

Test samples shall be stored in the relaxed state in air at 23 °C ± 2 °C and a relative humidity 45 % to 55 % for not less than 24 h and not more than 6 days, prior to test.

6.3 Preparation of test pieces

Test pieces with a minimum length of 100 mm and a maximum length of 500 mm shall be cut from various positions within the sample submitted for test. Care shall be taken to ensure that the test pieces have a good smooth finish and are free of blemishes or other flaws.

7 Test method iTeh STANDARD PREVIEW

7.1 Temperature and humidity tandards.iteh.ai)

The standard laboratory temperature shall be either 230°C or 25 °C, in accordance with national practice. The standard laboratory humidity shall be 45 % relative humidity at 23 °C or 55 % relative humidity at 25 °C.

6c50a72c1c85/sist-en-12365-2-2003

7.2 Determination of free height

Measure the free height (a) of the test piece, without creating significant deformation, either before or after mounting in the test apparatus.

The free height shall be determined within a limit deviation of ± 0.05 mm.

If any results are beyond the permitted tolerance then new test pieces shall be obtained.

NOTE Suitable non-contact measuring equipment include a shadowgraph, a laser light beam device or a travelling microscope.

7.3 Compression test

Examples of determining the working range of typical gaskets and weatherstripping are given in annex A.

Set the displacement dial gauge linear to zero at the position of free height in order to measure the amount of compression or deflection.

Set the force measurement gauge to zero at the position of free height.

Compress the specimen through its working range to its minimum width (b), at a speed not exceeding 10 mm/min ± 1 mm/min. Remove immediately, the initial force and re-set the apparatus to zero.

Compress the test piece through its working range to its minimum width (b), at a speed not exceeding $10 \text{ mm/min} \pm 1 \text{ mm/min}$. Record the force after it has been maintained for $30 \text{ s} \pm 5 \text{ s}$.

Repeat the above test procedure on three specimens of the same gasket or weatherstripping.

7.4 Expression of results

The results of three tests shall be computed and the average value recorded in N per metre length to an accuracy of one decimal place.

8 Test report

A test report shall be prepared which identifies the specimen(s) and records the performance level achieved together with the details of tests used in the assessment of that performance.

The following information shall be included in the test report:

- a) place of test;
- b) person or body carrying out the assessment;
- c) product designation according to the manufacturers standard literature;
- d) test results and any measurements or observations made at the time of the test;
- e) date and signature.

(standards.iteh.ai)

<u>SIST EN 12365-2:2003</u> https://standards.iteh.ai/catalog/standards/sist/3831fa55-e137-440b-b44d-6c50a72c1c85/sist-en-12365-2-2003