



SLOVENSKI STANDARD
SIST ISO 5631-1:2023

01-julij-2023

Papir, karton in lepenka - Določanje barve z razpršeno odsevnostjo - 1. del: Pogoji osvetlitve v prostoru (C/2°)

Paper and board — Determination of colour by diffuse reflectance — Part 1: Indoor daylight conditions (C/2°)

iTeh STANDARD PREVIEW
(standards.iteh.ai)

Papier et carton — Détermination de la couleur par réflectance diffuse — Partie 1: Conditions d'éclairage intérieur de jour (C/2°)

<https://standards.iteh.ai/catalog/standards/sist/38d13865-963f-4f95-ac00-160166545/sist-iso-5631-1:2023>

Ta slovenski standard je istoveten z: ISO 5631-1:2022

ICS:

85.060

Papir, karton in lepenka

Paper and board

SIST ISO 5631-1:2023

en,fr,de

INTERNATIONAL
STANDARD

ISO
5631-1

Third edition
2022-07

**Paper and board — Determination of
colour by diffuse reflectance —**

**Part 1:
Indoor daylight conditions (C/2°)**

*Papier et carton — Détermination de la couleur par réflectance
diffuse —*

Partie 1: Conditions d'éclairage intérieur de jour (C/2°)

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST ISO 5631-1:2023

<https://standards.iteh.ai/catalog/standards/sist/38d13865-963f-4f95-ac00-726215fc53c5/sist-iso-5631-1-2023>



Reference number
ISO 5631-1:2022(E)

© ISO 2022

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST ISO 5631-1:2023

<https://standards.iteh.ai/catalog/standards/sist/38d13865-963f-4f95-ac00-726215fc53c5/sist-iso-5631-1-2023>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2022

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

| | |
|--|-----------|
| Foreword | iv |
| Introduction | v |
| 1 Scope | 1 |
| 2 Normative references | 1 |
| 3 Terms and definitions | 1 |
| 4 Principle | 3 |
| 5 Apparatus | 3 |
| 5.1 Reflectometer..... | 3 |
| 5.2 Reference standards..... | 4 |
| 5.3 Working standards..... | 4 |
| 6 Sampling and conditioning | 4 |
| 7 Preparation of test pieces | 4 |
| 8 Procedure | 5 |
| 9 Calculation | 5 |
| 9.1 CIE tristimulus values..... | 5 |
| 9.2 CIELAB coordinates..... | 5 |
| 9.3 Dispersion of the results..... | 6 |
| 10 Expression of results | 6 |
| 11 Precision | 6 |
| 12 Test report | 6 |
| Annex A (normative) Spectral characteristics of reflectometers for determining tristimulus values | 8 |
| Bibliography | 13 |

ISO 5631-1:2022(E)**Foreword**

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

The committee responsible for this document is ISO/TC 6, *Paper, board and pulps*.

This third edition cancels and replaces the second edition (ISO 5631-1:2015), of which it constitutes a minor revision. The changes are as follows:

- update of the CIE and joint ISO/CIE Normative and Bibliographic references to current versions.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

The colour of an object can be uniquely characterized by means of a triplet of colour coordinates such as the CIE tristimulus values or the CIELAB 1976 L^* , a^* , b^* coordinates for a specified CIE illuminant and CIE standard observer.

Apart from the optical properties of the sample, the values of such coordinates depend upon the conditions of measurement, particularly the spectral and geometric characteristics of the instrument used. This document should therefore be read in conjunction with ISO 2469.

This document describes the measurement and description of colour in terms of the CIE illuminant C and the CIE 1931 (2°) standard observer. The other parts of the ISO 5631 series describe measurements and calculations carried out in an analogous manner using either the CIE standard illuminant D65 and the CIE 1964 (10°) standard observer or the CIE illuminant D50 and the CIE 1931 (2°) standard observer.

The choice of illuminant conditions is important when determining the colour coordinates of white papers containing a fluorescent whitening agent. In ISO 5631-2, the UV content of the illumination is much higher, approximating UV levels encountered in outdoor viewing conditions.

ISO 5631-3 describes the measurement and description of colour in terms of the CIE illuminant D50 and the CIE 1931 (2°) standard observer. This method is especially applicable to graphic arts situations since these illuminant/observer conditions are used within the graphic arts industry.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST ISO 5631-1:2023](https://standards.iteh.ai/catalog/standards/sist/38d13865-963f-4f95-ac00-726215fc53c5/sist-iso-5631-1-2023)

<https://standards.iteh.ai/catalog/standards/sist/38d13865-963f-4f95-ac00-726215fc53c5/sist-iso-5631-1-2023>

Paper and board — Determination of colour by diffuse reflectance —

Part 1: Indoor daylight conditions (C/2°)

1 Scope

This document specifies a method for measuring the colour of paper and board by the diffuse reflectance method with the elimination of specular gloss.

This document is not applicable to coloured papers or boards which incorporate fluorescent dyes or pigments. It may be used to determine the colour of papers or boards which contain fluorescent whitening agents provided the UV content of the illumination on the test piece has been adjusted to conform to that in the CIE illuminant C, using a fluorescent reference standard that fulfils the requirements for international fluorescent reference standards of level 3 (IR3) as prescribed by ISO 2469 with an assigned ISO brightness value provided by an authorized laboratory, as described in ISO 2470-1.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 186, *Paper and board — Sampling to determine average quality*

ISO 2469, *Paper, board and pulps — Measurement of diffuse radiance factor (diffuse reflectance factor)*

ISO 2470-1, *Paper, board and pulps — Measurement of diffuse blue reflectance factor — Part 1: Indoor daylight conditions (ISO brightness)*

ASTM E308, *Standard Practice for Computing the Colors of Objects by Using the CIE System*

CIE Publication 015:2018, *Colorimetry*, 4th ed.

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

ISO 5631-1:2022(E)

3.1 radiance factor

 β

ratio of the radiance of a surface element of a body in the direction delimited by a given cone, with its apex at the surface element, to that of the perfect reflecting diffuser under the same conditions of illumination

Note 1 to entry: For fluorescent (luminescent) materials, the total radiance factor, β , is the sum of two portions, the reflected radiance factor, β_R , and the luminescent radiance factor, β_L , so that $\beta = \beta_R + \beta_L$.

For non-fluorescent materials, the reflected radiance factor, β_R , is numerically equal to the reflectance factor, R .

3.2 intrinsic radiance factor

 β_∞

radiance factor (3.1) of a layer or pad of material thick enough to be opaque, such that increasing the thickness of the pad by doubling the number of sheets results in no change in the measured radiance factor

Note 1 to entry: The intrinsic radiance factor is often expressed as a percentage.

3.3 reflectance factor

 R

ratio of the radiation reflected by a surface element of a body in the direction delimited by a given cone, with its apex at the surface element to that of the perfect reflecting diffuser under the same conditions of illumination

Note 1 to entry: The ratio is often expressed as a percentage.

Note 2 to entry: The reflectance factor is influenced by the backing if the body is translucent.

3.4 intrinsic reflectance factor

 R_∞

reflectance factor (3.3) of a layer or pad of material thick enough to be opaque, such that increasing the thickness of the pad by doubling the number of sheets results in no change in the measured reflectance factor

Note 1 to entry: The reflectance factor of a non-opaque sheet is dependent on the background and is not a material property.

3.5 tristimulus values

 X, Y, Z

amount of the three reference colour stimuli, in a given chromatic system, required to match the colour of stimulus considered

Note 1 to entry: In this document, the CIE illuminant C and the CIE 1931 (2°) standard observer are used to define the trichromatic system.

Note 2 to entry: No subscript is applied to conform to the CIE convention that tristimulus values have no subscript when the CIE 1931 (2°) standard observer is used [the subscript 10 is applied for tristimulus values that are obtained using the CIE 1964 (10°) standard observer].

3.6

CIELAB colour space

three-dimensional, approximately uniform colour space, produced by plotting, in rectangular coordinates L^* , a^* , b^* , quantities defined by the formulae given in [Clause 9](#)

Note 1 to entry: The quantity, L^* , is a measure of the lightness of the test piece, where $L^* = 0$ corresponds to black and $L^* = 100$ is defined by the perfect reflecting diffuser. Visually, the quantities a^* and b^* represent respectively the red-green and yellow-blue axes in colour space, such that

- $+a^*$ is a measure of the degree of redness of the test piece,
- $-a^*$ is a measure of the degree of greenness of the test piece,
- $+b^*$ is a measure of the degree of yellowness of the test piece, and
- $-b^*$ is a measure of the degree of blueness of the test piece.

If both a^* and b^* are equal to zero, the test piece is achromatic.

4 Principle

The light reflected from a sample under specified conditions is analysed either by a tristimulus-filter colorimeter or by an abridged spectrophotometer, and the colour coordinates are then calculated for $C/2^\circ$ conditions.

5 Apparatus

5.1 Reflectometer

5.1.1 Reflectometer, having the geometric, spectral and photometric characteristics described in ISO 2469, and calibrated in accordance with the provisions of ISO 2469.

If materials containing fluorescent whitening agents are to be measured, the reflectometer shall be equipped with a radiation source having an adequate UV content control, adjusted to a UV condition corresponding to the C illuminant by the use of a reference standard, as described in ISO 2470-1.

5.1.2 In the case of a filter reflectometer, a set of filters that, in conjunction with the optical characteristics of the basic instrument, give overall responses equivalent to the CIE tristimulus values X , Y and Z of the CIE 1931 standard colorimetric system of the test piece evaluated for the CIE illuminant C.

In the case of a filter reflectometer, the radiation falling upon the test piece shall have a UV content corresponding to that of the CIE illuminant C.

5.1.3 In the case of an abridged spectrophotometer, the instrument shall have a function that permits calculation of the CIE tristimulus values X , Y and Z of the CIE 1931 standard colorimetric system of the test piece evaluated for the CIE illuminant C using the weighting functions given in [Annex A](#) where the [Tables A.1](#) and [A.2](#) are used for instruments without bandpass correction and [Tables A.3](#) and [A.4](#) are used for instruments with bandpass correction.

In the case of an abridged spectrophotometer, the instrument shall have an adjustable filter with a cut-off wavelength of 395 nm or some other equivalent system, and this filter shall be adjusted or the system shall be calibrated with the help of the fluorescent reference standard ([5.2.2](#)), so that the UV content of the illumination falling upon the sample corresponds to that of the CIE illuminant C.