



Designation: **C805/C805M—08 C805/C805M – 13**

Standard Test Method for Rebound Number of Hardened Concrete¹

This standard is issued under the fixed designation C805/C805M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope*

- 1.1 This test method covers the determination of a rebound number of hardened concrete using a spring-driven steel hammer.
- 1.2 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.
- 1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

- C42/C42M Test Method for Obtaining and Testing Drilled Cores and Sawed Beams of Concrete
- C125 Terminology Relating to Concrete and Concrete Aggregates
- C670 Practice for Preparing Precision and Bias Statements for Test Methods for Construction Materials
- E18 Test Methods for Rockwell Hardness of Metallic Materials

3. Terminology

3.1 Definitions:

- 3.1.1 For definitions of terms used in this test method, refer to Terminology C125.

4. Summary of Test Method

- 4.1 A steel hammer impacts, with a predetermined amount of energy, a steel plunger in contact with a surface of concrete, and the distance that the hammer rebounds is measured.

5. Significance and Use

5.1 This test method is applicable to assess the in-place uniformity of concrete, to delineate ~~regions in a structure of poorer quality or deteriorated concrete,~~ variations in concrete quality throughout a structure, and to estimate in-place ~~strength.~~ strength if a correlation is developed in accordance with 5.4.

5.2 For a given concrete mixture, the rebound number is affected by factors such as moisture content of the test surface, the type of form material or type of finishing used in construction of the surface to be tested, vertical distance from the bottom of a concrete placement, and the depth of carbonation. These factors need to be considered in interpreting rebound numbers.

5.3 Different instruments of the same nominal design may give rebound numbers differing from 1 to 3 units. Therefore, tests should be made with the same instrument in order to compare results. If more than one instrument is to be used, perform comparative tests on a range of typical concrete surfaces so as to determine the magnitude of the differences to be expected in the readings of different instruments.

¹ This test method is under the jurisdiction of ASTM Committee C09 on Concrete and Concrete Aggregates and is the direct responsibility of Subcommittee C09.64 on Nondestructive and In-Place Testing.

Current edition approved Aug. 1, 2008; Jan. 1, 2013. Published September 2008; January 2013. Originally approved in 1975. Last previous edition approved in 2002 as C805—02; C805—08. DOI: 10.1520/C0805—C0805M-08-10.1520/C0805_C0805M-13.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard

5.4 Relationships between rebound number and concrete strength that are provided by instrument manufacturers shall be used only to provide indications of relative concrete strength at different locations in a structure. To use this test method to estimate strength, it is necessary to establish a relationship between strength and rebound number for a given concrete mixture and given apparatus (see [Note 1](#)). Establish the relationship by correlating rebound numbers measured on the structure with the measured strengths of cores taken from corresponding locations (see [Note 2](#)). At least two replicate cores shall be taken from at least six locations with different rebound numbers. Select test locations so that a wide range of rebound numbers in the structure is obtained. Obtain, ~~moisture condition, prepare,~~ and test cores in accordance with Test Method [C42/C42M](#). If the rebound number is affected by the orientation of the instrument during testing, the strength relationship is applicable for the same orientation as used to obtain the correlation data (see [Note 3](#)). Locations where strengths are to be estimated using the developed correlation shall have similar surface texture and shall have been exposed to similar conditions as the locations where correlation cores were taken. The functionality of the rebound hammer shall have been verified in accordance with 6.4 before making the correlation measurements.

NOTE 1—See ACI 228.1R³ for additional information on developing the relationship and on using the relationship to estimate in-place strength.

~~5.3 For a given concrete mixture, the rebound number is affected by factors such as moisture content of the test surface, the method used to obtain the test surface (type of form material or type of finishing), vertical distance from the bottom of a concrete placement, and the depth of carbonation. These factors need to be considered in interpreting rebound numbers.~~

NOTE 2—The use of molded test specimens to develop a correlation may not provide a reliable relationship because the surface texture and depth of carbonation of molded specimens are not usually representative of the in-place concrete.

~~5.4 Different hammers of the same nominal design may give rebound numbers differing from 1 to 3 units. Therefore, tests should be made with the same hammer in order to compare results. If more than one hammer is to be used, perform tests on a range of typical concrete surfaces so as to determine the magnitude of the differences to be expected.~~

NOTE 3—The use of correction factors to account for instrument orientation may reduce the reliability of strength estimates if the correlation is developed for a different orientation than used for testing.

5.5 This test method is not suitable as the basis for acceptance or rejection of concrete.

6. Apparatus

6.1 *Rebound Hammer*, consisting of a spring-loaded steel hammer that when released strikes a steel plunger in contact with the concrete surface. The spring-loaded hammer must travel with a consistent and reproducible velocity. The rebound distance of the steel hammer from the steel plunger is measured on a linear scale attached to the frame of the instrument.

NOTE 4—Several types and sizes of rebound hammers are commercially available to accommodate testing of various sizes and types of concrete construction.

6.1.1 The manufacturer shall supply rebound number correction factors for instruments that require such a factor to account for the orientation of the instrument during a test. The correction factor is permitted to be applied automatically by the instrument. The manufacturer shall keep a record of test data used as the basis for applicable correction factors.

6.2 *Abrasive Stone*, consisting of medium-grain texture silicon carbide or equivalent material.

6.3 *Test Verification Anvil*, approximately 150-mm [6-in.] diameter by 150-mm [6-in.] high cylinder made of tool steel with an impact area hardened to 66 ± 2 HRC as measured by Test Methods used to check the operation of the rebound hammer. ~~E18.~~ An instrument guide is provided to center the rebound hammer over the impact area and keep the instrument perpendicular to the surface. The anvil shall be constructed so that it will result in a rebound number of at least 75 for a properly operating instrument (see [Note 5](#)). The manufacturer of the rebound hammer shall stipulate the type of verification anvil to be used and shall provide the acceptable range of rebound numbers for a properly operating instrument. The anvil manufacturer shall indicate how the anvil is to be supported for verification tests of the instrument, and shall provide instructions for visual inspection of the anvil surface for surface wear.

NOTE 5—A suitable anvil has included an approximately 150 mm [6 in.] diameter by 150 mm [6 in.] tall steel cylinder with an impact area hardened to an HRC hardness value of 64 to 68 as measured by Test Methods [E18](#).

6.4 *Verification*—Rebound hammers shall be serviced and verified annually and whenever there is reason to question their proper operation. Verify the functional operation of a rebound hammer using the test verification anvil described in 6.3. During verification, support the test anvil on a bare concrete floor or slab. The manufacturer shall report the rebound number to be obtained by a properly operating instrument when tested on an anvil of specified hardness: anvil as instructed by the anvil manufacturer.

NOTE 6—Typically, a rebound hammer will properly operating rebound hammer and a properly designed anvil should result in a rebound number of 80 ± 2 when tested on the anvil described in about 80. 6.3. The test anvil needs to be supported on a rigid base as stated by the anvil manufacturer to obtain reliable rebound numbers. Verification on the test anvil does not guarantee that the hammer will yield repeatable data: rebound numbers at other

³ ACI 228.1R-95; 228.1R, "In-Place Methods to Estimate Concrete Strength," American Concrete Institute (ACI), P.O. Box 9094, Farmington Hills, MI 48333-9094, <http://www.concrete.org>.