



Designation: G160 – 12

Standard Practice for Evaluating Microbial Susceptibility of Nonmetallic Materials By Laboratory Soil Burial¹

This standard is issued under the fixed designation G160; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This practice is limited to the method of conducting an evaluation of a nonmetallic material's microbiological susceptibility when in contact with the natural environment of the soil under use conditions. This practice is intended for use on solid material test specimens that are no larger than approximately 2 cm (0.79 in.) thick and 100 cm² (15.5 in.²) or on film forming materials such as coatings which may be tested in the form of films at least 50 by 50 mm (2 by 2 in.) in size. This practice may be applied to articles that do not spend the majority of their service life in soil.

1.2 A wide variety of properties may be affected by microbial attack depending on material or item characteristics. Standard methods (where available) should be used for each different property to be evaluated. This practice does not attempt to enumerate all of the possible properties of interest nor specify the most appropriate test for those properties. Test methods must, however, be appropriate to the material being tested.

1.3 Materials intended for use in soil burial applications are often subjected to periods of exposure to solar radiation and other elements of weather for some time before they are buried. Because these exposures may alter the ability of a material to resist the effects of soil-borne microorganisms, it is recommended that this practice be combined with appropriate environmental exposures (for example, solar simulating weathering devices, the hydrolytic effects of extended aqueous contact, or extraneous nutrients) or fabrication into articles (for example, adhesive bonding of seams) which may promote microbiological susceptibility during the service life of the material.

1.4 The values stated in SI units are to be regarded as standard. The values given in parentheses are provided for information purposes only.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the*

responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

2. Referenced Documents

2.1 *ASTM Standards:*²

G154 Practice for Operating Fluorescent Ultraviolet (UV) Lamp Apparatus for Exposure of Nonmetallic Materials

G155 Practice for Operating Xenon Arc Light Apparatus for Exposure of Non-Metallic Materials

3. Significance and Use

3.1 These results may be used to compare the susceptibility of materials when exposed to this test procedure.

3.2 Microbiological susceptibility may be reflected by a number of changes including staining, weight loss, or reduction in tensile or flexural strength.

3.3 This practice may be considered an inoculation with a mixed culture of fungi and bacteria.

4. Soil

4.1 *Composition*—Soil shall be composed of equal parts of fertile topsoil (soil with a high clay content should not be used), well-rotted and shredded horse manure, and coarse sand (10 to 40 mesh).

4.2 *Mixing*—The soil composition of 4.1 should be prepared by simple mixing and sifting through ¼-in. mesh screen.

4.3 *Aging*—The mixture is aged for three months and resifted twice at four-week intervals during the three months. After three months, a viability control of untreated cotton cloth, 400 to 475 g/m² (12 to 14 oz/yd²), buried in the soil shall have a tensile strength loss of at least 50 % after five days.

NOTE 1—The soil mixture may be used for sequential tests as long as the cotton cloth control degrades within the specified time period.

4.4 *pH*—The soil shall have a pH between 6.5 to 7.5, checked periodically, and maintained by the addition of ground

¹ This practice is under the jurisdiction of Committee G03 on Weathering and Durability and is the direct responsibility of Subcommittee G03.04 on Biological Deterioration.

Current edition approved Nov. 1, 2012. Published January 2013. Originally approved in 1998. Last previous edition approved in 2009 as G160 – 03(2009). DOI: 10.1520/G0160-12.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.