

# INTERNATIONAL STANDARD

**ISO**  
**3167**

Third edition  
1993-06-15

---

---

## Plastics — Multipurpose test specimens

*Plastiques — Éprouvettes à usages multiples*

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[ISO 3167:1993](https://standards.iteh.ai/catalog/standards/sist/6345c770-9264-42c1-9e60-d1c5e29d2a8e/iso-3167-1993)

<https://standards.iteh.ai/catalog/standards/sist/6345c770-9264-42c1-9e60-d1c5e29d2a8e/iso-3167-1993>



Reference number  
ISO 3167:1993(E)

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 3167 was prepared by Technical Committee ISO/TC 61, *Plastics*, Sub-Committee SC 2, *Mechanical properties*.

This third edition cancels and replaces the second edition (ISO 3167:1983), which has been extended to introduce the preferred specimen type A with a smaller radius, in order to facilitate the testing of parts with simple machining for a variety of tests.

With respect to existing moulds, the specimen type described in the second edition is included as type B. It may be possible to eliminate type B at the next revision of this International Standard.

The designations of dimensions are harmonized with those of the International Standards for testing which relate to a multipurpose test specimen, in accordance with ISO 31.

Annexes A and B of this International Standard are for information only.

© ISO 1993

All rights reserved. No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization  
Case Postale 56 • CH-1211 Genève 20 • Switzerland

Printed in Switzerland

# Plastics — Multipurpose test specimens

## 1 Scope

**1.1** This International Standard specifies requirements relating to multipurpose test specimens for plastic moulding materials intended for processing by injection or direct compression moulding.

**1.2** Specimens of types A and B are tensile test specimens, from which with simple machining, specimens for a variety of other tests can be taken (see annex A). Because they have such wide utility, these tensile specimens are referred to in this International Standard as multipurpose test specimens.

**1.3** The principal advantage of a multipurpose test specimen is that it allows all the test methods mentioned in annex A to be carried out on the basis of comparable mouldings. Consequently, the properties measured are coherent as all are measured with specimens in the same state. In other words, it can be expected that test results for a given set of specimens will not vary appreciably due to unintentionally different moulding conditions. On the other hand, if desired, the influence of moulding conditions and/or different states of the specimens can be assessed without difficulty for all of the properties measured.

**1.4** For quality-control purposes, the multipurpose test specimen may serve as a convenient source of further specimens not readily available. Furthermore, the fact that only one mould is required may be advantageous.

**1.5** The use of multipurpose test specimens shall be agreed upon by the interested parties, because there may be significant differences between properties of the multipurpose test specimens and those specified in the relevant test methods.

## 2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this International Standard. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 293:1986, *Plastics — Compression moulding test specimens of thermoplastic materials.*

ISO 294:—<sup>1)</sup>, *Plastics — Injection moulding of test specimens of thermoplastic materials.*

ISO 295:1991, *Plastics — Compression moulding of test specimens of thermosetting materials.*

ISO 2818:—<sup>2)</sup>, *Plastics — Preparation of test specimens by machining.*

## 3 Dimensions of test specimens

For the purposes of this International Standard, the preferred multipurpose test specimen is the tensile specimen type A according to figure 1. This can be made suitable for a variety of other tests by simple cutting, because the length  $l_1$  of its narrow parallel portion is  $80 \text{ mm} \pm 2 \text{ mm}$ .

## 4 Preparation of test specimens

### 4.1 Moulding of multipurpose test specimens

The specimens shall be moulded as specified in ISO 293, ISO 294 and ISO 295, as appropriate, and

1) To be published. (Revision of ISO 294:1975)

2) To be published. (Revision of ISO 2818:1980)

under conditions defined for the material under examination.

Strict control of moulding conditions is essential to ensure that all test specimens in a set are actually in the same state.

## 4.2 Machining of test specimens

**4.2.1** Machining of specimens from the multipurpose test specimens shall be performed either as specified in ISO 2818, or as agreed upon by the interested parties. The surface of the central parallel-sided portion of the test specimens shall remain as moulded.

**4.2.2** Test specimens having a width of 10 mm shall be cut symmetrically from the central parallel-sided portion of the multipurpose test specimen.

**4.2.3** For test specimens longer than 80 mm, the broad ends of the multipurpose test specimen type A (or type B for test specimens longer than 60 mm) shall be machined to the width of the central parallel-sided portion. During the machining operation, care shall be taken to avoid any damage to the moulded surfaces of the central portion. The width of the machined portions of the specimen shall be not less than

that of the central parallel-sided portion, but may exceed the width of the latter by not more than 0,2 mm.

## 5 Report on preparation of test specimens


The report shall contain the following information:

- a) reference to this International Standard;
- b) indication of specimen type (A or B);
- c) type, source, manufacturer's code, grade and form, including history, etc. if known;
- d) method of moulding and the conditions used;
- e) method of machining and the conditions used;
- f) number of test specimens;
- g) the standard atmosphere for conditioning, plus any special conditioning treatment if required by the standard for the material or product concerned;
- h) date of preparation.

(standards.iteh.ai)

ISO 3167:1993

<https://standards.iteh.ai/catalog/standards/sist/6345c770-9264-42c1-9e60-d1c5e29d2a8e/iso-3167-1993>



Dimensions in millimetres

Specimen type	A	B
$l_3$ Overall length		$\geq 150$ <sup>1)</sup>
$l_1$ Length of narrow parallel-sided portion	$80 \pm 2$	$60,0 \pm 0,5$
$r$ Radius	20 to 25	$\geq 60$ <sup>2)</sup>
$l_2$ Distance between broad parallel-sided portions	104 to 113 <sup>3)</sup>	106 to 120 <sup>3)</sup>
$b_2$ Width at ends		$20,0 \pm 0,2$
$b_1$ Width of narrow portion		$10,0 \pm 0,2$
$h$ Thickness		$4,0 \pm 0,2$

1) For some materials, the length of the tabs may need to be extended (e.g.  $l_3 = 200$  mm) to prevent breakage or slippage in the jaws of the testing machine.

ISO 3167:1993

<https://standards.iteh.ai/catalog/standards/sist/6345c770-9264-42c1-9e60-d1c5e29d2a8e/iso-3167-1993>

$$2) \quad r = \frac{(l_2 - l_1)^2 + (b_2 - b_1)^2}{4(b_2 - b_1)}$$

3) Resulting from  $l_1$ ,  $r$ ,  $b_1$  and  $b_2$ , but within the indicated tolerance.

Figure 1 — Multipurpose test specimen types A and B

## Annex A (informative)

### Recommended applications for multipurpose test specimens or parts thereof

Method	Reference <sup>1)</sup>	Type of specimen and/or dimensions mm
Tensile test	ISO 527-2	A or B
Tensile creep test	ISO 899	A or B
Flexural test	ISO 178	80 × 10 × 4
Flexural creep test	ISO 6602	80 × 10 × 4
Compressive test	ISO 604	(10 to 40) × 10 × 4
Impact strength — Charpy	ISO 179	80 × 10 × 4
Impact strength — Izod	ISO 180	80 × 10 × 4
Impact strength — tensile	ISO 8256	80 × 10 × 4
Temperature of deflection under load	ISO 75	(110 or 80) × 10 × 4
Vicat softening temperature	ISO 306	10 × 10 × 4
Hardness, ball indentation	ISO 2039-1	(≥ 20) × 20 × 4
Environmental stress cracking	ISO 4599 } ISO 4600 }	A or B or 80 × 10 × 4
Density	ISO 1183, method A	30 × 10 × 4
Oxygen index	ISO 4589	80 × 10 × 4
Comparative tracking index (CTI)	IEC 112	> 15 × 15 × 4
Electrolytic corrosion	IEC 426	30 × 10 × 4
Linear expansion		> 30 × 10 × 4

1) See annex B.

## Annex B

(informative)

### Bibliography

- [1] ISO 75:1987, *Plastics and ebonite — Determination of temperature of deflection under load.*
- [2] ISO 178:1993, *Plastics — Determination of flexural properties.*
- [3] ISO 179:1993, *Plastics — Determination of Charpy impact strength.*
- [4] ISO 180:1993, *Plastics — Determination of Izod impact strength.*
- [5] ISO 306:1987, *Plastics — Thermoplastic materials — Determination of Vicat softening temperature.*
- [6] ISO 527-2:1993, *Plastics — Determination of tensile properties — Part 2: Test conditions for moulding and extrusion plastics.*
- [7] ISO 604:1973, *Plastics — Determination of compressive properties.*
- [8] ISO 899:1981, *Plastics — Determination of tensile creep.*
- [9] ISO 1183:1987, *Plastics — Methods for determining the density and relative density of non-cellular plastics.*
- [10] ISO 2039-1:1987, *Plastics — Determination of hardness — Part 1: Ball indentation method.*
- [11] ISO 4589:1984, *Plastics — Determination of flammability by oxygen index.*
- [12] ISO 4599:1986, *Plastics — Determination of resistance to environmental stress cracking (ESC) — Bent strip method.*
- [13] ISO 4600:1992, *Plastics — Determination of environmental stress cracking (ESC) — Ball or pin impression method.*
- [14] ISO 6602:1985, *Plastics — Determination of flexural creep by three-point loading.*
- [15] ISO 8256:1990, *Plastics — Determination of tensile-impact strength.*
- [16] ISO 10350:—<sup>3)</sup>, *Plastics — Acquisition and presentation of comparable single-point data.*
- [17] IEC 112:1979, *Method for determining the comparative and the proof tracking indices of solid insulating materials under moist conditions.*
- [18] IEC 426:1973, *Determining electrolytic corrosion with insulating materials.*

3) To be published.

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

ISO 3167:1993

<https://standards.iteh.ai/catalog/standards/sist/6345c770-9264-42c1-9e60-d1c5e29d2a8e/iso-3167-1993>

---

---

**UDC 678.073:620.115**

**Descriptors:** plastics, thermoplastic resins, moulding materials, tests, test specimens, specimen preparation.

Price based on 5 pages

---

---