

PROOF/ÉPREUVE

iTeh Standards (https://standards.iteh.ai) Document Preview

ISO/PRF 12224-2

https://standards.iteh.ai/catalog/standards/iso/bbb53719-69b7-4bab-9dff-d5b5e891a7dc/iso-prf-12224-2



COPYRIGHT PROTECTED DOCUMENT

© ISO 2024

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office CP 401 • Ch. de Blandonnet 8 CH-1214 Vernier, Geneva Phone: +41 22 749 01 11 Email: copyright@iso.org Website: <u>www.iso.org</u>

Published in Switzerland

PROOF/ÉPREUVE © ISO 2024 – All rights reserved

Contents

Forew	ordiv
1	Scope 1
2	Normative references 1
3	Terms and definitions 1
4	Principle1
5	Apparatus1
6	Materials2
7	Procedure 2
	7.1 General
	7.2 Method A
	7.3 Method B
	7.4 Method C
8	Expression of results for both methods 3
9	Test report 3

iTeh Standards (https://standards.iteh.ai) Document Preview

<u>ISO/PRF 12224-2</u>

https://standards.iteh.ai/catalog/standards/iso/bbb53719-69b7-4bab-9dff-d5b5e891a7dc/iso-prf-12224-2

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 44, *Welding and allied processes*, Subcommittee SC 12, *Soldering and brazing materials*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 121, *Welding and allied processes*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This second edition cancels and replaces the first edition (ISO 12224-2:1997), which has been technically revised. $\underline{ISO/PRF|2224-2}$

https://standards.iteh.ai/catalog/standards/iso/bbb53719-69b7-4bab-9dff-d5b5e891a7dc/iso-prf-12224-2 The main changes are as follows:

- <u>5.2</u>: quartz glass crucible added;
- <u>5.6</u>: Bunsen burner with tripod added;
- <u>7.4</u>: method C with Bunsen burner added.

A list of all parts in the ISO 12224 series can be found on the ISO website.

should be Any feedback or questions on this document directed to the user's standards body. А complete listing of these bodies found national can be at www.iso.org/members.html. Official interpretations of ISO/TC 44 documents, where they exist, are available from this page: https://committee.iso.org/sites/tc44/home/interpretation.html.

Solder wire, solid and flux-cored — Specification and test methods —

Part 2: **Determination of flux content**

1 Scope

This document specifies two methods for the determination of the flux content of a sample flux-cored solder wire.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 9453, Soft solder alloys — Chemical compositions and forms

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

ISO Online browsing platform: available at https://www.iso.org/obp

— IEC Electropedia: available at <u>https://www.electropedia.org/</u>

4 Principle

A known mass of the sample of flux-cored solder wire is melted, separated from the flux medium and weighed. The flux content is calculated and expressed as a percentage by mass of the original wire.

5 Apparatus

The usual laboratory apparatus and, in particular, the following shall be used.

- **5.1 Balance**, having a measurement uncertainty of ±0,001 g.
- 5.2 Porcelain or quartz glass crucible, capacity 30 ml.
- **5.3** Scraper, stainless steel.
- 5.4 Crucible tongs.

5.5 Solder bath, containing solder according to ISO 9453 maintained at a temperature of (50 ± 5) °C above the liquidus temperature of the wire under test.

PROOF/ÉPREUVE © ISO 2024 – All rights reserved

5.6 Bunsen burner with tripod.

- 5.7 Tissues.
- **5.8 Glass beaker**, heat resistant borosilicate glass, 100 ml to 150 ml.

6 Materials

Use only materials of recognized analytical grade and only distilled water or water of equivalent purity.

6.1 **Degreasing solvent**, such as propan-2-ol or the solvent recommended by the manufacturer.

6.2 Glycerol.

7 Procedure

7.1 General

Clean the sample length of the flux-cored solder wire under test with a tissue (5.7) soaked in the degreasing solvent (6.1). Follow either method A, method B or method C, as shown in the following subclauses.

7.2 Method A

Carry out the test in duplicate.

iTeh Standards

Using the balance (5.1), weigh (50 ± 5) g of the cleaned wire to 0,001 g. Record the mass of the sample, m_w . Form the sample into a ball and transfer it to the cleaned crucible (5.2) or the beaker (5.8).

Clean the surface of the molten solder in the solder bath (5.5) by means of the scraper (5.3).

Holding the crucible or beaker with the tongs (5.4), partially immerse it in the solder bath (5.5), maintained at a temperature (50 ± 5) °C above the liquidus temperature of the wire under test. Turn the crucible or beaker gently until the solder has melted into one pellet. Leave the crucible or beaker immersed in the solder bath for 10 s to 15 s after the solder has melted.

Remove the crucible or beaker from the solder bath and allow it to cool until the solder has just solidified. Pour off as much flux as possible while the flux remains warm.

Remove the pellet from the crucible or beaker. Clean it thoroughly with degreasing solvent (6.1) to remove all traces of flux. Dry the pellet with a clean tissue (5.7). Using the balance (5.1), weigh the dry pellet to a constant mass, to 0,001 g. Record the mass of the pellet, m_s .

7.3 Method B

Carry out the test in duplicate.

Using the balance (5.1), weigh (30 ± 2) g of the cleaned wire to 0,001 g. Record the mass of the sample, m_{w} .

Transfer the solder wire to the beaker (5.8) with sufficient glycerol (6.2) to cover the sample (approximately 50 ml of glycerol).

Clean the surface of the molten solder in the solder bath (5.5) by means of the scraper (5.3).

Holding the beaker with the tongs (5.4), partially immerse it in the solder bath (5.5), maintained at a temperature (50 \pm 5) °C above the liquidus temperature of the wire under test. Turn the beaker until the solder has melted into one pellet. Leave the beaker immersed in the solder bath for 10 s to 15 s after the solder has melted, while turning gently.

PROOF/ÉPREUVE © ISO 2024 – All rights reserved