



Designation: D2308 – 07 (Reapproved 2013)

Standard Specification for Thermoplastic Polyethylene Jacket for Electrical Wire and Cable¹

This standard is issued under the fixed designation D2308; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers a thermoplastic jacketing compound for 2 to 35 kV wire and cable, of at least 0.030 in. (0.76 mm) nominal thickness, consisting substantially of pigmented polyethylene.

1.2 In many instances the jacket material cannot be tested unless it has been formed around a conductor or cable. Therefore, tests done on jacketed wire and cable in this specification are solely to determine the relevant property of the jacket material and not to test the jacketed conductor or completed cable.

1.3 Whenever two sets of values are presented, in different units, the values in the first set are the standard, while those in parentheses are for information only.

2. Referenced Documents

2.1 *ASTM Standards*:²

D1248 Specification for Polyethylene Plastics Extrusion Materials for Wire and Cable

D1693 Test Method for Environmental Stress-Cracking of Ethylene Plastics

D1711 Terminology Relating to Electrical Insulation

D2633 Test Methods for Thermoplastic Insulations and Jackets for Wire and Cable

D3349 Test Method for Absorption Coefficient of Ethylene Polymer Material Pigmented with Carbon Black

3. Terminology

3.1 *Definitions*:

3.1.1 Refer to Terminology **D1711** for definitions of terms used in this specification.

3.2 *Definitions of Terms Specific to This Standard*:

¹ This specification is under the jurisdiction of ASTM Committee **D09** on Electrical and Electronic Insulating Materials and is the direct responsibility of Subcommittee **D09.07** on Electrical Insulating Materials.

Current edition approved March 1, 2013. Published March 2013. Originally approved in 1964. Last previous edition approved in 2007 as D2308 – 07. DOI: 10.1520/D2308-07R13.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

3.2.1 *aging, (act of), n*—exposure of materials to air at 100 °C for either 24 or 48 h.

4. Physical Properties

4.1 The polyethylene before application to the wire or cable shall comply with the requirements for Type I, Class C, Category 4 or 5, Grade E5 or J3 of Specification **D1248**, or Class B with equivalent weathering requirements to Class C materials. The requirements of Specification **D1248** shall not apply to the jacket removed from the wire or cable. The compound is suitable for exposure to sunlight and other atmospheric environments at temperatures between –55 and +75 °C, and a minimum installation temperature of –40 °C.

4.2 Specimens removed from the wire or cable and tested at 20 to 28 °C (68 to 82 °F) shall conform to the requirements for physical properties specified in **Table 1**. Alternatively, the jacket shall be air-oven aged without removal from the conductor.

4.3 *Environmental Stress-Cracking Test*—The jacket shall conform to the requirements for Grade E5 as specified in **Table 3** of Specification **D1248**.

4.4 *Absorption Coefficient*—See Test Method **D3349**. Instead of testing the jacket removed from the conductors, a certification by the polyethylene compound manufacturer that this requirement has been complied with shall suffice.

5. Electrical Properties

5.1 The polyethylene jacket shall conform to the requirements for electrical properties specified in **Table 2**.

6. Sampling

6.1 Unless otherwise instructed, sample the jacket in accordance with Test Methods **D2633**.

7. Test Methods

7.1 Unless otherwise instructed, test the jacket in accordance with Test Methods **D2633**.

7.2 *Environmental Stress-Cracking Test*— Test in accordance with Test Method **D1693**, Condition A, using undiluted Igepal CO 630 as specified in Specification **D1248**.