



Designation: D3554 – 07 (Reapproved 2013)

# Standard Specification for Track-Resistant Black Thermoplastic High-Density Polyethylene Insulation for Wire and Cable, 75 °C Operation<sup>1</sup>

This standard is issued under the fixed designation D3554; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This specification covers track-resistant black thermoplastic high-density polyethylene insulation. Before application to the conductor, the insulation shall comply with the requirements of Specification [D1248](#), Type III, Class C, Category 5, Grade E10, J4, or J5. The requirements of Specification [D1248](#) shall not apply to the insulation removed from the conductor.

1.2 This type of insulation is considered suitable for use on wire or cable that will be used for continuous operation at conductor temperatures up to 75 °C.

1.3 This insulation is suitable for use on wire or in cable used for power transmission in overhead spaced-line service, installed at temperatures above –25 °C and exposed to sunlight and other atmospheric environments between –55 and +75 °C.

1.4 In many instances, the insulation cannot be tested unless it has been formed around a conductor. Therefore, tests done on insulated wire in this standard are solely to determine the relevant property of the insulation and not to test the conductor or completed cable.

1.5 Whenever two sets of values are presented, in different units, the values in the first set are the standard, while those in parentheses are for information only.

## 2. Referenced Documents

2.1 *ASTM Standards*:<sup>2</sup>

[D1248 Specification for Polyethylene Plastics Extrusion Materials for Wire and Cable](#)

[D1693 Test Method for Environmental Stress-Cracking of Ethylene Plastics](#)

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee D09 on Electrical and Electronic Insulating Materials and is the direct responsibility of Subcommittee D09.07 on Electrical Insulating Materials.

Current edition approved March 1, 2013. Published March 2013. Originally approved in 1977. Last previous edition approved in 2007 as D3554 – 07. DOI: 10.1520/D3554-07R13.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

[D1711 Terminology Relating to Electrical Insulation](#)  
[D1928 Practice for Preparation of Compression-Molded Polyethylene Test Sheets and Test Specimens](#) (Withdrawn 2001)<sup>3</sup>

[D2132 Test Method for Dust-and-Fog Tracking and Erosion Resistance of Electrical Insulating Materials](#)

[D2633 Test Methods for Thermoplastic Insulations and Jackets for Wire and Cable](#)

## 3. Terminology

3.1 *Definitions*:

3.1.1 For definitions of terms used in this specification, refer to Terminology [D1711](#).

3.2 *Definitions of Terms Specific to This Standard*:

3.2.1 *aging, (act of), n*—exposure of materials to air at a temperature of 100 °C for 48 h.

## 4. Physical Properties

4.1 When tested for physical and aging requirements, heat distortion, cold bend, U-bend discharge, and surface resistivity in accordance with Test Methods [D2633](#), environmental cracking in accordance with Test Method [D1693](#), and track resistance in accordance with Test Method [D2132](#), the track-resistant black thermoplastic high-density polyethylene insulation shall meet the requirements specified in [Table 1](#).

## 5. Electrical Requirements

5.1 Subject cable specimens to a 5 min ac or dc voltage withstand test at voltages which are based on the nominal thickness of the insulation. Conduct tests in accordance with Test Methods [D2633](#) using 125 V/mil (5 kV/mm) for ac tests or 375 V/mil (15 kv/mm) for dc tests.

## 6. Sampling

6.1 Sample the insulation in accordance with Test Methods [D2633](#) and Test Method [D1693](#).

<sup>3</sup> The last approved version of this historical standard is referenced on www.astm.org.

**TABLE 1 Physical Requirements for Track-Resistant Black Thermoplastic High-Density Polyethylene Insulation**

Physical requirements (unaged):	
Tensile strength, min, psi (MPa)	2500 (17.2)
Elongation at rupture, min, %	300
Physical requirements [after aging in an air oven at 100 ± 1 °C for 48 h]:	
Tensile strength, min, % of unaged value	75
Elongation at rupture, min, % of unaged value	75
Heat distortion at 90± 1 °C, max, % of unaged thickness:	
4/0 AWG (107 mm <sup>2</sup> ) and smaller (insulation on cable)	30
Larger than 4/0 AWG (107 mm <sup>2</sup> ) (buffed sample of insulation)	10
Cold bend, at – 25± 1°C for 1 h	no cracks
Environmental cracking, 48 h	no cracks
U-bend discharge, 125 V/mil (5 kV/mm)	no cable failures or cracks in insulation surface
Surface resistivity, min, MΩ	200 000
Track Resistance:	
Average time to failure, min (h)	200 (3.33)

## 7. Test Methods

7.1 Test the insulation in accordance with Test Methods **D2633** and Test Method **D1693**, modified as noted in **Table 1**, and noted as follows.

7.2 To test for environmental cracking in accordance with Test Method **D1693**, test specimens shall be molded in accordance with Procedure C of Practice **D1928** and the test reagent shall be 10 % Igepal CO-630.<sup>4</sup>

<sup>4</sup> The sole source of supply of Igepal CO-630 known to the committee at this time is Rhone-Poulenc Inc. If you are aware of alternative suppliers, please provide this information to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee,<sup>1</sup> which you may attend.

7.3 Test the track resistance in accordance with Test Method **D2132**.

## 8. Keywords

8.1 ac test; cold bend; dc test; elongation; environmental cracking; heat distortion; high-density polyethylene; surface resistivity; tensile strength; thermoplastic; track-resistant; u-bend discharge

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/*