



Designation: **B327—12 B327 – 13**

## Standard Specification for Master Alloys Used in Making Zinc Die Casting Alloys<sup>1</sup>

This standard is issued under the fixed designation B327; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reappraisal.

### 1. Scope\*

1.1 This specification covers aluminum–base and zinc–base master alloys used to make zinc die-casting alloys. Alloy compositions specified for aluminum–base master alloys (hardeners) are designated as shown in **Table 1**. Alloy compositions specified for the zinc-base master alloys are designated as shown in **Table 2**.

1.2 Aluminum alloy hardeners are added to Special High Grade zinc (per Specification **B6**) in the proper alloying ratios, as shown in **Table 1**, to produce zinc alloys for die casting.

1.3 Zinc-base master alloy is added to Special High Grade zinc (per Specification **B6**) in the proper alloying ratio, as shown in **Table 3**, to produce zinc alloy for die casting.

1.4 Master alloys may be supplied in the form of shot, bar, ingot or jumbo ingot as specified by the purchaser.

1.5 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.6 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to become familiar with all hazards including those identified in the appropriate Material Safety Data Sheet (MSDS) for this product/material as provided by the manufacturer, to establish appropriate safety and health practices, and determine the applicability of regulatory limitations prior to use.*

### 2. Referenced Documents

2.1 The following documents of the issue in effect on date of order acceptance form a part of this specification to the extent referenced herein:

2.2 *ASTM Standards:*<sup>2</sup>

**B6 Specification for Zinc**

**B899 Terminology Relating to Non-ferrous Metals and Alloys**

**B908 Practice for the Use of Color Codes for Zinc Casting Alloy Ingot**

**B949 Specification for General Requirements for Zinc and Zinc Alloy Products**

**E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications**

**E34 Test Methods for Chemical Analysis of Aluminum and Aluminum-Base Alloys**

**E88 Practice for Sampling Nonferrous Metals and Alloys in Cast Form for Determination of Chemical Composition**

**E527 Practice for Numbering Metals and Alloys in the Unified Numbering System (UNS)**

**E536 Test Methods for Chemical Analysis of Zinc and Zinc Alloys**

**E1251 Test Method for Analysis of Aluminum and Aluminum Alloys by Spark Atomic Emission Spectrometry**

2.3 *ISO Standards:*<sup>3</sup>

**ISO 3815-1 Zinc and zinc alloys — Part 1: Analysis of solid samples by optical emission spectrometry**

**ISO 3815-2 Zinc and zinc alloys — Part 2: Analysis by inductively coupled plasma optical emission spectrometry**

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee **B02** on Nonferrous Metals and Alloys and is the direct responsibility of Subcommittee **B02.04** on Zinc and Cadmium.

Current edition approved ~~May 1, 2012~~ Feb. 1, 2013. Published ~~July 2012~~ March 2013. Originally approved in 1958. Last previous edition approved in ~~2009~~ 2012 as B327 – 09<sup>12</sup> <sup>ε1</sup>. DOI: ~~10.1520/B0327-12~~ 10.1520/B0327-13.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

\*A Summary of Changes section appears at the end of this standard

TABLE 1 Chemical Requirements for Aluminum-Base Master Alloys

NOTE 1—The following applies to all specified limits in this table: For purposes of determining conformance with this specification, the observed value or calculated value obtained from analysis shall be rounded off “to the nearest unit” in the last right hand place of figures used in expressing the specified limit, in accordance with the rounding method of Practice E29.

ASTM Alloy†	Composition, percent												Usage
	Aluminum, min	Copper	Iron, max	Silicon, max	Manganese, max	Magnesium <sup>A</sup>	Zinc	Chromium, max	Nickel, max	Tin, max	Lead, max <sup>A</sup>	Cadmium, max <sup>A</sup>	
ZG71A†	87.0	1.7 max	0.8	0.7	0.50	0.65–1.05	6.5–7.5	0.20	0.20	0.02	0.020	0.010	1 part by weight of ZG71A, 21 parts by weight of Special High Grade zinc <sup>B</sup> to make ASTM zinc Alloy Z33520 (AG40A)

†Editorially corrected.

TABLE 1 Chemical Requirements for Aluminum-Base Master Alloys

NOTE 1—The following applies to all specified limits in this table: For purposes of determining conformance with this specification, the observed value or calculated value obtained from analysis shall be rounded off “to the nearest unit” in the last right hand place of figures used in expressing the specified limit, in accordance with the rounding method of Practice E29.

ASTM Alloy (UNS)	Composition, percent												Usage
	Aluminum, min	Copper	Iron, max	Silicon, max	Manganese, max	Magnesium <sup>A</sup>	Zinc	Chromium, max	Nickel, max	Tin, max	Lead, max <sup>A</sup>	Cadmium, max <sup>A</sup>	
ZG71A (A07131)	87.0	1.7 max	0.8	0.7	0.50	0.65–1.05	6.5–7.5	0.20	0.20	0.02	0.020	0.010	1 part by weight of ZG71A, 21 parts by weight of Special High Grade zinc <sup>B</sup> to make ASTM zinc Alloy Z33524 (AG40A)

<sup>A</sup> Carried to one additional decimal place to ensure proper control in the final alloy.

<sup>B</sup> ASTM Specification B6, for Zinc.

TABLE 2 Chemical and Color Code Requirements for Zinc-Base Master Alloys<sup>A,B,C</sup>

TABLE 3 Weight Requirements for Zinc-Base Master Alloy Jumbo Ingots

Common (UNS) Color Code<sup>D</sup> Aluminum

These requirements are based on the use of nominal 2400 lb or 1200 lb jumbo ingots of V12 (Z33730).

Nominal Weight, lb	Weight Range, lb <sup>A</sup>		Usage
	Minimum	Maximum	
2400	2325	2475	1 part by weight of V12-3 (one 2400 lb jumbo ingot), 2 parts by weight (two 2400 lb jumbo ingots) of Special High Grade zinc to make zinc alloy 3 (Zamak 3, UNS Z33520, AG40A)
2400	2325	2475	1 part by weight of V12-3 (one 2400 lb jumbo ingot), 2 parts by weight (two 2400 lb jumbo ingots) of Special High Grade zinc to make zinc alloy 3 (Zamak 3, UNS Z33524, AG40A)
2400			or
2400			1 part by weight of V12-5 (one 2400 lb jumbo ingot), 2 parts by weight (two 2400 lb jumbo ingots) of Special High Grade zinc to make zinc alloy 5 (Zamak 5, UNS Z35531, AC41A)
2400			1 part by weight of V12-5 (one 2400 lb jumbo ingot), 2 parts by weight (two 2400 lb jumbo ingots) of Special High Grade zinc to make zinc alloy 5 (Zamak 5, UNS Z35532, AC41A)
1200	1150	1250	1 part by weight of V12-3 (one 1200 lb jumbo ingot), 2 parts by weight (one 2400 lb jumbo ingot) of Special High Grade zinc to make zinc alloy 3 (Zamak 3, UNS Z33520, AG40A)
1200	1150	1250	1 part by weight of V12-3 (one 1200 lb jumbo ingot), 2 parts by weight (one 2400 lb jumbo ingot) of Special High Grade zinc to make zinc alloy 3 (Zamak 3, UNS Z33524, AG40A)
1200			or
1200			1 part by weight of V12-5 (one 1200 lb jumbo ingot), 2 parts by weight (one 2400 lb jumbo ingot) of Special High Grade zinc to make zinc alloy 5 (Zamak 5, UNS Z35531, AC41A)
1200			1 part by weight of V12-5 (one 1200 lb jumbo ingot), 2 parts by weight (one 2400 lb jumbo ingot) of Special High Grade zinc to make zinc alloy 5 (Zamak 5, UNS Z35532, AC41A)

<sup>A</sup> Remaining outside the above weight limits may be acceptable depending upon the chemistry, if mutually agreed upon between the producer and purchaser.

3. Terminology

3.1 Terms shall be defined in accordance with Terminology B899.

3.2 Definitions of Terms Specific to This Standard:

3.2.1 hardener, n—an aluminum-base master alloy added to Special High Grade Zinc (SHG) to produce a zinc alloy for die casting.

4. Ordering Information

Orders for master alloys under this specification shall include the following information:

4.1 Alloy (Table 1 or Table 2),

- 2.1–3.3
- 0.005
- 0.004
- 0.003

Remainder

V12-5