ISO/FDIS 6508-3 ISO/TC 164/SC 3 Date: 2023-01-10 ISO 6508-3:2022(E) ISO/TC 164/SC 3/WG Secretariat: DIN Date: 2023-08-02

Metallic materials — Rockwell hardness test —

Part 3: Calibration of reference blocks Standards.iteh.ai)

Matériaux métalliques — Essai de dureté Rockwell — Deument Preview

Partie 3: Étalonnage des blocs de référence

ISO 6508-3 https://standards.iteh.ai/catalog/standards/sist/255e63fe-8672-45df-9c40-c54bd4a08088/iso-6508-3

FDIS stage

© ISO<u>-2022 2023</u>

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office CP 401 • Ch. de Blandonnet 8 CH-1214 Vernier, Geneva Phone: + 41 22 749 01 11 EmailE-mail: copyright@iso.org Website: www.iso.orgwww.iso.org

Published in Switzerland

iTeh Standards (https://standards.iteh.ai) Document Preview

<u>ISO 6508-3</u>

https://standards.iteh.ai/catalog/standards/sist/255e63fe-8672-45df-9c40-c54bd4a08088/iso-6508-3

ii

ii

© ISO 2022 - All rights reserved

© ISO 2023 – All rights reserved Edited DIS - MUST BE USED FOR FINAL DRAFT

ISO/DISFDIS 6508-3:20222023(E)

Contents Page

Forew	ordiv		
1	Scope1		
2	Normative references		
3	Terms and definitions		
4	Manufacture of reference blocks		
5	Calibration machine and calibration indenter2		
5.1	General		
5.2	Direct verification of the calibration machine		
5.3	Calibration diamond indenter		
5.4	Calibration ball indenter		
5.5	Performance verification of the calibration machine and indenter		
6	Reference block calibration procedure7		
7	Number of indentations		
8	Uniformity of hardness		
9	Marking		
10	Calibration certificate		
11	Validity		
Annex	Number of indentations 8 Uniformity of hardness 8 Marking 9 0 Calibration certificate 9 1 Validity 9 annex A (informative) Uniformity of reference blocks 11 unnex B (informative) Uncertainty of the mean hardness value of hardness-reference blocks 15		
Annex B (informative) Uncertainty of the mean hardness value of hardness-reference blocks			
Annex	C (normative) Requirements for reference diamond indenters		
Annex	D (normative) Control verification of the calibration machine		
	graphy		

https://standards.iteh.ai/catalog/standards/sist/255e63fe-8672-45df-9c40-c54bd4a08088/iso-6508-3

© ISO 2023 – All rights reserved

iii

© ISO 2022 – All rights reserved

ISO/DISFDIS 6508-3:20222023(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documentsdocument should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawnISO draws attention to the possibility that some of the elementsimplementation of this document may beinvolve the subjectuse of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents-, ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This fourth edition cancels and replaces the third edition (ISO 6508-3:2015), which has been technically revised.

The main changes are as follows:

iv

iv

 <u>Removedremoved</u> all statements of requirements, permissions, and recommendations from the Scope of the document <u>(Clause 1)-()</u>:

<u>Additionaddition</u> of <u>Clause 3 Clause 3</u>, Terms and definitions.;

© ISO 2022 – All rights reserved

© ISO 2023 – All rights reserved

- Modification modification of the requirements for the calibration and verification of the machine and indenter (Clause 5, Clause 5):
- Addedadded a performance verification for the calibration machine and indenter (Clause 5, Clause 5, -);
- <u>Addedadded</u> a requirement to conduct a control verification prior to the calibration of reference blocks <u>(Clause 6; Clause 6;);</u>
- <u>Addedadded</u> a normative <u>Annex D</u> for the control verification of the calibration machine <u>(Annex D</u>(<u>Annex D</u>)).

A list of all parts in the ISO 6508 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html

iTeh Standards (https://standards.iteh.ai) Document Preview

ISO 6508-3

https://standards.iteh.ai/catalog/standards/sist/255e63fe-8672-45df-9c40-c54bd4a08088/iso-6508-3

© ISO 2023 – All rights reserved

© ISO 2022 - All rights reserved

iTeh Standards (https://standards.iteh.ai) Document Preview

ISO 6508-3

https://standards.iteh.ai/catalog/standards/sist/255e63fe-8672-45df-9c40-c54bd4a08088/iso-6508-3

Metallic materials - Rockwell hardness test -

Part 3: Calibration of reference blocks

1 Scope

This document specifies a method for the calibration of reference blocks to be used for the indirect and daily verification of Rockwell hardness testing machines and indenters, as specified in ISO 6508–2. This document also specifies requirements for Rockwell machines and indenters used for calibrating reference blocks and specifies methods for their calibration and verification.

Attention is drawn to the fact that the use of hard metal for ball indenters is considered to be the standard type of Rockwell indenter ball.

2 Normative references

The following documents, are referred to in wholethe text in such a way that some or in part, are normatively referenced inall of their content constitutes requirements of this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 376, Metallic materials — Calibration of force-proving instruments used for the verification of uniaxial testing machines

ISO 6508–<u>1:-1</u>, Metallic materials — Rockwell hardness test — Part 1: Test method

ISO 6508-2:-2. Metallic materials — Rockwell hardness test — Part 2: Verification and calibration df testing machines and indenters

3 Terms and definitions hai/catalog/standards/sist/255e63fe-8672-45df-9c40-c54bd4a08088/iso-6508-3

No terms and definitions are listed in this document.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

— ISO Online browsing platform: available at https://www.iso.org/obp

— — IEC Electropedia: available at <u>https://www.electropedia.org/</u>

4 Manufacture of reference blocks

4.1 The block shall be specially manufactured for use as a hardness-reference block.

NOTE Attention is drawn to the need to use a manufacturing process, which will give the necessary homogeneity, stability of structure, and uniformity of surface hardness.

© ISO 2022 – All rights reserved

Fifth edition under preparation. Stage at the time of publication: ISO/FDIS 6508-1:2023.
Fourth edition under preparation. Stage at the time of publication: ISO/FDIS 6508-2:2023.

4.2 Each hardness reference block shall be of a thickness not less than 6 mm. To minimize the effect of hardness change with increasing number of indents, thicker blocks should be used.

4.3 The reference blocks shall be free of magnetism. It is recommended that the manufacturer ensure that the blocks, if made of steel, have been demagnetized at the end of the manufacturing process (before calibration).

4.4 The deviation from surface flatness of the top and bottom surfaces shall be $\leq 0,01$ mm. The bottom of the blocks shall not be convex. The deviation from parallelism of the top and bottom surfaces shall be $\leq 0,02$ mm per 50 mm.

4.5 The test surface and bottom surface shall be free from damage, such as notches, scratches, oxide layers, etc., which can interfere with the measurement of the indentations. The surface roughness, *Ra*, shall not exceed 0,3 μ m for the test surface and 0,8 μ m for the bottom surface. Sampling length is *l* = 0,8 mm (see ISO 4287:1997, 3.1.9).

4.6 To verify that no material is subsequently removed from the reference block, the thickness at the time of calibration shall be marked on it, to the nearest 0,1 mm, or an identifying mark shall be made on the test surface [see 9.18.1 e)].

5 Calibration machine and calibration indenter

5.1 General

5.1.1 Calibrations and verifications of Rockwell calibration machines and calibration indenters shall be carried out at a temperature of (23 ± 5) °C.

5.1.2 The instruments used for calibration and verification shall be traceable to national standards.

5.2 Direct verification of the calibration machine

5.2.1 In addition to fulfilling the <u>"General-conditions" clause specified</u> in ISO 6508–2:<u>—</u>³. <u>Clause 4</u>, the calibration machine shall also meet the requirements given in <u>5.2.2, 5.2.3, 5.2.4, 5.2.5</u><u>5.2.2, 5.2.3, 5.2.4, 5.2.5</u><u>5.2.2, 5.2.3, 5.2.4, 5.2.5</u><u>5.2.4, 5.2.5</u><u>5.2.2, 5.2.4, 5.2.5</u><u>5.2.4, 5.2.5</u><u>5.2.2, 5.2.3, 5.2.4, 5.2.5</u><u>5.2.2, 5.2.3, 5.2.4, 5.2.5</u><u>5.2.2, 5.2.3, 5.2.4, 5.2.5</u><u>5.2.2, 5.2.3, 5.2.4, 5.2.5</u><u>5.2.2, 5.2.5, 5.2.6, 5.2.6</u> and <u>5.2.7</u><u>5.2.7</u> determined by the procedures specified in the <u>"Direct verification of the testing machine" clause of ISO 6508-2_2: —, Clause 5</u>.

5.2.2 The machine shall be directly verified annually, not to exceed 13 months. Direct verification involves calibration and verification of the following:

- a) a) test force;
- b) b) measuring system;
- c) c)-testing cycle; if this is not possible, at least the force versus time behaviour.
- d) d)-machine hysteresis test.

³ Fourth edition under preparation. Stage at the time of publication: ISO/FDIS 6508-2:2023.

2

2

© ISO 2022 – All rights reserved

© ISO 2023 - All rights reserved

5.2.3 The test force shall be measured by means of an elastic proving device (according to ISO 376) class 0,5 or better and calibrated for reversibility, or by another method having the same or better accuracy.

Evidence should be available to demonstrate that the output of the force-proving device does not vary by more than 0,1 % in a period of 1 s to 30 s, following a stepped change in force.

5.2.4 Each test force shall be measured and shall agree with the nominal preliminary test force, F_0 , to within ±0,2 % and the nominal total test force, F, to within ±0,1 %.

5.2.5 The measuring system shall have a resolution of $\pm 0,0001$ mm and a maximum expanded uncertainty of 0,000 2 mm, when calculated with a confidence level of 95 % over its working range.

5.2.6 The testing cycle shall be timed with an uncertainty less than ± 0.5 s and shall conform to the testing cycle of <u>Clause 6-Clause 5.</u>

5.2.7 The average of the last three tests when evaluating the hysteresis of the calibration machine shall indicate a hardness number of (130 ± 0.5) Rockwell units when the regular Rockwell ball scales B, E, F, G, H, and K are used, or within (100 ± 0.5) Rockwell units when any other Rockwell scale is used.

5.3 Calibration diamond indenter

5.3.1 The geometric shape and performance of calibration diamond indenters shall be calibrated as specified below. Direct verification of the geometric shape shall be made before first use. The condition of the diamond shall be checked at frequent intervals using appropriate optical devices (microscope, magnifying glass, etc.) as specified in ISO 6508–1:–--,:__4 Annex F.

Verification of the indenter performance, as specified in $5.3.34.3.3_{\mu}$ shall be made before first use and annually, not to exceed 13 months.

5.3.2 The diamond indenter shall be measured on at least eight unique axial section planes equidistant from each other (e.g. the eight cross-sections will be spaced approximately 22,5° apart at 0°, 22,5°, 45°, 67,5°, 90°, 112,5°, 135°, 157,5°), and shall meet the following requirements:

- a) a)—The cone angle shall be measured adjacent to the blend. The diamond cone shall have a mean included angle of $(120 \pm 0,1)^{\circ}$. In each measured axial section, the included angle shall be $(120 \pm 0,17)^{\circ}$.
- b) -The mean deviation from straightness of the generatrix of the diamond cone adjacent to the blend shall not exceed 0,000 5 mm over a minimum length of 0,4 mm. In each measured section, the deviation shall not exceed 0,000 7 mm.
- c) c)—The radius of the spherical tip of the diamond shall be measured adjacent to the blend. The tip shall have a mean radius of $(0,200 \pm 0,005)$ mm. In each measured section, the radius shall be within $(0,200 \pm 0,007)$ mm and local deviations from a true radius shall not exceed 0,002 mm.

NOTE The tip of the diamond indenter is usually not truly spherical, but often varies in radius across its surface. Depending on the crystallographic orientation of the diamond stone with respect to the indenter axis, diamond tends to preferentially polish away more easily or with more difficulty at the tip, producing an increasingly flat or sharp surface in the central indenter axis region. The sphericity of the diamond tip can be

4 Fifth edition under preparation. Stage at the time of publication: ISO/FDIS 6508-1:2023.

© ISO 2023 – All rights reserved

© ISO 2022 - All rights reserved

ISO/DISFDIS 6508-3:20222023(E)

4

4

better evaluated by measuring multiple measurement windows of varying width. The measurement window would be bounded by widths measured along a line normal to the indenter axis. For example, the following window sizes can be evaluated:

- between ±80 μm from the indenter axis;
- between ±60 μm from the indenter axis;
 - ———between ±40 μm from the indenter axis.
- d) d)—The surfaces of the cone and the spherical tip shall blend in a smooth tangential manner. The location where the spherical tip and the cone of the diamond blend together will vary depending on the values of the tip radius and cone angle. Ideally for a perfect indenter geometry, the blend point is located at 100 µm from the indenter axis measured along a line normal to the indenter axis. To avoid including the blend area in the measurement of the tip radius and cone angle, the portion of the diamond surface between 90 µm and 110 µm should be ignored.
- e) e)—The inclination of the axis of the diamond cone to the axis of the indenter holder (normal to the seating surface) shall be within 0,3°.

5.3.3 Calibration diamond indenters shall be performance verified by performing comparison tests with reference diamond indenter(s) that meet the requirements of <u>Annex C, Annex C,</u> Calibration diamond indenters can be verified for use on either regular or superficial Rockwell diamond scales or both. The test blocks used for the comparison testing shall meet the requirements of <u>Clause 4 Clause 3</u> and be calibrated at the hardness levels given in <u>Table 1, Table 2, Table 3, Table 2, Table 3, or <u>Table 4, depending on the scales for which the indenter is verified. The testing shall be carried out in accordance with ISO 6508–1.</u></u>

NOTE The alternate hardness levels given in <u>Table 2</u> are provided to accommodate indenters calibrated to other International Standards. It is believed that calibrations conducted to <u>Table 1</u> or <u>Table 2</u> will yield equivalent results.

For each block, the mean hardness value of three indentations made using the calibration diamond indenter to be verified shall not differ from the mean hardness value of three indentations obtained with a reference diamond indenter by more than ±0,4 Rockwell units. The indentations made with the -c54bd4a08088/iso-6508-3 calibration diamond indenter to be verified and with the reference diamond indenter should be adjacent.

Table 1 — Hardness levels for indenters to be used for calibrating Rockwell regular and
superficial scale test blocks (A, C, D, and N }]

Scale	Nominal hardness	Ranges
HRC	23	20 to 26
HRC	55	52 to 58
HR45N	43	40 to 46
HR15N	91	88 to 94

Table 2 — Alternate hardness levels for indenters to be used for calibrating Rockwell regular and superficial scale test blocks (A, C, D, and N})

© ISO 2022 – All rights reserved

© ISO 2023 – All rights reserved

Scale	Nominal hardness	Ranges
HRC	25	22 to 28
HRC	63	60 to 65
HR30N	64	60 to 69
HR15N	91	88 to 94

Table 3 — Hardness levels for indenters to be used for calibrating Rockwell regular scale test blocks only (A, C, and D))

Scale	Nominal hardness	Ranges
HRC	25	22 to 28
HRC	45	42 to 50
HRC	63	60 to 65
HRA	81	78 to 84

Table 4 — Hardness levels for indenters to be used for calibrating Rockwell superficial scale test blocks only (N)

blocks only (17)				
Scale	Nominal hardness	Ranges		
HR15N	91 / / /	88 to 94		
HR30N	64	60 to 69		
HR30N	46	42 to 50		
HR45N	25	22 to 29		
indenter	ISO 6508.			

5.4 Calibration ball indenter

5.4.1 The calibration tungsten carbide composite ball shall be replaced at a frequency no greater than 13 months.

5.4.2 Calibration tungsten carbide composite balls shall meet the requirements of ISO 6508–2, with the exception of the following tolerances for the ball diameter:

<u>+</u>±0,002 mm for the ball of diameter 1,587 5 mm;

— ±0,003 mm for the ball of diameter 3,175 mm.

5.5 Performance verification of the calibration machine and indenter

5.5.1 Performance verification involves verification of the calibration machine with the calibration indenter by performing comparisons with laboratories having measurement capabilities with lower or equivalent uncertainties. The comparisons shall be made by one or more of the following procedures:

— tests on primary reference blocks calibrated by National Metrology Institutes:

© ISO 2023 – All rights reserved

© ISO 2022 - All rights reserved