



Designation: **A455/A455M – 12** **A455/A455M – 12a**

Standard Specification for Pressure Vessel Plates, Carbon Steel, High-Strength Manganese¹

This standard is issued under the fixed designation A455/A455M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

- 1.1 This specification² covers high-tensile strength carbon-manganese steel plates intended for welded pressure vessels.
- 1.2 This steel is usually made to a semi-killed or capped deoxidation practice; however, at the purchaser's or the steel producer's option, the steel may be made silicon-killed or aluminum-killed.
- 1.3 The maximum thickness of plates furnished under this specification shall be $\frac{3}{4}$ in. [20 mm].
- 1.4 For plates produced from coil and furnished without heat treatment or with stress relieving only, the additional requirements, including additional testing requirements and the reporting of additional test results, of Specification **A20/A20M** apply.
- 1.5 The values stated in either inch-pound units or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system must be used independently of the other. Combining values from the two systems may result in nonconformance with the specification.

2. Referenced Documents

- 2.1 *ASTM Standards*:³
A20/A20M Specification for General Requirements for Steel Plates for Pressure Vessels

3. General Requirements and Ordering Information

- 3.1 Material supplied to this material specification shall conform to Specification **A20/A20M**. These requirements outline the testing and retesting methods and procedures, permitted variations in dimensions, and mass, quality and repair of defects, marking, loading, and ordering information.
- 3.2 In addition to the basic requirements of this specification, certain supplementary requirements are available when additional control, testing, or examination is required to meet end use requirements. The purchaser is referred to the listed supplementary requirements in this specification and to the detailed requirements in Specification **A20/A20M**.
- 3.3 Coils are excluded from qualification to this specification until they are processed into finished plates. Plates produced from coil means plates that have been cut to individual lengths from coil. The processor directly controls, or is responsible for, the operations involved in the processing of coils into finished plates. Such operations include decoiling, leveling, cutting to length, testing, inspection, conditioning, heat treatment (if applicable), packaging, marking, loading for shipment, and certification.

NOTE 1—For plates produced from coil and furnished without heat treatment or with stress relieving only, three test results are reported for each qualifying coil. Additional requirements regarding plates from coil are described in Specification **A20/A20M**.

- 3.4 If the requirements of this specification are in conflict with the requirements of Specification **A20/A20M**, the requirements of this specification shall prevail.

4. Heat Treatment

- 4.1 Plates are normally supplied in the as-rolled condition. The plates may be ordered normalized or stress relieved, or both.

¹ This specification is under the jurisdiction of ASTM Committee **A01** on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee **A01.11** on Steel Plates for Boilers and Pressure Vessels.

Current edition approved ~~May 1, 2012~~ Nov. 1, 2012. Published ~~June 2012~~ March 2013. Originally approved in 1961. Last previous edition approved in 2007/2012 as **A455/A455M – 03 (2007)**; **A455/A455M – 12**. DOI: ~~10.1520/A0455_A0455M-12~~ 10.1520/A0455_A0455M-12A.

² For ASME Boiler and Pressure Vessel Code applications, see related Specification SA-455/SA-455M in Section II of that Code.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard