



Designation: C1688/C1688M – 13

Standard Test Method for Density and Void Content of Freshly Mixed Pervious Concrete¹

This standard is issued under the fixed designation C1688/C1688M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This test method covers determining the density of freshly mixed pervious concrete under standardized conditions and gives formulas for calculating the void content of pervious concrete. Test results are not intended to represent the in-place density and void content.

1.2 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use. (Warning—Fresh hydraulic cementitious mixtures are caustic and may cause chemical burns to skin and tissue upon prolonged exposure.²)*

1.4 The text of this test method references notes and footnotes that provide explanatory information. These notes and footnotes (excluding those in tables) shall not be considered as requirements of this test method.

2. Referenced Documents

2.1 ASTM Standards:³

¹ This test method is under the jurisdiction of ASTM Committee C09 on Concrete and Concrete Aggregates and is the direct responsibility of Subcommittee C09.49 on Pervious Concrete.

Current edition approved Feb. 1, 2013. Published March 2013. Originally approved in 2008. Last previous edition approved in 2012 as C1688/C1688M-12. DOI: 10.1520/C1688_C1688M-13.

² Section on Safety Precautions, Manual of Aggregate and Concrete Testing, *Annual Book of ASTM Standards*, Vol 04.02.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

- C29/C29M Test Method for Bulk Density (“Unit Weight”) and Voids in Aggregate
- C125 Terminology Relating to Concrete and Concrete Aggregates
- C127 Test Method for Density, Relative Density (Specific Gravity), and Absorption of Coarse Aggregate
- C128 Test Method for Density, Relative Density (Specific Gravity), and Absorption of Fine Aggregate
- C150/C150M Specification for Portland Cement
- C172/C172M Practice for Sampling Freshly Mixed Concrete
- C188 Test Method for Density of Hydraulic Cement
- C192/C192M Practice for Making and Curing Concrete Test Specimens in the Laboratory
- C231/C231M Test Method for Air Content of Freshly Mixed Concrete by the Pressure Method
- C311 Test Methods for Sampling and Testing Fly Ash or Natural Pozzolans for Use in Portland-Cement Concrete
- C595/C595M Specification for Blended Hydraulic Cements
- C989/C989M Specification for Slag Cement for Use in Concrete and Mortars
- C1157/C1157M Performance Specification for Hydraulic Cement
- C1240 Specification for Silica Fume Used in Cementitious Mixtures
- D698 Test Methods for Laboratory Compaction Characteristics of Soil Using Standard Effort (12 400 ft-lbf/ft³ (600 kN-m/m³))

3. Terminology

3.1 Definitions:

3.1.1 For definitions of terms used in this standard, refer to Terminology C125.

3.2 Definitions of Terms Specific to This Standard:

3.2.1 *concrete, pervious, n*—hydraulic cement concrete with distributed, interconnected macroscopic voids that allow water to pass through the material with little resistance.

*A Summary of Changes section appears at the end of this standard

3.3 Symbols:

D	=	density (unit weight) of concrete kg/m^3 [lb/ft^3]
M_s	=	total mass of all materials batched, kg [lb] (see Note 1)
M_c	=	mass of the measure filled with concrete, kg [lb]
M_m	=	mass of the measure, kg [lb]
T	=	theoretical density of the concrete computed on an airfree basis, kg/m^3 [lb/ft^3] (see Note 1)
U	=	percentage of voids in the fresh pervious concrete, including entrained and entrapped air voids in the cement paste.
V_s	=	sum of the absolute volumes of the component ingredients in the batch, m^3 [ft^3]
V_m	=	volume of the measure, m^3 [ft^3]

NOTE 1—The theoretical density is a laboratory determination, and is assumed to remain constant for all batches made using identical component ingredients and proportions.

4. Summary of Test Method

4.1 A sample of fresh pervious concrete is placed and consolidated in a standard measure. The concrete is consolidated using a standard Proctor hammer. The density and void content of the pervious concrete are calculated based on the measured mass of the consolidated concrete specimen, the volume of the measure, and the total mass of materials batched.

5. Significance and Use

5.1 This test method provides a procedure for determining the density and void content of freshly mixed pervious concrete.

5.2 This test method is applicable to pervious concrete mixtures containing coarse aggregate with a nominal maximum size of 25 mm [1 in.] or smaller.

5.3 The measured fresh density may be used as verification of mixture proportions.

5.4 This method uses a standard consolidation procedure to measure fresh density and void content of a pervious concrete mixture as delivered. Test results are not intended to represent the density and void content of the in-place pervious concrete. This method shall not be used to determine the in-place void content or yield of the pervious concrete.

6. Apparatus

6.1 *Balance*—A balance or scale accurate to 50 g [0.1 lb] or to within 0.3 % of the test load, whichever is greater, at any point within the range of use. The range of use shall be considered to extend from the mass of the empty measure to the mass of the measure filled with concrete having an assumed density of 2600 kg/m^3 [160 lb/ft^3].

6.2 *Standard Proctor Hammer*—A device used to compact a pervious concrete specimen that conforms to Test Method [D698](#).

6.3 *Measure*—A cylindrical container made of steel or other suitable metal with a capacity of $7.0 \pm 0.6 \text{ L}$ [$0.25 \pm 0.02 \text{ ft}^3$] and a diameter equal to 0.75 to 1.25 times the height (See [Note 2](#)). The volume of the measure shall be determined as described in Test Method [C29/C29M](#). The top rim of the container shall be plane within 0.3 mm [0.01 in.] (See [Note 3](#)).

NOTE 2—The metal should not be attacked readily by cement paste. However, a reactive material such as aluminum alloy may be used if, as a result of an initial reaction, a surface film is formed that protects the metal against further corrosion. The measuring bowl of an air meter

conforming to Test Method [C231/C231M](#) can meet the requirements for the measure.

NOTE 3—The top rim is satisfactorily plane if a 0.3 mm [0.01-in.] wire feeler gauge cannot be inserted between the rim and a piece of 6 mm [$\frac{1}{4}$ -in.] or thicker plate glass laid over the top of the measure.

6.4 *Strike-Off Plate*—A flat rectangular metal plate at least 6 mm [$\frac{1}{4}$ in.] thick or a glass or acrylic plate at least 12 mm [$\frac{1}{2}$ in.] thick with length and width that are at least 50 mm [2 in.] greater than the diameter of the measure with which it is to be used. The edges of the plate shall be straight within a tolerance of 2 mm [$\frac{1}{16}$ in.].

6.5 *Scoop*—Of a size large enough so each amount of pervious concrete obtained from the sampling receptacle is representative and small enough so that the concrete is not spilled during placement in the measure.

7. Sampling

7.1 For field placements, obtain the sample of freshly-mixed pervious concrete in accordance with Practice [C172/C172M](#).

7.1.1 Start the test for density within 5 min after obtaining the final portion of the composite sample.

7.2 For laboratory testing, obtain the sample of freshly-mixed pervious concrete in accordance with Practice [C192/C192M](#).

7.2.1 Start the test for density within 5 min after obtaining the sample.

8. Procedure

8.1 Place the measure on a flat, level surface free from vibration. Moisten the inside of the measure before placing pervious concrete. Remove any standing water from the bottom of the container using a moistened sponge. Place the pervious concrete in the measure in two layers of approximately equal thickness using the scoop described in [6.5](#). During filling of the measure, move the scoop around the perimeter of the opening to ensure an even distribution of the concrete with minimal segregation. Drop the hammer vertically 20 times per layer at the full 305 mm [12 in.] drop height. For each layer, distribute the position of the tamper so that the entire surface area of the pervious concrete in the measure is consolidated equally. Before consolidating the final layer, fill the measure to overflowing. After completion of consolidation, the measure must contain about 3 mm [$\frac{1}{8}$ in.] of excess pervious concrete protruding above the top of the measure. If after 10 hammer drops to the final layer it appears that there will be insufficient concrete, add a small quantity of concrete to correct the deficiency. If after 10 hammer drops to the final layer it appears that there will be too much concrete in the measure, remove a representative portion of excess concrete with a trowel or scoop. Complete the consolidation of the final layer.

8.2 *Strike Off*—After consolidation, strike off the top surface of the concrete and finish it flat with the strike-off plate so that the concrete surface is level with the top of the measure. Accomplish the strike-off by pressing the strike-off plate on the top surface of the measure to cover about two thirds of the surface and withdrawing the plate with a sawing motion to strike off the area originally covered. Then place the plate on