

---

---

**Extenders — Specifications and  
methods of test —**

**Part 18:  
Precipitated sodium aluminium  
silicate**

*Matières de charge — Spécifications et méthodes d'essai —  
Partie 18: Silicoaluminate de sodium précipité*

*iTeh STANDARD PREVIEW  
(standards.iteh.ai)*

[ISO 3262-18:2023](https://standards.iteh.ai/catalog/standards/sist/131b9927-42be-4e9e-b2bf-ba4b1250b850/iso-3262-18-2023)

[https://standards.iteh.ai/catalog/standards/sist/131b9927-42be-4e9e-b2bf-  
ba4b1250b850/iso-3262-18-2023](https://standards.iteh.ai/catalog/standards/sist/131b9927-42be-4e9e-b2bf-ba4b1250b850/iso-3262-18-2023)



iTeh STANDARD PREVIEW  
(standards.iteh.ai)

ISO 3262-18:2023

<https://standards.iteh.ai/catalog/standards/sist/131b9927-42be-4e9e-b2bf-ba4b1250b850/iso-3262-18-2023>



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2023

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

	Page
Foreword.....	iv
<b>1 Scope.....</b>	<b>1</b>
<b>2 Normative references.....</b>	<b>1</b>
<b>3 Terms and definitions.....</b>	<b>1</b>
<b>4 Requirements and test methods.....</b>	<b>2</b>
<b>5 Sampling.....</b>	<b>2</b>
<b>6 Determination of silica content.....</b>	<b>2</b>
6.1 Principle.....	2
6.2 Reagents.....	2
6.3 Apparatus.....	3
6.4 Procedure.....	3
6.4.1 Number of determinations.....	3
6.4.2 Test portion.....	4
6.4.3 Determination.....	4
6.4.4 Determination of the total loss on ignition.....	4
6.5 Expression of results.....	5
6.6 Precision.....	5
6.6.1 Repeatability, $r$ .....	5
6.6.2 Reproducibility, $R$ .....	5
<b>7 Determination of the composition by spectrometry.....</b>	<b>5</b>
7.1 Principle.....	5
7.2 Reagents and materials.....	6
7.3 Apparatus.....	6
7.4 Procedure.....	7
7.4.1 Preparation of standard matching solutions.....	7
7.4.2 Spectrometric measurement.....	7
7.4.3 Calibration graph.....	8
7.4.4 Preparation of the test solution.....	8
7.4.5 Determination.....	8
7.5 Expression of results.....	9
7.5.1 Concentration of Al, Na and Si.....	9
7.5.2 Calculation of the oxide content for each element.....	9
7.6 Precision.....	9
7.6.1 Repeatability, $r$ .....	9
7.6.2 Reproducibility, $R$ .....	10
<b>8 Determination of residue on sieve.....</b>	<b>10</b>
8.1 Principle.....	10
8.2 Materials.....	10
8.3 Apparatus.....	10
8.4 Procedure.....	10
8.4.1 Number of determinations.....	10
8.4.2 Test portion.....	10
8.4.3 Determination.....	11
8.5 Expression of results.....	11
8.6 Precision.....	11
<b>9 Test report.....</b>	<b>11</b>
<b>Bibliography.....</b>	<b>12</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at [www.iso.org/patents](http://www.iso.org/patents). ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 256, *Pigments, dyestuffs and extenders*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 298, *Pigments and extenders*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This second edition cancels and replaces the first edition (ISO 3262-18:2000), which has been technically revised.

The main changes are as follows:

- the first part of the title has been changed to “Extenders”;
- the normative references have been updated.

A list of all parts in the ISO 3262 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

# Extenders — Specifications and methods of test —

## Part 18: Precipitated sodium aluminium silicate

### 1 Scope

This document specifies requirements and corresponding methods of test for precipitated sodium aluminium silicate.

### 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 648, *Laboratory glassware — Single-volume pipettes*

ISO 787-2, *General methods of test for pigments and extenders — Part 2: Determination of matter volatile at 105 °C*

ISO 787-5, *General methods of test for pigments and extenders — Part 5: Determination of oil absorption value*

ISO 787-9, *General methods of test for pigments and extenders — Part 9: Determination of pH value of an aqueous suspension*

ISO 3262-1, *Extenders — Specifications and methods of test — Part 1: Introduction and general test methods*

ISO 3696, *Water for analytical laboratory use — Specification and test methods*

ISO 5794-1:2022, *Rubber compounding ingredients — Silica, precipitated, hydrated — Part 1: Non-rubber tests*

ISO 15528, *Paints, varnishes and raw materials for paints and varnishes — Sampling*

ISO 18451-1, *Pigments, dyestuffs and extenders — Terminology — Part 1: General terms*

### 3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 18451-1 and the following apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

#### 3.1

##### **precipitated sodium aluminium silicate**

amorphous silicate precipitated by the reaction of sodium silicate solution with a mineral acid and/or an aluminium salt

## 4 Requirements and test methods

For precipitated sodium aluminium silicate complying with this document, the essential requirements are specified in [Table 1](#) and the conditional requirements are listed in [Table 2](#). The test methods listed in [Tables 1](#) and [2](#) shall apply.

**Table 1 — Essential requirements**

Characteristic	Unit	Requirement	Test method
Silica content, min.	% mass fraction	75	See <a href="#">Clause 6</a> or <a href="#">7</a>
Oxide content — Na <sub>2</sub> O		3 to 10	See <a href="#">Clause 7</a>
— Al <sub>2</sub> O <sub>3</sub>		5 to 15	
Residue on 45 µm sieve, max.	% mass fraction	2	See <a href="#">Clause 8</a>
Lightness, min.	%	95	Test method in preparation
Matter volatile at 105 °C, max.	% mass fraction	10	ISO 787-2
Loss on ignition	% mass fraction	3 to 12	ISO 3262-1
Oil absorption value <sup>a</sup> , min.	g/100 g	70	ISO 787-5
pH value of aqueous suspension	—	7 to 12	ISO 787-9

<sup>a</sup> A test method with higher reproducibility and repeatability is described in ASTM D2414. However, the results cannot be compared directly with oil absorption values determined in accordance with ISO 787-5.

**Table 2 — Conditional requirements**

Characteristic	Unit	Requirement	Test method
Particle size distribution (instrumental method)	% mass fraction	To be agreed between the interested parties	To be agreed between the interested parties
Specific surface area	m <sup>2</sup> /g		ISO 5794-1:2022, Annex D

## 5 Sampling

Take a representative sample of the product to be tested, in accordance with ISO 15528.

## 6 Determination of silica content

### 6.1 Principle

A test portion is repeatedly treated with hydrochloric acid and evaporated to dryness. To render the dehydrated silicic acid thus formed as insoluble as possible, it is then heated for 2 h at (140 ± 5) °C. Any chlorides present are removed by extracting the precipitate with hot dilute hydrochloric acid.

The precipitate is ignited at 1 000 °C, giving impure silicon dioxide, which is treated with sulfuric and hydrofluoric acid. The silicon tetrafluoride formed is evaporated off and the silica content is calculated from the resulting loss in mass.

### 6.2 Reagents

Use only reagents of recognized analytical grade and only water of at least grade 3 purity as specified in ISO 3696.

**6.2.1 Hydrochloric acid**, CAS Registry Number<sup>®1)</sup> 7647-01-0, concentrated, (approximately 32 % mass fraction,  $\rho \approx 1,16$  g/ml).

**6.2.2 Hydrochloric acid**, CAS Registry Number<sup>®</sup> 7647-01-0, diluted 1 + 1.

Add 1 part by volume of concentrated hydrochloric acid (6.2.1) slowly to 1 part by volume of water.

**6.2.3 Sulfuric acid**, CAS Registry Number<sup>®</sup> 7664-93-9, diluted 1 + 1.

Add 1 part by volume of concentrated sulfuric acid, (approximately 96 % mass fraction,  $\rho \approx 1,84$  g/ml), slowly to 1 part by volume of water.

**6.2.4 Hydrofluoric acid**, CAS Registry Number<sup>®</sup> 7664-39-3, concentrated, (approximately 40 % mass fraction,  $\rho \approx 1,13$  g/ml).

### 6.3 Apparatus

Use ordinary laboratory apparatus and glassware, together with the following.

**6.3.1 Dish**

**6.3.2 Platinum crucible**

**6.3.3 Water bath**, capable of being maintained at 100 °C.

**6.3.4 Infrared evaporator**

**6.3.5 Muffle furnace**, capable of being maintained at  $(1\ 000 \pm 20)$  °C.

<https://standards.iteh.ai/catalog/standards/sist/131b9927-42be-4e9e-b2bf->

**6.3.6 Drying oven**, capable of being maintained at  $(140 \pm 5)$  °C.

**6.3.7 Filter paper**

The filter paper used for filtration of the silica shall be of such texture as to retain the smallest particles of precipitate and nevertheless permit rapid filtration. For example, it is possible to use Whatman No. 40 or 41 or Schleicher und Schüll No. 589/2 "Weißband".<sup>2)</sup>

**6.3.8 Desiccator**, containing magnesium perchlorate as desiccant.

**6.3.9 Balance**, with an accuracy of 0,000 1 g.

### 6.4 Procedure

#### 6.4.1 Number of determinations

Carry out the determination in duplicate.

1) Chemical Abstracts Service (CAS) Registry Number<sup>®</sup> is a trademark of the American Chemical Society (ACS). This information is given for the convenience of users of this document and does not constitute an endorsement by ISO of the product named. Equivalent products may be used if they can be shown to lead to the same results.

2) Whatman No. 40 or 41 or Schleicher und Schüll No. 589/2 "Weißband" are examples of suitable products available commercially. This information is given for the convenience of users of this document and does not constitute an endorsement by ISO of these products.

#### 6.4.2 Test portion

Weigh, to the nearest 0,2 mg, approximately 1 g ( $m_0$ ) of the sample (see [Clause 5](#)) into a dish ([6.3.1](#)).

#### 6.4.3 Determination

Add slowly 20 ml of concentrated hydrochloric acid ([6.2.1](#)) and evaporate to dryness under the infrared evaporator ([6.3.4](#)). Add again 20 ml of concentrated hydrochloric acid and evaporate to dryness. Repeat this step once more. After the third evaporation, place the dish in the drying oven ([6.3.6](#)), maintained at  $(140 \pm 5)$  °C, and leave for 2 h.

Remove the dish from the oven and allow to cool. Add 50 ml of 1 + 1 hydrochloric acid ([6.2.2](#)) to the residue in the dish and warm it for approximately 20 min on the water bath ([6.3.3](#)) at 100 °C. Filter through a suitable filter paper ([6.3.7](#)) and wash the residue on the filter with hot water until the washings are neutral.

Pour the filtrate and washings into the original dish and evaporate to dryness. Repeat this evaporation step another two times, adding each time 10 ml of concentrated hydrochloric acid to the residue. After the third evaporation, heat at  $(140 \pm 5)$  °C for 2 h in the drying oven.

Add 20 ml of 1 + 1 hydrochloric acid to the residue in the dish and warm it for approximately 10 min on the water bath at 100 °C. Filter through a fresh filter paper and wash the residue on the filter with hot water until the washings are neutral.

If necessary, check the filtrate for any silicon which may have passed through the filter.

Place the two filter papers with the washed precipitates in the platinum crucible ([6.3.2](#)). Dry, reduce to ashes at low temperature, ignite in the muffle furnace ([6.3.5](#)) at  $(1\ 000 \pm 20)$  °C to constant mass (this should take approximately 1 h) and allow to cool in the desiccator ([6.3.8](#)). Weigh the ignited precipitate to the nearest 0,2 mg ( $m_1$ ).

Wet the ignited precipitate in the platinum crucible with 2 ml to 3 ml of water, add 1 ml of 1 + 1 sulfuric acid ([6.2.3](#)) and 15 ml of hydrofluoric acid ([6.2.4](#)) and evaporate to a syrup, taking care to avoid loss by spitting. Allow to cool and wash the sides down with small quantities of water. Then add a further 10 ml of hydrofluoric acid and evaporate to dryness. If the evaporation of the silicon tetrafluoride is not complete, add a further 10 ml of hydrofluoric acid and evaporate to dryness again.

Heat the residue until white fumes are no longer evolved, then ignite for 30 min in the muffle furnace at  $(1\ 000 \pm 20)$  °C. Remove from the furnace, allow to cool in the desiccator and weigh to the nearest 0,2 mg ( $m_2$ ).

#### 6.4.4 Determination of the total loss on ignition

Weigh, to the nearest 0,2 mg, approximately 1 g ( $m_3$ ) of the sample (see [Clause 5](#)) into a platinum crucible.

NOTE Weighing out the test portions for the determination of the silica content (see [6.4.2](#)) and the total loss on ignition can be carried out at the same time.

Ignite the test portion to constant mass in the muffle furnace at  $(1\ 000 \pm 20)$  °C (this should take approximately 2 h) and allow to cool in the desiccator. Weigh the ignited test portion to the nearest 0,2 mg ( $m_4$ ).

Calculate the total loss on ignition  $w_{TLI}$ , expressed as a percentage by mass, using the [Formula \(1\)](#):

$$w_{TLI} = \frac{m_3 - m_4}{m_3} \times 100 \quad (1)$$



where

$m_3$  is the mass, expressed in grams, of the test portion before ignition;

$m_4$  is the mass, expressed in grams, of the ignited test portion.

Calculate the mean of the two determinations and report the result to the nearest 0,1 %.

## 6.5 Expression of results

Calculate the silica content  $w(\text{SiO}_2)$ , expressed as a percentage by mass, using the [Formula \(2\)](#):

$$w(\text{SiO}_2) = \frac{(m_1 - m_2)}{m_0 \times \left[ 1 - \frac{w_{\text{TLI}}}{100} \right]} \times 100 \quad (2)$$

where

$m_0$  is the mass, expressed in grams, of the test portion (see [6.4.2](#));

$m_1$  is the mass, expressed in grams, of the dehydrated impure silica after ignition at  $(1\,000 \pm 20)^\circ\text{C}$  to constant mass (see [6.4.3](#));

$m_2$  is the mass, expressed in grams, of the silica after treatment with hydrofluoric acid and ignition to constant mass (see [6.4.3](#));

$w_{\text{TLI}}$  is the total loss on ignition determined in [6.4.4](#).

Calculate the mean of the two determinations and report the result to the nearest 0,1 %.

## 6.6 Precision

### 6.6.1 Repeatability, $r$

The repeatability,  $r$ , is the value below which the absolute difference between two single test results, each the mean of duplicates, can be expected to lie when this method is used under repeatability conditions. In this case, the test results are obtained on identical material by one operator in one laboratory within a short interval of time. For this document,  $r$  is 0,6 %, with a 95 % probability.

### 6.6.2 Reproducibility, $R$

No reproducibility data are currently available.

## 7 Determination of the composition by spectrometry

### 7.1 Principle

This spectrometric method gives the aluminium oxide and sodium oxide contents as well as the aluminium silicate content, although the precision of the determination of the aluminium silicate content can be lower than that of the method described in [Clause 6](#).

The elements aluminium, sodium and silicon are analysed using either flame atomic absorption spectrometry (FAAS) or inductively coupled plasma atomic emission spectrometry (ICP-AES), depending on which type of instrument is available in the laboratory.

The test solution is prepared by fusing a test portion of precipitated sodium aluminium silicate with lithium metaborate and dissolving the melt in a mixture of nitric acid and tartaric acid.

The advantages of the ICP-AES method include its wide dynamic range and multi-element capabilities. Both methods (FAAS and ICP-AES) are relative analytical techniques. For quantitative analytical results, both measurement techniques shall be calibrated using standard matching solutions.

## 7.2 Reagents and materials

Use only reagents of recognized analytical grade and only water of at least grade 3 purity as defined in ISO 3696.

**7.2.1 Lithium metaborate**, CAS Registry Number® 13453-69-5.

### 7.2.2 Acid mixture

Add 50 ml of nitric acid, CAS Registry Number® 7697-37-2, (approximately 65 % mass fraction,  $\rho \approx 1,40$  g/ml) and then 17 g of tartaric acid, CAS Registry Number® 526-83-0, to 500 ml of water. After dissolution, make up to 1 000 ml with water and mix well.

### 7.2.3 Caesium chloride buffer solution

Dissolve 50 g of caesium chloride, CAS Registry Number® 7647-17-8, in approximately 500 ml of water and add 50 ml of 30 % mass fraction hydrochloric acid, CAS Registry Number® 7647-01-0, ( $\rho \approx 1,15$  g/ml). Make up to 1 000 ml with water and mix well.

**7.2.4 Standard stock solutions**, containing 1,000 g/l of aluminium, sodium and silicon, respectively.

Store each solution in a fluorinated-polyethylene/polypropylene (FEP) bottle.

**7.2.5 Matrix solution**, free from aluminium, sodium and silicon.

Dissolve 2 g of lithium metaborate, CAS Registry Number® 13453-69-5, in 60 ml of the acid mixture (7.2.2) in a 200 ml polypropylene one-mark volumetric flask (7.3.7). Make up to 200 ml with water and mix well.

**7.2.6 Acetylene** (C<sub>2</sub>H<sub>2</sub>), CAS Registry Number® 74-86-2, commercial grade, in a steel cylinder.

**7.2.7 Compressed air**

**7.2.8 Dinitrogen oxide** (N<sub>2</sub>O), CAS Registry Number® 10024-97-2, commercial grade, in a steel cylinder.

## 7.3 Apparatus

Use ordinary laboratory apparatus and glassware, together with the following.

**7.3.1 Flame atomic absorption spectrometer (FAAS)**, suitable for measurements at the following wavelengths:

- 309,3 nm for aluminium (Al),
- 589,0 nm for sodium (Na),
- 251,6 nm for silicon (Si),

fitted with a suitable burner fed with:

- an N<sub>2</sub>O/C<sub>2</sub>H<sub>2</sub> mixture for Al and Si determinations,
- a C<sub>2</sub>H<sub>2</sub>/air mixture for Na determinations,