



FINAL DRAFT International Standard

ISO/FDIS 6224

Thermoplastics hoses, textile-reinforced, for general-purpose water applications — Specification

Tuyaux en matières thermoplastiques à armature textile d'usage général pour l'eau — Spécifications

ISO/TC 45/SC 1

Secretariat: DIN

Voting begins on:
2024-01-26

Voting terminates on:
2024-03-22

iTech Standards
(<https://standards.iteh.ai>)
Document Preview

[ISO/FDIS 6224](#)

<https://standards.iteh.ai/catalog/standards/iso/4d3160c7-15fa-4037-adc5-115e8dff5e8d/iso-fdis-6224>

ISO/CEN PARALLEL PROCESSING

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[ISO/FDIS 6224](https://standards.iteh.ai/catalog/standards/iso/4d3160c7-15fa-4037-adc5-115e8dff5e8d/iso-fdis-6224)

<https://standards.iteh.ai/catalog/standards/iso/4d3160c7-15fa-4037-adc5-115e8dff5e8d/iso-fdis-6224>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2024

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Classification	2
5 Materials and construction	2
6 Dimensions	2
6.1 Inside diameters and tolerances on inside diameter.....	2
6.2 Concentricity.....	3
6.3 Tolerance on length.....	3
6.4 Minimum wall thickness.....	3
7 Physical properties	3
7.1 Thermoplastic materials.....	3
7.2 Finished hoses.....	4
8 Type, routine and production testing	4
9 Test certificate/report	4
10 Marking	5
11 Packaging and storage	5
Annex A (normative) Type testing and routine testing	6
Annex B (informative) Recommended tests for production testing	7
Bibliography	8

ITeH Standards
<https://standards.iteh.ai>
 Document Preview

[ISO/FDIS 6224](#)

<https://standards.iteh.ai/catalog/standards/iso/4d3160c7-15fa-4037-adc5-115e8dff5e8d/iso-fdis-6224>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 1, *Rubber and plastics hoses and hose assemblies*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 218, *Rubber and plastics hoses and hose assemblies*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This fifth edition cancels and replaces the fourth edition (ISO 6224:2011), which has been technically revised. The main changes are as follows:

- the normative references have been updated;
- [Table 3](#) has been moved to [Clause 7](#);
- the explanation of type, routine and production tests have been updated in [Clause 8](#);
- marking in [Clause 10](#) has been updated.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Thermoplastics hoses, textile-reinforced, for general-purpose water applications — Specification

WARNING — Persons using this document should be familiar with normal laboratory practice. This document does not purport to address all the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate health and safety practices and to determine any national regulatory conditions applicable.

1 Scope

This document specifies the requirements for general-purpose textile-reinforced thermoplastics water-discharge hoses.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 176:2005, *Plastics — Determination of loss of plasticizers — Activated carbon method*

ISO 188:2023, *Rubber, vulcanized or thermoplastic — Accelerated ageing and heat resistance tests*

ISO 527-2, *Plastics — Determination of tensile properties — Part 2: Test conditions for moulding and extrusion plastics*

ISO 1307, *Rubber and plastics hoses — Hose sizes, minimum and maximum inside diameters, and tolerances on cut-to-length hoses*

ISO 1402, *Rubber and plastics hoses and hose assemblies — Hydrostatic testing*

ISO 4671, *Rubber and plastics hoses and hose assemblies — Methods of measurement of the dimensions of hoses and the lengths of hose assemblies*

ISO 8033, *Rubber and plastics hoses — Determination of adhesion between components*

ISO 8330, *Rubber and plastics hoses and hose assemblies — Vocabulary*

ISO 10619-1:2017, *Rubber and plastics hoses and tubing — Measurement of flexibility and stiffness — Part 1: Bending tests at ambient temperature*

ISO 10619-2:2021, *Rubber and plastics hoses and tubing — Measurement of flexibility and stiffness — Part 2: Bending tests at sub-ambient temperatures*

ISO 30013:2011, *Rubber and plastics hoses — Methods of exposure to laboratory light sources — Determination of changes in colour, appearance and other physical properties*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 8330 apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

— ISO Online browsing platform: available at <https://www.iso.org/obp>

— IEC Electropedia: available at <https://www.electropedia.org/>

4 Classification

Hoses are designated as one of the following types, depending on their pressure rating:

- Type 1: Low pressure — Designed for a maximum working pressure of 0,6 MPa (6 bar) at 23 °C and 0,36 MPa (3,6 bar) at 60 °C.
- Type 2: Medium pressure — Designed for a maximum working pressure of 1,0 MPa (10 bar) at 23 °C and 0,65 MPa (6,5 bar) at 60 °C.
- Type 3: High pressure — Designed for a maximum working pressure of 2,5 MPa (25 bar) at 23 °C and 1,6 MPa (16 bar) at 60 °C.

These hoses are not intended to be used for conveyance of potable (drinking) water, for washing-machine inlets, as fire-fighting hoses, for special agricultural machines or as gardening hoses for the consumer market.

5 Materials and construction

The hose shall consist of:

- a flexible thermoplastic lining;
- a reinforcement of natural or synthetic textile, applied by any suitable technique;
- a flexible thermoplastic cover.

The lining and the cover shall be of uniform thickness, concentric, fully gelled and free from visible cracks, porosity, foreign inclusions and other defects. The cover may have a smooth or fluted finish.

6 Dimensions

6.1 Inside diameters and tolerances on inside diameter

When measured in accordance with ISO 4671, the inside diameter and its tolerances shall conform to the values specified in [Table 1](#).

Table 1 — Inside diameters, tolerances and minimum wall thicknesses

Inside diameter Mm	Tolerance on inside diameter mm	Minimum wall thickness		
		mm		
		Type 1	Type 2	Type 3
4	±0,50	2,00	2,00	2,50
6	±0,50	2,00	2,00	2,50
8	±0,60	2,00	2,00	2,80
9	±0,60	2,00	2,00	2,80
10	±0,75	2,00	2,00	2,80
12,5	±0,75	2,00	2,50	3,00
16	±0,75	2,00	2,80	3,00

NOTE 1 For smaller or larger diameters, it is recommended that values be chosen from the R10 series of preferred numbers (see ISO 3), with tolerances as specified in ISO 1307.

NOTE 2 For intermediate diameters, it is recommended that values be chosen from the R20 series of preferred numbers (see ISO 3).