

~~ISO17717:2024(E)~~

~~ISO-PRF 17717~~

~~ISO/TC-045-45/SC-4/WG-5~~

~~Date: 2023-12-31~~

Secretariat: DSM

Date: 2024-02-16

Style Definition ...

Formatted: Right: 1.5 cm, Bottom: 1 cm, Gutter: 0 cm,
Section start: New page, Header distance from edge:
1.27 cm, Footer distance from edge: 1.27 cm

Meteorological balloons — Specification

Ballons météorologiques — Spécifications

Formatted: Cover Title_A1

iTeh Standards
(<https://standards.iteh.ai>)
PROOF Document Preview

ISO/PRF 17717

<https://standards.iteh.ai/catalog/standards/iso/b2fe2808-b6cc-4faa-905e-a7f40e1e5f86/iso-prf-17717>

© ISO 2023/2024

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Formatted: Font: Bold

Formatted: Font: Bold

Formatted: HeaderCentered

Formatted: Font: Bold

Formatted: Indent: Left: 0 cm, Right: 0 cm, Space Before: 0 pt, No page break before, Adjust space between Latin and Asian text, Adjust space between Asian text and numbers

Formatted: Default Paragraph Font, French (Switzerland)

Formatted: French (Switzerland)

Formatted: French (Switzerland)

Formatted: French (Switzerland)

Formatted: French (Switzerland)

Formatted: French (Switzerland)

iTeh Standards (<https://standards.iteh.ai>) Document Preview

ISO/PRF 17717

<https://standards.iteh.ai/catalog/standards/iso/b2fe2808-b6cc-4faa-905e-a7f40e1e5f86/iso-prf-17717>

Formatted: FooterPageRomanNumber

Formatted: Font: Bold

Formatted: Font: Bold

Formatted: HeaderCentered, Left

Formatted: Font: Bold

Contents

Foreword v

1 Scope 1

2 Normative references 1

3 Terms and definitions 1

4 Requirements 2

4.1 Colour 2

4.2 Appearance 2

4.3 Size, mass and dimensions 2

4.4 Tensile Property 4

4.4.1 General 4

4.4.2 Tensile strength and elongation at break before accelerated ageing 4

4.4.3 Tensile strength and elongation at break after accelerated ageing 4

4.5 Bursting diameters 5

4.6 Ozone resistance 5

5 Sampling 6

6 Packing, marking, transport and storage 6

6.1 Packing 6

6.2 Marking 7

6.2.1 Paper box 7

6.2.2 Container 7

6.2.3 Certification of proof 7

6.3 Transport and storage 8

Annex A (normative) Visual inspection of meteorological balloons 9

Annex B (normative) Inflatable inspection of meteorological balloons 11

Annex C (normative) Mass measurement 14

Annex D (normative) Dimension measurement 15

Annex E (normative) Burst test of meteorological balloons 19

Annex F (normative) Test method of ozone ageing of meteorological balloons 22

Bibliography 24

ITeh Standards
 (https://standards.iteh.ai)
 Document Preview

ISO/PRE 17717
 https://standards.iteh.ai/catalog/standards/sist/426299815-46-005/iso-prf-17717

Formatted: FooterPageRomanNumber

Formatted: Font: Bold

Formatted: Font: Bold

Formatted: HeaderCentered

Formatted: Font: Bold

Foreword — iv

1 — Scope — 1

2 — Normative references — 1

3 — Terms and definitions — 1

4 — Requirements — 2

4.1 — Colour — 2

4.2 — Appearance — 2

4.3 — Size, mass and dimensions — 3

4.4 — Tensile Property — 5

4.5 — Bursting diameters — 5

4.6 — Ozone resistance — 6

5 — Sampling — 6

6 — Packing, marking, transport and storage — 7

6.1 — Packing — 7

6.2 — Marking — 7

6.3 — Transport and storage — 8

Annex A (normative) Visual inspection of meteorological balloons — 9

Annex B (normative) Inflatable inspection of meteorological balloons — 11

Annex C (normative) Mass measurement — 14

Annex D (normative) Dimension measurement — 15

Annex E (normative) Burst test of meteorological balloons — 18

Annex F (normative) Test method of ozone ageing of meteorological balloons — 20

Bibliography — 22

iTeh Standards

<https://standards.itih.ai>

Document Preview

<https://standards.itih.ai/catalog/standards/iso/b2fe2808-b6cc-4faa-905e-a7f40e1e5f86/iso-prf-17717>

Formatted: FooterPageRomanNumber

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part-1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part-2 (see www.iso.org/directives).

~~Attention is drawn to the possibility that some of the elements of this document may be involved in the subject of a patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).~~

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 45, Rubber and rubber products, Subcommittee SC4, Products (other than hoses).

This second edition cancels and replaces the first edition (ISO 17717:2017), which has been technically revised.

The main changes compared to the previous edition are as follows:

- ~~In table 3 of 4.3, in Table 3, the size of 10 and its specified values has been added.~~
- ~~In table 6 of 4.5, in Table 6, the sizes of 10 to 100 and their specified values have been added.~~
- ~~In table B.2 of Annex B, in Table B.2, the sizes of 10 to 100 and their specified values have been added.~~
- ~~In table 8 of clause 5 and in C.3.2, in Table 8 and C.3.2, the mass range by mass has been changed to the size range by size.~~
- ~~In A.2.4 and B.3.1, in A.2.4 and B.3.1, thin cotton gloves without coating on palm for precision work have been added.~~

Formatted: Font: Bold

Formatted: Font: Bold

Formatted: HeaderCentered, Left

Formatted: Font: Bold

Formatted: English (United Kingdom)

Field Code Changed

Formatted: FooterPageRomanNumber

ISO/PRF 17717:2024 (En)

— In E.3, in E.3, the statement has been changed to ~~that~~ "the number of samples shall be in accordance with table 8, Table 8".

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Formatted: Font: Bold

Formatted: Font: Bold

Formatted: HeaderCentered

Formatted: Font: Bold

Formatted: English (United Kingdom)

Field Code Changed

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

ISO/PRF 17717

<https://standards.iteh.ai/catalog/standards/iso/b2fe2808-b6cc-4faa-905e-a7f40e1e5f86/iso-prf-17717>

Formatted: FooterPageRomanNumber

Meteorological balloons — Specification

Warning — Persons using this document should be familiar with laboratory practice. This document does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to determine the applicability of any other restrictions.

1 Scope

This document specifies the minimum requirements and the test methods for meteorological balloons made from natural rubber latex or natural rubber latex compounded with synthetic rubber emulsion.

This document applies to two types of balloons:

- Type 1: meteorological balloon by dipping process;
- Type 2: meteorological balloon by moulding process.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 37, Rubber, vulcanized or thermoplastic — Determination of tensile stress-strain properties

ISO 188, Rubber, vulcanized or thermoplastic — Accelerated ageing and heat resistance tests

ISO 2859-1, Sampling procedures for inspection by attributes — Part 1: Sampling schemes indexed by acceptance quality limit (AQL) for lot-by-lot inspection

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

3.1

air bubble

thin portion with definite edge, concave or convex, which is created by air in the balloon film

3.2

body thickness

single-walled thickness of a meteorological balloon

3.3

cracking

localized cracks in the balloon film

Formatted: Adjust space between Latin and Asian text, Adjust space between Asian text and numbers, Tab stops: Not at 0.7 cm + 1.4 cm + 2.1 cm + 2.8 cm + 3.5 cm + 4.2 cm + 4.9 cm + 5.6 cm + 6.3 cm + 7 cm

Formatted: Adjust space between Latin and Asian text, Adjust space between Asian text and numbers

Formatted: Default Paragraph Font

Formatted: Adjust space between Latin and Asian text, Adjust space between Asian text and numbers, Tab stops: Not at 0.7 cm + 1.4 cm + 2.1 cm + 2.8 cm + 3.5 cm + 4.2 cm + 4.9 cm + 5.6 cm + 6.3 cm + 7 cm

Formatted: Default Paragraph Font

Formatted: Default Paragraph Font

Formatted: Default Paragraph Font

Formatted: Default Paragraph Font

Formatted: Default Paragraph Font

Formatted: Default Paragraph Font

Formatted: Default Paragraph Font

Formatted: Default Paragraph Font

Formatted: Default Paragraph Font

Formatted: Adjust space between Latin and Asian text, Adjust space between Asian text and numbers

Formatted: Adjust space between Latin and Asian text, Adjust space between Asian text and numbers, Tab stops: Not at 0.7 cm + 1.4 cm + 2.1 cm + 2.8 cm + 3.5 cm + 4.2 cm + 4.9 cm + 5.6 cm + 6.3 cm + 7 cm

Formatted: Adjust space between Latin and Asian text, Adjust space between Asian text and numbers

Formatted: Adjust space between Latin and Asian text, Adjust space between Asian text and numbers

Formatted: Adjust space between Latin and Asian text, Adjust space between Asian text and numbers

3.4 grease mark

stains on the balloon film due to machine grease or oil

3.5 hole

opening due to a ruptured *air bubble* (3.1), (3.1), foreign body impurities or other external factors

3.6 latex coagulum

gel adhered to inside and outside of the balloon film

3.7 permanent creases with adhesion of the film

localized occurrence of the balloon film folding over and sticking to itself

3.8 thin spot

portion of the balloon which has no defined edge and has a film thickness which is less than that of the average thickness of the balloon film

4 Requirements

4.1 Colour

The balloon shall be natural colour unless otherwise specified.

4.2 Appearance

When inspected in accordance with Annex A, Annex A, the appearance of the balloon shall conform to requirements in Table 1, Table 1. If the defect cannot be confirmed by visual inspection, then Annex B, Annex B shall be carried out.

Table 1 — Appearance ISO/PRF 17717

Defects		Requirements
Serious defects	hole, cracking	Non-existent
	grease mark	Non-existent
	permanent creases with adhesion of the film	Non-existent
Light defects	air bubble, latex coagulum	Air bubble and latex coagulum are allowed to exist, which is not concentrated, obviously thin, not more than 5 mm in diameter and does not affect the balloon film stretching.
	thin spot	The thin spot is allowed to exist, which is not concentrated, not obvious, and does not affect the balloon film stretching and the length is not more than 10 mm, double layer thickness is not more than 0,12 mm.

4.3 Size, mass and dimensions

When measured in accordance with Annex C and Annex D, Annex C and Annex D, the size, masses and dimensions of the type 1 meteorological balloons shall conform to the values given in Table 2, Table 2, the size,

Formatted: Font: Bold
 Formatted: Font: Bold
 Formatted: HeaderCentered
 Formatted: Font: Bold

Formatted: Font: Not Bold, Font color: Auto
 Formatted: Indent: First line: 0 cm, Adjust space between Latin and Asian text, Adjust space between Asian text and numbers, Tab stops: Not at 7.41 cm + 16.4 cm

Formatted: Font: Not Bold, Font color: Auto
 Formatted Table
 Formatted: Font color: Auto
 Formatted: Font color: Auto
 Formatted: Font color: Auto

Formatted: Adjust space between Latin and Asian text, Adjust space between Asian text and numbers, Tab stops: Not at 7.41 cm + 16.4 cm
 Formatted: Adjust space between Latin and Asian text, Adjust space between Asian text and numbers, Tab stops: Not at 7.41 cm + 16.4 cm

Formatted: Font color: Auto
 Formatted: Font color: Auto
 Formatted: Adjust space between Latin and Asian text, Adjust space between Asian text and numbers, Tab stops: Not at 7.41 cm + 16.4 cm

Formatted: Font color: Auto
 Formatted: Font color: Auto
 Formatted: Font color: Auto
 Formatted: Font color: Auto

Formatted: Adjust space between Latin and Asian text, Adjust space between Asian text and numbers, Tab stops: Not at 7.41 cm + 16.4 cm
 Formatted: Font color: Auto
 Formatted: Adjust space between Latin and Asian text, Adjust space between Asian text and numbers, Tab stops: Not at 7.41 cm + 16.4 cm

Formatted: Font color: Auto
 Formatted: Font color: Auto
 Formatted: FooterPageRomanNumber

Size	Mass g	Dimension				
		Body length mm	Body thickness mm	Neck diameter mm	Neck length mm	Neck thickness mm
20	20 ± 4	250 to 380	0,15 ± 0,05	12 to 18	70 to 100	1,1 ± 0,5
30	30 ± 4	300 to 420	0,15 ± 0,05	12 to 18	70 to 100	1,1 ± 0,5
50	50 ± 4	360 to 560	0,15 ± 0,05	12 to 18	70 to 100	1,1 ± 0,5
70	70 ± 5	550 to 750	0,15 ± 0,05	12 to 18	70 to 100	1,1 ± 0,5
100	100 ± 10	600 to 800	0,15 ± 0,05	12 to 18	70 to 100	1,1 ± 0,5
200	200 ± 12	850 to 1 050	0,15 ± 0,05	25 to 35	100 to 140	1,5 ± 0,5
300	300 ± 15	950 to 1 150	0,15 ± 0,05	25 to 35	100 to 140	1,5 ± 0,5
350	350 ± 20	1 100 to 1 350	0,15 ± 0,05	25 to 35	100 to 140	1,5 ± 0,5
400	400 ± 22	1 150 to 1 400	0,15 ± 0,05	25 to 35	100 to 140	1,5 ± 0,5
500	500 ± 25	1 400 to 1 700	0,15 ± 0,05	25 to 35	100 to 140	1,5 ± 0,5
600	600 ± 27	1 600 to 1 900	0,15 ± 0,05	25 to 35	100 to 140	1,5 ± 0,5
700	700 ± 28	1 700 to 1 950	0,15 ± 0,05	25 to 35	100 to 140	1,5 ± 0,5
800	800 ± 30	1 800 to 2 050	0,15 ± 0,05	25 to 35	100 to 140	1,5 ± 0,5
1 000	1 000 ± 35	1 950 to 2 150	0,15 ± 0,05	25 to 35	100 to 140	1,5 ± 0,5
1 200	1 200 ± 40	2 200 to 2 500	0,15 ± 0,05	25 to 35	100 to 140	1,5 ± 0,5
1 500	1 500 ± 45	2 300 to 2 600	0,15 ± 0,05	25 to 35	120 to 160	2,15 ± 0,55
1 600	1 600 ± 50	2 300 to 2 700	0,15 ± 0,05	25 to 35	120 to 160	2,15 ± 0,55
2 000	2 000 ± 80	2 800 to 3 300	0,15 ± 0,05	40 to 60	160 to 200	2,15 ± 0,55
3 000	3 000 ± 110	3 200 to 3 800	0,15 ± 0,05	40 to 60	160 to 200	2,15 ± 0,55

NOTE—In addition to the above sizes given in this table, balloons of other sizes are also available for customers with special requirements.

4.4 Tensile Property

4.4.1 General

Tensile properties of balloons shall be measured in accordance with ISO 37, using three test pieces of Type 1 or Type 1A dumb-bell and taking the median value as the test result. Test pieces shall be taken from the middle part of balloon and equidistantly distributed along the circumference of the balloon body. The test pieces shall also be flat and the edge shall be smooth.

4.4.2 Tensile strength and elongation at break before accelerated ageing

Tensile strength and elongation at break of the balloons before accelerated ageing shall comply conform with the requirements given in Table 4.

4.4.3 Tensile strength and elongation at break after accelerated ageing

Accelerated ageing shall be conducted in accordance with the method specified in ISO 188. The accelerated ageing condition is (8 ± 0,25) h at (100 ± 1) °C or (168 ± 2) h at (70 ± 1) °C. For reference purposes, the



